FED. SUP CLASS
2620

THE TIRE SHALL BE IN ACCORDANCE WITH THE APPLICATION REQUIREMENTS OF MIL-R-7726 EXCEPT AS SPECIFIED HEREIN

MS PART NO.	SIZE	PLY RATING 1/	STATIC LOAD RATING LBS.	INFL. PRESS. PSI RATED	BEAD WIDTH IN. MAX.	WEIGHT LBS MAX.	STATIC UNBAL OZ-IN MAX.	TREAD 2/	MOLD SKID DEPTH MIN.	DEFLC + 3% - 4%
MS3387-1	40X14	26TL	30,500	175	3.10	140	20	RIB	.30	32%
MS3387-2	40X14	28TL	33,500	200	3.10	140	20	RIB	.30	32%

1/TL - TUBELESS

2/AT LEAST THREE, BUT NOT MORE THAN SEVEN CONTINUOUS CIRCUMFERENTIAL RIBS

RIM DATA:

WIDTH BETWEEN FLANGES (INCH)	LEDGE DIAMETER (INCH)	FLANGE HEIGHT (INCH)	MIN. LEDGE WIDTH (INCH)	MIN. FLANGE WIDTH (INCH)	FLANGE RADIUS (INCH)	HEEL RADIUS (INCH)	FLANGE EDGE RADIUS (INCH)
11.0	16.0	1.625	3.10	1.125	.812	.366	.094

THE TIRE MAXIMUM TREAD PROFILE IS DEFINED BY A SINGLE RADIUS, HAVING ITS CENTER ON THE TIRE VERTICAL CENTER LINE, TANGENT TO THE OUTSIDE DIAMETER AND PASSING THROUGH THE SHOULDER POINT.

THE TIRE COVERED BY THIS DRAWING SHALL BE SUITABLE FOR USE AND PROVIDE REASONABLE SERVICE LIFE DURING ALL NORMAL OPERATIONS AT TAKE-OFF SPEEDS OF NOT MORE THAN 200 MPH AND LANDING SPEEDS OF NOT MORE THAN 185 MPH ON ALL TYPES OF RUNWAYS AND ON AIRCRAFT CARRIERS.

THE TIRE SHALL WITHSTAND WITHOUT FAILURE THE FOLLOWING TESTS:

TIRE 1:

DYNAMIC TEST - THE TIRE SHALL SATISFACTORILY WITHSTAND 50 CYCLES OF TEST "A" WITHOUT EVIDENCE OF FAILURE.

TEST A - THE TIRE SHALL BE TAXIED ON THE FLYWHEEL AT 30 MPH FOR 10,000 FEET UNDER A 30,500 POUND LOAD FOR 26 PLY AND 33,500 POUND LOAD FOR 28 PLY RATED TIRES. UPON COMPLETION OF THE TAXI, THE FLYWHEEL SHALL BE STOPPED AND IMMEDIATELY ACCELERATED AT A RATE OF 6FT/SEC/SEC FROM 0 TO 200 MPH. THE TIRE SHALL BE UNLANDED AFTER A TAKEOFF ROLL DISTANCE OF 9,000 FEET HAS BEEN COVERED IN APPROXIMATELY 55 SECONDS. THE INITIAL LOAD SHALL BE LINEARLY DECREASED TO 26,900 POUNDS FOR 26 PLY AND 30,000 LBS FOR 28 PLY FROM 0 TO 15 SECONDS, THEN DECREASED LINEARLY TO 7,200 POUNDS FOR 26 PLY AND 8,000 POUNDS FOR 28 PLY AT THE TIME THE TIRE IS UNLANDED.

TIRE 2:

GOVT LAB TEST - THIS TIRE SHALL BE REBUILT FROM THE SAME BATCH AS TEST TIRE 1 AND SHALL BE IDENTICALLY PROCESSED. THIS TIRE SHALL NOT BE CONTRACTOR TESTED AND SHALL BE PROVIDED FOR GOVERNMENT LABORATORY TESTING.

SECTION - A REPRESENTATIVE SECTION OF TIRE 1 SHALL BE SUBMITTED TO A GOVERNMENT LABORATORY AS SPECIFIED IN MS 3377.

AIR RETENTION - THE TUBELESS TIRE SHALL BE INFLATED TO A PRESSURE OF 280 PSI FOR THE 26 PR OR 320 PSI FOR THE 28 PR AND ALLOWED TO STAND FOR A PERIOD OF 4 HOURS AT WHICH TIME THE PRESSURE DROP DUE TO GROWTH SHALL BE REPLACED. THE TIRE SHALL THEN STAND FOR AN ADDITIONAL 12 HOURS AT WHICH TIME THE PRESSURE SHALL BE MEASURED AND THE TIRE INSPECTED. THE AIR PRESSURE LOSS SHALL NOT EXCEED 5 PERCENT AND THE TIRE SHALL NOT REVEAL ANY APPEARANCE OR PERFORMANCE DEFECTS, SUCH AS SIDEWALL BLISTERS, TREAD SEPARATION, ETC.

NOTES:

1. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATIONS FOR BIDS, OR REQUEST FOR PROPOSAL EXCEPT THAT REFERENCE INDUSTRY STANDARDS SHALL GIVE THE DATE OF THE ISSUE ADOPTED.
2. FOR DESIGN FEATURE PURPOSES, THIS STANDARD TAKES PRECEDENCE OVER PROCUREMENT DOCUMENTS REFERENCED HEREIN.

APPROVED 18 FEB 1969 REVISED (A) 1 APR 1981

(A) ENTIRE STANDARD REVISED

This military standard is approved by NAVAL AIR SYSTEMS COMMAND, Department of the Navy and is mandatory for use by that activity. All other military activities are required to employ this standard where suitable.

P.A. NAVY - AS Other Cust	TITLE: TIRE, PNEUMATIC, AIRCRAFT, REBUILT, 40X14, TYPE VII (NAVY)	MILITARY STANDARD MS3387(AS)
PROCUREMENT SPECIFICATION MIL-R-7726	SUPERSEDES:	SHEET 1 OF 1

DD FORM 1 SEP 7 672-1 (Limited coordination) PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE. PROJECT NO. 2620-R213

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:03Z
Check the source to verify that this is the current version before use.