
FED. SUP CLASS
6640



PART NUMBER	DIMENSIONS FLAT WIDTH* mm	DIAMETER* mm	THICKNESS	LENGTH m
MS36239-1	10			30.5
MS36239-2	23			30.5
MS36239-3	25			30.5
MS36239-4				30.5
MS36239-5				30.5
MS362[illegible]				[illegible]
MS[illegible]				[illegible]
MS[illegible]				[illegible]
MS[illegible]				[illegible]
MS36[illegible]				[illegible]
MS362[illegible]				15.3
MS3621[illegible]				15.3
MS3623[illegible]			.0034	15.3
MS36239[illegible]			.0036	15.3
MS36239-[illegible]		[illegible]ul	.0040	15.3

* Average [illegible]s.

CANCELLED
CANCELLED AFTER 3 SEP 1991
NO SUPERSEDING STANDARD

MATERIAL: The membrane shall be made of regenerated cellulose tubing which is prepared from cotton linters.

DESIGN: Dialysis tubing shall be formed in such a manner that it may be shipped and stored flat.

NOTES:

1. Cotton linters cellulose has more that trace amounts of glycerine and sulfur compounds. The glycerine can be removed by washing the tubing in running water for 3-4 hours. The sulfur compounds may be removed by treating the tubing with sodium sulfide solution (0.2%) at 80°C for one minute, wash with hot water (60°C) for two minutes, followed by acidification with sulfuric acid (0.2%), and washing with hot water (60°C) to remove the acid.

2. Items differing from this Military Standard by minor variations in design or dimensions are considered standard under this document, provided such variations do not affect performance and are not in conflict with the material requirements specified herein.

Ⓐ CANCELLATION

P.A. EA	INTERNATIONAL INTEREST	TITLE	MILITARY STANDARD
Other Cust MS 99		MEMBRANE TUBING, DIALYSIS	MS36239
Procurement Specifications NONE	SUPERSEDES:		SHEET 1 OF 1

DD FORM 672 (COORDINATED) PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

CANCELLATION

Project Number 6640-1732-02

APPROVED 22 JUN 1983 REVISED Ⓐ 3 SEP 1991

USER ACTIVITIES: ARMY - MD, OH
NAVY - MS

REVIEWER ACTIVITIES: ARMY - ME
NAVY - OS
AIR FORCE - 82

MISC N/A
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T17:36Z
Check the source to verify that this is the current version before use.