
MS9813

FED. SUP CLASS
5306



PART NUMBER	L	K	APPROX WEIGHT LB/100
MS9813-04	1.125	.129- .149	23.54
MS9813-05	1.188	.129- .149	24.24
MS9813-06	1.250	.129- .149	24.94
MS9813-07	1.312	.129- .149	25.64
MS9813-08	1.375	.129- .149	26.32
MS9813-09	1.438	.129- .149	27.02
MS9813-10	1.500	.129- .149	27.71
MS9813-11	1.562	.129- .149	28.41
MS9813-12	1.625	.129- .149	29.10
MS9813-13	1.688	.129- .149	29.79
MS9813-14	1.750	.129- .149	30.49
MS9813-15	1.812	.129- .149	31.18
MS9813-16	1.875	.129- .149	31.87
MS9813-17	1.938	.129- .188	32.56
MS9813-18	2.000	.190- .250	33.26
MS9813-19	2.125	.315- .375	34.64
MS9813-20	2.250	.440- .500	36.03
MS9813-21	2.375	.565- .625	37.41
MS9813-22	2.500	.690- .750	38.79
MS9813-23	2.625	.815- .875	40.18
MS9813-24	2.750	.940-1.000	41.56
MS9813-25	2.875	1.065-1.125	42.95
MS9813-26	3.000	1.190-1.250	44.33
MS9813-27	3.125	1.315-1.375	45.72
MS9813-28	3.250	1.440-1.500	47.10
MS9813-29	3.375	1.565-1.625	48.49
MS9813-30	3.500	1.690-1.750	49.88
MS9813-31	3.625	1.815-1.875	51.26
MS9813-32	3.750	1.940-2.000	52.65
MS9813-33	3.875	2.065-2.125	54.03
MS9813-34	4.000	2.190-2.250	55.42
MS9813-35	4.125	2.315-2.375	56.80
MS9813-36	4.250	2.440-2.500	58.19
MS9813-37	4.375	2.565-2.625	59.57
MS9813-38	4.500	2.690-2.750	60.96
MS9813-39	4.625	2.815-2.875	62.34
MS9813-40	4.750	2.940-3.000	63.72
MS9813-41	4.875	3.065-3.125	65.11
MS9813-42	5.000	3.190-3.250	66.49
MS9813-43	5.125	3.315-3.375	67.88
MS9813-44	5.250	3.440-3.500	69.26
MS9813-45	5.375	3.565-3.625	70.65
MS9813-46	5.500	3.690-3.750	72.04
MS9813-47	5.625	3.815-3.875	73.43
MS9813-48	5.750	3.940-4.000	74.81
MS9813-49	5.875	4.065-4.125	76.19
MS9813-50	6.000	4.190-4.250	77.58

1. SHANK SHALL BE STRAIGHT WITHIN .002 TOTAL PER INCH OF BOLT LENGTH.
2. THE CONCENTRICITY OF THREAD PD IN RELATION TO THE SHANK SHALL BE WITHIN .006 FIR.
3. THE CONCENTRICITY OF THE SHANK IN RELATION TO THE WASHER FACE DIAMETER AND HEXAGON SHALL BE WITHIN .032 FIR.
4. INCOMPLETE THREADS NOT TO ENTER FILLET.
5. MATERIAL: CORROSION RESISTANT STEEL AMS 5643.
6. HARDNESS: .ROCKWELL C32-38.
7. MANUFACTURING SPECIFICATION: AMS 7474.
8. FLUORESCENT PENETRANT INSPECTION PER AMS 2645.
9. SURFACE TEXTURE: USAS B46.1-1962. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 MICROINCHES EXCEPT UPSET HEAD.
10. BREAK SHARP EDGES .003-.015 UNLESS OTHERWISE SPECIFIED.
11. DIMENSIONS IN INCHES. UNLESS OTHERWISE SPECIFIED, TOLERANCES: LINEAR DIMENSIONS ±.010, ANGULAR DIMENSIONS ±5°.
12. DO NOT USE UNASSIGNED PART NUMBERS.

(B) REINSTATED 15 AUG 84

AS & AMS ARE SOCIETY OF AUTOMOTIVE ENGINEERS, INC. PUBLICATIONS.
THIS STANDARD WAS DEVELOPED COOPERATIVELY WITH THE MILITARY SERVICES BY THE SAE AEROSPACE PART STANDARDS DIV.

APPROVED 11 MAR 70 REVISED (A) 21 DEC 83 (B) 15 AUG 84

Review activities:
AIR FORCE-82
DLA-IS

(B)

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document when applicable.

P.A.	INTERNATIONAL INTEREST	TITLE	MILITARY STANDARD
AS		BOLT, MACHINE - HEXAGON HEAD,	MS9813
Other Cust. AV (B) 99	(B)	PD SHANK, AMS 5643, .750-16 UNJF-3A	
PROCUREMENT SPECIFICATION NONE	SUPERSEDES:		PAGE 1 OF 1

DD FORM 672-1 (Coordinated) PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE 5306-0858

☆U.S. GOVERNMENT PRINTING OFFICE: 1985 — 505-038/20585

Source: https://assist.dla.mil -- Downloaded: 2026-10-25 13:26Z
Check the source to verify that this is the current version before use.