MIL-L-16462B
12 April 1967
SUPERSEDING
MIL-L-16462A
30 June 1960

MILITARY SPECIFICATION

LITTER, FOLDING, RIGID POLE

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers one type of rigid, aluminum pole, folding litter.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

Federal

V-T-276	Thread, Cotton.
V-T-285	Thread, Polyester.
QQ-A-200/3	Aluminum Alloy Bar, Rod, Shapes, and Tube, Extruded, 2024.
QQ-A-225/5	Aluminum Alloy Bar, Rod, and Wire, Rolled, Drawn, or Cold Finished, 2017.
QQ-A-225/6	Aluminum Alloy Bar, Rod and Wire, Rolled, Drawn, or Cold Finished, 2024.
QQ-A-225/8	Aluminum Alloy Bar, Rod, Wire, and Special Shapes, Rolled, Drawn, or Cold Finished, 6061.
QQ-B-613	Brass, Leaded and Non-Leaded, Plate, Rolled Bar, Sheet and Strip.
QQ-S-763	Steel Bars, Shapes, and Forgings, Corrosion Resisting.

FSC 6530

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

TT-E-527	Enamel, Alkyd, Lusterless.
TT-P-659	Primer - Surfacer, Synthetic, Tints and White, for Metal and Wood Surfaces.
WW-T-700/6	Tube, Aluminum Alloy, Drawn, Seamless, 6061 and 6062.
CCC-C-419	Cloth, Duck, Cotton, Unbleached, Plied Yarns, Army and Numbered.
CCC-D-950	Dyeing and Aftertreating Processes for Cotton Cloths.
CCC-T-191	Textile Test Methods.
PPP-B-566	Box, Folding, Paperboard.
PPP-B-576	Box, Wood, Cleated, Veneer, Paper Overlaid.
PPP-B-585	Box, Wood, Wirebound.
PPP-B-601	Box, Wood, Cleated-Plywood.
PPP-B-621	Box, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-B-676	Box, Setup.

Military

MIL-F-495	Finish, Chemical, Black, for Copper Alloy.
MIL-C-496	Clips, End, Strap.
MIL-W-530	Webbing, and Tape, Textile, Cotton, General Purpose, Natural or in Colors.
MIL-B-543	Buckles, Tongueless and Web Strap.
MIL-T-3530	Thread and Twine, Mildew-Resistant or Water Repellent Treated.
MIL-C-5541	Chemical Films and Chemical Film Materials for Aluminum and Aluminum Alloys.
MIL-P-8585	Primer Coating, Zinc Chromate, Low-Moisture-Sensitivity.
MIL-L-10547	Liners, Case, and Sheet, Overwrap, Water-Vaporproof or Waterproof, Flexible.
MIL-S-13518	Sealer, Surface, Wood Preservative.

STANDARDS

Federal

FED-STD-151	Metals, Test Methods.
FED-STD-595	Colors.
FED-STD-751	Stitches, Seams, and Stitchings.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

the ensuing contract period, the Federal Supply ... said contractor's immediate ... whose ...

Military

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 Marking for Shipment and Storage.

DRAWING

DEFENSE PERSONNEL SUPPORT CENTER

20017 Litter, Folding, Rigid Pole, Aluminum Pole.

(Copies of specifications, standards, drawing, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

COLOR ASSOCIATION OF THE UNITED STATES, INC.

United States Army Standard Color Card for the Official Standardized Shades of Sewing Threads.

(Application for copies should be addressed to the Color Association of the United States, Inc., 200 Madison Avenue, New York, N.Y. 10016.)

3. REQUIREMENTS

3.1 Preproduction sample approval. When specified, before production is commenced, a sample of the finished item shall be submitted or made ready for the contracting officer or his authorized representative, for inspection as specified in 4.2. The approval of the preproduction sample authorizes the commencement of production but does not relieve the supplier of responsibility for compliance with all applicable provisions of this specification. The preproduction sample shall be manufactured by the supplier in the same facilities to be used for the manufacture of the production items.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

3.2 Material. Except as hereinafter specified, materials shall conform to the applicable portions of the specifications, standards, and drawing listed in section 2, and be subjected to the tests and meet the requirements specified therein. The metals shall conform to the chemical requirements of their applicable specifications when tested as specified in 4.5.2. When materials to be used are not specifically deignated, those used shall be entirely suitable for the purpose intended.

3.2.1 Litter poles. Litter poles shall be made of aluminum-alloy tubing 6061-T6, 1-1/2 inches outside diameter, 0.120 inch thick (No. 11, Birmingham Wire gage), conforming to WW-T-700/6.

3.2.2 Stirrups. Stirrups shall be formed from 6061-T6 aluminum, conforming to QQ-A-225/8.

3.2.3 Spreader bar, coupler, bolt block, plug insert, and saddle. Spreader bar, coupler, bolt block, plug insert, and saddle shall be formed from 2024-T4 aluminum, conforming to QQ-A-200/3 or QQ-A-225/6.

3.2.4 Stop lug. Stop lug shall be formed from 2017-T4 aluminum, conforming to QQ-A-225/5.

3.2.5 Stirrup bolt, rivets, and drive pin. Stirrup bolt, rivets, and drive pin shall be formed from corrosion-resisting steel conforming to class 302 or 304 of QQ-S-763.

3.2.6 Nut for bolt. Nut for bolt shall be elastic stop, self-locking type, made of carbon steel, 18-thread, with fiber insert an integral part of the nut.

3.2.7 Bushing. Bushing shall be made of brass suitable for the purpose intended.

3.2.8 Litter cover. Litter cover shall be made of cotton duck.

3.2.8.1 Cotton duck. The cotton duck, before finishing, shall be type I, No. 10, hard texture, conforming to CCC-C-419.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

3.2.8.1.1 Color and treatment. Cotton duck shall be vat-dyed olive-drab No. 7, conforming to type I, class B of CCC-D-950, except that the cloth shall be made mildew resistant by treatment limited to one of the following mildew inhibitors only: (a) 2,2' methylene-bis (4 chlorophenol). (b) copper-8-quinolinolate.

3.2.9 Thread. Thread for stitching the litter shall be cotton, conforming to type III A or III B, 3 ply, ticket No. 10/3 of V-T-276; or polyester conforming to type I, class I, size FF, of V-T-285. All references to approved shade standard, approved standard shade sample, and approved standard shade in paragraph titled certification in both thread specifications shall not apply (see 4.1.2).

3.2.9.1 Color. The cotton thread shall be dyed to match olive-drab, shade S-1, cable 66022, and the polyester thread shall be dyed to match olive-green, shade S-1, cable 66022 of the United States Army Standard Color Card for the Offical Standardized Shades of Sewing Threads.

3.2.9.2 Treatment. The cotton thread shall be mildew resistant in accordance with type I, class I of MIL-T-3530. The finished cotton thread shall show good color fastness to laundering, chlorine bleaching, and weather.

3.2.10 Securing straps. Securing straps shall be type III, class 4 webbing, one inch wide, 1.33 ounces per linear yard, vat-dyed olive drab No. 7, conforming to MIL-W-530.

3.2.11 End clips. End clips shall be type I, brass, one inch, conforming to MIL-C-496, except material shall conform to QQ-B-613. Finish shall be as specified in MIL-F-495.

3.2.12 Buckles, tongueless, double bar. Buckles shall be type II, class I or 2, style 4, one inch, conforming to MIL-B-543.

3.2.13 Handles. Handles shall be thoroughly seasoned, kiln dried, hard (sugar) maple, ash, beech, true hickory, oak, pecan hickory, or birch, free from knots or checks.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

3.3 Construction. Construction shall conform to Drawing 20017. Each complete litter shall be furnished assembled with two complete spreader bar and stirrup assemblies, two poles with handles, canvas cover, and two securing straps. The complete unit shall pass the tests specified in 4.5.1.

3.3.1 Spreader bar, stirrup assemblies, and poles. Spreader bar, stirrup assemblies, and poles shall be as shown on the drawing. All sharp edges shall be removed, and corners shall be slightly rounded.

3.3.2 Handles. Handles shall be turned from hardwood as specified in 3.2.13. The end, fitted to the inside circumference of the pole, except the 1/8 inch taper for starting into the pole, shall be smooth, true, and not tapered. The handle shank shall be driven the entire length into place in the litter pole, and shall be secured in position with a drive pin passing through one thickness of the tubing. The pin shall be set flush with the outside of the pole.

3.3.2.1 Drive pin. Drive pin shall be a corrosion-resisting steel headless nail, overall length 1 inch, diameter 1/8 inch, with a 60 degree conical point on one end.

3.3.3 Canvas cover. Canvas cover shall be fabricated from one piece of cotton duck, and shall conform in all details to the drawing. The cover shall be so constructed that when placed on the litter, the warp shall run parallel to the long axis of the litter. Turnunders and seams shall be neat. No loose or raveled edges shall be exposed. When bought separately, covers shall be furnished without bolt holes.

3.3.3.1 Stitching. All stitching shall be machine stitching conforming to stitch type 301 of FED-STD-751. There shall be a minimum of eight stitches per inch. When machine stitching is not a continuous thread, it shall be backstitched not less than 1/2 inch at each break. All stitching shall be backtacked not less than 1/4 inch, at the ends to prevent raveling, except where ends are turned under in a hem or held down by other stitching. Thread tension shall be properly maintained so that the lock shall be embedded in the center of the materials sewed. All edges which are not selvaged shall be hemmed with stitching type EFb-1. All seams shall be straight and evenly spaced.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

3.3.4 Securing straps. Securing straps shall be clamped between the bolt block and the litter cover. The free end of each strap shall be provided with a ball type end clip, so constructed that it shall pass freely through the buckle. The end clip shall be firmly attached without cutting the webbing. The webbing shall be inserted the full depth and lie flat at the point where it enters. The free end shall be impregnated with a hardening material to prevent ravelling. When procured separately, securing straps shall be furnished without bolt holes. Each strap shall be supplied with a buckle and end clip as specified.

3.4 Finish.

3.4.1 Degreasing. All surfaces shall be thoroughly cleaned and chemically degreased prior to chemical treatment or plating.

3.4.2 Aluminum parts. All aluminum surfaces shall be finished with a chemical film conforming to MIL-C-5541.

3.4.3 Steel parts. All steel parts, other than corrosion-resisting steel parts, shall be zinc coated.

3.4.4 Primer. After degreasing, chemical treatment, or coating, a primer coat shall be applied to all metal parts other than corrosion-resisting steel parts. The primer shall be zinc chromate conforming to MIL-P-8585. The primer coat shall form a grounding bond and base for the enamel.

3.4.5 Enamel. The primer coat shall be followed by one coat of lustreless olive-drab enamel conforming to TT-E-527. The resultant finish shall be hard, smooth, and highly resistant to abrasion, chipping, and cracking.

3.4.5.1 Color. The color of the final finish shall be lustreless olive-drab conforming to color X34087 of FED-STD-595 (see 6.3).

3.4.6 Handles. Prior to finishing, the handles shall be sanded smooth, then immersed in wood sealer, conforming to type I or type II of MIL-S-13518, for three minutes. Handles shall be in final form before dipping. After dipping, handles shall be allowed to air-dry approximately one hour for rapid-drying seals, or 18 hours for slow-drying seals. The handles

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

shall then receive a coat of refinishing primer, conforming to TT-P-659, 0.7 mil minimum dry-film thickness. This coat shall be allowed to air-dry until dry enough to recoat (approximately four hours). A minimum dry-film thickness of 1.5 mils of lustreless olive-drab enamel, conforming to TT-E-527 and to color X34087 (see 6.3) of FED-STD-595, shall be applied to the primed surfaces and baked.

3.4.7 Lubrication. All parts shall be free of oil and grease, except the joints of moving parts, which shall be lubricated with an intimate mixture of equal parts, by weight, of zinc dust and petroleum jelly.

3.5 Identification marking. The spreader bar and stirrup assemblies, the canvas cover, and the undersurface of the litter securing straps shall be permanently and legibly marked with the name or registered trademark of the manufacturer. On the underside of the litter cover, approximately four inches from one end and centrally located, shall be placed the letters U.S. four inches high. The litter cover shall also be marked with the contract number. Marking shall be done with black waterproof ink or waterproof stencil paint. When the spreader bar and stirrup assembly is procured separately, the underside of the spreader bar shall be permanently and legibly marked with the name or registered trade mark of the manufacturer, and the contract number.

3.6 Workmanship. Workmanship shall be first class throughout. Litters shall be free from defects which detract from their appearance or may impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 202610-18T09:01Z
Check the source to verify that this is the current version before use.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual, auditory and investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.2 Certificates of quality. When available, certificates of quality, supplied by the manufacturer of the component or material, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

4.1.3 Government furnished material. Government furnished material shall not be sampled or tested, unless specifically requested by the Government.

4.2 Preproduction sample inspection. When required, the preproduction sample submitted in accordance with 3.1, will be inspected as specified in 4.4 and 4.5 for compliance with design, construction, workmanship and dimensional requirements.

4.3 Sampling.

4.3.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105.

	Inspection level	AQL (percent defective)
For visual examination*		
Major defects (each component).	II	1.0
Minor defects (each component).	II	2.5
For dimensional examination.	S-3	2.5

* When the complete litter assembly is examined, each component shall be examined in accordance with the classification of defects for that component in addition to that for the complete litter assembly.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

4.3.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105.

Table I. Test requirements

Item	Inspection level	Percent defective AQL	Minimum sample size
Component material testing	S-1	*	3
End item testing	S-2	1.5	

* Acceptance number shall be zero for all sample sizes.

4.3.3 Component materials. Sufficient samples of the component materials shall be selected from each lot of material used in the manufacture of the litter to perform tests as required by the applicable subsidiary specifications or by tests specified herein. When sample size for component material covered by the subsidiary specifications is not specified, the sample size for each test shall be as indicated in 4.3.2. The unit of product for testing shall be the quantity of material necessary to perform all required tests one time each. The same material may be used to perform two or more tests. Lot sizes are expressed in multiples of the following:

Duck	- Yard or fraction of a yard.
Webbing	- Yard or fraction of a yard.
Thread	- Cone or spool.
Buckles	- Each.
End clips	- Each.
Enamel	- Gallon or fraction of a gallon.

4.3.4 For chemical testing of metals. Four ounces of each lot of each metal used in the construction of the litters shall be selected for chemical analysis as specified in 4.5.2.

4.4 Examination. The litters shall be examined to determine compliance with all requirements contained in this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

4.4.1 Classification of defects. Examination shall be conducted in accordance with the following classification of defects:

Categories and defects*

Major A Litter.
- 101 Litter not complete with all component parts, assemblies, and subassemblies.
- 102 Components not properly assembled of aligned.
- 103 Exposed and accessible edges and surfaces not free from sharp edges and burs.
- 104 Center-to-center distance between poles (when litter is spread) not within tolerances specified.
- 105 Longitudinal distance between bolt holes on pole not within tolerances specified.
- 106 Bolt holes in poles not centered.
- 107 Wood handle not a secure fit in pole.
- 108 Headless nail protrudes from pole.
- 109 Canvas cover not a taut fit when litter is spread.
- 110 Litter cannot be spread.

Major B Litter cover.
- 121 Cover not fabricated from one piece of cotton duck.
- 122 Cover not constructed so that warp runs parallel to the long axis of the litter.
- 123 Raw edges not hemmed.
- 124 Width of the cover not within tolerances specified.
- 125 Cover pockets do not accommodate poles.

Major C Spreader bar and stirrup assembly.
- 131 Spreader bar and stirrup assembly not complete with all component parts.
- 132 Component parts not properly assembled or aligned.
- 133 Exposed and accessible corners and surfaces not free from sharp edges and burs.
- 134 Spreader bars bind in coupler.
- 135 Center-to-center distance between bolt holes not within tolerances specified.
- 136 Nut for stirrup bolt not elastic stop, self-locking type.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

Categories and defects*

Major D		Strap, securing.
	141	Strap not complete with all component parts (buckle and end clip).
	142	End clip end of strap does not readily pass through buckle.
	143	Raw end of strap not impregnated with a hardening material.
	144	Strap not free of cuts and tears.
Major E		Handle, wood.
	151	Handle not free of splits, slivers, checks, and knots.
	152	Handle not turned for a drive fit into poles.
	153	Handle not drilled for drive pin.
Major F		Nail, headless.
	161	Style and design not in accordance with drawing.
Minor A		Litter.
	201	Style, design, and construction not as shown on drawing.
	202	Litter does not rest evenly on a flat surface.
	203	Joints of moving parts not lubricated.
	204	Enamelled surfaces not free of chipped, cracked, nonadherent, and bare surfaces.
	205	Identification marking not complete, not legible, and not waterproof.
Minor B		Litter cover.
	221	Style, design, and construction not as shown on drawing.
	222	Turnunders, seams, and stitch lines not straight or evenly spaced.
	223	Cover not free from loose or ravelled edges.
	224	Stitching less than eight stitches per inch.
	225	Thread breaks backstitched less than 1/2 inch.
	226	Ends of stitching not turned under or held down by other stitching, back tacked less than 1/4 inch.
	227	Cover not permanently and legibly identified with the name or registered trademark of the manufacturer, the letters U.S., and contract number with black waterproof ink or paint.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

Minor C Spreader bar and stirrup assembly.
231 Style, design, and construction not as shown on drawing.
232 Aluminum parts not chemically treated as specified.
233 Enamelled surfaces not free of chipped, cracked, nonadherent, and bare surfaces.
234 Joints of moving parts not lubricated.
235 Identification marking not permanently or legibly accomplished.

Minor D Strap, securing.
241 Style, design, and construction not as shown on drawing.
242 Strap not permanently and legibly identified with the name or registered trademark of the manufacturer in black waterproof ink.

Minor E Handle, wood.
251 Style, design, and construction not as shown on drawing.
252 Finish not as specified.

*Examination shall not be restricted to the preceding listed possible defects.

4.4.2 Dimensional examination. The litters shall be examined for defects in dimensions. Any dimension not within the tolerances specified in the drawing shall be classified as a defect.

4.5 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.5.1 Performance tests on litters.

4.5.1.1 Two hundred pounds shall be placed on the litter canvas with the litter suspended from four points located 37-1/2 inches from the center of each pole. This weight shall be distributed as follows: 100 pounds shall be distributed over the center 18-inch length (full width) of the canvas; 30 pounds each on the adjacent 15-inch lengths (full width) of the litter canvas; and 20 pounds each on the adjacent 12-inch lengths (full width) of the litter canvas. The downward deflection of the poles shall not exceed 1-1/4 inches.

Source: https://assist.dla.mil -- Downloaded: 20261O-18T09:01Z
Check the source to verify that this is the currentversion before use.

4.5.1.2 With the litter resting on the stirrups, 1600 pounds shall be placed on a board, 18 inches wide, resting crosswise on the poles at the center of the litter. This weight shall be built up in a period of five minutes, allowed to remain for five minutes, than removed. The permanent downward deflection or set in the poles shall not exceed 5/8 inch.

4.5.1.3 Litter shall be so constructed that the tension of the canvas cover, when dry, shall require no less than 55 and no more than 70 pounds static load placed at the approximate center of the spreader bar, to open one end of the litter.

4.5.2 Chemical analysis of the metals. The samples selected in accordance with 4.3.4 shall be analyzed in conformance with methods 111 or 112 of FED-STD-151. In case of dispute, method 111 shall be used for referee analysis.

4.5.2.1 Corrosion-resisting steel. Tests for chemical analysis shall be conducted in accordance with method 111.1 or 112.1 of FED-STD-151.

4.5.2.2 Aluminum. Tests for chemical and mechanical properties shall be conducted in accordance with the test procedures of the respective specifications.

4.5.3 Enamel. Tests on enamel shall be conducted in accordance with the procedures outlined in TT-E-527.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. One litter, one cover, one strap or one spreader bar, as specified, constitutes one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in table I shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

Table I. Packaging quantities

Item	Unit package	Intermediate package	Exterior container
Litter	Not required	Not required	6 units
Cover	1 unit	Not required	36 units
Strap	1 unit	12 units	288 units
Spreader Bar	1 unit	Not required	8 units

5.1.2.1 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Unit package. Unit package shall be a carton of appropriate size constructed in accordance with PPP-B-566 or PPP-B-676, except commercial colors will be acceptable. Closure shall be adequate to prevent accidental opening.

5.1.3.2 Intermediate package. Intermediate package shall be a carton of appropriate size constructed in accordance with PPP-B-566 or PPP-B-676, except commercial colors will be acceptable. Closure shall be adequate to prevent accidental opening.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing.

5.2.1 Level A.

Source: https://assist.dla.mil -- Downloaded: 20261O-18T09:01Z
Check the source to verify that this is the current version before use.

5.2.1.1 Exterior container (litter). Three litters shall be packed side by side with stirrups in a vertical position, with six handles against one end of the container. Three litters shall than be packed in a reverse position with the stirrups interlocked and six handles positioned against the opposite end of the container. Litters shall be packed in such a manner as to prevent damage of or shifting of the litters within the container. Exterior container shall be designed for type 3 load, and constructed in accordance with PPP-B-601, table II, using type III, class 1 plywood; or PPP-B-621, table IV.

5.2.1.2 Exterior container (cover, strap and spreader bar). Exterior container shall be designed for type 2 load, and constructed in accordance with PPP-B-585, style 3, for class 3 use; PPP-B-601, table II, using type III, class 1 plywood; PPP-B-621, table III; or PPP-B-636, type CF, class weather-resistant.

5.2.1.3 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard box or box containing litters.

5.2.1.4 Closure. Closure of wood boxes shall be in accordance with appendix of applicable box specification. Closure of each fiberboard box shall be as specified in the appendix, and waterproofing shall conform with PPP-B-636.

5.2.1.5 Strapping. Strapping, when required, shall be in accordance with appendix of applicable box specification.

NOTE: Strapping shall not be required for shipments forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

5.2.2 Level B.

5.2.2.1 Exterior container (litter). Litters shall be packed as specified in 5.2.1.1, except the container shall be constructed in accordance with PPP-B-601, table I, using type III, class 1 plywood.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

5.2.2.2 Exterior container (cover, strap and spreader bar). Exterior container shall conform to PPP-B-601, table I, using type III, class 1 plywood; or shall be designed for type 2 load, and constructed in accordance with PPP-B-585, style 3, for class 2 use; PPP-B-621, table I; or PPP-B-636, type CF, class domestic and method I closure shall be utilized.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The letter covered by this specification is intended for use by the Military Medical Services, for the transportation of sick and injured personnel.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) When preproduction sample is required (see 3.1).
(c) Where preproduction sample shall be sent (see 3.1).
(d) Packaging and packing levels (see 5.1 and 5.2).

6.3 Availability of Color Chips. The individual 3 by 5 inch chips of the color referenced in 3.4.5.1 and 3.4.6 are available from Commanding Officer, U.S. Naval Depot, 5801 Tabor Avenue, Philadelphia, Pa. 19120.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

6.4 This specification does not include all types, classes, grades, or sizes of the commodity indicated by the title of this specification, or which are commercially available, but is intended to cover the items which are normally procured to meet Military requirements.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

CATEGORY: N

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 4966 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
ATTN: DPSC-LS
2800 South 20th Street
Philadelphia, PA 19101

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:01Z
Check the source to verify that this is the current version before use.