GG-F-599B
9 September 1988
SUPERSEDING
GG-F-00599A (DSA-DM)
5 January 1970
Interim Revision of
GG-F-599
2 May 1961

FEDERAL SPECIFICATION

FORCEPS, DRESSING (Dental)

This specification is approved by the Commissioner Federal Supply Service, General Services Administration for the use of all Federal Agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers dressing forceps for use in dental operative procedures.

1.2 Classification. Forceps shall be of the following types and classes, as specified (see 6.1).

Type I. Meriam.

Type II. No. 17.

Class 1. Smooth jaws.
Class 2. Serrated jaws.

Type III. Amalgam Reinforcement Pin.

Type IV. Endodontic.

AMSC N/A FSC 6520

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-RSTS, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:51Z
Check the source to verify that this is the current version before use.

1.2.1 Types and classes. The forceps shall be furnished in the type and class specified for the applicable stock number and item identification.

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issue in effect on the date of invitations for bid or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Boxes, Shipping, Fiberboard.
PPP-B-676	Boxes, Setup.

STANDARDS

Federal

FED-STD-151	Metals; Test Methods.

(Activities outside the Federal Government may obtain copies of Federal specifications, standards, and commercial item descriptions as outlined under General Information in the Index of Federal Specifications, Standards and Commercial Item Descriptions. The Index, which includes cumulative bimonthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, US Government Printing Office, Washington, DC 20402).

(Copies of listed federal and military standards, specifications, Commercial Item Descriptions (CIDS), handbooks and associated documents listed in the Department of Defense Index of Specifications and Standards (DoDISS), should be obtained from the DoD Single Stock Point, Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120. Copies of industry association documents should be obtained from the sponsor. Copies of all other listed documents should be obtained from the contracting activity or as directed by the contracting activity).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.

(Federal Government activities may obtain copies of Federal standardization documents and the Index of Federal Specifications, Standards and Commercial Item Descriptions from established distribution points in their agencies).

SPECIFICATIONS

Military

MIL-P-116	Methods of Preservation.

STANDARDS

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.
MIL-STD-147	Palletized Unit Loads.
MIL-STD-794	Parts and Equipment, Procedures for Packaging of.

DRAWINGS DEFENSE PERSONNEL SUPPORT CENTER (DPSC)

20216	Forceps, Dressing
23322	Forceps, Endodontic, 6 Inch
24116	Forceps, Dressing

(Copies of specifications and standards, required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity).

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitations for bid or requests for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM E18	Tests for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials.
ASTM E92	Tests for Vickers Hardness of Metallic Materials.
ADA No. 29	General Specification for Hand Instruments.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103).

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification takes precedence. Nothing in this specification, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General requirements. The forceps shall be in accordance with the applicable requirements of ADA No. 29 and with the requirements specified herein.

3.2 Drawings. The drawings forming a part of this specification are specification control drawings. The supplier is responsible for preparing his own shop drawings. Where tolerances prescribed could cumulatively result incorrect fits, the supplier shall provide tolerances within those prescribed on the drawings to insure correct fit, assembly, and operation of the forceps. No deviation from the prescribed dimensions or tolerances is permissible without prior approval of the contracting officer.

3.3 Material. The forceps shall be Class 4, martensitic stainless steel, type 410 or 420, or Class 6, ferritic stainless steel, type 430. As an alternate, type III forceps shall be Class 3, austenitic stainless steel, type 302, 303 or 304.

3.4 Hardness. After proper stress relieving, the Rockwell hardness of the operative ends of forceps fabricated from the following steels shall be as specified below. Hardness shall be determined as specified in 4.4.2.

Class 3, Austenitic stainless steel.....B85 minimum
Class 4, Martensitic stainless steel.....C40-45
Class 6, Ferritic stainless steel.....C10 minimum

3.5 Style, design, and dimensions. Forceps shall be suitable for use in placing, holding, and removing various dental materials during dental operative procedures and as hereinafter specified. All mating members of forceps shall be properly oriented with respect to each other and shall properly align when forceps are closed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.

3.5.1 Type I. Type I forceps shall be of the Meriam design and of the style and dimensions in accordance with Defense Personnel Support Center (DPSC) Drawing 20216 for style specified.

3.5.2 Type II. The style, design, and dimensions of Type II, No. 17, forceps shall be in accordance with Defense Personnel Support Center (DPSC) Drawing 20216 for style specified. The inside surfaces of the jaws of Type II, class 1, forceps shall be smooth. The inside surfaces of the jaws of Type II, class 2, forceps shall be serrated with 70 ± 15 serrations per inch.

3.5.3 Type III. The style, design, and dimensions of Type III, amalgam reinforcement pin forceps shall be in accordance with Defense Personnel Support Center (DPSC) Drawing 24116. The forceps shall be suitable for use in placing amalgam reinforcement pins into prepared tooth cavities. The inside surfaces of the jaws shall be grooved, serrated, and slotted. The slots and grooved of mating member jaws shall align with each other when forceps are closed.

3.5.4 Type IV. The style, design, and dimensions for type IV, endodontic forceps shall be in accordance with Defense Personnel Support Center (DPSC) Drawing 23322. The forceps shall be suitable for use in holding filling and absorbent points during endodontic procedures. Shall be a thumb type forceps with angulated operative tips, having one serrated jaw and one smooth jaw. Smooth jaw shall have a groove extending from blunt end to point of angulation. Forceps shall have a locking device and corresponding chamfered hole in opposing forceps members to insure proper mating and locking of forceps members in a closed position until released. Forceps shall also have a guide pin and corresponding chamfered hole in opposing forceps members to assure proper alignment of operative tips.

3.6 Serrations. Jaw and handle serrations shall be in accordance with the applicable figure herein and in accordance with the applicable requirements of ADA No. 29. Serrations shall be uniform in length, width, and depth.

3.7 Joints. The two members of the forceps shall be joined together to form a permanently secured joint. The members shall be joined together by spot welding.

3.8 Finish. The forceps shall have a mirror finish except for the serrated portions which shall have a bright finish. The grooves and slots of type III forceps shall have a bright finish.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:51Z
Check the source to verify that this is the currentversion before use.

3.9 Deflection. The operative ends (jaw tips) shall coincide when tested in accordance with 4.4.4.

3.10 Corrosion resistance. The forceps shall meet the requirements as specified in ADA No. 29 for resistance to copper sulfate test and resistance to boil test for the applicable type of material, when tested as specified in 4.4.3.1 and 4.4.3.2.

3.11 Identification marking. The forceps shall be permanently and legibly marked in accordance with the requirements of ADA No 29. In addition, forceps of foreign manufacture shall also be marked "stainless". Type II forceps shall be marked with the number "17".

3.12 Workmanship. Forceps shall be free from defects which detract from their appearance or impair their serviceablility, proper functioning, and intended use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification, where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of the raw material, may be furnished in lieu of actual performance of such testing by the contractor, provided that lot identity has been maintained and can be demonstrated to the Government.

4.2 Quality conformance inspection. The examinations and tests required to assure conformance of those items or lots of items to be offered for acceptance are classified as specified in Tables I and III (see 4.2.1 and 4.3) and Table II (see 4.2.2).

4.2.1 Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105. The inspection levels and acceptable quality levels (AQLs) shall be as indicated in Table I. The unit of product for examination purposes shall be one forcep.

TABLE I. Examination critieria.

Type defect	Inspection level	AQL (percent defective)
Major A	II	1.0
Major B	S-2	1.5
Minor A	II	2.5
Minor B	S-2	4.0

4.2.2 Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105, and as indicated in Table II. The unit of product for test purposes shall be one instrument.

TABLE II. Sampling for tests.

Characteristic	Requirement	Test procedure	Inspection level	AQL
Material	3.3	4.4.1	See 4.2.3	1/
Hardness	3.4	4.4.2	S-2	1.5
Deflection	3.9	4.4.4	S-2	1/
Copper Sulfate test	3.10	4.4.3.1	S-2	1.0
Boil test	3.10	4.4.3.2	S-2	1.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.

1/ Acceptance number shall be zero for all sample sizes.

4.2.3 Sampling of raw materials. A sufficient amount from each lot of raw material used in the fabrication of the forceps shall be selected for chemical analysis.

4.3 Examination. The forceps shall be examined for defects including, but not limited to, those listed in Table III.

TABLE III. Classification of defects.

Categories	Defects
Critical:	None defined.
Major A:	
101	Style and design not as specified for type and class of forceps.
102	Operative end (jaw) serrations, where applicable, incomplete, not properly formed, or uniform in length, width, and depth.
103	Operative end not free from cracks, nicks or burrs.
104	Members of forceps not permanently secured.
105	Operative end (jaw) grooves and slots (Type III forceps) do not align when jaws mate.
106	Mating members do not align with each other when forceps are closed (use only slight pressure so that tips touch).
107	Guide pin is not aligned with guide pin hole.
108	Finish on inside of jaws not as specified.
109	Locking device (Type IV) is not aligned with locking device hole.
110	Mating members do not align with each other when forceps are closed by locking device (Type IV).
Major B:	
151	Operative end (jaw) dimensions not as specified.
152	Number of serrations, where applicable, on inside surfaces of jaws not as specified.
Minor A:	
201	Finish, other than inside of jaws (108), not as specified.
202	Forceps not free from dirt, oil, polishing compound, or foreign matter.
203	Marking on forceps neither legible nor permanent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.

TABLE III. Classification of defects (cont'd.)

Categories	Defects
Minor A:	
204	Marking either missing or incorrect.
205	Serrations, other than those covered in 102, incomplete, improperly formed or not uniform in length, width, and depth.
206	Instrument not free from cracks, nicks, or burrs (other than those covered in 103).
Minor B:	
251	Dimensions (other than those covered in 151 and 152) not as specified.

4.4 Test procedures.

4.4.1 Chemical composition. In the absence of certificates of quality for the raw material, chemical analysis shall be conducted in accordance with method 111 or 112 of FED-STD-151. In the event of a conflict, method 111 shall be used for referee analysis.

4.4.2 Hardness. Hardness shall be determined in accordance with ASTM Designation E 18 (Rockwell) or E 92 (Vickers or Diamond Pyramid).

4.4.3 Corrosion resistance.

4.4.3.1 Cooper sulfate test. The forceps shall be subjected to the copper sulfate test as specified in ADA No. 29.

4.4.3.2 Boil test. The forceps shall be subjected to the boil test as specified in ADA No. 29.

4.4.4 Deflection test. The forceps shall be placed on its side (outside face of one member) on a level table and shall be subjected to a downward load of 4 ounces minimum and 12 ounces maximum, applied at 3-5/8 to 3-3/4 inches from the proximal (joined) end.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.

4.5 Inspection of packaging. The sampling and inspection of the preservation and interior package marking shall be in accordance with groups A and B quality conformance inspection requirements of MIL-P-116. The sampling and inspection of the packing and marking for shipment and storage shall be in accordance with the quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or C, as specified (see 6.1).

5.1.1 Level A.

5.1.1.1 Cleaning and drying. Forceps shall be cleaned and dried in accordance with MIL-P-116.

5.1.1.2 Preservative applications. Preservatives shall not be used.

5.1.1.3 Unit package. Each forceps shall have the jaws protected with a plastic cap or other suitable material. The forceps shall be further packaged in accordance with MIL-P-116, method IC-1 or IC-3.

5.1.1.4 Intermediate package. Twelve unit packages containing forceps of one type and class only shall be packaged in a box conforming to PPP-B-566 or PPP-B-676. "Closure shall be adequate to prevent accidental opening." "Closure shall be as specified in the applicable box specification.

5.1.2 Level C.

5.1.2.1 Unit package. Preservation for forceps shall conform to the requirements of MIL-STD-794 or level C.

5.1.2.2 Intermediate package. Twelve unit packages containing forceps of one type and class only shall be packaged in accordance with the requirements of MIL-STD-794 for level C. "Closure shall be adequate to prevent accidental opening.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.

5.2.1 Level A. Forty-eight intermediate packages (576 units) containing forceps of one type and class only shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-601, overseas type, PPP-B-621, class 2, or PPP-B-636, class weather-resistant. Closure and strapping strapping shall be as specified in the applicable box specification.

5.2.1.1 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall be as specified in the liner specification. Case liner shall not be required for fiberboard boxes. Each fiberboard box shall be waterproofed as specified in PPP-B-636.

5.2.2 Level B. Forty-eight intermediate packages (576 units) containing forceps of one type and class only shall be packed in an exterior container 5 designed for a type 2 load and conforming to PPP-B-601, domestic type, PPP-B-621, class 1, or PPP-B-636, class domestic. Closure shall be as specified in the applicable box specification.

5.2.3 Level C. Forty-eight intermediate packages (576 units) containing forceps of one type and class only shall be packed in accordance with the requirements of MIL-STD-794 for level C.

5.2.4 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.2.5 Unitized loads. Unitized loads, commensurate with the level of packing specified in the contract or order, shall be used whenever total quantities for shipment to one destination exceed 250 pounds or 20 cubic feet. Loads shall be unitized on pallets conforming to MIL-STD-147. Quantities less than 20 cubic feet need not be unitized. Pallet loads including the pallet shall not exceed 54 inches in height, 52 inches in width, and 43 inches in length. Pallet shall conform to Type IV or Type V.

5.2.5.1 Levels A and B. Forceps of one type and class only packed as specified in 5.2.1 and 5.2.2 shall be unitized on pallets as specified in 5.2.5.

5.2.5.2 Level C. Forceps of one type and class only packed as specified in 5.2.3 shall be unitized as specified in MIL-STD-794.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:51Z
Check the source to verify that this is the currentversion before use.

5.3 Marking.

5.3.1 Levels A, B and C. Each unit pack, intermediate package exterior container and unitized load shall be marked as specified in MIL-STD-129.

5.4 General.

5.4.1 Exterior container. Exterior container (see 5.2.1, 5.2.2, and 5.2.3) shall be of minimum tare and cube consistent with the protection required and shall contain equal quantities of identical stock numbered items to the greatest extent practicable.

5.4.2 Packaging inspection. The inspection of these packaging requirements shall be in accordance with 4.5.

6. NOTES

6.1 Ordering data.

6.1.1 Acquisition requirements. Acquisistion documents should specify the following:

(a) Title, number, and date of this specification.
(b) Specify type and class of forceps required (see 1.2).
(c) Selection of applicable levels of packaging and packing (see 5.2.1 and 5.2).

6.2. National Stock Number (NSN) coverage. This specification covers the following items appearing in the Federal Supply Catalog:

National Stock Number	Item Identification
6520-00-299-9671	FORCEPS, DRESSING, Meriam, 6 inch (15.24 cm)
6520-00-542-7000	FORCEPS, DRESSING, No. 17, 6-1/4 inch (15.87 cm)
6520-00-935-1092	FORCEPS, DRESSING, Restorative Retention Pin, 6-5/16 inch (16.03 cm)
6520-01-070-1498	FORCEPS, ENDODONTIC, 6 inch (15.24) cm)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.

6.3 Subject term (key word) listing.
Dressing
Endodontic
Forceps
Meriam
Restorative Retention Pin

MILITARY INTERESTS:

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Civil Agency Coordinating Activities:
VA-OSS
PHS
FDA-MPQAS

PREPARING ACTIVITY:

DoD - MB

AGENT:

DLA-DM

Project No. 6520-1979

Location: NCR Disk #8

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 4966 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
ATTN: DPSC-~~ASTE~~
2800 South 20th Street
Philadelphia, Pennsylvania 19101-8419

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:51Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
GG-F-599B	FORCEPS, DRESSING (Dental)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:51Z
Check the source to verify that this is the current version before use.