GG-S-621C
July 14, 1977
SUPERSEDING
GG-S-621b
August 12, 1957

FEDERAL SPECIFICATION

SPLINT, WOOD

This specification was approved by the Commissioner, Federal Supply Service, General Service Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers wood splints (see 6.1).

1.2 Classification. Wood splints shall be one type and furnished in the following sizes, as specified (see 6.2).

Size 1 - 18 inches by 4 inches by 3/16 inch.
Size 2 - 6 feet by 4 inches by 3/16 inch.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

PPP-B-566 - Boxes, Folding, Paperboard.
PPP-B-636 - Boxes, Fiberboard.
PPP-B-676 - Boxes, Setup.

Federal Standards:

Fed. Std. No. 101 - Preservation, Packaging and Packing Levels.

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

FSC 6515

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:52Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, US Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices, in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	-	Marking for Shipment and Storage.
MIL-STD-1363	-	Measurement of Wood Moisture Content.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material. The splints shall be made of basswood as specified herein.

3.1.1 Basswood. The basswood shall be either white wood (sapwood) or heart wood. The wood shall be clean, sound, free of checks, splits, shakes, pitchpockets, fungus and dry rot. Mineral stain is permissible.

3.1.1 Knots. Pin knots over 1/8 inch in diameter shall not exceed four per linear foot. Knots under 1/8 inch shall not exceed permissible limit (see 4.3).

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:52Z
Check the source to verify that this is the current version before use.

3.2 Moisture content. The basswood shall have a moisture content of between 8 and 15 percent when tested as specified in 4.4.

3.3 Configuration. The splint shall be sawn flat wood, dimensioned as specified herein.

3.4 Dimensions. The dimensions shall be as specified for the particular size (1.2). Size 1 shall be 18 inches long, 4 inches wide and 3/16 inch thick. Size 2 shall be 6 feet long, 4 inches wide and 3/16 inch thick.

3.4.1 Tolerances. A tolerance of ± 1/8 inch on length, ± 1/8 inch on width and ± 1/64 inch in thickness shall be permitted. Deviation from flatness in the longitudinal direction shall not exceed 1/16 inch for size 1 and 1/4 inch for size 2. Deviation from flatness in the transverse direction up to 1/16 inch shall be permitted.

3.5 Finish. All edges of splints (side edges and end edges) shall be smooth and free of splinters. Splints shall be dressed on two sides to a clean, smooth flat surface.

3.6 Workmanship. Workmanship shall be first class throughout. Splints shall be surfaced to uniform thickness and width and shall be free from defects which detract from their appearance or may impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

Source: https://assist.dla.mil -- Downloaded: 20260-26T11:52Z
Check the source to verify that this is the current version before use.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality, furnished by the supplier of the wood, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the National Stock Number (NSN), the item identification, the name of the component/material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results and the specification requirements.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as indicated in table I. The unit of product for examination purposes shall be one splint.

TABLE I. Sampling criteria for examination.

Type of defect	Inspection level	AQL (Percent defective)
Major	I	1.0
Minor	I	4.0
Dimensional	S-2	4.0

4.2.2 For test. Sampling for moisture content shall be conducted in accordance with MIL-STD-105, Inspection level S-2, except that a minimum of five samples shall be taken and the acceptable quality level shall be 1.0. The test specimens shall be selected from different splints.

4.3 Examination. The splints selected as described in 4.2.1 shall be examined for but not restricted to the defects listed in table II. Additional defects shall be classified in accordance with MIL-STD-105.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:52Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of defects

Category	Defect
Major	
101	Wood contains excessive pin knots or knot holes, exceeding 1/8 inch in diameter (visual).
102	Surfaces not finished, smooth and free of splinters (including edges).
103	Wood not free of checks, splits, shakes, pitch-pockets, fungus, and dry rot.
Minor	
201	Splints not clean and free from foreign matter.
202	Knot holes under 1/8 in diameter.

4.3.1 Dimensional examination. Any dimension not within the specified tolerance shall be classified as a defect.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Moisture content. Samples shall be tested by the moisture meter method of MIL-STD-1363. In case of dispute the oven-drying method of MIL-STD-1363 shall be used.

4.5 Preparation for delivery. An examination shall be made to determine whether the packaging, packing and marking comply with the requirements of Section 5. Defects shall be scored as specified, but not limited to those defects in table III. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with an AQL of 4.0 expressed in terms of percent defective.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:52Z
Check the source to verify that this is the current version before use.

TABLE III. Examination of preparation for delivery.

Examination	Defect
Containers	Not as specified.
Contents	Not as specified.
Markings	Omitted; incorrect; illegible; improper size, location, sequence, or method of application.
Packaging and packing materials	Any component missing or damaged.
Workmanship	Bulging or distortion of containers. Cushioning inadequate, improper or missing.

4.5.1 Examination of closure, waterproofing and banding for containers. When containers are required to comply with PPP-B-676 or PPP-B-636, examination for defects in closure, waterproofing and banding shall be in accordance with the appendix to that specification.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Unit package.

5.1.1.1.1 Size 1. Twelve splints shall be neatly stacked and packaged in a box conforming to PPP-B-676. Closure shall be as specified in the appendix of the box specification.

5.1.1.1.2 Size 2. Each splint shall be wrapped in kraft paper or other suitable material. The wrap shall be secured with tape or by other suitable means.

5.1.1.2 Intermediate package. Ten unit packages containing size 1 splints or twenty-five packages containing size 2 splints shall be packaged in a box conforming to PPP-B-636, class domestic. Closure shall be as specified in the appendix of the box specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:52Z
Check the source to verify that this is the current version before use.

5.1.2 Level C. Splints shall be clean, dry and packaged in a manner that will afford adequate protection against deterioration and physical damage during shipment from the supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Level A. Two intermediate packages containing size 1 or size 2 splints shall be packed in an exterior container designed for a size 2 load and conforming to PPP-B-636, class weather-resistant. Closure, banding and waterproofing shall be as specified in the appendix of the box specification.

5.2.2 Level B. Splints shall be packed as specified in 5.2.1, except that the exterior container shall conform to PPP-B-636, class domestic. In addition, waterproofing and banding shall not be required.

5.2.3 Level C. The packaged splints shall be packed in shipping containers that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the applicable carrier's rules and regulations.

5.3 Marking. Each unit package, intermediate and exterior container shall be marked in accordance with Fed. Std. No. 123 for civil agencies or MIL-STD-129 for military agencies.

6. NOTES

6.1 Intended use. The splints covered by this specification are intended to hold injured or fractured limbs in place.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents.

(a) Title, number and date of this specification.
(b) Size required (see 1.2).
(c) Selection of applicable level of packaging and packing required (see 5.1 and 5.2).
(d) Applicable NSN.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:52Z
Check the source to verify that this is the current version before use.

6.3 National stock number. This specification covers the following items appearing in the Federal Supply Catalog:

National Stock Number	Item Identification
6515-00-372-1200	SPLINT,WOOD, 18 by 4 by 3/16 inch, 12s
6515-00-372-1310	SPLINT, WOOD, 6 feet by 4 inches by 3/16 inch

MILITARY CUSTODIANS:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
DLA-DM

Civil Agency Coordinating Activitie
HEW - FDA, HSM
VA - DMS

Project No. 6515-2040

Orders for this publication are to be placed with the General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 35 each.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:52Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

GG-S-621C - SPLINT, WOOD

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

☆ GPO 1974—603-680/6126 2-1

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:52Z
Check the source to verify that this is the current version before use.

Photofluorographic Medical Film

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 South 20th Street
Philadelphia, PA 19101

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY
DoD • 304

U.S.MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:52Z
Check the source to verify that this is the current version before use.