FED. SUP CLASS
6850

| PART NUMBER | SPECIFICATION | PACKAGING |
|---|---|---|
| MS36424-1 | P-C-444 Type I | 1 gal can |
| MS36424-2 | P-C-444 Type I | 55 gal drum |
| MS36424-3 | P-C-444 Type II | 1 gal can |
| MS36424-4 | P-C-444 Type II | 5 gal pail |
| MS36424-5 | P-C-444 Type II | 55 gal drum |

TYPE I - Nonphenolic
TYPE II - Phenolic - 15 percent by volume min of phenolic material
- 25 percent by volume max of phenolic material

SAFETY PRECAUTIONS: Type I compound will have an irritating action on contact with the skin and eyes; therefore, rubber gloves and goggles are recommended to be worn by personnel using the compound.
Type II
POISON! DANGER! HAZARDOUS LIQUID
RAPIDLY ABSORBED THROUGH SKIN
CAUSES SEVERE BURNS

Do not get in eyes, on skin, on clothing. Avoid breathing vapor. Do not take internally. In case of contact, immediately remove all contaminated clothing, including shoes, and flush skin or eyes with plenty of water for at least 15 minutes; for eyes, get medical attention. Wash clothing before re-use.

INTENDED USE: TYPE I - For general cleaning of painted as well as unpainted surfaces and parts.
TYPE II - For heavy-duty cleaning of unpainted surfaces.

MATERIAL: Liquid, concentrated.

REQUIREMENTS: Qualification required. When compounded, ingredients shall form solvent emulsion type grease cleaning compounds. The Type II compound shall contain not more than 3 percent by weight of phenol ($C_6H_5OH$). The compounds shall not contain free alkali. Minimum flash point, 110 degrees Fahrenheit; maximum pour point, 35 degrees Fahrenheit.

DIRECTIONS FOR USE: Compound is normally used in concentrations ranging from 1 part compound and 9 parts mineral spirits to 1 part compound and 4 part mineral spirits by volume depending upon the degree of soil. Solutions may be applied by rag, spray or immersion followed by thorough rinsing with clear water immediately after application. Compound will generally remove hard and soft film corrosion preventive coatings and should not be used on parts thus protected unless removal of such coatings is desired.

NOTES:
1. TYPE II compound should be used with extreme caution on rubber, plastics, decals and painted surfaces as the compound will soften these if allowed to remain on the surface too long.
2. Referenced documents shall be of the issue in effect on date of invitations for bid.

REVIEWER: GL MD MI MR PS
USER: MO SM

APPROVED 12 March 1965 REVISED

This standard approved by the Munitions Command Department of the Army and is mandatory for use by the activity. All other military activities are required to employ this standard where suitable.

| P.A. MU | TITLE | MILITARY STANDARD |
|---|---|---|
| Other Cust | CLEANING COMPOUND, SOLVENT grease emulsifying | MS36424(MU) |
| Procurement Specification P-C-444 | SUPERSEDES: | SHEET 1 OF 1 |

DD FORM 1 SEP 57 672 (Limited coordination) PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T17:40Z
Check the source to verify that this is the current version before use.