A-A-53714
23 September 1988

COMMERCIAL ITEM DESCRIPTION

WAX, DENTAL (Casting)

The General Services Administration has authorized the use of this commercial item description as a replacement for Federal Specification U-W-00140A which is cancelled.

This commercial item description covers three classes of casting dental wax.

Salient characteristics:

General. The three classes of casting dental wax shall be:

Class 1 28-gage sheet.
Class 2 30-gage sheet.
Class 3 Assortment.

The casting wax shall be suitable for use in preparation of dental patterns and as a relief wax when duplicating casts in the dental laboratory.

Class 1. The 28-gage sheet casting wax shall be pink, and shall be furnished in sheets 3-1/2 ± 1/8 inches square and 0.0126 ± 0.0010 inch thick.

Class 2. The 30-gage sheet casting wax shall be green, and shall be furnished in sheets 3-1/2 ± 1/8 inches square and 0.0100 ± 0.0010 inch thick.

Class 3. The casting wax in the assortment shall be dark blue or dark green, and shall be furnished in lengths of 4 ± 1/8 inches. Shapes and gages of the wax shall be as specified in Table I. The wax shall be furnished in the assortment specified in Table I. A minimum of 330 of the ready-made shapes constitute one assortment.

AMSC N/A FSC 6520

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:23Z
Check the source to verify that this is the current version before use.

Table I. Assortment Class 3

Shape	B & S Commercial Gage *	Diameter, Inch **	Assortment Quantity ***
Round	18	0.0403	50 each
Round	14	0.0641	50 each
Round	10	0.1019	30 each
1/2 Round	14	0.0641	50 each
1/2 Round	12	0.0808	65 each
1/2 Round	8	0.1285	40 each
1/2 Round	6	0.1620	25 each
1/2 Pear	6	0.1620	20 each

* For information only.

** A tolerance of ± 10 percent in the diameter will be permitted.

*** The quantity for any one gage and shape shall be within ± 10 percent of the quantity specified in the table.

Material. Casting wax shall be a uniform mixture of waxes, resins, and hydrocarbons of the paraffin series, combined in such proportions as will result in a material possessing the characteristics specified herein.

Physical properties.

Softening point. The softening point of the wax shall be from 60.0 to 70.0°C when tested in accordance with ASTM E28.

Flow. The maximum flow of the wax at 35.0°C shall be 10.0 percent, and the minimum flow at 38.0C shall be 60 percent when tested in accordance with ANSI/ADA No.4.

Breaking Point. The wax shall not fracture, when tested as specified in test section under Breaking point.

Residue. The melted wax shall leave no solid residue in excess of 0.10 percent of the original weight of the specimen, when tested in accordance with ANSI/ADA No. 4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:23Z
Check the source to verify that this is the current version before use.

Working properties. The wax shall be pliable and readily adaptable at temperatures of 40.0 to 45.0 degrees Centrigrade (^{0}C), and shall copy accurately the surface against which it is pressed. The wax shall cool and harden quickly, shall not be brittle, and shall be easy to trim with a sharp instrument.

Separation. The class 1 and class 2 wax shall be interleaved with glazed or other paper suitable for ease of separation. Class 3 wax assortment shapes shall be suitably partitioned so that each shape has its own compartment. Each compartment shall be identified as to shape, gage, quantity and diameter.

Delivery schedule. Not more than three months shall have elapsed from date of manufacture of the wax to date of delivery to the Government.

Workmanship. The wax shall be furnished clean free of particulate matter, lumps, or particles or any other, defects which detract from its appearance or impairs its serviceability.

Unit. Package (PG). The casting dental wax shall be unit packaged as follows:

Class 1 - One package consisting of thirty-two sheets of wax, as specified, constitutes a unit.

Class 2 - One package consisting of thirty-two sheets of wax, as specified, consitutes a unit.

Class 3 - One package of assorted casting wax, as specified, constitutes a unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:23Z
Check the source to verify that this is the current version before use.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for inspection. Sampling for inspection shall be conducted in accordance with MIL-STD-105. Where feasible, the same sample shall be used for the determination of two or more characteristics. The unit of product for inspection purposes shall be one package of casting wax. Sampling for examination shall be conducted at inspection level II, AQL 2.5. Examination shall include, but shall not be limited, to the following defects.

Defects
Wax assortment shapes not separate from each other.
Wax brittle to touch.
Wax not homogeneous or uniform in appearance.
Color not as specified.

Tests. Sampling for tests to include dimensions, shall be conducted at inspection level S-1, AQL 1.0.

Breaking point. A sample of the casting wax at 23.0 $\pm$ 1.1^{0}C shall be bent for 10 seconds at a uniform rate until it is bent double, with the two halves of the specimen in contact for their entire length.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:23Z
Check the source to verify that this is the current version before use.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended, and as implemented for Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

NATIONAL STOCK NUMBER	ITEM IDENTIFICATION	CLASS
6520-00-567-2150	WAX ASSORTMENT, DENTAL, Casting Blue, Ready-made shapes, 330s	3
6520-00-567-2400	WAX, DENTAL, Casting, 32s	2
6520-00-567-3000	WAX, DENTAL, Casting, 32s	1

Ordering data. Intermediate/exterior quantities, labeling, and marking must be as specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:23Z
Check the source to verify that this is the current version before use.

A-A-53714

MILITARY INTEREST:

Custodians:

Army-MD
Navy-MS
Air Force - 03

Preparing Activity:

DoD-MB

AGENT:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

Project No. 6520-2092

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:23Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1 DOCUMENT NUMBER	2 DOCUMENT TITLE
A-A-53714	WAX, DENTAL (Casting)

3a NAME OF SUBMITTING ORGANIZATION	4 TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b ADDRESS *(Street City State ZIP Code*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*

5 PROBLEM AREAS

a Paragraph Number and Wording

b Recommended Wording

c Reason Rationale for Recommendation

6 REMARKS

7a NAME OF SUBMITTER *Last First, MI)* – Optional	b WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c MAILING ADDRESS *(Street City State ZIP Code)* – Optional	8 DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE

(FOLD ALONG THIS LINE)

(FOLD ALONG THIS LINE)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:23Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge (*DO NOT STAPLE*), and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 4956 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENC

Commander
Defense Personnel Support Center
ATTN DPSC-RSTE
2800 South 20th Street
Philadelphia, Pennsylvania 19101-8419

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:23Z
Check the source to verify that this is the current version before use.