MIL-HDBK-699B(MR)
28 February 1989
SUPERSEDING
MIL-HDBK-699A(MR)
25 February 1977

MILITARY STANDARDIZATION HANDBOOK
A GUIDE TO THE SPECIFICATIONS FOR
FLEXIBLE RUBBER PRODUCTS

AMSC N/A FSC 9320
DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-26T13:46Z
Check the source to verify that this is the current version before use.

DEPARTMENT OF DEFENSE

WASHINGTON, D.C.

MIL-HDBK-699B(MR)

A Guide to the Specifications for Flexible Rubber Products

1. This standardization handbook was developed by the Department of Defense in accordance with established procedures.

2. This publication was approved on 28 February 1989 for printing and inclusion in the Military Standardization Handbook series.

3. This handbook provides information concerning all known Federal, Military and nationally recognized technical society specifications and standards for those flexible rubber products considered to be of interest to the Department of Defense. The handbook is not intended to be referenced in purchase specifications or other contractual documents nor shall it supersede any specification requirements.

4. Every effort has been made to reflect the latest information on specifications for flexible rubber products. It is the intent to review this handbook periodically to insure its completeness and currency. Users of this document are encouraged to report any errors discovered and any recommendations for changes to U.S. Army Materials Technology Laboratory, ATTN: SLCMT-MEE, Watertown, MA 02172-0001.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

CONTENTS

	Page
FOREWORD.	1
Table I - Types of Government and Technical Society Specifications for Rubber	4
Specifications for Multipurpose Rubbers	5
Specifications for Cellular Materials	17
Specifications for Clothing and Protective Equipment	29
Specifications for Coated Fabrics	32
Specifications for Hose, Duct and Tubing	49
Specifications for Mats and Floor Coverings	72
Specifications for O-Rings	74
Specifications for Packings and Gaskets	79
Specifications for Tires, Tubes and Related Items	90
Specifications for Wire, Cable and Related Electrical Items	94
Specifications for Miscellaneous Items	112
Metric Units.	120
Abbreviations	120

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

FOREWORD

The purpose of this handbook is to provide information concerning all known Federal, Military and nationally recognized technical society specifications for flexible rubber products. Specifications from the following technical societies are included:

ASTM (American Society For Testing and Materials)
1916 Race Street, Philadelphia, PA 19103

American National Standards Institute (ANSI)
1430 Broadway, New York City, NY 10018

Society of Automotive Engineers (SAE and AMS)
400 Commonwealth Drive, Warrendale, PA 15096

The following types of information are furnished for each specification:

1. Specification number, title, and where applicable, the Federal Supply Classification (FSC) code number.

2. Whether or not a Qualified Products List (QPL) has been issued.

3. The type of rubber (natural, neoprene, butyl, etc.) from which the product is usually fabricated.

4. A brief description of the rubber product in terms of the specification requirements (tensile strength, resistance to high and low temperatures, resistance to fluids, etc.)

5. A brief description of the construction characteristics of those products which are composites of rubber and other materials. For example, the type, number and weight of the fabric plies in rubber coated fabrics.

The information provided by this handbook is designed to assist the user in answering questions similar to these:

1. Does a specification exist which described rubber O-rings suitable for use at 500°F?

2. Is there a specification for rubber hose suitable for use with gasoline and flexible at -40°F?

3. Which specification(s) describes closed cell silicone rubber sponge?

4. Is there a specification for neoprene jacketed electrical cable and does this specification provide a list of suppliers (QPL)?

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

The handbook describes seven types of specifications, as shown in Table I. Particular products are covered in the following sections of the handbook: Cellular materials, Clothing and protective equipment, Coated fabrics, Hose, duct and tubing, Mats and floor covering, O-Rings, Packings and gaskets, Tires and tubes, Wire and cable and Miscellaneous.

The general product specifications are covered in the "Multipurpose Rubbers" section of the handbook. As the word "multipurpose" implies, any one of these specifications may be used for the procurement of a variety of products. For example, under Specification MIL-R-3065, one may procure molded products, extruded shapes, calendered goods and sheet packings. The handbook lists about 60 multipurpose rubber specifications, encompassing approximately 100 different grades of rubber. Because of their broad coverage of rubber grades and product types, the multipurpose rubber specifications should prove to be very helpful to users of this handbook, especially when a search of a particular product section has failed to reveal a specification having a desired set of requirements. For example, suppose that a specification is sought for an O-ring which will be non-brittle at -40°F, which will show good strength retention after exposure in air at 212°F and which need not be oil resistant. The O-ring section of the handbook does not list such a specification. However, the multipurpose rubber section does list the desired specification, namely, MIL-R-3065 (and its accompanying document (MIL-STD-417), for Class RN or Class RS rubber. Thus, the O-ring having the desired characteristics may be procured by furnishing the supplier a dimensional drawing which cites a material reference to an appropriate rubber (class and code number) under MIL-R-3065.

It should be noted that the handbook descriptions of the specification requirements are incomplete, since in very few instances have all of the requirements of a specification been listed. The information given in the handbook is intended to guide the user to the specification(s) which best meets his needs, however, to verify the validity of his choice, the user should always obtain the selected specification(s) in order to ascertain its complete scope.

The chief criterion for determining whether or not a specification for a rubber product was to be included in the handbook was the flexibility of the product. Specifications were included only for those products which were believed to be capable of being hand flexed.

The majority of the listed specifications are for vulcanized products, however, unvulcanized products such as inner tube repair patches, retread rubber and room temperature vulcanizing (RTV) potting and encapsulating compounds are included.

Some specifications for products fabricated from materials which are commonly considered to be plastic (polyvinyl chloride), but which exhibit rubber-like properties, are included.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

Excluded from the handbook are specifications for hard rubber (ebonite) products, adhesives, coatings, sealers and tapes. Also excluded are composites in which rubber is in admixture with other ingredients, as in rubber-asbestos packings or rubber-cork gaskets. Complex items are assemblies, such as certain oxygen masks and fuel tanks have also been omitted. A large number of specifications for rubber products which were deemed to be of no interest to the Department of Defense, such as surgical operating pads, rubber bands and ice bags, were excluded.

Unless otherwise noted, the specification requirements given in the tabular sections of the handbook pertain to tests performed on the complete product.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

TABLE I - Types of government and technical society specifications for rubber.

I. Broad Multipolymer - A large number of grades of rubber compounds based on a wide variety of polymers (MIL-STD-417, ASTM D2000)

II. Limited Multipolymer - Several grades of rubber compounds based on a few types of polymers (MIL-R-6855)

III. Broad Single Polymer - Several grades of rubber compositions based on one polymer family (ZZ-R-765)

IV. Single Composition - One grade having specific properties (MIL-R-43109, AMS 3000 series)

V. Composition and Product - One or two grades of rubber compounds baded on one polymer plus an item made from that compound (MIL-R-7362, MIL-R-25897)

VI. Single Product - One item (MIL-P-5315, AMS 7000 series)

VII. Multi Product - Several classes of items (MIL-C-20696, MIL-C-13777)

WP# ID-0398A/DISC-0128A. (FOR MTL USE ONLY)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

MULTIPURPOSE RUBBERS[1]

SPECIFICATION TEST CONDITIONS				ELASTOMER SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
ENVIRONMENT AND TEST	TEMP, °F	TIME, HRS.	SPECIFICATION REQUIREMENTS					
Air, original properties	Ambient	-	T, 1000-3500 psi, E, 100-600%, H, 30-90	Natural rubber		9320	Rubber Composition, Vulcanized	MIL-STD-417[2]
Cooling medium, ASTM D746	-67	-	F_2 suffix, no cracks				General Purpose, Solid	Type R,
Cooling medium, ASTM D746	-40	-	F_1 suffix, no cracks				(Symbols and Tests)	Class RN
Air, compression set	158	22	Basic cmpd., 50% max; B suffix, 25% max					
Air, original properties	Ambient	-	T, 1000-2500 psi, E, 100-400%, H, 30-90	SBR or Butyl		9320	Rubber Composition, Vulcanized	MIL-STD-417[2]
Cooling medium, ASTM D746	-67	-	F_2 suffix, no cracks				General Purpose, Solid	Type R,
Cooling medium, ASTM D746	-40	-	F_1 suffix, no cracks				(Symbols and Tests)	Class RS
Air, oven aging	212	70	A_1 suffix, max. change T, -25%, E, -35%					
Air, original properties	Ambient	-	T,500-2000 psi, E, 100-400%; H, 40-90	Polysulfide		9320	Rubber Composition, Vulcanized	MIL-STD-417[2]
Cooling medium, ASTM D746	-67	-	F_2 suffix with H, 40-60, no cracks				General Purpose, Solid	Type S,
Cooling medium, ASTM D746	-40	-	F_1 suffix, no cracks				(Symbols and Tests)	Class SA
Air, oven aging	212	70	A_1 suffix, max. change T, -10%; E, -30%					
ASTM #3 petroleum oil	212	70	Volume change, 0 to + 10%					
Air, original properties	Ambient	-	T, 500-2000 psi; E, 100-450%; H, 40-90	Nitrile		9320	Rubber, Composition, Vulcanized	MIL-STD-417[2]
Cooling medium, ASTM D746	-67	-	F_2 suffix, no cracks				General Purpose, Solid	Type S,
Cooling medium, ASTM D746	-40	-	F_1 suffix, no cracks				(Symbols and Tests)	Class SB
Air, compression set	212	70	Basic cmpd, 60% max, B_1 suffix, 35% max					
ASTM #3 petroleum oil	212	70	Volume change, 0 to + 40%					
Air, original properties	Ambient	-	T, 500-2500 psi, E, 200-400% H, 30-90	Chloroprene		9320	Rubber Composition, Vulcanized	MIL-STD-417[2]
Cooling medium, ASTM D746	-67	-	F_2 suffix with H, 30-60, no cracks				General Purpose, Solid	Type S,
Cooling medium, ASTM D746	-40	-	F_1 suffix, no cracks				(Symbols and Tests)	Class SC
Air, compression set	158	22	50% max					
ASTM #3 petroleum oil	212	70	Volume change, 0 to + 120%					
Air, original properties	Ambient	-	T, 500-1200 psi, E, 50-500%, H, 40-80	Silicone		9320	Rubber, Composition, Vulcanized	MIL-STD-417[2]
Cooling medium, ASTM D746	-67	-	No cracks				General Purpose, Solid	Type T,
Cooling medium, ASTM D746	-103	-	F_3 suffix, no cracks				(Symbols and Tests)	Class TA
Air, oven aging	437	70	Max. change T, -50%, H, +15					
ASTM #1 petroleum oil	302	70	B_1 suffix, volume change, 0 to +20%					

[1]For those entries which cover more than one grade of rubber (for example, Class RN, MIL-STD-417, a range of property values is given (tensile strength 1000-3500 psi)).
[2]Valid for replenishment shares only. New designs should use ASTM D2000.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER SPECIFIED OR				
ENVIRONMENT AND TEST	TEMP, °F	TIME, HRS	SPECIFICATION REQUIREMENTS	COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T, 500-1500 psi, E, 100-200%, H, 40-80	Polyacrylate		9320	Rubber Composition, Vulcanized	MIL-STD-417[1]
Air, oven aging	347	70	Max. change T, -30%, E, -50%, H + 10				General Purpose, Solid	Type T,
Air, compression set	302	70	60% max				(Symbols and Tests)	Class TB
ASTM #3 petroleum oil	302	70	Volume change, 0 to +20%					
(All Grades Covered by this Document are also Covered Under MIL-STD-417 and ASTM D2000)							Elastomer Compounds for Automotive Applications	ASTM D735/[2] (SAE J14)
Air, original properties	Ambient	-	T, 700-500 psi, E, 250-125%, H, 40-80	Silicone		9320	Rubber, Silicone	ZZ-R-765
Cooling medium, ASTM D746	-103	0.05	No cracks					Classes 1a
Air, oven aging	437	70	T change, -30% max, E change, -50% max					and 1b
ASTM #1 petroleum oil	212	70	Volume change, +10 to +15					
Air, original properties	Ambient	-	T, 700-650 psi, E, 400-60%, H, 40-80	Silicone		9320	Rubber, Silicone	ZZ-R-765
Cooling medium, ASTM D746	-80	0 05	No cracks					Classes 2a
Air, oven aging	437	70	T change, -20% max, E change, -40% max					and 2b
ASTM #1 petroleum oil	302	70	Volume change, +15% max					
Air, original properties	Ambient	-	T, 800-1200 psi, E, 500-400%, H, 25-80	Silicone		9320	Rubber, Silicone	ZZ-R-765
Cooling medium, ASTM D746	-103	0.05	No cracks (for grades 25, 50 and 60)					Class 3a
Cooling medium, ASTM D746	-80	0 05	No cracks (for grade 60)					and 3b
ASTM #1 petroleum oil	302	70	Volume change, +5% max					
(Many grades available Following is a typical example)								
Air, original properties	Ambient	-	T, 2000 psi min, E, 500% min, H, 45± 5	Natural			Latex Dipped Goods and Coatings for Automotive Applications	ASTM D1746/ (SAE J19) Type LR
Air, oven aging	158	70	Min values: T, 1500 psi, E, 400%					
(Many grades available Following is a typical example)								
Air, original properties	Ambient	-	T, 1500 psi min, E, 400% min; H, 55± 5	Chloroprene			Latex Dipped Goods and Coatings for Automotive Applications	ASTM D1764 (SAE J19) Type LS, Class LSC
Air, oven aging	212	70	Min values. T, 1200 psi, E, 300%					
ASTM #2 petroleum oil	212	22	Volume change % max, Basic cmpd, 80, B_2 suffix, 50					
Air, original properties	Ambient	-	T, 500-3500 psi, E, 75-600%, H, 30-90	Natural Rubber,			Elastomeric Materials for Automotive Applications	ASTM D2000/ (SAE J200) Material AA
Cooling medium, ASTM D746	-40	-	F17 suffix, pass	SBR or				
Air, oven aging	158	70	Max change T, ± 30%, E, -50%, H, ± 15	Butyl				
Air, compression set	158	22	Basic cmpd, 50% max, B13 suffix, 25% max					

[1]Valid for replenishment shares only New designs should use ASTM D2000
[2]Document cancelled Use ASTM D2000

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T, 1000-2500 psi, E, 100-400%; H, 30-90	SBR or butyl			Elastomeric Materials for Automotive Applications Material BA	ASTM D2000 (SAE J200)
Cooling medium, ASTM D746	-40	-	F17 suffix, pass					
Air, oven aging	212	70	Max change T, ± 30%; E, -50%, H, ± 15					
Air, compression set	158	22	50% max.					
Air, original properties	Ambient	-	T, 500-3400 psi; E, 50-500%; H, 30-90	Chloroprene			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200) Material BC
Cooling Medium, ASTM D746	-40	-	F17 suffix, pass					
Air, oven aging	212	70	Max change. T, ± 30%; E, -50%; H, ± 15					
Air, compression set	212	22	Basic cmpd, 80% max, B14 suffix, 35% max.					
ASTM #3 petroleum oil	212	70	Volume change, +120% max.					
Air, original properties	Ambient	-	T, 500-2500 psi, E, 100-500%; H, 40-90	Chloroprene			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200) Material BE
Cooling medium, ASTM D746	-13	-	F15 suffix, pass					
Air, oven aging	212	70	Max, change T, ± 30%, E, -50%; H, ± 15					
Air, compression set	212	22	Basic cmpd, 40-50%, B14 suffix, 25% max.					
ASTM #3 petroleum oil	212	70	Volume change, + 80% max.					
Air, original properties	Ambient	-	T, 500-2500 psi, E, 100-350%; H, 60-80	Nitrile			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200) Material BF
Cooling medium, ASTM D746	-67	-	F19 suffix, pass					
Air, oven aging	212	70	Max change T, ± 30%; E, -50%; H, ± 15					
Air, compression set	212	22	50% max.					
ASTM #3 petroleum oil	212	70	Volume change, +60% max.					
Air, original properties	Ambient	-	T, 500-4000 psi; E, 50-450%; H, 40-90	Polyurethane			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200) Material BG
Cooling medium, ASTM D746	-40	-	F17 suffix, pass					
Air, oven aging	212	70	Max change T, ± 30%; E, -50%; H, ± 15					
Air, compression set	212	22	Basic cmpd, 50% max; B14 suffix, 25 or 50% max.					
ASTM #3 petroleum oil	212	70	Volume change, +40% max					
Air, original properties	Ambient	-	T, 500-2500 psi; E, 54-400%; H, 40-90	Polysulfide			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200) Material BK
Cooling medium, ASTM D746	-40	-	F17 suffix, pass					
Air, oven aging	212	70	Max change T, ± 30%; E, -50%; H, ± 15					
ASTM #3 petroleum oil	212	70	Volume change, 10% max.					
Isooctane	Ambient	70	Volume change, E51 suffix, ± 5%					
Air, original properties	Ambient1	-	T, 1000-2500 psi, E, 200-400%; H, 50-80	Hypalon			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200) Material CE
Cooling medium, ASTM D746	-67	-	F19 suffix, pass					
Air, oven aging	257	70	Max change: T, ± 30%, E, -50%; H, ± 15%					
ASTM #3 petroleum oil	257	70	Volume change; 80% max.					

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T, 500-2500 psi, E, 50-350%, H, 60-90	Nitrile			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200) Material CH
Cooling medium, ASTM D746	-40	-	F17 suffix, pass					
Air, oven aging	257	70	Max change. T, ± 30%; E, -50%; H, ± 15					
ASTM #3 petroleum oil	257	70	Volume change, +50% max					
Air, original properties	Ambient	-	T, 800-1200 psi, E, 100-225%; H, 40-90	Polyacrylate			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200) Material DF
Cooling medium, ASTM D746	0	-	F14 suffix, pass					
Air, oven aging	302	70	Max change. T, ± 30%; E, -50%; H, ± 15					
ASTM #3 petroleum oil	302	70	Volume change, +60% max.					
Air, original properties	Ambient	-	T, 800-1500 psi, E, 100-300%; H, 40-90	Polyacrylate			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200) Material DH
Cooling medium, ASTM D746	+14	-	F13 suffix, pass					
Air, oven aging	302	70	Max. change. T, ± 30%; E, -50%; H, ± 15					
ASTM #3 petroleum oil	302	70	% max. vol. chg. basic cmpd, +30; F36 suffix, +25					
Air, original properties	Ambient	-	T, 500-1200 psi; E, 200-500%; H, 30-70	Silicone			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200) Material FC
Cooling medium, ASTM D746	-103	-	F1-11 suffix, pass					
Air, oven aging	392	70	Max change T, ± 30%; E, -50%; H, + 15					
ASTM #3 petroleum oil	302	70	Volume change, +120% max					
Air, original properties	Ambient	-	T, 400 psi min; E, 400% min; H, 30 ± 5	Silicone			Elastomeric Materials For Automotive Applications	ASTM D2000 (SAE J200 Material FE
Cooling medium, ASTM D746	-67	-	F19 suffix, pass					
Air, oven aging	392	70	Max change T, ± 30%; E, -50%; H, ± 15					
ASTM #3 petroleum oil	302	70	Volume change, +80% max.					
Air, original properties	Ambient	-	T, 800 psi min; E, 150% min; H, 60 ± 5	Fluorosilicone			Elastomeric Materials For Automotive Applications	ASTM D2000/ (SAE J2000) Material FK
Cooling Medium, ASTM D746	-67	-	F19 suffix, pass					
Air, oven aging	392	70	Max change. T, ± 30%, E, -50%; H, ± 15					
ASTM #3 petroleum oil	302	70	Volume change, +10% max.					
Air, original properties	Ambient	-	T, 500-700 psi; E, 50-400% H, 30-80	Silicone			Elastomeric Materials For Automotive Applications	ASTM D2000/ (SAE J200) Material GE
Cooling medium, ASTM D746	-67	-	F19 suffix, pass					
Air, oven aging	437	70	Max change. T, ± 30%, E, -50%; H, ± 5					
ASTM #3 petroleum oil	302	70	Volume change, +80%					
Air, original properties	Ambient	-	T, 1000-2000 psi, E, 100-200%, H, 60-80	Fluorocarbon			Elastomeric Materials For Automotive Applications	ASTM D2000/ (SAE J200) Material HK
Cooling medium, ASTM D746	-13	-	F15 suffix, pass					
Air, oven aging	482	70	Max change T, ± 30%, E, -50%; H ± 15					
ASTM #3 petroleum oil	302	70	Volume change, +10% max					
70/30 Isooctane/toluene	Ambient	70	E61 suffix, volume change, 0 to ± 10%					

(For description of grades covered see MIL-STD-417 and ASTM D2000)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T, 1400 psi min, E, 250% min, H, 60 ± 5	Nitrile			Synthetic Rubber, Hydraulic Fluid (Petroleum Base) Resistant (55-65)	AMS 3200
Cooling medium, ASTM D746	-40	-	No cracks					
Air, oven aging	212	70	Max change. T, -10%, E, -45%; H, 0 to +15					
ASTM #3 petroleum oil	212	70	Volume change, 0 to +25%					
Air, original properties	Ambient		T, 1000 psi min, E, 300% min, H, 30± 5	Nitrile			Synthetic Rubber Dry Heat Resistant (35-45)	ASM 3201
Air, ASTM D736 bent loop	-40	5	No cracks					
Air, test tube aging	300	70	Max change: t, -60%; E, -70%; H, 0 to +20					
Air, compression set	212	70	75% max					
ASTM #3 petroleum oil	212	70	Volume change, -10 to +50%					
Air, original properties	Ambient	-	T, 1500 psi min, E, 250% min; H, 60± 5	Nitrile			Synthetic Rubber, Dry Heat Resistant (55-65)	AMS 3202
Air, ASTM D736 bent loop	-40	5	No cracks					
Air, test tube aging	300	70	Max change. T, -60%; E, -70%, H, 0 to + 20					
Air compression set	212	70	50% max.					
ASTM #3 petroleum oil	212	70	Volume change, -10 to +50%					
Air, original properties	Ambient	-	T, 1000 psi. min; E, 350% min; H, 30 ± 5	Nitrile			Synthetic Rubber, Low Temperature Resistant (25 to 35)	AMS 3204
Cooling medium, ASTM D746	-60	.2	No cracks					
Air, oven aging	212	70	Max change: T, -35%; E, -35%; H, 0 to +15					
ASTM #3 petroleum oil	158	70	Volume change, 0 to +75%					
Air, original properties	Ambient	-	T, 1200 psi. min; E, 300% min; H, 70± 5	Nitrile			Synthetic Rubber, Low Temperature Resistant (45-55)	AMS 3205
Cooling medium, ASTM D746	-55	.2	No cracks					
Air, oven aging	212	70	Max change: T, -20%; E, -40%; H, 0 to +15					
ASTM #3 petroleum oil	158	70	Volume change, 0 to +80%					
Air, original products	Ambient	-	T, 500 psi. min; E, 400% min; H, 30 ± 5	Chloroprene			Synthetic Rubber, Weather Resistant, Chloroprene Type (25 -35)	AMS 3207
Cooling medium, ASTM D746	-40	-	No cracks					
Air, oven aging	212	70	Max change: T, -25%; E, -30%; H, 0 to +15					
ASTM #3 petroleum oil	212	70	Volume change, +90 to +150%					
Air, original properties	Ambient	-	T, 1200 psi min; E, 300% min; H, 50 ± 5	Chloroprene			Synthetic Rubber, Weather Resistant, Chloroprene Type (45-55)	AMS 3208
Cooling medium, ASTM #746	-40	-	No cracks					
Air, oven aging	212	70	Max change: T, -25%; E, -40%; H, 0 to +15					
ASTM #3 petroleum oil	212	70	Volume change, +50 to +110%					
Air, original properties	Ambient	-	T, 1700 psi. min; E, 200% min; H, 70 ± 5	Chloroprene			Synthetic Rubber, Weather Resistant, Chloroprene Type (65-75)	AMS 3209
Cooling medium, ASTM #746	-40	-	No cracks					
Air, oven aging	212	70	Max change. T, -20%; E, -50%; H, 0 to +10					
ASTM #3 petroleum oil	212	70	Volume change, +40 to +100%					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS					
Air, original properties	Ambient	-	T, 1000 psi. min; E, 400% min; H, 70 ± 5	Chloroprene			Synthetic Rubber, Electrical Resistant, Chloroprene Type (65-75)	AMS 3210
Cooling medium, ASTM #746	-30	-	No cracks					
Air, oven aging	212	70	Max change: T, -35%; E, -50%; H, 0 to +10					
Electricity	Ambient	-	Dielectric value, 300 volts/mil., min.					
Air original properties	Ambient	-	T, 1700 psi, min; E, 300%; H, 60 ± 5	Nitrile			Synthetic Rubber, Aromatic Fuel REsistant (55-65)	AMS 3212
Cooling medium, ASTM D746	-10	.2	No cracks					
Air, oven aging	212	70	Max change T, -20%; E, -50%; H, 0 to +10					
Isooctane	80	24	Volume change, -5% max.					
Air, original properties	Ambient	-	T, 1500 psi. min; E, 150% min; H, 80 ± 5	Nitrile			Synthetic Rubber, Aromatic Fuel Resistant (75-85)	AMS 3213
Cooling medium, ASTM D746	-10	.2	No cracks					
Air, compression set	212	70	50% max.					
Isooctane	80	24	Volume change, -5% max.					
Air, original properties	Ambient	-	T, 1000 psi. min; E, 400% min; H, 40± 5	Nitrile			Synthetic Rubber, Aromatic Fuel Resistant (35-45)	AMS 3214
Cooling medium, ASTM D746	-20	.2	No cracks					
Air, oven aging	212	70	Max change. T, -20%; E, -50%; H, 0 to +15					
Isooctane	80	24	Volume change, -5% max.					
Air, original properties	Ambient	-	T, 1500 psi. min; E, 250% min; H, 70± 5	Nitrile			Synthetic Rubber Aromatic Fuel Resistant (65-75)	AMS 3215
Cooling medium ASTM D746	-10	.2	No cracks					
Air, oven aging	212	70	Max change. T, -20%, E, -40%; H, 0 to +10					
Isooctane	80	24	Volume change, -5% max.					
Air, original properties	Ambient	-	E, 200% min; H, 60± 5	Chloroprene			Synthetic Rubber (55-65)	AMS 3220
Air, oven aging	212	15	E, 150% min, H, 70 max.					
ASTM #1 petroleum oil	300	5	E, 150% min. H, 70 max.					
Isooctane	80	5	Volume change, 0 to +30%					
Air, original properties	Ambient	-	T, 1500 psi, min; E, 400% min; H, 50± 5	Chloroprene			Synthetic Rubber, Hot Oil Resistant, High Swell (45-55)	AMS 3222
Air, ASTM D736 bent loop	-40	5	No cracks					
Air, oven aging	212	70	Max change. T, -40%; E, -50%; H, 0 to +10					
ASTM #1 petroleum oil	300	70	Volume change, +15 to +40%					
Air, original properties	Ambient	-	T, 1200 psi, min, E, 350% min; H, 50± 5	Nitrile			Nitrile Rubber, Hot Oil and Coolant Resistant Low Swell (45-55)	AMS 3226
Air, ASTM D736 bent loop	-40	5	No cracks					
Air, oven aging	212	70	Max change. T, -40%, E, -50%; H, 0 to +10					
ASTM #3 petroleum oil	300	70	Volume change, 0 to +50%					
Ethylene glycol	300	70	Volume change, 0 to +25%					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T, 1500 psi, min; E, 300% min; H, 60± 5	Nitrile			Nitrile Rubber, Hot Oil and Coolant Resistant Low Swell (55-65)	AMS 3227
Air, ASTM D736 bent loop	-40	5	No cracks					
Air, oven aging	212	70	Max change: T, -25%; E, -40%; H, 0 to +10					
ASTM #3 petroleum oil	300	70	Volume change, 0 to +45%					
Ethylene glycol	300	70	Volume change, 0 to +25%					
Air, original properties	Ambient	-	T, 1000 psi, min; E, 250% min; H, 70 ± 5	Nitrile			Nitrile Rubber, Hot Oil and Coolant Resistant (65-75)	AMS 3228
Air, ASTM D736 bent loop	-40	5	No cracks					
Air, oven aging	212	70	Max change: T, -25%; E, -40%; H, 0 to +10					
ASTM #3 petroleum oil	300	70	Volume change, 0 to +45%					
Ethylene glycol	300	70	Volume change, 0 to +20%					
Air, original properties	Ambient	-	T, 1000 psi, min; E, 150% min; H, 80 ± 5	Nitrile			Nitrile Rubber Hot Oil Resistant, Low Swell (75-85)	AMS 3229
Air, ASTM D736	-40	5	No cracks					
Air, compression set	250	70	50% max.					
ASTM #3 petroleum oil	300	70	Volume change, 0 to +45%					
Air, original properties	Ambient	-	T, 1100 psi, in; E, 550% min; H, 40± 5	Butyl			Synthetic Rubber, Phosphate Ester Resistant, Butyl Type (35-45)	AMS 3237
Cooling medium, ASTM #746	-40	.2	No cracks					
Air, oven aging	212	70	Max change: T, -25%; E, -50%; H, 0 to + 15					
Tri-n-butyl phosphate	212	70	Volume change, 0 to +35%					
Air, original properties	Ambient	-	T, 1500 psi. min; E, 300% min; H, 70 ± 5	Butyl			Synthetic Rubber, Phosphate Ester Resistant, Butyl Type	AMS 3238
Cooling medium, ASTM #746	-40	.2	No cracks					
Air, oven aging	212	70	Max change: T, -20%; E, -40%; H, 0 to +10					
Tri-n-butyl phosphate	212	70	Volume change, 0 to +30%					
Air, original properties	Ambient	-	T, 1500 psi. min, E, 200% min; H, 90 ± 5	Butyl			Synthetic Rubber, Phosphate Ester Resistant, Butyl Type (85-95)	AMS 3239
Cooling medium, ASTM D746	-35	.2	No cracks					
Air, oven aging	212	70	Max change: T, -15%; E, -35%; H, 0 to +5					
Tri-n-butyl phosphate	212	70	Volume change, 0 to +30%					
Air, original properties	Ambient	-	T, 900 psi. min; E, 350% min; H, 40 ± 5	Chloroprene			Synthetic Rubber, Weather Resistant, Chloroprene Type (35-45)	AMS 3240
Cooling medium, ASTM D746	-40	-	No cracks					
Air, oven aging	212	70	Max change: T, -25%; E, -50%; H, 0 to +15					
ASTM #3 petroleum oil	212	70	Volume change, +60 to +120%					
Air, original properties	Ambient	-	T, 1500 psi. min; E, 250% min; H, 60 ± 5	Chloroprene			Synthetic Rubber, Weather Resistant, Chloroprene Type	AMS 3241
Cooling medium, ASTM D746	-40	-	No cracks					
Air, oven aging	212	70	Max change: T, -25%; E, -40%; H, 0 to +10					
ASTM #3 petroleum oil	212	70	Volume change, +40 to +100%					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T, 1900 psi. min; E, 150% min; H, 80 ± 5	Chloroprene			Synthetic Rubber, Weather Resistant, Chloroprene Type (75-85)	AMS 3242
Cooling medium, ASTM D746	-40	-	No cracks					
Air, oven aging	212	70	Max change: T, -20%; E, -50%; H, 0 to +10					
ASTM #3 petroleum oil	212	70	Volume change, +30 to +90%					
Air, original properties	Ambient	-	T, 900 psi. min, E, 200% min, H, 60 ± 5	Chloroprene			Synthetic Rubber, Flame Resistant, Chloroprene Type (75-85)	AMS 3243
Cooling medium, ASTM D746	-40	.2	No cracks					
Air, oven aging	250	70	Max change: T, -20%; E, -50%; H, 0 to +10					
ASTM #3 petroleum oil	212	70	Volume change, +30 to +90%					
Air, original properties	Ambient	-	T, 900psi, min; E, 200% min, H, 60 ± 5	Chloroprene			Synthetic Rubber, Flame Resistant Chloroprene Type (55-65)	AMS 3243
Cooling medium, ASTM D746	-40	.2	No cracks					
Air, oven aging	250	70	Max change. T, -30%; E, -50%, H, 0 to +20					
ASTM #3 petroleum oil	212	24	Volume change, +40 to +100%					
70/30 Isooctane/toluene	80	24	Volume change, 0 to +80%					
Air, original properties	Ambient	-	T, 1000 psi. min; E, 200%; H, 70 ± 5	Chloroprene			Synthetic Rubber, Flame Resistant, Chloroprene Type (65-75)	AMS 3244
Cooling medium, ASTM D746	-40	.2	No cracks					
Air, oven aging	250	70	Max change: T, -30%; E, -50%; H, 0 to +20					
ASTM #3 petroleum oil	212	24	Volume change, +30 to +90%					
70/30 Isooctane/toluene	80	24	Volume change, 0 to +80%					
Air, original properties	Ambient	-	T, 500 psi, min; E, 250%; H, 40 ± 5	Silicone			Silicone Rubber, General Purpose (35-45)	AMS 3301
Cooling medium, ASTM D746	-85	.2	No cracks					
Air, oven aging	450	24	Max change. T, -15%; E, -25%; H, -5 to +10					
ASTM #1 petroleum oil	350	70	Volume change, 0 to +20%					
Air, original properties	Ambient	-	T, 700 psi min, E, 200% min; H, 50 ± 5	Silicone			Silicone Rubber, General Purpose (45-55)	AMS 3302
Cooling medium, ASTM D746	-85	.2	No cracks					
Air, oven aging	450	24	Max change: T, -10%; E, -25%; H, -5 to +10					
ASTM #1 petroleum oil	350	70	Volume change, 0 to +15%					
Air, original properties	Ambient	-	T, 600 psi. min; E, 100% min; H, 60 ± 5	Silicone			Silicone Rubber, General Purpose (55-65)	AMS 3303
Cooling medium, ASTM D746	-65	.2	No cracks					
Air, oven aging	450	24	Max change T, -20%; E, -35%; H, -5 to +10					
ASTM #1 petroleum oil	350	70	Volume change, 0 to +10%					
Air, original properties	Ambient		T, 500 psi. min, E, 60% min, H, 70 ± 5	Silicone			Silicone Rubber General Purpose (65-75)	AMS 3304
Cooling medium, ASTM D746	-65	.2	No cracks					
Air, oven aging	450	24	Max change T, -10%; E, -30%, H, -5 to +10					
ASTM #1 petroleum oil	350	70	Volume change, 0 to +10%					
Air, original properties	Ambient	-	T, 500 psi min; E, 60% min; H, 80 ± 5	Silicone			Silicone Rubber, General Purpose (75-85)	AMS 3305
Cooling medium, ASTM D746	-65	.2	No cracks					
Air, oven aging	450	24	Max change. T, -15%; E, -35%, H, -5 to +10					
ASTM #1 petroleum oil	350	70	Volume change, 0 to +10%					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T, 750 psi. min, E, 150% min; H, 60 ± 5	Silicone			Silicone Rubber, Fuel and	AMS 3325
Cooling medium, ASTM D746	-80	.2	No cracks				Oil Resistant (55-65)	
Air, oven aging	450	24	Change: T, ±30%; E, ±25%; H, -5 to ± 10					
Di-2-ethylhexyl sebacate	300	48	Volume change, +15% max.					
Air, original properties	Ambient	-	T, 800 psi. min; E, 130% min; H, 50 to 65	Silicone			Silicone Rubber, Fuel and	AMS 3326
Cooling medium, ASTM D746	-80	.2	No cracks				Oil Resistant (50-65)	
Air, oven aging	450	24	Max change; T, -25%; E, -15%; H, ± 5					
SAE phosphate ester fluid 1A	158	48						
Air, original properties	Ambient	-	T, 400 psi min; E, 350% min, H, 15 to 30	Silicone			Silicone Rubber, Extreme	AMS 3332
Cooling medium, ASTM D746	-110	1	No cracks				Low Temperature Resistant	
Air, oven aging	450	24	Max change: T, -15%; E, -20%; H, -5 to +10				(15-30)	
ASTM #1 petroleum oil	350	70	Volume change, 0 to +25%					
Air, original properties	Ambient	-	T, 500 psi. min; E, 250% min; H, 40 ± 5	Silicone			Silicone Rubber, Extreme	AMS 3334
Cooling medium, ASTM D746	-100	-	No cracks				Low Temperature Resistant	
Air, oven aging	212	24	Max change: T, -10%; E, -15%; H, 0 to ±5				(35-45)	
ASTM #1 petroleum oil	212	70	Volume change, 0 to +15%					
Air, original properties	Ambient	-	T, 600 psi. min; E, 175% min; H, 50 ± 5	Silicone			Silicone Rubber, Extreme	AMS 3335
Cooling medium, ASTM D746	-100	-	No cracks				Low Temperature Resistant	
Air, oven aging	212	24	Max change: T, -10%; E, -15%; H, 0 to +5				(45-55)	
ASTM #1 petroleum oil	212	70	Volume change, 0 to +10%					
Air, original properties	Ambient	-	T, 600 psi. min; E, 150% min; H, 60 ± 5	Silicone			Silicone Rubber, Extreme	AMS 3336
Cooling medium, ASTM D746	-100	-	No cracks				Low Temperature Resistant	
Air, oven aging	212	24	Max change· T, -10%; E, -15%; H, 0 to +5				(55-65)	
ASTM #1 petroleum oil	212	70	Volume change, 0 to +10%					
Air, original properties	Ambient	-	T, 600 psi. min; E, 150% min; H, 70 ± 5	Silicone			Silicone Rubber, High and	AMS 3337
Cooling medium, ASTM D746	-110	.2	No cracks				Extreme Low Temperature	
Air, oven aging	450	24	Max change: T, -15%; E, -20%, H, -5 to +10				Resistant (65-75)	
ASTM #1 petroleum oil	350	70	Volume change, 0 to 25%					
Air, original properties	Ambient	-	T, 600 psi. min; E, 60% min, H, 80 ± 5	Silicone			Silicone Rubber, Extreme	AMS 3338
Cooling medium, ASTM D746	-100	.2	No cracks				Low Temperature Resistant	
Air, oven aging	212	24	Max. change: T, -10%, E, -15%; H, 0 to +5				(75-85)	
ASTM #1 petroleum oil	212	70	Volume change, 0 to +10%					

Source: https://assist.dla.mil -- Downloaded: 2026/10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T, 1800 psi. min; E, 500% min; H 50 ± 5	Silicone			Silicone Rubber - 1800 psi. (45-55)	AMS 3344*
Cooling medium, ASTM D746	-105	.2	No cracks					
Air, oven aging	400	70	Max change: T, -30%; E, -30%; H, 0 to +10					
ASTM #1 petroleum oil	300	70	Volume change, 0 to +15%					
Air, original properties	Ambient	-	T, 1000 psi. min, E, 450% min; H, 50 ±5	Silicone			Silicone Rubber, 1000 psi. (45-55)	AMS 3345
Cooling medium, ASTM D746	-105	.2	No cracks					
Air, oven aging	400	70	Max change. T, -40%; E, -50%; H, 0 to +15					
ASTM #1 petroleum oil	300	70	Volume change, 0 to +15%					
Air, original properties	Ambient	-	T, 1000 psi. min; E, 400% min; H, 60 ±5	Silicone			Silicone Rubber, 1000 psi. (55-65)	AMS 3346
Cooling medium, ASTM D746	-105	-	No cracks					
Air, oven aging	400	70	Max change· T, -40%; E, -50%; H, 0 to +20					
ASTM #1·petroleum oil	300	70	Volume change, 0 to +15%					
Air, original properties	Ambient	-	T, 600 psi. min, E, 175% min, H, 60 ± 5	Silicone			Silicone Rubber, Lubricating Oil and Compression Set Resistant, Electrical Grade (55-65)	AMS3356
Cooling medium, ASTM D746	-65	-	No cracks					
Air, oven aging	450	24	Max change: T, -15%; E, -20%; H, 0 to +10					
ASTM #1 petroleum oil	350	70	Volume change, 0 to +15%					
Electricity	Ambient	-	Dielectric value, 350 volts/mil., min.					
Air, original properties	Ambient	-	T, 600 psi. min; E, 150% min; H, 70 ± 5	Silicone			Silicone Rubber, Lubricating Oil and Compression Set Resistant,(65-75)	AMS 3357
Cooling medium, ASTM D746	-65	-	No cracks					
Air, oven aging	450	24	Max change: T, -15%; E, -20%; H, -5 to +10					
ASTM #1 petroleum oil	350	70	Volume change, 0 to +25%					
Air, original properties	Ambient	-	T, 100 psi min, E, 100% min; H, 30-45	Silicone			Silicone Rubber Compound Room Temperature Vulcanizing -50,000 Centipoises Viscosity (30-45)	AMS 3363
Cooling medium, ASTM D746	-67	.2	No cracks					
Air, oven aging	450	24	Max change: T, -40%; E, -10%; H, -25 to +10					
Air, compression set	212	22	35% max.					
Air, original properties	Ambient	-	T, 350 psi. min; E, 100% min; H, 40-50	Silicone			Silicone Rubber Compound Room Temperature Vulcanizing -35,000 Centipoises Viscosity (40-55)	AMS 3365
Cooling medium, ASTM D746	-67	.2	No cracks					
Air, oven aging	450	24	Max change: T, -35%; E, -25%; H, ± 10					
Air, compression set	212	22	60% max.					
Air, original properties	Ambient	-	T, 450 psi. min, E, 70% min, H, 55-70	Silicone			Silicone Rubber Compound-Room Temperature Vulcanizing -55,000 Centipoises Viscosity (55-70)	AMS 3366
Cooling medium, ASTM D746	-67	.2	No cracks					
Air, oven aging	450	24	Max change: T, 35%; E, -25%; H ± 10					
Air, compression set	212	22	60% max.					

*Non-current

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T, 700-500 psi; E, 250-125% H, 35-85	Silicone		9320	Rubber, Silicone; Low -	ZZ-R-765
Cooling medium, ASTM D746	-103	-	No cracks				and High - Temperature -	Class 1a
Air, compression set	212	22	35 to 45%				and Tear Resistant	
ASTM #1 petroleum oil	212	70	Volume change, +10 and +15%					
Air, original products	Ambient	-	T, 700-500 psi; E, 250-125%; H, 35-85	Silicone		9320	Rubber, Silicone; Low -	ZZ-R-765
Cooling medium, ASTM D746	-103	-	No cracks				and High - Temperature -	Class 1b
Air, compression set	302	70	35 to 45%				and Tear Ressitant	
ASTM #1 petroleum oil	212	70	Volume change, +10 to +15%					
Air, original properties	Ambient	-	T, 700-650 psi; E, 240-100%; H, 35-85	Silicone		9320	Rubber, Silicone; Low -	ZZ-R-765
Cooling medium, ASTM D746	-80	-	No cracks				and High - Temperature	Class 2a
Air, compression set	302	70	35 to 45%				and Tear Resistant	
ASTM #1 petroleum oil	302	70	Volume change, +15% max.					
Air, original properties	Ambient	-	T, 700-650 psi; E, 240-60%; H, 35-85	Silicone		9320	Rubber, Silicone; Low -	ZZ-R-765
Cooling medium, ASTM D746	-80	-	No cracks				and High - Temperature	Class 2b
Air, compression set	302	70	25 to 40%				and Tear Resistant	
ASTM #1 petroleum oil	302	70	Volume change, +15% max.					
Air, original properties	Ambient	-	T, 800-1200 psi; E, 500-200%; H, 20-85	Silicone		9320	Rubber, Silicone; Low -	ZZ-R-765
Cooling medium, ASTM D746	(Applicable for H. range 20-65) No cracks						and High - Temperature -	Class 3b
Cooling medium, ASTM D746	(Applicable for H. range 80 ±5) No cracks						and Tear Resistant	
Air, compression set	212	70	40% max.					
ASTM #1 petroleum oil	302	70	Volume change, +15% to +20%					
Air, original properties	Ambient	-	T, 1000-1600 psi; E, 500-200%; H, 30-80	Nitrile		9320	Rubber; Synthetic, Sheeted,	MIL-R-6855
Air, ASTM D736 bent loop	-67	5	No cracks				Molded, and Extruded	Class 1
Air, compression set	212	70	40% max.					
70/30 Isooctane/toluene	Ambient	168	Volume change, +25 to +40%					
Air, original properties	Ambient	-	T, 1500-1600 psi; E, 500-150%; H, 30-80	Chloroprene		9320	Rubber; Synthetic, Sheeted,	MIL-R-6855
Air, ASTM D736 bent loop	-67	5	No cracks				Molded, and Extruded	Class 2
Air, compression set	212	70	40 to 50%					
ASTM #1 petroleum oil	212	70	Volume change, ±10%					
Air, original properties	Ambient	-	T, 1000-1500 psi; E, 450-150%; H, 30-80	SBR		9320	Rubber; Synthetic, Sheeted,	MIL-R-6855
Air, ASTM D736 bent loop	-67	5	No cracks				Molded, and Extruded	Class 3
Air, compression set	212	70	40% max.					
Water	212	70	Volume change, 0 to +25%					

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T, 1100-1500 psi; E, 450-150%; H, 30-80	Nitrile		9320	Rubber; Synthetic, Sheeted, Molded, and Extruded	MIL-R-6855 Class 4
Air, ASTM D736 bent loop	-67	5	No cracks					
Air, compression set	212	70	50% max.					
ASTM #1 petroleum oil	212	70	Volume change, ± 10%					
Air, original properties	Ambient	-	T, 1000-1300 psi; E, 450-150%; H, 30-80	SBR		9320	Rubber, Synthetic, Sheeted, Molded, and Extruded	MIL-R-6855 Class 5
Air, ASTM D736 bent loop	-67	5	No cracks					
Air, compression set	212	70	40% max.					
Water	212	70	Volume change, 0 to +25%					
Air, original properties	Ambient	-	T, 1500 psi. min, E, 250% min, H, 70 ±5	Nitrile	Yes	9320	Rubber Sheet, Solid, Molded and Extruded Shapes, Synthetic Oil Resistant	MIL-R-7362 Type II, Comp. A
Cool. med, ASTM D1329 TR-10	-40	-	10% recovery @ 50% elongation					
Air, oven aging	275	70	Max change: T, -20%; E, -80%					
Di-2-ethylhexyl sebacate	257	70	Volume change, +2 to +15%					
Air, original properties	Ambient	-	T, 1475 psi min, E, 400% min; H, 55 ±3	SBR		9320	Synthetic Rubber Compound, Butadiene-Styrene Type, Ozone Resistant, For Low Temperature Service	MIL-S-21923
Air, ball drop test	-65	4	No breaks, cracks or ruptures					
Air, oven aging	212	70	Max change: T, ± 15%; E, -20%, H, 60					
Water	212	70	Volume change, +5%					
Ozone, 50 pphm	100	168	Crack free @ 20X magnification					
Air, original properties	Ambient	-	T, 1600 psi min; E, 125% min; H, 75 ±5	Fluorocarbon		9320	Rubber, Fluorocarbon Elastomer, High Temperature, Fluid, and Compression Set Resistant	MIL-R-83248 Type II Class 1
Air, oven aging	528	70	Max, change T -35%; E, -15, H, +10-5					
70/30 Isooctane/toluene	Ambient	70	Vol. change. 1 to +10%					
Air, original properties	Ambient	-	T, 1600 psi. min; E, 100% min; H, 90 ±5	Fluorocarbon		9320	Rubber, Fluorocarbon Elastomer, High Temperature, Fluid and Compression Set Resistant	MIL-R-83248 Type II Class 2
Air, oven aging	528	70	Max change: T, -45%; E, -20; H, +10-5					
70/30 Isooctane/toluene	Ambient	70	Vol. change: 1 to +10%					

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

CELLULAR MATERIALS

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP, °F	TIME, HRS	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, indent defl @ 25% defl.	73	0 02	Available in defl range 2 to 205 lb/50 sq in				Flexible Foams Made From Polymers or Co-polymers of Vinyl Chloride	SAE J15[1]
Air, oven aging	158	22	Deflection change, ± 20%					
Air, compression set	212	22	15% max					
Air, indent defl @ 25% defl	73	-	Available in defl range 2 to 205 lb/50 sq in	Nat and/or re-claimed and/or synthetic			Latex Foam Rubbers	SAE J17
Air, compression deflection	-40	5	Fl suffix, defl change, 75% max					
Air, oven aging	212	22	Deflection change, ± 20%					
Air, comp defl @ 25% defl	Ambient	-	Available in defl range 1/2 to 24 psi	Nat, reclaimed or synthetic			Sponge and Expanded Cellular - Rubber Products	SAE J18 Type R Grade RO
Air, compression deflection	-40	5	Fl suffix, defl. change, 25% max					
Air, oven aging	158	168	Deflection change, ± 20%					
Air, comp. defl. @ 25% defl	Ambient	-	Available in defl range 2 to 24 psi	Nat., reclaimed or synthetic			Sponge and Expanded Cellular - Rubber Products	SAE J18 Type R Grade RE
Water	80	0.05	Volume change, ± 1% max					
Air, comp defl @ 25% defl.	Ambient	-	Available in defl range 1/2 to 24 psi	Nat., reclaimed or synthetic			Sponge and Explanded Cellular - Rubber Products	SAE J18 Type S Class SB Grade SBO
Air compression deflection	-40	5	Fl suffix, defl change, 50% max.					
Air, oven aging	158	168	Deflection change, ± 20%					
ASTM #3 petroleum oil	158	22	Volume change, -25 to +10%					
Air, comp defl @ 25% defl	Ambient	-	Available in defl range 2 to 24 psi	Nat, reclaimed or synthetic			Sponge or Expanded Cellular - Rubber Products	SAE J18 Type S Class SB Grade SBE
Water	80	0 05	Volume change, +1% max					
Air, comp. defl @ 25% defl	Ambient	-	Available in defl. range 1/2 to 24 psi.	Nat, reclaimed or synthetic			Sponge or Expanded Cellular - Rubber Products	SAE J18 Type S Class SC Grade SCO
Air, compression deflection	-40	5	Fl suffix, defl. change, 50% max.					
Air, oven aging	158	168	Deflection change, ± 20%					
ASTM #3 petroleum oil	158	22	Volume change, +10 to +60%					
Air, comp defl @ 25% defl	Ambient	-	Available in defl. range 2 to 24 psi	Nat reclaimed or synthetic			Sponge and Expanded Cellular - Rubber Products	SAE J18 Type S Class SC Grade SCE
Water	80	0 05	Volume change, +1% max					
(Covered in ASTM D1752)						5330-3610	Filler, Expansion Joint, Bituminous, (Asphalt and Tar) and Nonbituminous (Performed for Concrete)	HH-F-341[2] Type II Class A

[1]Document cancelled without replacement
[2] Document cancelled Use ASTM D1752 for Type II

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS					
Air, original properties	Ambient	-	Min: D, 1.5 lb/cu ft, T, 12 psi, E, 250%	Water or fluoro-hydrocarbon blown		9330	Plastic Material, Cellular, Urethane	L-P-00386 Class 1
Air, indent. defl @ 25% defl	Ambient	-	Deflection, 10 to 20 lb/50 sq. in					
Steam, autoclave	220	3	Deflection change, -20% max.					
Flame	-	-	Self burning, 30 sec. max.					
Air, original properties	Ambient	-	Min: D, 1 5 lb/cu ft; T, 12 psi; E,250%	Water or fluoro-hydrocarbon blown		9330	Plastic Material, Cellular, Urethane	L-P-00386 Class 2
Air, indent. defl @ 25% defl	Ambient	-	Deflection, 20 to 35 lb/50 sq in					
Steam, autoclave	220	3	Deflection change, -20% max					
Flame	-	-	Self burning, 30 sec max					
Air, original properties	Ambient	-	Min D, 1 5 lb/cu ft, T, 12 psi, E,250%	Water or fluoro-hydrocarbon blown		9330	Plastic Material, Cellular, Urethane	L-P-00386 Class 3
Air, indent defl @ 25% defl	Ambient	-	Deflection, 35 to 55 lb/50 sq. in.					
Steam, autoclave	220	3	Deflection change, -20% max					
Flame	-	-	Self burning, 30 sec. max					
Air, original properties	Ambient	-	Density 5 to 8 5 lb/cu ft	Synthetic		5640	Insulation Thermal, Flexible Unicellular (Sheet & Pipe Covering)	HH-I-00573[1]
Air, thermal conductivity	-	-	K=0 30 BTU/hr/ft^2/°F/in max					
Water	Ambient	168	Volume change, +5% max.					
Air, indent defl @ 25% defl	Ambient	-	Available in defl. range 2 to 205 lb/50 sq. in	Natural or SBR, open cell, latex foam		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Type R Grades RC & RU
Air, compression deflection	-40	5	Fl suffix, defl change, 75% max					
Air, oven aging	212	22	Deflection change, ± 20%					
Air, comp. set @ 50% defl	158	22	20% max					
Air, comp. set @ 50% defl	Ambient	-	Available in defl range 1/2 to 23 psi	Natural or SBR, open cell, sponge		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Type R Grade RO
Air, comp defl	-67	5	F2 suffix, defl change, 25% max.					
Air, oven aging	158	168	Deflection change, ± 20%					
Air, comp set @ 50% defl	158	22	15% max					
Air, comp. defl @ 25% defl	Ambient	-	Available in defl. range 2-1/2 to 23 psi	Natural or SBR, closed cell		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Type R Grade RE
Water	Ambient	0 05	L Suffix, weight change, +1% max					
Air, comp defl @ 25% defl	Ambient	-	Available in defl range 1/2 to 23-1/2 psi	Nitrile, open cell, sponge and foam		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Type S Class SB Grade SBO
Air, compression deflection	-40	5	Fl suffix, defl change, 50% max					
Air, oven aging	158	168	Deflection change, ± 20%					
ASTM #3 petroleum oil	158	22	Volume change, -25 to +10%					
Air, comp. defl @ 25% defl	Ambient	-	Available in defl range 1-1/2 to 23-1/2 psi	Nitrile, closed cell		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Type S Class SB Grade SBE
Water	Ambient	0 05	L suffix, weight change, +1% max					

[1] Document cancelled Use ASTM C534

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP, °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, comp. defl @ 25% defl.	Ambient	-	Available in defl range 1/2 to 23-1/2 psi	Chloroprene, open cell, sponge and foam		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Type S Class SC Grade SCO
Air compression deflection	-40	5	F1 suffix, defl change, 50% max					
Air, oven aging	158	168	Deflection change, ± 20%					
ASTM #3 petroleum oil	158	22	Volume change, +10 to +60%					
Air, comp. defl. @ 25% defl.	Ambient	-	Available in defl range 1-1/2 to 23-1/2 psi.	Chloroprene, closed cell		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Type S Class SC Grade SCE
Water	Ambient	0.05	L suffix, weight change, +1% max					
Air, comp defl at 25% defl	Ambient	-	Available in defl. range 1-1/2 to 23-1/2 psi.	Silicone, closed cell, sponge		9320	Classification System and Tests for Cellular	MIL-STD-670 Type T
Air, compression deflection	-102	5	F3 suffix, defl. change, 25% max.				Elastomeric Materials	Grade TE
Air, heat aging	347	22	A4 suffix, defl. change, ± 25%					
Water	Ambient	0.05	L suffix, weight change, +2% max.					
Air, comp. defl. @ 25% defl	Ambient	-	Available in defl. range 1-1/2 to 23-1/2 psi	Silicone, open cell, sponge		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Type T Grade TO
Air, compression deflection	-67	5	Deflection change, ± 5%					
Air, heat aging	302	22	Deflection change, ± 5%					
Air, indent, defl @ 25% defl	Ambient	-	Available in defl range 7-36 lb/50 sq. in	Urethane, open cell, foam		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Type U Grades UC & UU
Air, compression deflection	-40	5	F1 suffix, defl change, 100% max.					
Air, compression deflection	220	3	Deflection change, 20% max.					
Air, heat aging	257	22	A2 suffix, defl. change, ± 20%					
Air, indent defl @ 25% defl.	Ambient	-	Available in defl range 2-205 lb/50 sq. in	PVC, open cell, foam		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Tyve V Grades VC & VU
Air, compression deflection	-40	5	F1 suffix, defl. change, 100% max					
Air, oven aging	212	22	Deflection change, ± 20%					
ASTM #3 petroleum oil	158	22	E suffix, Vol change, +10 to +60%					
Flame	-	-	Self extinguishing					
Air, comp. defl @ 25% defl	Ambient	-	Available in defl range 1-1/2 to 17 psi.	PVC, open cell foam		9320	Classification System and Tests for Cellular Elastomeric Materials	MIL-STD-670 Type V Grade VO
Air, compression deflection	-40	5	F1 suffix, defl change, 100% max.					
Air, indent. defl.	212	22	Defl change, ± 20%					
ASTM #3 petroleum oil	158	22	E suffix, Vol. change, +10 to +60%					
Flame	-	-	Self extinguishing					
Air, comp. defl. @ 25% defl.	Ambient	-	Available in defl. range 1/2 to 23-1/2 psi.	PVC, closed cell, foam		9320	Classification System and Tests for Cellular Elastomeric Materials	
Flame			Self extinguishing					

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Density, 0.006 to 0 015 lb/cu. in.	Natural or Syn., open cell		7210	Cushions, Chair; Sponge-Rubber and Synthetic Rubber	ZZ-C-00766 Class 1
Air, comp. defl. @ 25%	Ambient	-	Deflection, 5 psi. max.					
Oxygen, aging	158	120	No cracks or loss of properties					
Air, original properties	Ambient	-	Density, 0.006 to 0.020 lb/cu. in.	Natural or Syn., closed cell		7210	Cushions, Chair, Sponge-Rubber and Synthetic Rubber	ZZ-C-00766 Class 2
Air, comp. defl.	Ambient	-	Deflection, 5 to 9 psi					
Oxygen, aging	158	120	No cracks or loss of properties					
(Test on Elastometer only)								
Air, compression deflection	158	70	Thickness change 5-9 lb/in.^{2}	Natural or Syn.		7220	Cushion (Under lay) Carpet and Rug, Cellular Rubber	ZZ-C-00811 Types I and II Class 1
Aging, oven	158	166	-20% max. deflection change					
Compression set	158	22	-15% max.					
Air, compression deflection	158	70	Thickness change 2.5 - 5 lb/in.^{2}	Natural or Syn.		7220	Cushion (Under lay) Carpet and Rug, Cellular Rubber	ZZ-C-00811 Types I and II Class 2
Aging, oven	158	166	-20% max. deflection change					
Compression set	158	22	-17.5% max.					
Air, compression deflection	158	70	Thickness change, 1-2.5 lb/in.^{2}	Natural or Syn.		7220	Cushion (Under lay) Carpet and Rug, Cellular Rubber	ZZ-C-00811 Types I and II Class 3
Aging, oven	158	166	-20% max. def. change					
Compression set	158	22	-20% max. def/ change					
Air, compression stiffness	Ambient	-	Strain @ 40 psi., 0.75 in/in			8135	Cushioning Material, Polystyrene, Expanded, Resilient (For Packaging Uses)	PPP-C-850 Class 1 Types I and II
Air, mandrel bend	-65		No cracks, tears or separation					
Air, shrinkage	165	24	Linear change, -0.5% max.					
Water	Ambient	24	Volume change, +5% max.					
Air, compression stiffness	Ambient	-	Strain @ 40 psi. 0.71 in/in			8135	Cushioning Material, Polystyrene, Expanded, Resilient (For Packaging Uses)	PPP-C-850 Class 2 Types I and II
Air, mandrel bend	-65	-	No cracks, tears or separation					
Air, shrinkage	165	24	Linear change, -1.0% max.					
Water	Ambient	-	Volume change, +5% max.					
Air, compressive stiffness	Ambient	-	Strain @ 40 psi. 0.62 in/in			8135	Cushioning Material, Polystyrene, Expanded, Resilient (For Packaging Uses)	PPP-C-850 Class 3 Types I and II
Air, mandrel bend	-65	-	No cracks, tears of separation					
Air, shrinkage	165	24	Linear change, -1.5% max.					
Water	Ambient	24	Volume change, +5% max.					
Air, compressive stiffness	Ambient	-	Strain @ 40 psi. 0.64 in/in			8135	Cushioning Material, Polystyrene, Expanded, Resilient (For Packaging Uses)	PPP-C-850 Class 4 Types I and II
Air, mandrel bend	-65	-	No cracks, tears of separation					
Air, shrinkage	165	24	Linear change, -1.5% max.					
Water	Ambient	24	Volume change, +5% max.					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER SPECIFIED OR	QPL	FSC		SPECIFICATION
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMMONLY USED	ISSUED	CLASS	SPECIFICATION TITLE	NUMBER
(All Grades Covered in MIL-STD-670, Type R, Grades RC and RU)							Latex Foam Rubbers	ASTM D 1055
(All Grades Covered in MIL-STD-670, Type R, Grades RO, RE, and Type S)							Sponge and Expanded Cellular Rubber Products	ASTM D 1056
(All Grades Covered in MIL-STD-670, Type U)							Flexible Urethane Foam	ASTM D 1564[1]
(All Grades Covered in MIL-STD-670, Under Grades VC, VU and VO)							Flexible Foams Made From Polymers or Co-polymers of Vinyl Chloride	ASTM D 1565
(All Grades Covered in MIL-STD-670, Under Grade VE)							Sponge Made From Closed Cell Poly (Vinyl Chloride) or Copolymers Thereof	ASTM D 1667
Air, original properties	Ambient	-	Density, 40 lb/cu. ft. min.	Synthetic or			Performed Expansion Joint Fillers For Concrete Paving and Structural Construction	ASTM D 1752 Type I
Air, comp.defl. @ 50% defl.	Ambient	0.17	Available in Defl. range 50 to 1500 psi	natural sponge				
(All Grades Covered in MIL-STD-670)						9320	Cellular Elastomeric Materials, Fabricated Parts	MIL-C-3133
Air, original properties	Ambient	-	Density, 0.020 lb/cu. in. max.	Closed cell			Silicone Rubber Sponge, Medium Low Temperature	AMS 3193
Air, comp. defl. @ 25% defl.	78	-	Deflection, 6 to 14 psi.					
Air, ASTM D736	-130	5	No cracks					
Air, comp. set @ 50% defl.	212	22	60% max.					
Air, original properties	Ambient	-	Density, 0.030 lb/cu. in. max.	Closed cell			Silicone Rubber Sponge, Closed Cell, Firm, Extreme Low Temperature	AMS 3194
Air, comp. defl. @ 25% defl.	78	-	Deflection, 12-30 psi.					
Air, ASTM D736	-130	5	No cracks					
Air, comp. set @ 50% defl.	212	22	60% max.					
Air, original properties	Ambient	-	Density, 0.020 lb/cu. in. max.	Closed cell			Silicone Rubber Sponge, Closed Cell - Medium	AMS 3195
Air, comp. defl. @ 25% defl.	78	-	Deflection, 6 to 14 psi.					
Air, ASTM D736	-100	5	No cracks					
Air, comp. set @ 50% defl.	212	22	60% max.					

[1] Document cancelled. Use ASTM D3574.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Density 0.030 lb/cu. in. max.	Closed cell			Silicone Rubber Sponge, Closed Cell - Firm	AMS 3196
Air, comp. defl. @ 25% defl.	78	-	Deflection, 12 to 20 psi.					
Air, ASTM D736	-100	5	No cracks					
Air, comp. set @ 50 defl.	212	22	60% max.					
Air, comp. defl. @ 25% defl.	78	-	Deflection, 1 to 4 psi.	Open cell			Sponge, Chloroprene Rubber, Soft	AMS 3197
Air, oven aging	212	22	Deflection change, -5 to +30%					
Air, comp. defl. @ 25% defl.	78	-	Deflection, 6 to 13 psi.	Open cell			Sponge, Chloroprene Rubber, Medium	AMS 3198
Air, oven aging	212	22	Deflection change, -5 to +30%					
Air, comp defl. @ 25% defl.	78	-	Deflection, 15 to 22 psi.	Open cell			Sponge, Chloroprene Rubber, Firm	AMS 3199
Air, oven aging	212	22	Deflection change, -5 to +30%					
Air, indent. defl. @ 25% defl.	Ambient	-	Deflection, 50 to 80 lb/50 sq. in.				Flexible Polyurethane Foam, Open Cell, Medium Flexibility 2.5 lb/cu. ft.	AMS 3570
Air, compression deflection	-40	5	Thickness change, -20% max.					
Air, comp. defl. @ 25% defl.	212	48	Thickness change, -12% max.					
Flame	-	-	Self extinguishing in 3 sec.					
Air, original properties	Ambient	-	Density, 8.5 lb/cu. ft.				Plastic Sheet - Cellular, Shock Absorbing, (Closed Cell, Foamed Modified Vinyl Sheet)	AMS 3635
Air, comp. defl. @ 25% defl.	77	-	Deflection, 5 psi.					
Air, oven aging	160	168	No loss of properties					
Flame	-	-	Self burning 5 sec. max.					
(All Grades Covered in MIL-STD-670)				Natural or SBR sponge		5340	Bumpers, Rubber, Duplex Round	MIL-B-4792 Type I
(All Grades Covered in MIL-R-6130 Type II, Grade A Med.)				Chloroprene		5340	Bumpers, Rubber, Duplex Round	MIL-B-4792 Type II
Air, original properties	Ambient	-	Available in density range 0.0050 to 0.0069 lb/cu. in./in.	Chloroprene, open cell	Yes	9320	Rubber; Latex Foam Sponge	MIL-R-5001 Type I Grade A
Air, indent. defl.	Ambient	-	Available in defl. range to 10 to 55 psi.					
Air, oven aging	212	70	Deflection change, ± 15%					
Flame	-	-	Self burning, 50 sec. max.					
Air, original properties	Ambient	-	Available in density range 0.0039 to 0.0058 lb/cu. in./in.	SBR, open cell	Yes	9320	Rubber, Latex Foam Sponge	MIL-R-5001 Type I Grade B
Air, indent. defl. @ 25% defl	Ambient	-	Available in defl. range 10 to 55 psi.					
Air, oven aging	212	70	Deflection change, ± 15%					

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Available in density range 0 0039 to 0.0058 lb/cu in./in.	Natural, open cell	Yes	9320	Rubber, Latex Foam Sponge	MIL-R-5001 Type I Grade C
Air, indent. defl @ 25% defl	Ambient	-	Available in defl range 10 to 55 psi.					
Air, oven aging	212	70	Deflection change, ± 15%					
Air, original properties	Ambient	-	Available in density range 0.0060 to 0 0120 lb/cu in	Chloroprene, open cell	Yes	9320	Rubber, Latex Foam Sponge	MIL-R-5001 Type II Grade A
Air, indent defl @ 25% defl	Ambient	-	Available in defl. range 0.20 to 1/70 psi.					
Air, indentation deflection	-40	5	Deflection change, -70% max					
Air, oven aging	212	70	Deflection change, ± 15%					
Flame	-	-	Self burning, 50 sec. max.					
Air, original properties	Ambient	-	Available in density range 0.0045 to 0.0075 lb/cu. in	SBR, open cell	Yes	9320	Rubber, Latex Foam Sponge	MIL-R-5001 Type II Grade B
Air, indent. defl. @ 25% defl.	Ambient	-	Available in defl. range 0.20 to 1.70 psi.					
Air, indentation deflection	-40	5	Deflection change, -60% max.					
Air, oven aging	212	70	Deflection change, ± 15%					
Air, original properties	Ambient	-	Available in density range 0.0045 to 0 0075 lb/cu. in	Natural, open cell	Yes	9320	Rubber, Latex Foam Sponge	MIL-R-5001 Type II Grade C
Air, indent defl. @ 25% defl.	Ambient	-	Available in defl. range 0.20 to 1 70 psi.					
Air, indentation deflection	-40	5	Deflection change, -25% max					
Air, oven aging	212	70	Deflection change, ± 15%					
Air, comp defl @ 25% defl	Ambient	-	Available in defl. range 2 to 21 psi.	Chloroprene, open cell	Yes	9320	Rubber, Cellular, Chemically Blown	MIL-R-6130 Type I Grade A
Air, compression deflection	-42	5	Deflection change, -70% max					
Air, oven aging	212	70	Deflection change, -45 to +45%					
ASTM #2 petroleum oil	158	70	Volume change, -15 to +30%					
Air, comp defl @ 25% defl	Ambient	-	Available in defl range 2 to 21 psi.	SBR, open cell cell	Yes	9320	Rubber, Cellular, Chemically Blown	MIL-R-6130 Type I Grade B
Air, compression deflection	-42	5	Deflection change, -70% max					
Air, oven aging	212	70	Deflection change, -45 to +45%					
Air, compl defl @ 25% defl	Ambient	-	Available in defl range 2 to 21 psi	Natural, open cell	Yes	9320	Rubber, Cellular, Chemically brown	MIL-R-6130 Type I Grade C
Air, compression deflection	-67	5	Deflection change, -55% max.					
Air, oven aging	212	70	Deflection change, -45 to +45%					
Air, compl. defl. @ 25% defl	Ambient	-	Available in defl range 2 to 21 psi.	Chloroprene, closed cell	Yes	9320	Rubber, Cellular, Chemically brown	MIL-R-6130 Type II Grade A
Air, compression deflection	-24	5	Deflection change, -70% max					
Air, oven aging	212	70	Deflection change, -30 to +30%	ASTM #2 petroleum oil	158	70	Volume change, -15 to +30%	
Water	75	22	Weight change, +5% max.					

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	ELASTOMER SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, compl. defl. @ 25% defl.	Ambient	-	Available in defl. range 2 to 21 psi.	SBR, closed cell closed cell	Yes	9320	Rubber, Cellular, Chemically brown	MIL-R-6130 Type II Grade B
Air, compression deflection	-24	5	Deflection change, -70% max.					
Air, oven aging	212	70	Deflection change, -30 to +30%					
Water	75	22	Weight change, +5% max.					
Air, compl defl. @ 25% defl	Ambient	-	Available in defl. range 2 to 21 psi.	Natural, closed cell	Yes	9320	Rubber, Cellular, Chemically brown	MIL-R-6130 Type II Grade C
Air, compression deflection	-67	5	Deflection change, -55% max.					
Air, oven aging	212	70	Deflection change, -30 to +30%					
Water	75	22	Weight change, +5% max.					
Air, original properties	Ambient	-	Tensile, 185 to 450 psi	Urethane	Yes	9330	Core Material, Foamed - In-Place, Urethane	MIL-C-8087 Type I Class 1
Air, oven aging	165	0.5	Tensile change, -30% max.					
Electricity	Ambient	-	Dielectric constant, 1.26 to 1.51					
Air, 100% relative humidity	100	240	Weight change, +1.8 to +6.5%					
Air, original properties	Ambient	-	Tensile, 185 to 450 psi.	Urethane	Yes	9330	Core Material, Foamed - In-Place, Urethane	MIL-C-8087 Type I Class 2
Air, oven aging	165	0.5	Tensile change, -30% max.					
Air, 100% relative humidity	100	240	Weight change, +1.8 to +6.5%					
Air, original properties	Ambient	-	Tensile, 130 to 330 psi.	Urethane	Yes	9330	Core Material, Foamed - In-Place, Urethane	MIL-C-8087 Type II Class 1
Air, oven aging	350	0.5	Tensile change, -30% max.					
Electricity	Ambient	-	Dielectric constant, 1.26 to 1.51					
Air, 100% relative humidity	100	240	Weight change, +1 8 to +6.5%					
Air, original properties	Ambient	-	Tensile, 130 to 330 psi	Urethane	Yes	9330	Core Material, Foamed - In-Place, Urethane	MIL-C-8087 Type II Class 2
Air, oven aging	350	0.5	Tensile change, -30% max					
Air, 100% relative humidity	100	240	Weight change, +1 8 to +6.5%					
(All Grades Covered in MIL-STD-670, Grades RE or RO)				Natural or SBR, closed cell		2040	Fenders, Marine, Rubber-Filled	MIL-F-11435
Air, original properties	Ambient	-	T, 60 psi. min, E, 50% min, D, 7 lb/cu ft.	Vinyl, Nitrile or other rubber		9330	Plastic Material	MIL-P-12420 Type I Class 1
Air, compression set	Ambient	22	12% max.					
Air, oven aging	200	96	T, 60 psi. min; E, 50% min					
Water	Ambient	48	Weight change, 50% max.					
Air, original properties	Ambient	-	T, 80 psi min; E, 100% min, D, 7 lb/ft.^{3}	Vinyl, Nitrile or other rubber		9330	Plastic Material Cellular, Elastomeric	MIL-P-12420 Type I Class 2
Air, compression set	Ambient	22	20% max.					
Air, oven aging	200	96	T, 80 psi. min; E, 100% min.					
Water	Ambient	48	Weight change, 50% max.					

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS					
Air, original properties	Ambient	-	T, 90 psi. min; E, 100% min; D, 7 lb/ft ^{3}	Vinyl, Nitrile or other rubber		9330	Plastic Material Cellular, Elastomeric	MIL-P-12420 Type I Class 3
Air, compression set	Ambient	22	30% max.					
Air, oven aging	200	96	T, 90 psi. min; E, 100% min.					
Water	Ambient	48	Weight change, 50% max					
Air, original properties	Ambient	-	T, 30 psi. min; E, 150% min, D, 5 lb/ft^3	Vinyl, Nitrile or other rubber		9330	Plastic Material Cellular Elastomeric	MIL-P-12420 Type II Class 4
Air, mandrel bend	-40	-	No breaking, cracking or bending					
Air, oven aging	200	96	T, 30 psi. min; E, 150% min.					
Water	Ambient	48	Weight change, 60% max.					
Air, original properties	Ambient	-	T, 50 psi. min; E, 200% min; D, 6 lb/ft^3	Vinyl, Nitrile or other rubber		9330	Plastic Material Cellular Elastomeric	MIL-P-12420 Type II Class 5
Air, mandrel bend	-40	-	No breaking, cracking or bending					
Air, oven aging	200	96	T, 50 psi. min; E, 150% min.					
Water	Ambient	48	Weight change, 50% max.					
Air, original properties	Ambient	-	T, 100 psi. min; E, 200%, min. D, 10 lb/ft^3	Vinyl, Nitrile or other rubber		9330	Plastic Material Cellular Elastomeric	MIL-P-12420 Type III
Air, oven aging	200	96	T, 100 psi. min; E, 150% min.					
Water	Ambient	48	Weight change, 50% max.					
(Covered in MIL-STD-670 RE)				SBR closed cell		2590	Pads Cushioning; Personnel - Protection, Vehicular	MIL-P-14401 Class CS
(Covered in MIL-STD-670 RE)				PVC closed cell		2590	Pads Cushioning; Personnel - Protection, Vehicular	MIL-P-14401 Class VS
(Covered in MIL-R-17252, Type II, Class 1)				Natural or chloroprene		2590	Pads Cushioning; Personnel - Protection, Vehicular	MIL-P-14401 Class FR
Air, comp. defl. @ 25% defl.	Ambient	-	Deflection, 2.0 to 3.5 psi.	Closed cell		5970	Insulation Sheet, Cellular Plastic; Thermal	MIL-I-4511
Air, 180° bend	-65	-	No cracks					
Water	-	24	Weight change, +2% max.					
Flame	-	-	Self extinguishing					
Air, comp. defl. @ 25% defl.	Ambient	-	Deflection, 2.0 to 6.0 psi.			9330	Plastic Material, Unicellular (sheet & tube)	MIL-P-15280 Form T
Air, oven aging	180	168	No cracking					
Fuel oil	Ambient	70	No softening or swelling					
Compression set			24% max.					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, comp. defl. @ 25% defl	Ambient	-	Deflection, 3 to 6 psi			9330	Plastic Material, Unicellular (sheet & tube)	MIL-P15280 Form S
Air, mandrel bend	28	4	No cracking					
Fuel oil	Ambient	70	No softening or swelling					
Compression set	Ambient	-	24% max.					
Air, comp. defl. @ 25% defl.	70	-	Deflection, 2 psi.	Closed cell		5640	Insulation, Synthetic, Rubber-Like, Chemically Expanded, Cellular (Sheet Form)	MIL-I-16562
Air, 180° bend	-50	-	No cracking					
Air, oven aging	140	168	Volume change, ± 5% max.					
Petroleum oil	212	70	No swelling or softening					
Flame	-	-	Self burning, 2 sec. max.					
Air, comp. defl. @ 25% defl.	80	-	Available in defl. range 0.10 to 1 70 psi.	Natural, open cell		9320	Rubber, Cellular (Bonded Shredded)	MIL-R-17252[1] Class 1 Types I & II
Air, compression deflection	-20	5	Deflection change, -70% max.					
Air, heat aging @ 60 psi.	260	2	No hardening or softening					
Flame	-	-	Self burning, 30 sec. max.					
Air, comp defl. @ 25% defl	80	-	Available in defl. range 0.10 to 1.70 psi.	Natural, open cell		9320	Rubber, Cellular (Bonded Shredded)	MIL-R-17252[1] Class 2 Types I & II
Air, compression deflection	-20	5	Deflection change, -70% max.					
Air, heat aging @ 60 psi.	260	2	No hardening or softening					
Air, original properties	Ambient	-	Density, 5.5 lb/cu. ft. max.	Polychloroprene		7210	Mattresses, Berth, Synthetic Sponge	MIL-M-18351
Air, oven aging	212	70	Deflection change 20% max Rubber, Naval Shipboard					
Air, original properties	80	-	Available in density range 5.5 to 8 1 PCF	Chloroprene		9320	Rubber Sheets and Molded Shapes, Cellular, Synthetic, Open Cell (Foamed Latex)	MIL-R-20092 Type 1 Class 1
Air, comp. defl. @ 25% defl.	70	-	Available in defl. range 5 to 55 psi.					
Air, oven aging	212	70	Deflection change, 15% max.					
Flame	-	-	Self burning, 30 sec. max.					
Air, original properties	80	-	Available in density range 5.5 to 8.1 PCF	Chloroprene		9320	Rubber Sheets and Molded Shapes, Cellular, Synthetic, Open Cell (Foamed Latex)	MIL-R-20092 Type 1 Class 4
Air, comp. defl. @ 25% defl	70	-	Available in defl range 5 to 55 psi.					
Air, oven aging	212	70	Deflection change, 15% max					
Fire resistance	-	2	Flame 10 sec. max					
Air, original properties	Ambient	-	Available in density range 10-4 to 19 0 PCF	Chloroprene		9320	Rubber Sheets and Molded Shapes, Cellular, Synthetic, Open Cell (Foamed Latex)	MIL-R-20092 Type II Class 1
Air, comp. defl.	70	-	Available in defl. range 0 20 to 1 70 psi					
Air, compression deflection	-20	5	Deflection range, -70% max					
Air, oven aging	212	70	Deflection Change, 15% max.					

[1] Document cancelled. No replacement

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, comp. defl. @ 25% defl.	70	-	Available in defl. range 0.20 to 1.70 psi.	Chloroprene		9320	Rubber Sheets and Molded Shapes, Cellular, Synthetic, Open Cell (Foamed Latex)	MIL-R-20092 Type II Class 4
Air, compression deflection	-20	5	Deflection change, -70% max.					
Air, oven aging	212	70	Deflection change, 15% max.					
Fire resistance	-	2	Flame 10 sec. max.					
Air, 95% rel. humid. @ 60% strain	120	336	Stress change, ± 10%	Urethane		8135	Polyurethane Foam, Rigid or Flexible, For Packaging	MIL-P-26514 Class 1
Air, comp. set @ 20% strain	Ambient	4	+10% max.	Urethane		8135	Polyurethane Foam, Rigid or Flexible, For Packaging	MIL-P-26514 Class2
Air, 180° bend	-65	4	No cracks, tears or separations					
Air, 95% rel. humid	120	336	Stress change, ± 10% max.					
Air, original properties	Ambient	-	Available in density range 2 to 12 lb/cu. ft.	Not known		8135	Cushioning Material, Elastic Type, General	MIL-C-26861
Air, compression set	Ambient	4	15% max.					
Air, 95% rel. humid	120	336	Stress change, ± 10%					
Air, original properties	Ambient	-	T, 15 psi, E, 200%; D, 2 lb/ft.^{3}	Polyether poly-urethane, open cell		1660	Seat Cushion Insert, Polyurethane Foam, Plastic, General Specification For	MIL-S-27332
Air, compression set	158	22	15% max.					
Air, oven aging	212	3	Weight change, 2% max.					
Autoclave humidity	220	3	Thickness change, -15% max.					
Air, original properties	Ambient	-	T, 800 to 1150 psi; E, 100 to 350%	Fluorosilicone		5330	Rubber Fluorosilicone Elastomer, Oil & Fuel Resistant, Sheets, Strips & Molded Parts & Extruded Shapes	MIL-R-25988 Type II
Air, compression set	75	70	15% max.					
(Covered in MIL-R-5001)				Natural, open cell		7210	Mattress, Bed: Foam - Rubber, Ambulance Stretcher	MIL-M-40024
Air, original properties	Ambient	-	Density, 2.0 lb/cu. ft.	Closed cell		9330	Plastic Foam Insulation, Thermal	MIL-P-43110[1] Class 1
Water	Ambient	24	Weight change, 0.06 lb/cu. ft.					
Flame	-	-	Self extinguishing					

[1] Document cancelled. Use MIL-P-21929 or HH-I-530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties Water Flame	Ambient Ambient -	- - -	Density, 4 ro 10 lb/cu. ft. Weight change, 0.06 lb/cu. ft. Self extinguishing	Closed cell		9330	Plastic Foam Insulation, Thermal	MIL-P-43110[1] Class 2
Air, tensile strength Air, ASTM D736 Water	Ambient -100 Ambient	- 2 24	40 psi. min. No cracks 5% absorption, max.	Closed cell silicone		9320	Rubber, Sponge, Silicone Closed Cell	MIL-R-46089
Air, density Air, load deflection @ 3 psi.	Ambient Ambient	- -	10+ 1 pounds per cubic foot 0.043 max.	Silicone		9320	Silicone, Foam, Low-Density, Room Temperature Vulcanizing	MIL-S-46090[2]

[1] Document cancelled. Use MIL-P-21929 or HH-I-530.
[2] Document cancelled. No replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

CLOTHING AND PROTECTIVE EQUIPMENT

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties Air, oven aging Air, breakdown voltage	Ambient 158 Ambient	- 168 -	T,2500 psi min; E, 600% min. Change in T and E, -25% max. 20,000 to 30,000 volts, depending on class	Type of rubber not specified			Rubber Insulating Gloves	ASTM D120
Air, hardness Air, oven aging	Ambient 212	- 24	Cl, 1,2&3, 60 to 75; Cl 5&6, 45 to 60 Hardness increase, 10 points max.	Natural or synthetic		8335	Heels; Rubber	ZZ-H-141 Classes 1, 2, 3, 5, and 6
Air, tensile strength Air, 3/4 ft. lb. impact Oxygen, bomb aging Sulfuric acid (15%)	Ambient -20 158 75	- - 70 46	Body, 1600 psi min; cuff, 1700 psi min No cracks Tensile strength, 1500 psi min Tensile strength, 1500 psi min	Type of rubber not specified		8415	Gloves, Rubber, Industrial	ZZ-G-381 Type I
Air, tensile strength Oxygen, bomb aging Isooctane/toluene, 70/30	Ambient 158 Ambient	- 70 70	Body, 1600 psi min; cuff, 1700 psi min Tensile strength, 1500 psi min Tensile strength, 1000 psi min	Type of rubber not specified		8415	Gloves, Rubber, Industrial	ZZ-G-381 Type II
Air, tensile strength Oxygen, bomb aging Organic solvent mixture	Ambient 158 Ambient	- 70 16	Body, 1600 psi min; cuff, 1700 psi min Tensile strength, 1500 psi min Tensile strength, 1500 psi min	Type of rubber not specified		8415	Gloves, Rubber, Industrial	ZZ-G-381 Type III
Air, original properties Air, oven aging	Ambient 158	- 168	T,2500 psi min; E,700% min T and E change, -20% max	Natural		8415	Gloves; Rubber (For) Electrical Workers (For Use in Connection With Apparatus or Circuits Not Exceeding 3000 Volts to Ground	ZZ-G-401
Air, tensile strength Oxygen, bomb aging @ 300 psi Oxygen, bomb aging @ 300 psi	Ambient 158 158	- 96 06	Gr A,4000 psi min; Gr B,3000 psi min Grade A, change in T, -25% max Grade B, change in T, -25% ,max	Natural		6515	Gloves, Rubber: Surgeons'	ZZ-G-421
(Tests on rubber only) Air, original properties Air, oven aging	Ambient 212	- 16	T,1450 psi min, E,350% min Change in T and E, -25% max	Natural or synthetic rubber, cotton cloth		8430	Overshoe, Rubber (Man's 5 Buckle Type)	MIL-O-836
Air, original properties Air, tension set Air, dielectric breakdown	Ambient Ambient Ambient	- - 0.05	T,1600 psi min; E,350% min 7% max No breakdown @20,000 volts	Natural or synthetic			Rubber Insulator Hoods (Proof Test 20,000 Volts, 3 minutes)	ASTM #1049

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER SPECIFIED OR	QPL	FSC		SPECIFICATION
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMMONLY USED	ISSUED	CLASS	SPECIFICATION TITLE	NUMBER
Air, original properties	Ambient	-	T,2600 psi min; E, 650% min	Natural		4240	Faceblanks, Field Protective Mask, Natural Rubber; General Specification	MIL-F-10135
Air, tear strength	Ambient	-	165 pounds per inch, min					
Air, oven aging	158	168	Max change T, -15%; E, -25%					
Air, original properties	Ambient	-	T,3000 psi min; E, 600% min	Natural		4240	Faceblanks, Field Protective Mask	MIL-F-0010135 (MU)
Air, tear strength	Ambient	-	300 pounds per inch, min					
Air, oven aging	158	168	Max change T-32%, E-30%					
Air, original properties	Ambient	-	T,1100 psi min, E, 400% min	Butyl		8415	Gloves Toxicological Agents, Protective	MIL-G-12223
Air, 0.75 ft. lb. impact	-20	1	No cracks					
Air, oven aging	212	48	T,1000 psi min; E, 350% min					
Liquid mustard, penetration	100	-	Min. time for penetration, 300 minutes					
Air, original properties	Ambient	-	T,1000 psi min; E, 400% min, H, 50 ± 5	Type of rubber not specified		1660	Mask, Oxygen and Smoke, Full Face	MIL-M-19417
Air, oven aging	212	72	Change in T and E, -15% max					
Air, compression set	212	72	35% max					
Ozone, 1000 pphm	100	1	No cracks under 10X magnification					
(Tests on rubber only)								
Air, original properties	Ambient	-	Hardness, 45± 5 tear, 150 lbs/in min	Silicone	Yes	1660	Mask, Oxygen, MBU-5/p	MIL-M-27274
Air, original properties	Ambient	-	Hardness, 72 to 85	Natural or synthetic		8335	Soles, Rubber, Shoe	MIL-S-40043 Classes 1, 2 and 5
Air, oven aging	212	24	Hardness, 72 to 90					
Air, original properties	Ambient	-	Hardness, 72 to 85	Synthetic rubber		8335	Soles, Rubber, Shoe	MIL-S-40043 Classes 3, 4 and 6
Air, oven aging	212	24	Hardness, 72 to 90					
Isooctane/toluene, 70/30	74	46	Volume change, +60 max					
(Tests on rubber only)								
Air, original properties	Ambient	-	T,2500 psi min; E, 500% min	Type of rubber not specified		8430	Boots, Insultated, Cold Weather, Rubber (Wet-Cold, Dry-Cold)	MIL-B-41816
Cooling medium, ASTM D1053	-40	0.08	Type I, Young's modulus 10,000 psi max					
Cooling medium, ASTM D1053	212	16	Change in T and E, -25% max					
Air, original properties	Ambient	-	T,3000 psi min; E, 600% min	Natural		4240	Faceblank, C17	MIL-F-50070
Air, flexibility	-25	72	5 fold increase in stiffness, max					
Air, oven aging	158	168	T,2550 psi min, E, 450% min					
Air, original properties	Ambient	-	T,3000 psi min, E, 600-700% min	Natural		4240	Faceblank, Protective Mask, C12R4	MIL-F-51109
Air, flexibility	-25	72	5 fold increase					
Air, oven aging	158	168	T,2550 psi min; E, 400% min					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T,1500 psi min, E, 400% min, H, 55 ± 5	EPDM Silicone, Tube and gaskets		4240	Rubber Fabricated Products for M171A1 Mask	MIL-R-51283
Compression set	155	22	25% max					
Low temp impact	-67		pass					
Air, original properties	Ambient	-	T,3500 psi min; E, 750% min	Natural		8415	Gloves, Radioactive Contaminants Protective	MIL-G-82242
Air, oven aging	158	72	T,2800 psi min, E, 600% min					
Water	158	46	T,2100 psi min; E, 600% max					
Water	158	46	Volume change, +15% max					
(Tests on rubber only)								
Air, original properties	Ambient	-	T,1200 psi min; E, 600% min	Flannel coated with chloroprene		8415	Gloves, Cloth, Vinyl Dipped, General Purpose	MIL-G-82253 Type I
Air, oven aged	194	22	T,1000 psi min; E, 500% min					
Water	194	22	Max change: T, -25%; E, -15%					
(Tests on PVC only)								
Air, original properties	Ambient	-	T,700 psi min; E, 350% min	Flannel coated with PVC		8415	Gloves, Cloth, Vinyl Dipped, General Purpose	MIL-G-82253 Type II
Air, oven aged	194	22	T,600 psi min; E, 300% min					
Water	194	22	Max change: T, -25%; E, -15%					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS			SPECIFICATION	CONSTRUCTION			QPL	FSC		SPECIFICATION
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD²	THICK, INCH	ISSUED	CLASS	SPECIFICATION TITLE	NUMBER
Air, original properties Air, low temperature set Air, low temperature elong. Air, oven aging	Ambient -25 -40 300	- 72 2 2	Permanent set, 8% max Permanent set, 35% max Elongation, 10% min Permanent set, 20% max	Cotton yarn and natural or synthetic rubber strands				8305	Webbing, Textile, (Cotton, Elastic)	JJ-W-155
Air, inflation @ 3 psi	Ambient	0.08	No leakage	Cotton sheet coated with natural, SBR, chloroprene or butyl				7210	Pillows; Air, Rubber and Synthetic Rubber	ZZ-P-351[1]
Air, breaking strength Oxygen, bomb aging @ 300 psi Ethyl alcohol	Ambient 158 Ambient	- 240 2	55 to 65 pounds, min No softening or stiffening No stickiness or hardening	Natural, synthetic or PVC coated fabric				7210	Blankets; Rubber and Synthetic-Resin	ZZ-B-426[1]
Air, breaking strength Air, oven aging Steam, sterilization	Ambient 158 250	- 166 0.3	Warp, 50 lbs; Fill, 50 lbs No deterioration No deterioration	Nat. or syn. Cotton or syn. Nat. or syn. Composite		 0.015		8305	Cloth, Coated (Rubber and Plastic) and Plastic Sheeting for Hospital Use	ZZ-C-450 Type I
Air, breaking strength Steam, sterilization	Ambient 250	- 0.3	Warp, 50 lbs; Fill, 50 lbs No deterioration	PVC Cotton or syn. PVC Composite		 0.015		8305	Cloth, Coated (Rubber and Plastic) and Plastic Sheeting for Hospital Use	ZZ-C-450 Type II
Air, tearing strength (For other properties see L-P-375)	Ambient	-	200 lbs/inch of thickness, min	PVC sheeting				8305	Cloth, Coated (Rubber and Plastic) and Plastic Sheeting Per Hospital Use	ZZ-C-450 Type III
Air, breaking strength	Ambient	-	Warp, 50 lbs; Fill, 40 lbs	Cotton Cell, nitrate Composite	4.8 1.5 6.3				Cloth, Coated: Pyroxylin Coated	CCC-C-501[1] Type I, Class 1
Air, breaking strength	Ambient	-	Warp, 40 lbs; Fill, 35 lbs	Cotton Cell, nitrate Composite	2.7 5.0 7.7			8305	Cloth, Coated: Proxylin Coated	CCC-C-501[1] Type I Class 2
Air, breaking strength	Ambient	-	Warp, 85 lbs; Fill, 75 lbs	Cotton Cell, nitrate Composite	8.2 3.8 12.0			8305	Cloth, Coated. Pyroxylin Coated	CCC-C-501[1] Type I, Class 3

[1] Document cancelled without replacement

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, breaking strength	Ambient	-	Warp, 110 lbs; Fill, 100 lbs	Cell, nitrate	3.65			8305	Cloth, Coated:	CCC-C-501[1]
				Cotton	8.20				Pyroxylin Coated	Type II,
				Cell, nitrate	3.65					Class 1
				Composite	15.50					
MIL-F-16884, Diesel Oil	73	22	No delamination	Cotton	8.0			8305	Cloth, Duck, Cotton,	MIL-C-882
MIL-F-16884, Diesel Oil	73	46	Volume change, 25% Max.	Chloroprene					Synthetic Rubber	Class I
Culture, mildew resistant	84	336	No fungus growth	Multilayer Laminate		1/4- 1			Impregnated and Laminated, Oil Resistant	
MIL-F-16884, Diesel Oil	73	22	No delamination	Cotton	8.0			8305	Cloth, Duck, Cotton,	MIL-C-882
MIL-F-16884, Diesel Oil	73	46	Volume change, 25% Max.	Nitrile					Synthetic Rubber	Class II
Culture, mildew resistant	84	336	No fungus growth	Multilayer Laminate		1/4- 1			Impregnated and Laminated, Oil Resistant	
Air, breaking through	Ambient	-	Warp, 70 lbs	Silicone Glass Silicone Composite	1.43 4.80	0.002 0.005			Fully Cured Silicone Rubber-Coated Glass Fabric and Tapes for Electrical Insulation	ASTM D 1931
Air, breaking strength	Ambient	-	Warp, 125 lbs	Silicone Glass Silicone Composite	3.16 7.68	0.004 0.007			Fully Cured Silicone Rubber-Coated Glass Fabric and Tapes for Electrical Insulation	ASTM D 1931
Air, breaking strength	Ambient	-	Warp, 125 lbs	Silicone Glass Silicone Composite	3.16 10.88	0.004 0.010			Fully Cured Silicone Rubber-Coated Glass Fabric and Tapes for Electrical Insulation	ASTM D 1931
Air, breaking strength	Ambient	-	Warp, 250 lbs	Silicone Glass Silicone Composite	6.00 14.40	 0.015			Fully Cured Silicone Rubber-Coated Glass Fabric and Tapes for Electrical Insulation	ASTM D 1931
Air, breaking strength	Ambient	-	Warp, 55 lbs min; Fill, 45 lbs min	Cotton cloth coated with synthetic rubber				8340	Tarpaulins, Waterproof, Special Purpose, 10 Feet Long By 8 Feet Wide	MIL-T-1956
Air, burst test	Ambient	-	25 psi min							
Air, burst test	-20	0.5	25 psi min							
Air, breaking strength	Ambient	-	Warp, 40 lbs; Fill, 40 lbs	Chloroprene Cotton Chloroprene Composite	8.0	0.008			Synthetic Rubber Sheet, Cotton Fabric Reinforced. Weather Resistant - Chloroprene Type	AMS 3270
Air, ASTM D746	-20	0.167	No cracks							
Air, oven aging	212	70	Flexible, no deterioration							
Isooctane	80	70	Vol. change, +20% Max.							
ASTM #3 petroleum oil	212	70	Vol. change, +20% to +65%							

[1] Document cancelled without replacement

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, breaking strength	Ambient	-	Warp, 37 lbs; Fill, 19 lbs	Chloroprene	1.87				Synthetic Rubber Sheet,	AMS 3270
Air, ASTM D746	-20	0.167	No cracks	Cotton	6.25				Cotton Fabric Rein-	
Air, oven aging	212	70	Flexible, no deterioration	Chloroprene	1.87				forced. Weather Re-	
Isooctane	80	70	Vol change, +20% Max.	Composite	9.99	0.010			sistant - Chloroprene	
ASTM #3 petroleum oil	212	70	Vol. change, +20% to +65%						Type	
Air, breaking strength	Ambient	-	Warp, 90 lbs; Fill, 90 lbs	Chloroprene					Synthetic Rubber Sheet,	AMS 3270
Air, ASTM D746	-20	0.167	No cracks	Cotton					Cotton Fabric Rein-	
Air, oven aging	212	70	Flexible, no deterioration	Chloroprene					forced. Weather Re-	
Isooctane	80	70	Vol. change, +20% Max.	Composite	27.0	0.025			sistant - Chloroprene	
ASTM #3 petroleum oil	212	70	Vol. change, +20% to +65%						Type	
Air, breaking strength	Ambient	-	Warp, 250 lbs; Fill, 170 lbs	Chloroprene					Synthetic Rubber Sheet,	AMS 3270
Air, ASTM D746	-20	0.167	No cracks	Cotton					Cotton Fabric Rein-	
Air, oven aging	212	70	Flexible, no deterioration	Chloroprene					forced. Weather Re-	
Isooctane	80	70	Vol. change, +20% Max.	Composite	35.0	0.035			sistant - Chloroprene	
ASTM #3 petroleum oil	212	70	Vol change, +20% to +65%						Type	
Air, breaking strength	Ambient	-	Warp, 250 lbs; Fill, 170 lbs	Chloroprene					Synthetic Rubber Sheet,	AMS 3270
Air, ASTM D746	-20	0 167	No cracks	Cotton					Cotton Fabric Rein-	
Air, oven aging	212	70	Flexible, no deterioration	Chloroprene					forced Weather Re-	
Isooctane	80	70	Vol. change, +20% Max.	Composite	54.0	0.050			sistant - Chloroprene	
ASTM #3 petroleum oil	212	70	Vol. change, +20% to +65%						Type	
Air, breaking strength	Ambient	-	Warp, 35 lbs; Fill, 35 lbs	Chloroprene					Synthetic Rubber Sheet,	AMS 3273
Air, ASTM D746	-65	0.167	No cracks	Nylon					Nylon Fabric Rein-	
Air, oven aging	212	70	No deterioration	Chloroprene					forced. Weather Re-	
Isooctane	80	70	Vol. change, -5% to +20%	Composite		0.008			sistant - Chloroprene	
ASTM #3 petroleum oil	212	70	Vol. change, +20% to +65%						Type	
Air, breaking strength	Ambient	-	Warp, 65 lbs, Fill, 60 lbs	Chloroprene					Synthetic Rubber Sheet,	AMS 3273
Air, ASTM D746	-65	0.167	No cracks	Nylon					Nylon Fabric Rein-	
Air, oven aging	212	70	No deterioration	Chloroprene					forced. Weather Re-	
Isooctane	80	70	Vol. change, -5% to +20%	Composite		0.010-			sistant - Chloroprene	
ASTM #3 petroleum oil	212	70	Vol. change, +20% to +65%			0.025			Type	
Air, breaking strength	Ambient	-	Warp, 300 lbs, Fill, 300 lbs	Chloroprene					Synthetic Rubber Sheets,	AMS 3273
Air, ASTM D746	-65	0.167	No cracks	Nylon					Nylon Fabric Rein-	
Air, oven aging	212	70	No deterioration	Chloroprene					forced. Weather Re-	
Isooctane	80	70	Vol. change, -5% to +20%	Composite		0 030-			sistant - Chloroprene	
ASTM #3 petroleum oil	212	70	Vol. change, +20% to +65%			0.050			Type	
Air, breaking strength	Ambient	-	Warp, 35 lbs; Fill, 35 lbs	Nitrile					Synthetic Rubber Sheet,	AMS 3274
Air, ASTM D746	-65	0 167	No cracks	Nylon					Nylon Fabric Rein-	
Air, oven aging	212	70	No deterioration	Nitrile					forced. Aromatic	
Isooctane	80	24	Vol change, -20% to +10%	Composite		0.008			Fuel Resistant	
70/30 isooctane/toluene	80	24	Vol. change, +35% Max							

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, breaking strength	Ambient	-	Warp, 65 lbs, Fill, 60 lbs	Nitrile					Synthetic Rubber Sheet,	AMS 3274
Air, ASTM D746	-65	0.167	No cracks	Nylon					Nylon Fabric Rein-	
Air, oven aging	212	70	No deterioration	Nitrile					forced. Aromatic	
Isooctane	80	24	Vol change, -25 to 0%	Composite		0 010-			Fuel Resistant	
70/30 isooctane/toluene	80	24	Vol change, +35% Max.			0.017				
Air, breaking strength	Ambient	-	Warp, 65 lbs; Fill, 60 lbs	Nitrile					Synthetic Rubber Sheet,	AMS 3274
Air, ASTM D746	-65	0.167	No cracks	Nylon					Nylon Fabric Rein-	
Air, oven aging	212	70	No deterioration	Nitrile					forced. Aromatic	
Isooctane	80	24	Vol. change, -25 to 0%	Composite		0.020+			Fuel Resistant	
70/30 isooctane/toluene	80	24	Vol. change, +40% Max			0.030				
Air, breaking strength	Ambient	-	Warp, 300 lbs, Fill, 300 lbs	Nitrile					Synthetic Rubber Sheet,	AMS 3274
Air, ASTM D746	-65	0.167	No cracks	Nylon					Nylon Fabric Rein-	
Air, oven aging	212	70	No deterioration	Nitrile					forced. Aromatic	
Isooctane	80	24	Vol change, -25 to 0%	Composite		0.025+			Fuel Resistant	
70/30 isooctane/toluene	80	24	Vol. change, +40% Max.			0.050				
Air, breaking strength	Ambient	-	Warp, 70 lbs; Fill, 70 lbs	Silicone					Silicone Rubber Sheet,	AMS 3315
Air, ASTM D736	-70	5	No cracks	Glass	3.16	0.004			Glass Fabric Rein-	
Air, oven aging	450	24	No deterioration	Silicone					forced	
ASTM #1 petroleum oil	350	70	Volume change, +10% Max.	Composite		0.010				
Air, breaking strength	Ambient	-	Warp, 200 lbs, Fill, 150 lbs	Silicone					Silicone Rubber Sheet,	AMS 3315
Air, ASTM D736	-70	5	No cracks	Glass	6.00	0.007			Glass Fabric Rein-	
Air, oven aging	450	24	No deterioration	Silicone					forced	
ASTM #1 petroleum oil	350	70	Volume change, +10% Max.	Composite		0.017				
Air, breaking strength	Ambient	-	Warp, 400 lbs; Fill, 300 lbs	Silicone					Silicone Rubber Sheet,	AMS 3315
Air, ASTM D736	-70	5	No cracks	Glass	12.4	0.015			Glass Fabric Rein-	
Air, oven aging	450	24	No deterioration	Silicone					forced	
ASTM #1 petroleum oil	350	70	Volume change, +10% Max.	Composite		0.032				
Air, breaking strength	Ambient	-	Warp, 800 lbs; Fill, 600 lbs	Silicone					Silicone Rubber Sheet,	AMS 3315
Air, ASTM D736	-70	5	No cracks	Glass	25.9	0.027			Glass Fabric Rein-	
Air, oven aging	450	24	No deterioration	Silicone					forced	
ASTM #1 petroleum oil	350	70	Volume change, +10% Max.	Composite		0.050				
Air, breaking strength	Ambient	-	Warp, 300 lbs; Fill, 300 lbs	Silicone					Silicone Rubber Sheet,	AMS 3320
Air, ASTM D736	-70	5	No cracks	Glass	25.9	0.027			Glass Fabric Rein-	
Air, oven aging	450	24	180° bend, no cracks	Silicone					forced. Heat and	
ASTM #1 petroleum oil	350	70	Volume change, +10% Max.	Composite		1/16- 1/8			Weather Resistant (60-80)	

Source: https://assist.dla.mil -- Downloaded: 2026/0-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, breaking strength	Ambient	-	Warp, 125 lbs; Fill, 100 lbs	PVC	0.85				Fabric, Glass, Vinyl	AMS 3663
Air, mandrel bend	-65	5	No cracks or delamination	Glass	2.80				Coated, Porous	
Air, oven aging	200	24	No deterioration	PVC	0.85					
Flame	-	-	Flame, 1 sec. Max.	Composite	4.50	0.004				
Air, breaking strength	Ambient	-	Warp, 160 lbs, Fill, 150 lbs	PVC	1 03				Fabric, Glass, Vinyl	AMS 3663
Air, mandrel bend	-65	5	No cracks or delamination	Glass	3.93	0.005			Coated, Porous	
Air, oven aging	200	24	No deterioration	PVC	1.03					
Flame	-	-	Flame, 1 sec. Max.	Composite	5.99	0.006				
Air, breaking strength	Ambient	-	Warp, 225 lbs; Fill, 150 lbs	PVC	0.81				Fabric, Glass, Vinyl	AMS 3663
Air, mandrel bend	-65	5	No cracks or delamination	Glass	5.37	0.006			Coated, Porous	
Air, oven aging	200	24	No deterioration	PVC	0.81					
Flame	-	-	Flame, 1 sec. Max.	Composite	6.99	0.008				
Air, breaking strength	Ambient	-	Warp, 70 lbs; Fill, 40 lbs	PVC	1.53				Fabric, Glass, Vinyl	AMS 3664
Air, mandrel bend	-65	5	No cracks or delamination	Glass	1.43	0.0020			Coated	
Air, oven aging	200	24	No deterioration	PVC	1.53					
Flame	-	-	Flame, 1 sec. Max.	Composite	4 49	0.0045				
Air, breaking strength	Ambient	-	Warp, 125 lbs; Fill, 100 lbs	PVC	1.10				Fabric, Glass, Vinyl	AMS 3664
Air, mandrel bend	-65	5	No cracks or delamination	Glass	2.80	0.004			Coated	
Air, oven aging	200	24	No deterioration	PVC	1.10					
Flame	-	-	Flame, 1 sec. Max.	Composite	5.00	0.005				
Air, breaking strength	Ambient	-	Warp, 190 lbs; Fill, 140 lbs	PVC	1.97				Fabric, Glass, Vinyl	AMS 3664
Air, mandrel bend	-65	5	No cracks or delamination	Glass	4 06	0.005			Coated	
Air, oven aging	200	24	No deterioration	PVC	1.97					
Flame	-	-	Flame, 1 sec. Max.	Composite	8 00	0.007				
Air, breaking strength	Ambient	-	Warp, 225 lbs; Fill, 195 lbs	PVC	2.81				Fabric, Glass, Vinyl	AMS 3664
Air, mandrel bend	-65	5	No cracks or delamination	Glass	5.37	0.0065			Coated	
Air, oven aging	200	24	No deterioration	PVC	2.81					
Flame	-	-	Flame, 1 sec. Max.	Composite	10.99	0.011				
Air, breaking strength	Ambient	-	Warp, 215 lbs; Fill, 120 lbs	Chloroprene	21.5			8305	Cloth, Coated, Asbestos	MIL-C-7637
Air, creased 180°	-20	0.5	No cracks or flaking	Asbestos	29.0					Type I
Air, mandrel bend	260	24	No cracks	Chloroprene	21.5					
Flame	-	-	No flame, no glow	Composite	72.0	0.070				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, breaking strength	Ambient	-	Warp, 165 lbs; Fill, 150 lbs	Chloroprene	23.0			8305	Cloth, Coated, Asbestos	MIL-C-7637
Air, creased 180°	-20	0.5	No cracks or flaking	Asb. and wire	30.0					Type II
Air, mandrel bend	260	24	No cracks	Chloroprene	23.0					
Flame	-	-	No flame, no glow	Composite	76.0	0.070				
Air, breaking strength	Ambient	-	Warp, 50 lbs; Fill, 50 lbs	Nylon	1.1	0.0032	Yes	8305	Cloth, Coated, Rubber	MIL-C-7966
Air, creased 180°	-65	0.5	No cracking or flaking	Nat. or syn.	1.9				Nylon Base	Variety S
Air, blocking	200	0.5	No blocking	Composite	3.0					
Air, breaking strength	Ambient	-	Warp, 200 lbs; Fill, 150 lbs	Nylon	3.50		Yes	8305	Cloth, Coated, Rubber	MIL-C-7966
Air, creased 180°	-65	0.5	No cracking or flaking	Nat. or syn.	3.25				Nylon Base	Variety P
Air, blocking	200	0.5	No blocking	Composite	6.75					
Air, Mullen burst	Ambient	-	125 points	Syn. rubber				8305	Cloth, Coated, Nylon	MIL-C-8068
Air, mandrel bend	-67	24	Flexible	Nylon	1.6	0.0042			Rubber Coated, Fuel-	Type I
Air, oven aging	212	70	No deterioration	Syn. Rubber					Resistant	
Isooctane	75	70	Mullen burst, 125 pts.	Composite		0.010-				
70/30 isooctane/toluene	75	70	Mullen burst, 125 pts.			0.020				
Air, Mullen burst	Ambient	-	500 points	Syn. rubber				8305	Cloth, Coated, Nylon	MIL-C-8068
70/30 isooctane/toluene	-65	24	Flexible	Nylon	5.5	0.013			Rubber Coated, Fuel-	Type II
Air, oven aging	212	70	No deterioration	Syn. Rubber					Resistant	
Isooctane	75	70	Mullen burst, 500 pts.	Composite		0.025+				
70/30 isooctane/toluene	75	70	Mullen burst, 500 pts.							
Air, Mullen burst	Ambient	-	125 points	Syn. rubber				8305	Cloth, Coated, Nylon	MIL-C-8068
Air, mandrel bend	-67	24	Flexible	Nylon	1.6	0.0042			Rubber Coated, Fuel-	Type III
Air, oven aging	212	70	No deterioration	Syn. Rubber					Resistant	(uncured)
Isooctane	75	70	Mullen burst, 125 pts.	Composite		0.012-				
70/30 isooctane/toluene	75	70	Mullen burst, 125 pts.			0.018				
Air, breaking strength	Ambient	-	Warp, 190 lbs; Fill, 140 lbs	Cotton	6.5			8305	Cloth, laminated,	MIL-C-9074
Air, creased 180°	-40	0.5	No cracks	Nat. or syn.	10.5				Sateen, Rubberized	
Oxygen, accelerated aging	158	192	Brk. strength, 15% loss Max.	Cotton	6.5					
				Composite	23.5					
Air, breaking strength	Ambient	-	Warp, 90 lbs; Fill, 90 lbs	Nat. or syn.				8305	Cloth, laminated and	MIL-C-10351
Air, cantilever stiffness	-65	0.5	Flexible	Nylon	1.6				Coated for Waterproof	Type I
Air, blocking	180	0.5	No blocking	Nat. or syn.					Containers	
Weatherometer, break, strength	135	100	Warp, 70 lbs; Fill, 70 lbs	Nylon	1.6					
				Nat. or syn.						
				Composite	9.3					

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, breaking strength	Ambient	-	Warp, 180 lbs; Fill, 170 lbs	Nat. or syn				8305	Cloth, laminated and	MIL-C-10351
Air, cantilever stiffness	-65	0.5	Flexible	Nylon	3.0				Coated for Waterproof	Type II
Air, blocking	180	0.5	No blocking	Nat. or syn.					Containers	
Weatherometer, break, strength	135	100	Warp, 160 lbs, Fill, 150 lbs	Nylon	3.0					
				Nat. or syn.						
				Composite	12.5					
(Tests on coated fabric)										
Air, breaking strength	Ambient	-	Warp, 72 lbs min; Fill,	Nylon cloth				8465	Mattress, Pneumatic	MIL-M-10747[1]
			52 lbs	coated with						
Air, 180° crease	-70	5	No cracks	natural or						
Air, burst test @ 40 psi	Ambient	-	No leakage	synthetic						
				rubber						
Air, breaking strength	Ambient	-	Warp, 140 lbs; Fill, 120 lbs	Silicone	6.0			8305	Cloth, Coated, Glass,	MIL-C-10797
Air, cantilever stiffness	-60	4	Flexible	Glass	6.0	0 007			Silicone Rubber	
Air, cantilever stiffness	600	4	Flexible	Silicone	6.0				Coated	
Flame	-	-	Flame, 13 sec Max.	Composite	18.0					
Air, breaking strength	Ambient	-	Warp, 80 lbs; Fill, 80 lbs	PVC				8305	Cloth, Coated, Cotton	MIL-C-10799
Air, mandrel bend	-40	4	No cracking or flaking	Cotton	4.5				Vinyl Coated, Fire and	Type I,
Air, blocking	180	0.5	No blocking	PVC					Mildew Resistant	Class 1
TT-S-735, 40% aromatic	Ambient	2	Creased 180°, no cracks	Composite	7.8					
Air, breaking strength	Ambient	-	Warp, 130 lbs; Fill, 75 lbs	PVC				8305	Cloth, Coated, Cotton	MIL-C-10799
Air, mandrel bend	-40	4	No cracking or flaking	Cotton	4.5				Vinyl Coated, Fire and	Type I,
Air, blocking	180	0.5	No blocking	PVC					Mildew Resistant	Class 3
TT-S-735, 40% aromatic	Ambient	2	Creased 180°, no cracks	Composite	10.0					
Air, breaking strength	Ambient	-	Warp, 160 lbs; Fill, 110 lbs	PVC				8305	Cloth, Coated, Cotton	MIL-C-10799
Air, mandrel bend	-40	4	No cracking or flaking	Cotton	9 85				Vinyl Coated, Fire and	Type II,
Air, blocking	180	0.5	Slight blocking	PVC					Mildew Resistant	Class 1
TT-S-735, 40% aromatic	Ambient	2	Creased 180°, no cracks	Composite	14.50					
Air, breaking strength	Ambient	-	Warp, 125 lbs, Fill, 120 lbs	PVC				8305	Cloth, Coated, Cotton	MIL-C-10799
Air, mandrel bend	-40	4	No cracking or flaking	Cotton	8.25				Vinyl Coated, Fire and	Type II,
Air, blocking	180	0.5	Slight blocking	PVC					Mildew Resistant	Class 3
TT-S-735, 40% aromatic	Ambient	2	Creased 180°, no cracks	Composite	12 00					
Air, breaking strength	Ambient	-	Warp, 210 lbs; Fill, 130 lbs	PVC				8305	Cloth, Coated, Cotton	MIL-C-10799
Air, mandrel bend	-40	4	No cracking or flaking	Cotton	12 29				Vinyl Coated, Fire and	Type II,
Air, blocking	180	0.5	Slight blocking	PVC					Mildew Resistant	Class 4
TT-S-735, 40% aromatic	Ambient	2	Creased 180°, no cracks	Composite	18.00					

[1] Document cancelled Use MIL-M-43968

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, breaking strength	Ambient	-	Warp, 235 lbs; Fill, 175 lbs	PVC				8305	Cloth, Coated, Cotton	MIL-C-10799
Air, mandrel bend	-40	4	No cracking or flaking	Cotton	14.77				Vinyl Coated, Fire and	Type II
Air, blocking	180	0.5	Slight blocking	PVC					Mildew Resistant	Class 5
TT-S-735, 40% aromatic	Ambient	2	Creased 180°, no cracks	Composite	22.00					
Air, breaking strength	Ambient	-	Warp, 80 lbs, Fill, 75 lbs	Chloroprene	2 5			8305	Cloth, Laminated:	MIL-C-11390
Weatherometer, break. strength	135	200	Loss 10% Max	Cotton	2.0				Cotton Balloon, 3 Ply, Air Retaining, Chloro-	
				Chloroprene	3.5				prene	
				Cotton bias	2.0					
				Chloroprene	3.5					
				Cotton	2.0					
				Chloroprene	3.0					
				Composite	18.5					
Air, breaking strength	Ambient	-	Warp, 180 lbs; Fill, 170 lbs	Butyl	11.0			8305	Cloth, Coated, Butyl	MIL-C-12189
Air, creased 180°	-40	4	Flexible	Cotton	4.25				Coated, Toxicological	
Air, blocking	180	0.5	No blocking	Butyl	2.80				Agents, Protective	
Weatherometer, break, strength	155	100	Warp, 170 lbs, Fill, 160 lbs	Composite	12.25					
Mustard gas (liquid)	100	-	100 M to indicator change							
Air, breaking strength	Ambient	-	Warp, 225 lbs; Fill, 195 lbs	PVC	2.75			8305	Cloth, Glass, Vinyl	MIL-C-12526[1]
Air, creased 180°	-40	4	No cracking or flaking	Glass	5.37	0.0065			Coated, Acid and	
Air, blocking	180	0 5	Slight blocking	PVC	8.00				Fuel Resistant	
Red fuming nitric acid	Ambient	0.05	No cracking or stiffening	Composite	16.12					
Air, breaking strength	Ambient	-	Warp, 50 lbs; Fill, 50 lbs	Nylon	1.5			8305	Cloth, Coated, Nylon,	MIL-C-14366
Air, cantilever stiffness	30	4	Flexible	Butyral	2.0					
Air, blocking	200	0.5	No blocking	Composite	3.5					
Air, breaking strength	Ambient	-	Warp, 153 lbs; Fill, 135 lbs	Chloroprene	1.20			8305	Cloth, Nylon, Poly-	MIL-C-14505
Air, creased 180°	-20	96	No cracks	Nylon	3.15				chloroprene Coated (For	Class 3
Air, oven aging	158	96	Break. strength, 15% loss Max.	Chloroprene	1.20				Pneumatic Floating Equipment)	Schedule B (vulcanized)
				Composite	5.55					
Air, breaking strength	Ambient	-	Warp, 350 lbs; Fill, 335 lbs	Chloroprene		0.010		8305	Cloth, Nylon, Poly-	MIL-C-14505
Air, creased 180°	-20	96	No cracks	Nylon	5.8				chloroprene Coated (For	Class 4
Air, oven aging	158	96	Break. strength, 15% loss Max.	Chloroprene		0.010			Pneumatic Floating Equipment)	(vulcanized)
Air, breaking strength	Ambient	-	Warp, 400 lbs; Fill, 400 lbs	Chloroprene		0.014		8305	Cloth, Nylon, Poly-	MIL-C-14505
Air, creased 180°	-20	96	No cracks	Nylon	8.5	0.020			chloroprene Coated (For	Class 6
Air, oven aging	158	96	Break. strength, 15% loss Max	Chloroprene		0.014			Pneumatic Floating Equipment)	(vulcanized)
				Composite		0.048				
Air, breaking strength	Ambient	-	Warp, 650 lbs, Fill, 650 lbs	Chloroprene		0.020		8305	Cloth, Nylon, Poly-	MIL-C-14505
Air, creased 180°	-20	96	No cracks	Nylon	13.3	0.029			chloroprene Coated (For	Class 7
Air, oven aging	158	96	Brk. strength, 15% loss Max.	Chloroprene		0.020			Pneumatic Floating Equipment)	(vulcanized)
				Composite		0.069				

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS			SPECIFICATION	CONSTRUCTION			QPL	FSC		SPECIFICATION
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT Oz/YD^2	THICK, INCH	ISSUED	CLASS	SPECIFICATION TITLE	NUMBER
Air, breaking strength	Ambient	-	Warp, 140 lbs; Fill, 120 lbs	Not known				8305	Cloth, Coated, Fire	MIL-C-15104
Air, creased 180°	0	2	No cracks	Cotton					Resistant, Berth and	Type I
Air, oven aging	158	168	Brk. strength, 25% loss Max.	Not known					Bedding Cover	
				Composite	25.0					
Air, breaking strength	Ambient	-	Warp, 135 lbs; Fill, 100 lbs	Not known				8305	Cloth, Coated, Fire	MIL-C-15104
Air, creased 180°	0	2	No cracks	Cotton					Resistant, Berth and	Type II
Air, oven aging	158	168	Brk. strength, 25% loss Max.	Not known					Bedding Cover	
				Composite	16.9					
Air, breaking strength	Ambient	-	Warp, 50 lbs; Fill, 50 lbs	Chloroprene	1.5			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Nylon	1.0				Webbing, Inflatable	Type 1
Air, blocking	180	0.5	No blocking	Chloroprene	2.5				Boat, and Miscellaneous	
Oxygen, accelerated aging	158	96	Brk. strength, 10% loss Max.	Composite	5.0				Use	
Air, breaking strength	Ambient	-	Warp, 180 lbs; Fill, 165 lbs	Chloroprene	3.0			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Nylon	2.5				Webbing, Inflatable	Type 2,
Air, blocking	180	0.5	No blocking	Chloroprene	3.0				Boat	Class A
Oxygen, accelerated aging	158	96	Brk. strength, 10% loss Max.	Composite	8.5					
Air, breaking strength	Ambient	-	Warp, 180 lbs; Fill, 165 lbs	Chloroprene	1.5			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Nylon	2.5				Webbing, Inflatable	Type 2,
Air, blocking	180	0 5	No blocking	Chloroprene	2.8				Boat	Class B
Oxygen, accelerated aging	158	96	Brk. strength, 10% loss Max.	Composite	6.8					
Air, breaking strength	Ambient	-	Warp, 45 lbs; Fill, 45 lbs	Chloroprene	1.0			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Cotton bias	2.1				Webbing, Inflatable	Type 3
Air, blocking	180	0.5	No blocking	Chloroprene	4.5				Boat	
Oxygen, accelerated aging	158	96	Brk. strength, 10% loss Max.	Composite	7.6					
Air, creased 180°	-20	94	No cracks	Natural	2.1			8305	Cloth, Coated, and	MIL-C-17415
Air, blocking	180	0.5	No blocking	Cotton	4.5				Webbing, Inflatable	Type 4,
Oxygen, accelerated aging	158	96	Brk. strength, 15% loss Max.	Natural	8 5				Boat	Class A
				Composite	15.0					
Air, creased 180°	-20	94	No cracks	Chloroprene	2.0			8305	Cloth, Coated, and	MIL-C-17415
Air, blocking	180	0.5	No blocking	Cotton bias	4.5				Webbing, Inflatable	Type 4,
Oxygen, accelerated aging	158	96	Brk. strength, 10% loss Max.	Chloroprene	3.5				Boat	Class B
				Composite	10.0					
Air, breaking strength	Ambient	-	Warp, 360 lbs; Fill, 360 lbs	Chloroprene	1.5			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Nylon	5.4				Webbing, Inflatable	Type 5
Air, blocking	180	0 5	No blocking	Chloroprene	16.5				Boat	
Oxygen, accelerated aging	158	96	Brk. strength, 10% loss Max.	Composite	23 4					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, creased 180°	-20	94	No cracks	Chloroprene	6.0			8305	Cloth, Coated, and	MIL-C-17415
Air, blocking	180	0.5	No blocking	Nylon					Webbing, Inflatable	Type 6
				Nylon pile	9.5	2 1/4-3			Boat	
				Nylon						
				Chloroprene	6.0					
				Composite	21.5					
Air, breaking strength	Ambient	-	Warp, 165 lbs, Fill, 160 lbs	Natural	11.5			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Cotton	7.0				Webbing, Inflatable	Type 7,
Air, blocking	180	0.5	No blocking	Natural	11.5				Boat	Class A
Oxygen, accelerated aging	158	96	Brk strength, 15% loss Max.	Composite	30.0					
Air, breaking strength	Ambient	-	Warp, 165 lbs; Fill, 160 lbs	Chloroprene	12.5			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Cotton	7.0				Webbing, Inflatable	Type 7,
Air, blocking	180	0.5	No blocking	Chloroprene	12.5				Boat	Class B
Oxygen, accelerated aging	158	96	Brk. strength, 10% loss Max.	Composite	32.0					
Air, breaking strength	Ambient	-	Warp, 50 lbs; Fill, 50 lbs	Natural	2.0			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Nylon bias	1.0				Webbing, Inflatable	Type 8,
Air, blocking	180	0.5	No blocking	Natural	3.5				Boat	Class A
Oxygen, accelerated aging	158	96	Brk. strength, 15% loss Max.	Composite	6.5					
Air, breaking strength	Ambient	-	Warp, 50 lbs; Fill, 50 lbs	Chloroprene	2.0			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Nylon bias	1.0				Webbing, Inflatable	Type 8,
Air, blocking	180	0.5	No blocking	Chloroprene	3.5				Boat	Class B
Oxygen, accelerated aging	158	96	Brk. strength, 10% loss Max.	Composite	6.5					
Air, breaking strength	Ambient	-	Warp, 360 lbs; Fill, 360 lbs	Chloroprene	12.5			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Nylon	5.4				Webbing, Inflatable	Type 9,
Air, blocking	180	0.5	No blocking	Chloroprene	12.5				Boat	Class A
Oxygen, accelerated aging	158	96	Brk. strength, 10% loss Max.	Composite	30.4					
Air, breaking strength	Ambient	-	Warp, 360 lbs; Fill, 360 lbs	Natural	14.0			8305	Cloth, Coated, and	MIL-C-17415
Air, creased 180°	-20	94	No cracks	Nylon	5.4				Webbing, Inflatable	Type 9,
Air, blocking	180	0.5	No blocking	Natural	14.0				Boat	Class B
Oxygen, accelerated aging	158	96	Brk. strength, 15% loss Max.	Composite	33.4					
Air, creased 180°	-20	94	No cracks	Chloroprene	1.5			8305	Cloth, Coated, and	MIL-C-17415
Air, blocking	180	0.5	No blocking	Nylon	1.0				Webbing, Inflatable	Type 10
				Chloroprene	8.5				Boat	
				Nylon						
				Nylon pile	9.5	2 1/4-3				
				Nylon						
				Chloroprene	8.5					
				Nylon	1.0					
				Chloroprene	1.5					
				Composite	31.5					

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, creased 180°	-20	94	No cracks	Chloroprene	5.0			8305	Cloth, Coated, and Webbing, Inflatable Boat	MIL-C-17415 Type 11
Air, blocking	180	0.5	No blocking	Nylon	2.0					
				Chloroprene	6.0					
				Nylon						
				Nylon pile	9.5	2 1/4-3				
				Nylon						
				Chloroprene	6.0					
				Nylon	2.0					
				Chloroprene	5 0					
				Composite	35.5					
Air, creased 180°	-20	94	No cracks	Chloroprene	16.8			8305	Cloth, Coated, and Webbing, Inflatable Boat	MIL-C-17415 Type 12
Air, blocking	180	0.5	No blocking	Nylon	1.0					
				Chloroprene	8.3					
				Nylon						
				Nylon pile	8.2	2-2 1/4				
				Nylon						
				Chloroprene	8.3					
				Nylon	1.0					
				Chloroprene	1.5					
				Composite	45.1					
Air, breaking strength	Ambient	-	Warp, 225 lbs, Fill, 225 lbs	Chloroprene	4.5			8305	Cloth, Coated, and Webbing, Inflatable Boat	MIL-C-17415 Type 13
Air, creased 180°	-20	94	No cracks	Nylon	3.1					
Air, blocking	180	0.5	No blocking	Chloroprene	4.5					
Oxygen, accelerated aging	158	96	Brk. strength, 10% loss Max.	Composite	12.1					
Air, breaking strength	Ambient	-	Warp, 180 lbs; Fill, 170 lbs	Nylon	3.1			8305	Cloth, Coated; and Tape, Coated Cloth - Chloroprene on Nylon, Pneumatic Life Preserver	MIL-C-19002 Type I
Air, creased 180°	-40	96	No cracks	Chloroprene	4.2					
Air, blocking	200	0.5	No blocking	Composite	7.3					
Air, tearing strength	Ambient	-	Warp, 1600 gm; Fill, 1600 gm	Cotton	5.9			8305	Cloth, Coated, Vapor Permeable, Water Impermeable	MIL-C-19208[1]
Air, blocking	200	0.5	No blocking	Chloroprene	4.9					
				Composite	10.8					
Air, breaking strength	Ambient	-	65 lbs. minimum	Polyethylene			Yes	8305	Cloth, Coated (For Aircraft Protectors)	MIL-C-19524[1]
Air, creased 180°	-40	96	No cracks	Nat. or syn.						
				Composite	6.5					

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS			SPECIFICATION	CONSTRUCTION			QPL	FSC		SPECIFICATION
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	ISSUED	CLASS	SPECIFICATION TITLE	NUMBER
Air, breaking strength	Ambient	-	Warp, 225 lbs, Fill, 210 lbs	Chloroprene	1.70			8305	Cloth, Laminated,	MIL-C-19555
Air, blocking	200	0.5	No blocking	Polyester	4.35				ZS2G-1 Type Airship	
Air, oven aging	158	96	Warp, 210 lbs, Fill, 190 lbs	Chloroprene	3.50				Envelope	
Weatherometer, break, strength	135	500	Warp, 210 lbs; Fill, 190 lbs	Polyester	3.50					
				Chloroprene	1.00					
				Hypalon	1.50					
				Composite	15.40					
Air, breaking strength	Ambient	-	Warp, 110 lbs, Fill, 95 lbs	Nylon	2.0			8305	Cloth, Coated	MIL-C-19699
Air, cantilever bending	-40	1	Flexible	Chloroprene	2.7				(Nylon Taffeta)	
Air, oven aging	160	200	Flexible	Composite	4.7					
Air, breaking strength	Ambient	-	Warp, 225 lbs; Fill, 210 lbs	Nylon	3.5			8305	Cloth, Coated	MIL-C-19699
Air, cantilever bending	-40	1	Flexible	Chloroprene	4.0				Nylon Twill, (Low	Type I
Air, oven aging	160	120	Flexible, no tackiness	Composite	7.5				Count)	
Air, breaking strength	Ambient	-	Warp, 225 lbs; Fill, 210 lbs	Chloroprene	1.5			8305	Cloth, Coated	MIL-C-19699
Air, cantilever bending	-40	1	Flexible	Nylon	3.5				Nylon Twill, (Low	Type II
Air, oven aging	160	120	Flexible, no tackiness	Chloroprene	4.0				Count)	
				Composite	9.0					
Air, breaking strength	Ambient	-	Warp, 120 lbs; Fill, 100 lbs	Chloroprene				8305	Cloth, Coated, Nylon,	MIL-C-20696
Air, cantilever bending	-40	4	Flexible	Nylon	2.3	0.007			Waterproof	Type I,
Oxygen, accelerated aging	158	168	Not stiff, brittle or tacky	Chloroprene						Class 1
MIL-L-6082, petroleum oil	Ambient	1	No leakage	Composite	8.0					
TT-S-735, 40% aromatic	Ambient	0.08	Shall not crack on creasing							
Air, breaking strength	Ambient	-	Warp, 120 lbs; Fill, 100 lbs	PVC				8305	Cloth, Coated, Nylon	MIL-C-20696
Air, cantilever stiffness	10	4	Flexible	Nykon	2.3	0.007			Waterproof	Type 1,
MIL-L-6082, petroleum oil	Ambient	1	No leakage	PVC						Class 2
TT-S-735, 40% aromatic	Ambient	0.08	Shall not crack on creasing	Composite	9.0					
Air breaking strength	Ambient	-	Warp, 120 lbs; Fill, 100 lbs	Chloroprene				8305	Cloth, Coated, Nylon,	MIL-C-20696
Air, cantilever stiffness	-40	4	Flexible	Nylon	2.3	0.007			Waterproof	Type 1
Oxygen, accelerated aging	158	168	Not stiff, brittle or tacky	Chloroprene						Class 3
MIL-L-6082	Ambient	1	No leakage	Composite	10.5					
TT-S-735, 40% aromatic	Ambient	0.08	Shall not crack on creasing							
Flame			Flame, 10 sec., Max; Char 3.5 in Max.							

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, breaking strength	Ambient	-	Warp, 325 lbs; Fill, 260 lbs	Chloroprene				8305	Cloth, Coated, Nylon,	MIL-C-20696
Air, cantilever stiffness	-40	4	Flexible	Nylon	5.5	0.015			Waterproof	Type II,
Oxygen, accelerated aging	168	168	Not stiff, brittle or tacky	Chloroprene						Class 1
MIL-L-6082, petroleum oil	Ambient	1	No leakage	Composite	16.0					
TT-S-735, 40% aromatic	Ambient	0.08	shall not crack on creasing							
Air, breaking strength	Ambient	-	Warp, 325 lbs; Fill, 260 lbs	PVC				8305	Cloth, Coated, Nylon,	MIL-C-20696
Air, cantilever stiffness	10	4	Flexible	Nylon	5.5	0.015			Waterproof	Type II,
MIL-L-6082, petroleum oil	Ambient	1	No leakage	PVC						Class 2
TT-S-735, 40% aromatic	Ambient	0.08	shall not crack on creasing	Composite	18.0					
Air, breaking strength	Ambient	-	Warp, 325 lbs; Fill, 260 lbs	Chloroprene				8305	Cloth, Coated, Nylon,	MIL-C-20696
Air, cantilever stiffness	-40	4	Flexible	Nylon	5.5	0.015			Waterproof	Type II,
Oxygen, accelerated aging	158	168	Not stiff, brittle or tacky	Chloroprene						Class 3
MIL-L-6082, petroleum oil	Ambient	1	No leakage	Composite	18.0					
TT-S-735, 40% aromatic	Ambient	0.08	shall not crack on creasing							
Flame	-	-	Flame, 10 sec. Max; Char 3.5							
Air breaking strength	Ambient	-	Warp 325 lbs; Fill 275 lbs	Nitrile/	7.25			8305	Cloth, Coated Nylon	MIL-C-20696
Air, creased 180°	-65	4	No cracks	Butadiene					Waterproof	Type III
Air, blocking	200	0.5	No blocking	Natural	2.0					Class 5
Air, oven aging	200	168	Not stiff, brittle or tacky	Composite	6.7					
Air breaking strength	Ambient	-	Warp 300 lbs; Fill 300 lbs	Natural	4.2			8305	Cloth, Coated, Raft	MIL-C-21109
Air, creased 180°	-65	4	No cracks	Nylon	6.0				Bottom	Type II
Air, blocking	200	0.5	No blocking	Natural	4.2					
Air, oven aging	200	168	Not stiff, brittle or tacky	Composite	14.4					
Air, tearing strength	Ambient	-	Warp, 130 lbs	Chloroprene				8305	Cloth, Laminated	MIL-C-21189
Air, blocking	200	0.5	No blocking	Polyester					ZPG2 and ZPG2W	
Air, oven aging	158	96	Tear strength, 5% loss Max.	Chloroprene					Type Airship	
Weatherometer, tear strength	135	500	5% loss, Max.	Polyester					Envelope	
				Chloroprene						
				Hypalon						
				Composite	16.5					
Air, breaking strength	Ambient	-	Warp, 90 lbs; Fill, 70 lbs	Aluminum	3.0			8305	Cloth, Coated (Neo-	MIL-C-21890[1]
Air, creased 180°	-20	1	No cracks	Glass	11.8				prene, Asbestos, Glass,	
Air, blocking	180	0.5	No blocking	Chloroprene	4.2				Cotton, Aluminized)	
Flame	-	-	Flame, 2.0 sec. Max; Char 1.5 in Max.	Composite	19.0					

[1] Document cancelled. Use MIL-C-82278

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS			SPECIFICATION	CONSTRUCTION			QPL	FSC		SPECIFICATION
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	ISSUED	CLASS	SPECIFICATION TITLE	NUMBER
Air, creased 180°	-65	4	No cracks	Natural	1 5			8305	Cloth, Laminated,	MIL-C-22427[1]
Air, blocking	200	0.5	No blocking	Nylon	1.0				Rubber on Nylon,	
Air, oven aging	158	168	Not stiff, brittle or tacky	Natural	9.5				Inflatable Floor	
				Nylon						
				Nylon pile	7.0	1.0				
				Nylon						
				Natural	9.5					
				Nylon	1.0					
				Natural	1.5					
				Composite	31.0					
Air, breaking strength	Ambient	-	Warp, 180 lbs, Fill, 160 lbs	Hypalon	4.9			8305	Cloth, Coated, Fire,	MIL-C-22524[2]
Air, creased 180°	-20	4	No cracks	Nylon	2.3				Water, Mildew and	Class 1
Air, blocking	180	0.5	No blocking	Hypalon	4.8				Weather Resistant	
Ozone, 100 PPM	77	50	No cracks	Composite	12.0					
Air, breaking strength	Ambient	-	Warp, 300 lbs; Fill, 260 lbs	Hypalon	5.5			8305	Cloth, Coated, Fire,	MIL-C-22524[2]
Air, creased 180°	-20	4	No cracks	Nylon	3.9				Water, Mildew and	Class 2
Air, blocking	180	0.5	No blocking	Hypalon	5.6				Weather Resistant	
Ozone, 100 PPM	77	50	No cracks	Composite	15.0					
Air, breaking strength	Ambient	-	Warp, 300 lbs; Fill, 300 lbs	Hypalon	6.5			8305	Cloth, Coated, Fire,	MIL-C-22524[2]
Air, creased 180°	-20	4	No cracks	Nylon	5.0				Water, Mildew and	Class 3
Air, blocking	180	0.5	No blocking	Hypalon	6.5				Weather Resistant	
Ozone, 100 PPM	77	50	No cracks	Composite	18.0					
Air, breaking strength	Ambient	-	Warp, 130 lbs; Fill 110 lbs	Glass	6.50			8305	Cloth, Coated, Fuel	MIL-C-22787
Air, blocking scale rating	-	-	3	Vinyl					and Flame Resistant	Type I
Air, breaking strength	Ambient	-	Warp, 130 lbs; Fill 110 lbs	Vinyl	6.50			8305	Cloth, Coated, Fuel	MIL-C-22787
Air, blocking scale rating	-	-	3	Modacrylic					and Flame Resistant	Type II
Air, breaking strength	Ambient	-	Warp, 180 lbs; Fill 175 lbs	Glass	5.10			8305	Cloth, Coated, Fuel	MIL-C-22787
Air, blocking scale rating	-	-	3	Vinyl					and Flame Resistant	Type III
Air, breaking strength	Ambient	-	Warp, 130 lbs; Fill 110 lbs	Nylon	12.50			8305	Cloth, Coated, Fuel	MIL-C-22787
Air, blocking scale rating	-	-	3	Vinyl					and Flame Resistant	Type IV
Air breaking strength	Ambient	-	Warp 185-300 lbs, Fill 110-250 lbs	Glass	7.0 to			8305	Cloth, Coated, Fuel and Flame Resistant	MIL-C-22787 Types V, VI,
Air Blocking Scale Rating	-	-	3	Vinyl	20.5					VII

[1] Document cancelled without replacement.
[2] Document cancelled. Use MIL-C-43006.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD²	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air breaking strength	Ambient	-	Warp 300 lbs; Fill, 250 lbs	Natural	1.5			8305	Cloth, Laminated, and Tape, Coated Cloth, Polyisoprene, Natural or Synthetic Rubber on Nylon	MIL-C-23070 Variety C
Air, creased 180°	-65	4	No cracks	Nylon	3.0					
Air, blocking	212	0.5	No blocking	Natural	4.0					
Air, oven aging	200	168	Break, strength, 10% loss Max.	Nylon bias	1.6					
Weatherometer, break. strength	135	300	25% loss Max.	Natural	1.5					
				Composite	11.6					
(Inner liner covered by Grade SB615A1E5 of MIL-R-3065 and MIL-STD-417 Outer cover covered by Grade SC615A1E5 of MIL-R-3065 and MIL-STD-417)				Outer cover-chloroprene				5430	Tank, Fabric, Collapsible, Liquid Fuel Cylindrical, 500 Gallon Capacity	MIL-T-23119
(Rubber covered by Grade RS-15L of MIL-H-3065 and MIL-STD-417)				SBR coated nylon cloth				5430	Tank, Fabric, Collapsible, Pillow Type, 3,000 Gallon Capacity (For Portable Water)	MIL-T-23268[1]
Air, breaking strength	Ambient	-	Wales 90 lbs; Courses 45 lbs	Nylon Polychloroprene	19.0			8305	Cloth, Coated and Laminated, Polychloroprene on Nylon, and Tape, Polychloroprene, Unsupported	MIL-C-23926[2] Type I
Air, Elongation	Ambient	-	Wales 100%; Courses 250%							
Air, breaking strength	Ambient	-	Wales 90 lbs; Courses 45 lbs	Nylon Polychloroprene	24.0			8305	Cloth, Coated and Laminated, Polychloroprene on Nylon, and Tape, Polychloroprene, Unsupported	MIL-C-23926[2] Type II
Air, Elongation	Ambient	-	Wales 100%; Courses 250%							
Air, breaking strength	Ambient	-	Wales 90 lbs; Courses 45 lbs	Nylon	23.0			8305	Cloth, Coated and Laminated, Polychloroprene on Nylon, and Tape, Polychloroprene, Unsupported	MIL-C-23926[2] Type IV
Air, Elongation	Ambient	-	Wales 100%; Courses 250%							
Air breaking strength	Ambient	-	Warp 575 lbs; Fill, 525 lbs	Chloroprene	16.2			8305	Cloth, Coated, Nylon Chloroprene Coated,	MIL-C-26712 Variety C
Air, mandrel bend	-67	24	No cracks	Nylon	8.5					
Air, blocking	180	0.5	No blocking	Chloroprene	16 3					
Air, oven aging	158	240	Break, strength, 10% loss Max.	Composite	41 0	0.045				
Air breaking strength	Ambient	-	Warp 150 lbs; Fill, 150 lbs	Aluminum			Yes	8305	Cloth, Coated, Glass, Aluminum Face, Silicone Rubber Back	MIL-C-27347
Air, mandrel bend	-65	4	No cracks	Glass	6.7	0.008				
Air, blocking	180	2	No blocking	Silicone						
Flame	-	-	Flame, 10 sec. Max	Composite	16 0	0.015				

1 Document cancelled Use MIL-T-52943(ME).
2 Document cancelled without replacement

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION						
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, breaking strength	Ambient	-	Warp, 185 lbs; Fill, 185 lbs	Butyl	6.3	0.003		8305	Cloth, Coated, Butyl,	MIL-C-38149
Air, creased 180°	-40	4	No cracks	Nylon	3.5	0.009			Polyamide, Nonmelt,	
Air, blocking	180	0.5	Slight blocking	Butyl	6.2	0.004			Fuel and Oxidizer Re-	
Nitrogen tetroxide fumes	80	1	Leakage, 0.01 mg/in^2 Max.	Composite	16.0	0.017			sistant	
Air, breaking strength	Ambient	-	Warp, 90 lbs; Fill, 80 lbs	PVC	1.0			8305	Cloth, Coated, Nylon,	MIL-C-40039
Air, creased 180°	0	0 6	No cracks	Nylon	1.6				Vinyl Coated	
Air, blocking	180	0.5	No blocking	PVC	4.1					
				Composite	6.7					
Air, breaking strength	Ambient	-	Warp, 125 lbs; Fill, 150 lbs	Chloroprene	0.5			8305	Cloth, Laminated,	MIL-C-40056[1]
Air, creased 180°	-20	96	No cracks	Nylon	0.9				Fabric, Air-Retain-	
				Chloroprene	6.0				ing Mattress	
				Nylon						
				Nylon pile	8.6	1/4-4				
				Nylon						
				Chloroprene	6.0					
				Nylon	0.9					
				Chloroprene	0.5					
				Composite	23.4					
Air breaking strength	Ambient	-	Warp 295 lbs; Fill, 295 lbs	PVC				8305	Cloth and Strip Lami-,	MIL-C-43006
Air, mandrel bend	-42	4	No cracks	Nylon					nated, Vinyl-Nylon,	Type I
Air, blocking	180	0 5	Slight blocking	PVC					High-Strength Flexible	
				Composite	18.4					
Air breaking strength	Ambient	-	Warp 90 lbs; Fill, 90 lbs	PVC				8305	Cloth and Strip Lami-,	MIL-C-43006
Air, mandrel bend	-42	4	No cracks	Nylon					nated, Vinyl-Nylon,	Type II
Air, blocking	180	0.5	No blocking	PVC					High-Strength Flexible	
				Composite	10.0					
Air breaking strength	Ambient	-	Warp 75 lbs; Fill, 75 lbs	PVC				8305	Cloth and Strip Lami-,	MIL-C-43006
Air, mandrel bend	-42	4	No cracks	Nylon					nated, Vinyl-Nylon,	Type III
Air, blocking	180	0.5	No blocking	PVC					High-Strength Flexible	
				Composite	6 0					
Air, breaking strength	Ambient	-	Warp 80 lbs; Fill, 80 lbs	Butyl	1.6			8305	Cloth, Coated, Cotton	MIL-C-43062
Air, Cantilever stiffness	-20	4	Flexible	Cotton	4.3				Resin Modified Butyl	(unvulca-
Air, blocking	180	0.5	No blocking	Butyl	4.6				Coated, Acid and Fuel	nized)
JP-4 fuel	Ambient	0.25	Shall not crack or stiffen	Composite	10.5				Resistant	
Air, breaking strength	Ambient	-	Warp, 300 lbs; Fill, 300 lbs	PVC	8.5			8305	Cloth, Coated, Nylon,	MIL-C-43086
Air, creased 180°	-10	0 5	No cracks	Nylon	5.9	0 009			Vinyl Coated (For Air-	
Air, blocking	170	2	Slight blocking	PVC	5.5				Supported Shelters)	

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS			SPECIFICATION	CONSTRUCTION			QPL	FSC		SPECIFICATION
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	REQUIREMENTS	TYPE AND ORDER OF COMPONENTS	WEIGHT OZ/YD^2	THICK, INCH	ISSUED	CLASS	SPECIFICATION TITLE	NUMBER
Air, breaking strength Air, blocking	Ambient 200	- 0.5	Warp, 160 lbs; Fill 160 lbs Slight blocking	Polyester Chloroprene Composite	13.0			8305	Cloth, Coated Chloroprene Base Coated, Chlorosulphonated Polyethylene Top Coated	MIL-C-43285 Type I
Air, breaking strength Air, blocking	Ambient 200	- 0.5	Warp, 275 lbs; Fill 275 lbs Slight blocking	Nylon Chloroprene Composite	13.0			8305	Cloth, Coated Chloroprene Base Coated, Chlorosulphonated Polyethylene Top Coated	MIL-C-43285 Type II
Air, breaking strength Air, Blocking Water absorption	Ambient 180 70	- 0.5	Warp, 50 lbs; Fill, 50 lbs Slight blocking 1%	Cotton PVC Chloroprene Composite	12.0			8305	Cloth, Coated Cotton Vinyl Chloride or Chloroprene Coated	MIL-C-43410
Air breaking strength Air, Blocking JP-4 Fuel	Ambient -85 Ambient	- 4 -	Warp, 160 lbs; Fill, 160 lbs Flexible Shall not crack or stiffen	Cotton Polyester Silicone Composite	10.0			8305	Cloth, Coated, Polyester, Silicone Rubber Coated	MIL-C-43656
(Tests on rubber only) Air, original properties (Test on coated fabric) Air, 180° crease	Ambient -20	- 96	T, 1800 psi min; E, 500% min No cracks	Chloroprene coated nylon fabric				5430	Cases: Nylon Neoprene-Coated	MIL-C-52186[1]
Air, breaking strength Air, blocking	Ambient 180	- 0.5	Warp, 245 lbs; Fill, 160 lbs Moderate blocking	Cotton Chloroprene Composite	55.0			8305	Cloth, Coated, Synthetic Rubber (Nitrile and Polychloroprene)	MIL-C-82255 Type II
Air, tensile strength Air, blocking	Ambient 180	- 0.5	Warp, 245 lbs; Fill, 160 lbs Moderate blocking	Cotton Nitrile Composite	43.0			8305	Cloth, Coated Synthetic Rubber (Nitrile & Polychloroprene)	MIL-C-82255 Type II
Air, tensile strength Air, blocking	Ambient 180	- 0.5	Warp, 90 lbs; Fill, 90 lbs Moderate blocking	Cotton Chlroprene Composite	29.5			8305	Cloth, Coated Synthetic Rubber (Nitrile & Polychloroprene)	MIL-C-82255
Air, breaking strength Air, blocking scale rating Water transmission	Ambient Ambient Ambient	- - -	Warp, 70 lbs; Fill, 65 lbs 2 20 grams/sq. Meter/hr. min	Urethane	6.3			8305	Cloth, Coated, Cotton and Nylon, Polyurethane (Microporous) Coated	MIL-C-83008[1] Type I
Air, breaking strength Air, blocking scale rating Water transmission	Ambient Ambient Ambient	- - -	Warp, 175 lbs; Fill, 175 lbs 2 9 grams/sq Meter/hr. min	Urethane	5.0			8305	Cloth, Coated, Cotton and Nylon, Polyurethane (Microporous) Coated	MIL-C-83008[1] Type II

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

HOSE, DUCT AND TUBING

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	ELASTOMER SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength	Ambient	-	Tube 1250 psi min; cover 1000 psi min	Nitrile tube & cover, fiber reinforcement			Coolant-System Hoses	SAE J20 Part I Class SB
Air, 50% compression	-40	5	No cracking					
Air, oven aging	158	96	Tube & cover max T change: -20%					
ASTM #3 petroleum oil	212	70	Tube & cover vol change: -5 to +25%					
Air, tensile strength	Ambient	-	Tube 1250 psi min, cover 1000 psi min	Chloroprene tube & cover, fiber reinforcement			Coolant-System Hoses	SAE J20 Part I Class SC
Air, 50% compression	-40	5	No cracking					
Air, oven aging	158	96	Tube & cover max T change: -15%					
ASTM #3 petroleum oil	212	70	Tube & cover vol change: +100%					
Air, tensile strength	Ambient	-	800 psi min	Chloroprene tube & cover, fiber reinforcement			Coolant-System Hoses	SAE J20 Part II Class SC
Air, 50% compression	-40	5	No cracking					
Air, oven aging	158	96	Max % T chg. tube -15; cover -20					
ASTM #3 petroleum oil	212	70	Tube & cover max vol change: +100%					
Air, tensile strength	Ambient	-	800 to 500 psi	Nat. or SBR tube & cover, fiber reinforcement			Coolant-System Hoses	SAE J20 Part II Class R Grades 1, 1A & 2
Air, 50% compression	-40	5	No cracking					
Air, oven aging	158	96	Tube & cover % T chg: -25 to -40					
Air, burst test	Ambient	-	3/8" to 3/4" ID, 200 to 125 psi	Chloroprene tube & cover, fiber reinforcement			Coolant-System Hoses	SAE J20 Part III Class SC
Air, 50% compression	-40	5	No cracking					
Air, oven aging	158	96	Max % T chg. tube -15; cover -20					
ASTM #3 petroleum oil	212	70	Tube & cover max vol change: +100%					
Air, burst test	Ambient	-	3/8" to 3/4" ID; 200 to 125 psi	Nat. or SBR tube & cover, fiber reinforcement			Coolant-System Hoses	SAE J20 Part III Class R Grade 1 & 2
Air, 50% compression	-40	5	No cracking					
Air, oven aging	158	96	Tube & cover max T chg: -25%					
Air, burst test	Ambient	-	3/8" to 3/4" ID; 200 to 125 psi	Nat. or SBR tube & cover, fiber reinforcement			Coolant-System Hoses	SAE J20 Part III Class R Grade 1A
Air, 50% compression	-40	5	No cracking					
Air, oven aging	250	70	Tube & cover max T chg: -40%					
Air, burst test	Ambient	-	3/8" to 2-1/4" ID; 90 to 60 psi	Chloroprene tube & cover, fiber reinforcement			Coolant-System Hoses	SAE J20 Part IV Class SC
Air, 50% compression	-40	5	No cracking					
Air, oven aging	158	96	Max % T chg: tube -15; cover -20					
ASTM #3 petroleum oil	212	70	Tube & cover max vol change: +100%					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test	Ambient	-	3/8" to 2-1/4" ID; 90 to 60 psi	Nat. or SBR tube &			Coolant-System Hoses	SAE J20
Air, 50% compression	-40	5	No cracking	cover, fiber rein-				Part IV
Air, oven aging	158	96	Tube & cover max T chg: -25%	forcement				Class R
								Grades 1 & 2
Air, burst test	Ambient	-	3/8" to 2-1/4" ID; 90 to 60 psi	Nat. or SBR tube &			Coolant-System Hoses	SAE J20
Air, 50% compression	-40	5	No cracking	cover, fiber rein-				Part IV
Air, oven aging	250	70	Tube & cover max T chg: -40%	forcement				Class R
								Grade 1A
Air, burst test	Ambient	-	175 psi min	Nitrile tube,			Fuel and Oil Hoses	SAE J30
Air, flexibility	-40	5	No cracking	synthetic cover,				R 1
Air, oven aging	212	70	Tube & cover max T chg: -20%	fabric rein-				
ASTM #3 petroleum oil	212	70	% V chg. tube -5 + 25, cover + 100 max	forcement				
Ozone, 50 pphm	100	72	No cracking					
Air, burst test	Ambient	-	0.115" to 0.773" ID; 700 to 500 psi	Nitrile tube,			Fuel and Oil Hoses	SAE J30
Air, ASTM D736	-40	5	No cracking	synthetic cover,				R 2
Air, oven aging	212	70	Tube & cover max T chg: -20%	fabric rein-				Type 1
ASTM #3 petroleum oil	212	70	% V chg tube -5 + 25; cover + 100 max	forcement				
Ozone, 50 pphm	100	72	No cracking					
Air, burst test	Ambient	-	0.115" to 2.039" ID; 700 to 250 psi	Nitrile tube,			Fuel and Oil Hoses	SAE J30
Air, ASTM D736	-40	5	No cracking	synthetic cover,				R 2
Air, oven aging	212	70	Tube & cover max T chg. -20%	fabric rein-				Type 2
ASTM #3 petroleum oil	212	70	% V chg: tube -5 + 25; cover + 100 max	forcement				
Ozone, 50 pphm	100	72	No cracking					
Air, burst test	Ambient	-	0.172" to 0.773" ID, 2000 to 1200 psi	Nitrile tube,			Fuel and Oil Hoses	SAE J30
Air, ASTM D736	-40	5	No cracking	synthetic cover,				R 2
Air, oven aging	212	70	Tube & cover max T chg: -20%	fabric rein-				Type 3
ASTM #3 petroleum oil	212	70	% V chg tube -5 + 25, cover + 100 max	forcement				
Ozone, 50 pphm	100	72	No cracking					
Air, burst test	Ambient	-	0.172" to 0.391" ID, 2000 to 900 psi	Nitrile tube,			Fuel and Oil Hoses	SAE J30
Air, flexibility	-40	5	No cracking	synthetic cover,				R 3
Air, oven aging	212	70	Tube & cover max T chg: -20%	fabric rein-				
ASTM #3 petroleum oil	212	70	Tube vol chg. -5% to 25%	forcement				
Ozone, 50 pphm	100	72	No cracking					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test	Ambient	-	0.172" to 0.531" ID; 1200 to 850 psi	Wire reinforced			Fuel and Oil Hoses	SAE J30
Air, flexibility	-40	5	No cracking	nitrile tube				R 4
Air, oven aging	212	70	Tube & cover max T chg -20%					Type 1
ASTM #3 petroleum oil	212	70	Tube max vol change: -40%					
Ozone, 50 pphm	100	72	No cracks					
Air, burst test	Ambient	-	0.172" to 0.531" ID, 2000 to 850 psi	Nitrile tube, syn-			Fuel and Oil Hoses	SAE J30
Air, flexibility	-40	5	No cracking	thetic cover, fab-				R 4
Air, oven aging	212	70	Tube & cover max T chg -20%	ric reinforcement				Type 2
ASTM #3 petroleum oil	212	70	Tube max vol change: -40%					
Ozone, 50 pphm	100	72	No cracks					
Air, burst test	Ambient	-	250 psi min	Rubber tube &			Windshield Wiper Hose	SAE J50
Air, flexibility	-20	5	No cracks	cover, fabric				
Air, flexibility	158	70	No cracks	reinforced				
Air, burst test	Ambient	-	1750 psi min	Nitrile tube &			Automotive Air Condi-	SAE J51
Air, flexibility	-20	5	No cracks	cover fabric			tioning Hose	Type A
Air, flexibility	250	168	No cracks	reinforced				
ASTM #3 petroleum oil	212	70	Max vol chg. tube -5 to +20%					
Air, burst test	Ambient	-	2500 psi min	Nitrile tube &			Automotive Air Condi-	SAE J51
Air, flexibility	-20	5	No cracks	cover wire			tioning Hose	Type B
Air, flexibility	250	168	No cracks	reinforced				
ASTM #3 petroleum oil	212	70	Max vol chg tube -5 to +20%					
Air, burst test	Ambient	-	1750 psi min	Nitrile tube &			Automotive Air Condi-	SAE J51
Air, flexibility	-20	5	No cracks	cover fabric			tioning Hose	Type A
Air, flexibility	250	168	No cracks	reinforced				
ASTM #3 petroleum oil	212	70	Max vol chg. tube -5 to +20%					
Air, burst test	Ambient	-	2500 psi min	Nitrile tube &			Automotive Air Condi-	SAE J51
Air, flexibility	-20	5	No cracks	cover wire			tioning Hose	Type B
Air, flexibility	250	168	No cracks	reinforced				
ASTM #3 petroleum oil	212	70	Max vol chg tube -5 to +20%					
Air, tensile strength	Ambient	-	1200 psi min	Rubber-lined			Woven Jacketed Rubber-Lined	ASTM D 296[1]
Oxygen, @ 300 psi	158	96	Max T change. -40%	woven jackets			Fire Hose For Public and Private Fire Department Use	

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength	Ambient	-	Tube 1250 psi; cover 1500 psi	Cotton or syn. fiber reinforced, static wire wound tube NR and chloroprene cover		4720	Hose & Hose Assembly, Rubber, Liquid Fuel Noncollapsible	MIL-H-370 Type I Tube Type I Cover
Air, 180° bend	-42	24	No cracking					
Oxygen, aging @ 300 psi	158	48	Tensile strength. -25% max					
70/30 isooctane/toluene	70	46	Volume change: +60% max					
Ozone, 50 pphm	104	72	No cracks					
Air, tensile strength	Ambient	-	Tube 1250 psi min	Nitrile tube, cotton or syn. fiber reinforced, static wire wound; CR		4720	Hose & Hose Assembly, Rubber, Liquid Fuel Noncollapsible	MIL-H-370 Type II Tube Type I Cover
Air, 180° bend	-42	24	No cracking					
Oxygen, aging @ 300 psi	158	48	Tensile strength: -25%					
70/30 isooctane/toluene	70	46	Volume change: +60% max					
Ozone, 50 pphm	104	72	No cracks					
Air, proof @ 400 psi	Ambient	-	No leakage	Nat. and/or syn. tube & cover, cotton reinforced		4210	Hose & Hose Assembly, Chemical (Industrial Fire)	ZZ-H-421[1] Types I & II
Oxygen, aging @ 300 psi	158	46	Tube & cover max T chg: -40%					
Air, kinking @ 250 psi	Ambient	-	No weakness					
Air, tensile strength	Ambient	-	Tube 1000 psi min; cover 1000 psi min	Tube & cover, fabric reinforced chloroprene		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Type I Grade A Class 2
Air, flexibility	-65	5	No cracks or breaks					
Air, heat aging	212	70	Tube & cover max T change: -15%					
Ozone, 50 pphm	100	168	No cracks					
ASTM #3 petroleum oil	212	70	Tube & cover max vol chg: +100%					
Fungus resistance	84	90	Proof pressure = 1/2 orig burst press.					
Air, tensile strength	Ambient	-	Tube 1000 psi min; cover 1000 psi min	Tube & cover, fabric reinforced nitrile		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Type I Grade B Class 1
Air, flexibility	-40	5	No cracks or breaks					
Air, heat aging	212	70	Tube & cover max T change: -20%					
ASTM #3 petroleum oil	212	70	Tube & cover vol change: -5 to +25%					
Air, tensile strength	Ambient	-	Tube 1000 psi min; cover 1000 psi min	Tube & cover, fabric reinforced chloroprene		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Types I & II Grade B Class 2
Air, flexibility	-40	5	No cracks or breaks					
Air, heat aging	212	70	Tube & cover max T change: -15%					
Ozone, 50 pphm	100	168	No cracks					
ASTM #3 petroleum oil	212	70	Tube & cover max vol chg: +100%					

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength	Ambient	-	Tube & cover; 1000 psi min	Tube & cover, fabric reinforced chloroprene		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Types III, IV Grade A Class 2
Air, flexibility	-65	5	No cracks or breaks					
Air, heat aging	212	70	Max % T chg: tube -15, cover -20					
Ozone, 50 pphm	100	168	No cracks					
ASTM #3 petroleum oil	212	70	Tube & cover max vol chg: +100%					
Fungus resistance	84	90	Proof pressure = 1/2 orig burst press.					
Air, tensile strength	Ambient	-	Tube & cover; 1000 psi min	Tube & cover, fabric reinforced butyl		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Types III, IV Grade A Class 4
Air, flexibility	-65	5	No cracks or breaks					
Air, heat aging	250	70	Tube & cover max T change: -40%					
Ozone, 50 pphm	100	168	No cracks					
Fungus resistance	84	90	Proof pressure = 1/2 orig burst press.					
Air, tensile strength	Ambient	-	Tube & cover, 1000 psi min	Tube & cover, fabric reinforced chloroprene		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Types III, IV Grade B Class 2
Air, flexibility	-40	5	No cracks or breaks					
Air, heat aging	212	70	Max % T chg: Tube -15; Cover -20					
Ozone, 50 pphm	100	168	No cracks					
ASTM #3 petroleum oil	212	70	Tube & cover max vol change: +100%					
Air, tensile strength	Ambient	-	Tube & cover; 1000 psi min	Tube & cover, fabric reinforced natural		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Types III, IV Grade B Class 3
Air, tensile strength	-40	5	No cracks or breaks					
Air, heat aging	212	70	Tube & cover max T change: -25%					
Air, tensile strength	Ambient	-	Tube & cover; 1000 psi min	Tube & cover, fabric reinforced butyl		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Types III, IV Grade B Class 4
Air, tensile strength	-40	5	No cracks or breaks					
Air, heat aging	250	70	Tube & cover max T change: -40%					
Ozone, 50 pphm	100	168	No cracks					
Air, tensile strength	Ambient	-	Tube 800 psi min; cover 800 psi min	Tube & cover, wire reinforced chloroprene		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Type V Grade A Class 2
Air, flexibility	-65	5	No cracks or breaks					
Air, heat aging	212	70	Tube & cover max T change: -15%					
ASTM #3 petroleum oil	212	70	Max % vol chg: tube +43; cover +74					
Ozone, 50 pphm	100	168	No cracks					
Fungus resistance	84	90	Proof pressure = 1/2 orig burst press.					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength	Ambient	-	Tube 800 psi min; cover 800 psi min	Tube & cover, wire reinforced natural		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Type V Grade A Class 3
Air, flexibility	-65	5	No cracks or breaks					
Air, heat aging	212	70	Tube & cover max T change: -25%					
Fungus resistance	84	90	Proof pressure = 1/2 orig burst press.					
Air, tensile strength	Ambient	-	Tube 800 psi min; cover 800 psi min	Tube & cover, wire reinforced nitrile		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Type V Grade B Class 1
Air, flexibility	-40	5	No cracks or breaks					
Air, heat aging	212	70	Tube & cover max T change: -15%					
ASTM #3 petroleum oil	212	70	Max % vol chg: tube +43; cover +74					
Air, tensile strength	Ambient	-	Tube 800 psi min, cover 800 psi min	Tube & cover, wire reinforced chloroprene		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Type V Grade B Class 2
Air, flexibility	-40	5	No cracks or breaks					
Air, heat aging	212	70	Tube & cover max T change: -15%					
Ozone, 50 pphm	100	168	No cracks					
ASTM #3 petroleum oil	212	70	Max % vol chg: tube +43; cover +74					
Air, tensile strength	Ambient	-	Tube 800 psi min; cover 800 psi min	Tube & cover, wire reinforced natural		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Type V Grade B Class 3
Air, flexibility	-40	5	No cracks or breaks					
Air, heat aging	212	70	Tube & cover max T change: -25%					
Air, tensile strength	Ambient	-	Tube 800 psi min; cover 800 psi min	Tube & cover, wire reinforced butyl		4720	Hose, Non-Metallic & Hose Preformed (For Coolant Systems of Automotive and Other Liquid-Cooled Engines)	ZZ-H-428 Type V Grade B Class 4
Air, flexibility	-40	5	No cracks or breaks					
Air, heat aging	212	70	Tube & cover max T change: -40%					
Ozone, 50 pphm	100	168	No cracks					
(Tests on rubber lining only)								
Air, tensile strength	Ambient	-	1200 psi min	Three ply cotton reinforced syn. rubber lining		4210	Hose, Fire; Cotton, Rubber-Lined	ZZ-H-451
Air, elongation	Ambient	-	400% min					
Air, set @ 300% elong	Ambient	0.17	25% max					
Oxygen, aging @ 300 psi	158	96	Tensile change: -40% max					
Air, tensile strength	Ambient	-	Tube and cover, 2200 psi min	Cotton duck coated with natural or syn rubber		4720	Sleeves; Dredging	ZZ-S-451
Air, elongation	Ambient	-	Tube 650% min; cover, 500% min					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test Air, ASTM D736 Oxygen, aging @ 300 psi	Ambient -40 158	- 5 46	Tube & cover· 600 to 700 psi min No cracks or breaks Tube & cover max T change: -25%	Fabric reinforced natural and/or syn. tube & cover		4720	Hose; Gas (Acetylene-Hydrogen, Air, and Oxygen)	ZZ-H-461
Air, tensile strength Gasoline	Ambient 75	- 48	Rubber tube: 700 psi min Max wt. change· -20%	Nat., nitrile, or chloroprene tube over metal tube, cotton jacket		4720	Hose; Gasoline, Rubber-Metal	ZZ-H-466
Air, burst test Air, 180° bend Oxygen, aging @ 300 psi 60/40 isooctane/aromatic	Ambient -40 158 75	- 24 46 46	3/4" to 3" ID; 500 to 325 psi No cracking Tube & cover max T change: -35% Max volume change: +100%	Cotton or nylon reinforced chloroprene tube w/chloroprene cover		4720	Hose, Gasoline, Synthetic-Rubber Wire-Stiffened	ZZ-H-471[1] Class 1
Air, burst test Air, 180° bend Oxygen, aging @ 300 psi 60/40 isooctane/aromatic	Ambient -40 158 75	- 24 46 46	3/4" to 3" ID; 500 to 325 psi No cracking Tube & cover max T change: -35% Max volume change: +20%	Polysulfide tube w/ chloroprene cover, cotton or nylon reinforced		4720	Hose; Gasoline, Synthetic-Rubber Wire-Stiffened	ZZ-H-471[1] Class 2
Air, burst test Air, 180° bend Oxygen, aging @ 300 psi 60/40 isooctane/aromatic	Ambient -40 158 75	- 24 46 46	3/4" to 3" ID; 500 to 325 psi No cracking Tube & cover max T change: -35% Max volume change: +60%	Nitrile tube w/ chloroprene cover, cotton or nylon reinforced		4720	Hose; Gasoline, Synthetic-Rubber Wire-Stiffened	ZZ-H-471[1] Class 3
Air, tensile strength Oxygen, aging @ 300 psi 60/40 diisobutylene/ aromatic	Ambient 158 135	- 46 48	Tube & cover· 1250 psi min Max tensile change: -35% Max volume change. +110%	1) Wire 2) Frictioned cotton 3) Chloroprene 4) Frictioned cotton 5) Embedded wire 6) Frictioned cotton 7) Chloroprene		4720	Hose; Oil & Gasoline, Suction and Discharge, Synthetic-Rubber, Wire Stiffened	ZZ-H-481 Class 1
Air, tensile strength Air, burst pressure Ozone, 50 pphm	Ambient Ambient 212	- - 72	Tube, 750 psi; Cover, 1200 psi min 1/4" to 2", 1000 psi to 600 psi min No cracks	Tube & cover synthetic rubber reinforced fabric		4720	Hose, Rubber, and Hose Assemblies, Rubber Pneumatic (Yarn or Fabric Reinforced)	ZZ-H-500 Class 1

[1] Document cancelled without replacement

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength Air, burst pressure	Ambient Ambient	- -	Tube, 750 psi; Cover, 1200 psi min 1/4" to 2", 1000 psi to 600 psi min	Tube & cover synthetic rubber reinforced fabric		4720	Hose, Rubber, and Hose Assemblies, Rubber Pneumatic (Yarn or Fabric Reinforced)	ZZ-H-500 Class II
Air, tensile strength Aging, oxygen	Ambient 212	- 48	Tube & cover, 2,000 psi min Tensile strength, -25% change max	Tube & cover synthetic rubber yarn reinforcement		4720	Hose, Rubber (Sleeves; Dredging)	ZZ-H-515[1]
Air, burst test	Ambient	-	3/16" to 2" ID; 12000 to 1500 psi	Syn. rubber tube & cover, high tensile steel wire reinforced			Hydraulic Hose	SAE J517 100 R1
Air, burst test	Ambient	-	3/16" to 2" ID; 20000 to 4500 psi	Syn. rubber tube & cover, plies of steel wire reinforced			Hydraulic Hose	SAE J517 100 R2
Air, burst test	Ambient	-	3/16" to 1-1/4" ID; 6000 to 1500 psi	Syn. rubber tube & cover, 2 plies of rayon reinforced			Hydraulic Hose	SAE J517 100 R3
Air, burst test	Ambient	-	3/4" to 3" ID; 1200 to 225 psi	Syn. rubber tube & cover, ply or plies of syn. fiber reinforced			Hydraulic Hose	SAE J517 100 R 4
Air, burst test	Ambient	-	3/16" to 1-13/16" ID; 12000 to 1400 psi	Syn. rubber tube, syn-rubber impregnated cotton & wire reinforcement			Hydraulic Hose	SAE J517 100 R5
Air, burst test	Ambient	-	3/16" to 5/8" ID; 2000 to 1400 psi	Syn. rubber tube & cover, rayon reinforced			Hydraulic Hose	SAE J517 100 R6
Air, burst test Oxygen, aging @ 300 psi Ethylacetate or acetone 60/40 isooctane/aromatic	Ambient 158 75 75	- 46 48 48	800 psi min Tube & cover max T change: -35% Max vol change: tube +30% Max vol change: cover, +100%	Nat. or syn. rubber tube & cover, cotton or syn. fiber reinforced		4720	Hose & Hose Assembly Nonmetallic, Spray	ZZ-H-521 Grade A Wrapped

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test	Ambient	-	800 psi min	Nat. and/or syn.		4720	Hose & Hose Assembly	ZZ-H-521
Oxygen, aging @ 300 psi	158	46	Tube & cover max T change. -35%	rubber tube &			Nonmetallic, Spray	Grade B
Ethylacetate or acetone	75	48	Max vol change tube +30%	cover w/cotton or				Braided
60/40 isooctane/aromatic	75	48	Max vol change: cover, +100%	syn. fiber rein-				
				forcement				
Air, tensile strength	Ambient	-	Tube 1000 psi min, cover 1200 psi min	Chloroprene cover		4720	Hose Rubber and Hose	ZZ-H-561
Oxygen, aging @ 300 psi	158	46	Tube & cover max T change: -25%	w/syn. tube, wire			Assembly; Rubber	Grade A
ASTM #3 oil	212	70	Cover, T.S. max change: -40%	& fiber reinforced			Smooth Bore, Water	Class 1
Ozone, 100 pphm	212	70	Cover, no cracks				Suction & Discharge	
Air, tensile strength	Ambient	-	Tube 1000 psi min; cover 1200 psi min	Syn. rubber tube		4720	Hose Rubber and Hose	ZZ-H-561
Oxygen, aging @ 300 psi	158	46	Tube & cover max T change: -25%	and cover, wire &			Assembly; Rubber	Grade B
				fiber reinforced			Smooth Bore, Water	Class 1
							Suction & Discharge	
Air, tensile strength	Ambient	-	Tube 1000 psi min; cover 1000 psi min	Chloroprene cover		4720	Hose Rubber and Hose	ZZ-H-561
Oxygen, aging @ 300 psi	158	46	Tube & cover max T change: -25%	w/syn. tube, wire			Assembly; Rubber	Grade A
ASTM #3 oil	212	70	Cover, T.S. max change: -40%	& fiber reinforced			Smooth Bore, Water	Class 2
Ozone, 100 pphm	212	70	Cover, no cracks				Suction & Discharge	
Water extraction	212	21 hrs	21 milligrams per sq. inch; tube only					
Air, tensile strength	Ambient	-	Tube & cover: 600 psi min	Nat. and/or syn.		2240	Hose; Tender (Locomotive),	ZZ-H-581
Air, 180° bend	Ambient	-	No kinking	tube & cover, wire			Corrugated	
Water	212	8	Tube max T change: -50%	& fiber reinforced				
Air, burst test	Ambient	-	1/2" to 1-1/2" ID, 600 to 450 psi	Syn. rubber tube		4720	Hose & Hose Assemblies,	ZZ-H-601
Oxygen, aging @ 300 psi	158	94	Tube & cover max T change: -25%	& cover			Rubber (Yarn & Fabric	Grade 1
Water	73	22	Tube & cover max vol change: +20%				Reinforced)	
Air, burst test	Ambient	-	1/4" to 4" ID, 600 to 400 psi	Chloroprene cover		4720	Hose, Rubber, Water	ZZ-H-601
Oxygen, aging @ 300 psi	158	94	Tube & cover max T change: -25%	w/syn. rubber tube,			(Yarn-Reinforced)	Grade 3
Water	73	22	Tube & cover max vol change: +20%	yarn reinforced				
Air, burst test	Ambient	-	1300 psi	Syn. tube & cover,	Yes	4720	Hose, Rubber; Windshield	ZZ-H-617
Air, mandrel bend	-67	5	No breaks or cracks	cotton or syn.			Wiper	
Air, oven aging	212	70	Max tensile change. -25%	fiber reinforced				
Ozone, 50 pphm	100	168	Cover, no cracks					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength Air, oven aging	Ambient 158	- 168	2400 psi min Max tensile change: -25%	Nat. and/or syn. rubber		4720	Tubing, Rubber and Plastic	ZZ-T-831 Type I
Air, tensile strength Air, oven aging	Ambient 158	- 168	1100 psi min Max tensile change: -25%	Syn. rubber		4720	Tubing, Rubber and Plastic	ZZ-T-831 Type II
Air, tensile strength Air, oven aging	Ambient 158	- 168	1200 psi min Max tensile change: -25%	Natural rubber		4720	Tubing, Rubber and Plastic	ZZ-T-831 Type III
Air, tensile strength Air, oven aging	Ambient 158	- 168	3500 psi min Max tensile change: -25%	Liquid latex, dipped		4720	Tubing, Rubber and Plastic	ZZ-T-831 Type IV
Air, tensile strength Air, oven aging	Ambient 158	- 168	3000 psi min Max tensile change: -25%	Natural rubber		4720	Tubing, Rubber and Plastic	ZZ-T-831 Type V
Air, vibration Air, vibration Flame	-65 275 -	6 72 -	No deterioration No deterioration Self burning: 15 sec max	Chloroprene impregnated fabric			Duct, Air, Flexible and Semi-Rigid	NAS 1369 Type A
Air, vibration Air, vibration Flame	-75 500 -	6 72 -	No deterioration No deterioration Self burning: 15 sec max	Silicone impregnated fabric			Duct, Air, Flexible and Semi-Rigid	NAS 1369 Type B
Air, tensile strength Oxygen, aging @ 300 psi Isooctane	Ambient 158 73	- 48 46	Tube 1600 psi min; cover 1800 psi min Tube & cover max T change. -25% Cover max vol change: +50%	Chloroprene cover syn. tube wire and fabric reinforcements	Yes	4720	Hose Assemblies, Wire-reinforced Synthetic Rubber, Submarine Rescue Chamber	MIL-H-2217
Air, burst test Oxygen, aging @ 300 psi	Ambient 158	- 48	1/4" to 1-1/2" ID, 1000 to 550 psi Tube & cover max T change: -25%	Neoprene cover w/neoprene, or SBR or nitrile tube cotton or syn fiber reinforced		4720	Hose, Pneumatic (Braided or Wrapped)	MIL-H-2699[1] Classes 1, 2 & 3
Air, burst test Oxygen, aging @ 300 psi Isooctane	Ambient 158 73	- 46 46	2400 psi min Tube & cover max T change. -25% Cover max vol change. +50%	Chloroprene cover w/SBR or chloroprene tube, cotton reinforced	Yes	4720	Hose Assemblies, Rubber, Diver's Breathing Air and Gas Supply	MIL-H-2815
Air, hardness Air, mandrel bend	Ambient Ambient	- -	90 to 95 No cracks	SBR		4710	Lining, Rubber (Synthetic), For Salt-Water Lines	MIL-L-2824[2]

[1] Documtnt cancelled. Use ZZ-H-500.
[2] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test	Ambient	-	1/8" to 1-3/8" ID, 6000 to 4000 psi	Teflon tube wire reinforcement			Hose, Polytetrafluoroethylene, TFE fluorocarbon Resin Wire Braid Reinforced	AMS 3380
Air, flexibility	-65	24	No cracking or breaking					
Air, burst test	Ambient	-	500 psi min	Syn. tube, fabric reinforced, chloroprene cover			Hose, Synthetic Rubber, Aircraft Fueling, Textile Reinforced, Collapsing	AMS 3386
70/30 isooctane/toluene	80	22	Max % vol chg. tube +50; cover +100					
Air, burst test	Ambient	-	1-1/2" to 3" ID; 800 to 650 psi	Syn. tube, fabric reinforced, chloroprene cover			Hose, Synthetic Rubber, Aircraft Fueling, Textile Reinforced, Noncollapsing	AMS 3388
70/30 isooctane/toluene	80	22	Max % vol chg. tube +50; cover +100					
Air, burst test	Ambient	-	2" to 3" ID, 1000 to 750 psi	Syn. tube, wire reinforced, chloroprene cover			Hose, Synthetic Rubber, Aircraft Fueling, Single Wire Braid Reinforced, Noncollapsing	AMS 3389
70/30 isooctane/toluene	80	22	Max % vol chg: tube +50; cover +100					
Air, original properties	Ambient	-	T, 3500 psi min; E, 800% min	Natural		6515	Tubes, Rubber, Penrose, Drainage	MIL-T-36092
Air, oven aging	158	166	Change in T and E, -25% max					
Air, tensile strength	Ambient	-	1250 psi min	PVC		4720	Hose, Sulfuric Acid Resistant (Thermoplastic)	MIL-H-3726[1]
Air, tensile strength	5	4	Tensile strength: 3000 psi min					
Air, oven aging	221	96	Tensile change: -80% max					
Sulfuric acid (Sp gr 1.27)	151	24	Tensile change: -80% max					
Air, burst test	Ambient	-	3/16" to 1/2" ID; 20000 to 14000 psi	Syn rubber tube w/ chloroprene cover, steel double-wire braid reinforced		4930	Hose Assemblies, Grease Gun High and Low Pressure	MIL-H-3868 Type I Grade A
Air, mandrel bend	-65	24	No cracks or breaks					
Air, oven aging	158	24	No deterioration					
ASTM #3 petroleum oil	73	46	Max % vol chg: Tube +35; cover +75					
Air, burst test	Ambient	-	3/16" to 1/2" ID; 20000 to 14000 psi	Syn. rubber tube w/ chloroprene cover, steel double-wire braid reinforced		4930	Hose Assemblies, Grease Gun High and Low Pressure	MIL-H-3868 Type I Grade B
Air, mandrel bend	-40	24	No cracks or breaks					
Air, oven aging	158	24	No deterioration					
ASTM #3 petroleum oil	73	46	Max vol chg: Tube +35; cover +75%					

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test Air, mandrel bend ASTM #3 petroleum oil	Ambient -65 73	- 24 46	3/16" to 3/4" ID; 1200 to 5000 psi No cracks or breaks Max % vol chg: tube +35; cover +75	Syn. rubber tube w/ chloroprene cover, steel wire braid reinforced		4930	Hose Assemblies, Grease Gun High and Low Pressure	MIL-H-3868 Type II Grade A
Air, burst test Air, mandrel bend ASTM #3 petroleum oil	Ambient -40 73	- 24 46	3/16" to 3/4" ID; 1200 to 5000 psi No cracks or breaks Max % vol chg: tube +35; cover +75	Syn. rubber tube w/ chloroprene cover, steel wire braid reinforced		4930	Hose Assemblies, Grease Gun High and Low Pressure	MIL-H-3868 Type II Grade B
Air, burst test Air, mandrel bend Air, oven aging Ozone, 50 pphm Isooctane	Ambient -65 212 100 Ambient	- 72 70 168 46	900 psi min No breaks or cracks No deterioration Cover, no cracking Max % vol chg: tube +35; cover +50	Syn. rubber tube rubber cover, cotton or syn. yarn reinforced	Yes	2530	Hose and Hose Assembly, Rubber; Air and Vacuum Brake, Automotive	MIL-H-3992 Type I Class 1 & 2
Air, burst test Air, mandrel bend Air, oven aging Ozone, 50 pphm Isooctane	Ambient -65 212 100 Ambient	- 72 70 168 46	3/16" to 5/8" ID; 10000 to 6000 psi No breaks or cracks No deterioration Cover, no cracking Max % vol chg: tube +35; cover +50	Syn. rubber tube and rubber cover, steel wire reinforced	Yes	2530	Hose and Hose Assembly, Rubber; Air and Vacuum Brake, Automotive	MIL-H-3992 Type I Class 3
Air, burst test Air, mandrel bend Air, oven aging Isooctane	Ambient -65 212 Ambient	- 72 70 46	3/15" to 5/8" ID; 1000 to 6000 psi No breaks or cracks No deterioration Tube max vol change: +35%	Syn. rubber tube and rubberized cotton cover, steel wire & cotton yarn reinforced	Yes	2530	Hose and Hose Assembly, Rubber; Air and Vacuum Brake, Automotive	MIL-H-3992 Type I Class 4
Air, mandrel bend Air, oven aging Ozone, 50 pphm Isooctane	-65 212 100 Ambient	72 70 168 48	No breaks or cracks No deterioration Cover, no cracks No sep. of tube or cover from plies	Syn. rubber tube and rubber cover, cotton and/or steel wire reinforcement	Yes	2530	Hose and Hose Assembly, Rubber; Air and Vacuum Brake, Automotive	MIL-H-3992 Type II Styles a & b
Air, burst test Air, 180° bend 70/30 isooctane/toluene	Ambient -67 75	- 72 24	1-1/4" to 3" ID; 500 to 375 psi No cracking Max % vol chg: tube +35; cover +75	Nitrile tube, chloroprene cover, wire reinforcement		4720	Hose, Rubber, Gasoline, Lightweight	MIL-H-4441[1]
Air, drum wrap 70/30 isooctane/toluene	-65 75	24 72	No cracking Max % vol chg: tube +35; cover +60	1) Tube, syn. rubber 2) Fabric 3) Wire 4) Syn. rubber layer 5) Wire braid 6) Cover, syn. rubber		4720	Hose Assembly, Rubber, Aerial Refueling	MIL-H-4495

[1] Document cancelled. Use MIL-H-27516.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test	Ambient	-	3/4" to 1-1/4" ID; 2500 to 1200 psi	Rubber tube & cover, cotton or syn. fiber reinforcement		4210	Hose, Cotton, Rubber Lined Water, Braided Construction, with Couplings	MIL-H-4497
Air, mandrel bend	-67	72	No cracks or breaks					
Air, oven aging	158	168	Tube & cover max T change: -25%					
Air, burst test	Ambient	-	1800 psi min	Syn. rubber tube & cover, cotton or syn. fiber reinforcement	Yes	4210	Hose, Rubber, Bromochloro-methane Resistant	MIL-H-4536[1]
Air, mandrel bend	-67	72	No cracks or breaks					
Bromochloromethane	Ambient	24	Tube max vol change: +60%					
Air, burst test	Ambient	-	15000 psi min	Wire reinforced rubber tube, rubber cover, wire braid reinforced	Yes	1660	Hose Assembly, High Pressure, Breathing Oxygen	MIL-H-4722[1]
Air, mandrel bend	-65	48	No cracks or breaks					
Oxygen, aging @ 300 psi	160	96	No change in tensile strength					
Air, burst test	Ambient	-	60 psi min	Nat. or syn. rubber tube & cover, wire & fabric reinforced	Yes	8415	Hose, Rubber, Anti-G Suit, Altitude Suit	MIL-H-5581[2]
Air, mandrel bend	-67	24	No cracking					
Air, oven aging	158	168	Tube & cover max T change: -20%					
Air, burst test	Ambient	-	1/8" to 5/8" ID; 2000 to 700 psi	Rubber tube & cover w/fabric reinforce-ment	Yes	4720	Hose; Aircraft, Low-Pressure, Flexible	MIL-H-5593
Air, mandrel bend	-67	72	No cracking					
Air, mandrel bend	158	3	No deterioration					
MIL-H-5606 mineral oil	158	168	Tube, vol change: ± 10%					
Air, burst test	Ambient	-	1/4" to 4" ID; 1000 to 300 psi	Syn. rubber tube, chloroprene cover, frictioning rein-forcement		4720	Hose; Rubber (Fuel, Oil, Coolant, Water and Alcohol)	MIL-H-6000
ASTM D736	-40	5	No cracks or breaks					
ASTM #1 petroleum oil	252	70	Tube, no decrease in volume					
Ethylene glycol	293	70	Tube, max vol change: -10%					
Isooctane and toluene	75	24	Max vol change: +85%					
Air, burst test	Ambient	-	2200 psi min	Innertube, rein-forcing material, braided outer sur-face	Yes	1660	Hose Assemblies, Low-Pressure, For Breathing Oxygen	MIL-H-6017[3]
Air, mandrel bend	-65	48	No breaks or cracks					
Oxygen, aging @ 300 psi	160	96	Tube max T change: -40%					
Air, burst test	Ambient	-	50 psi min	Syn. rubber tube, chloroprene cover, wire reinforced		4720	Hose, Rubber, Wire-Wound Synthetic, Ice Eliminating System	MIL-H-6399
Air, mandrel bend	-40	24	No cracks					
Air, burst test	Ambient	-	500 psi min	Rubber tube & cover, reinforced		4720	Hose, Rubber, Aircraft Paint Finish Remover	MIL-H-6439
Air, mandrel bend	-55	5	No cracks or breaks					
Paint remover	75	72	Tube & cover max vol change: ± 45%					

[1] Document cancelled without replacement
[2] Document cancelled. For AF use MIL-H-26385.
[3] Document cancelled. Use MIL-H-26626.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test	Ambient	-	1-1/4" to 4" ID; 800 to 500 psi	Syn. rubber tube, chloroprene cover, fabric & static wire reinforcement	Yes	4720	Hose Assemblies, Rubber, Fuel and Water with Reattachable Couplings, Low Temperature	MIL-H-6615
Air, U bend	-67	72	No cracks or breaks or straightening					
70/30 isooctane/toluene	75	24	Max % vol chg. tube +50; cover +100					
Air, burst test	Ambient	-	150 psi min	Compounded tube, chloroprene cover, fabric reinforced	Yes	4720	Hose, Aircraft, Self-Sealing, Aromatic Fuel	MIL-H-7061
60/40 isooctane/aromatic	Ambient	24	Tube & cover max vol change: +90%					
Isooctane, gunfire @ 16 psi	-20	-	Self sealing, 5 minutes					
Air, tensile load	Ambient	-	No damage under 250 lb load	Retractable hose, metal helical stiffener core		4720	Hose, Air Duct, For Ground Heaters	MIL-H-7365
Air, extension & retraction	-65	24	No deterioration					
Flame	-	-	Self burning, 3 sec max					
91 octane gasoline	Ambient	48	Max volume change. +22%					
SAF #10 engine oil	Ambient	48	Max volume change: +22%					
Air, burst test	Ambient	-	3/16" to 2" ID; 600 to 350 psi	Nitrile tube, chloroprene cover asbestos reinforced		4720	Hose, Rubber, Flame-Resistant	MIL-H-7938
Air, mandrel bend	-40	5	No cracking					
Isooctane	Ambient	48	Max volume change: +35%					
Air, burst test	Ambient	-	3" to 9-5/8" ID; 16000 to 10000 psi	Syn. rubber tube, chloroprene cover wire reinforced	Yes	4720	Hose, Hydraulic, High Pressure	MIL-H-8788
Air, mandrel bend	-65	24	No cracks or leakage					
MIL-H-5606 mineral oil	158	168	Max ID change: -10%					
(Hose covered in MIL-H-8788						4720	Hose Assemblies, Rubber, Hydraulic, High Pressure (3000 psi)	MIL-H-8790
Air, burst test	Ambient	-	3" to 33" ID, 12000 to 800 psi	Rubber tube, cotton braid reinforced syn. rubber cover, & wire brain reinforced	Yes	4720	Hose, Rubber, Hydraulic, Fuel, and Oil Resistant	MIL-H-8794
Air, 180° bend	-65	24	Flexible					
MIL-H-5606 mineral oil	158	168	Max ID change: -10%					
50/50 water/alcohol	158	24	Tube max T change: -35%					
70/30 isooctane/toluene	Ambient	72	Tensile strength: 900 psi min					
(Hose covered in MIL-H-8794)						4720	Hose Assemblies, Rubber, Hydraulic, Fuel and Oil Resistant	MIL-H-8795
Air, flexibility	-65	12	No cracking	Syn. rubber w/cotton, linen, fortisan or glass fibers w/wo wire reinforcement, convoluted		1660	Hose, Airduct, Flexible, Aircraft	MIL-H-8796 Class 1
Air, cyclic vibration	160	12	No deterioration					
Flame	-	-	Self burning, 30 sec max					
Isooctane	Ambient	8	No softening or tackiness					
MIL-J-5624 jet fuel	Ambient	8	No softening or tackiness					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, flexibility	-65	12	No cracking	Syn. rubber w/cotton, linen, fortisan or glass fibers w/wo wire reinforcement, convoluted		1660	Hose, Airduct, Flexible, Aircraft	MIL-H-8796 Class 2
Air, cyclic vibration	300	12	No deterioration					
Flame	-	-	Self burning, 30 sec max					
Isooctane	Ambient	8	No softening or tackiness					
MIL-J-5624 jet fuel	Ambient	8	No softening or tackiness					
Air, flexibility	-65	12	No cracking	Syn. rubber w/cotton, linen, fortisan or glass fibers w/wo wire reinforcement, convoluted		1660	Hose, Airduct, Flexible, Aircraft	MIL-H-8796 Class 3
Air, cyclic vibration	300	12	No deterioration					
Flame	-	-	Self burning, 30 sec max					
MIL-J-5624 jet fuel	Ambient	8	No softening or tackiness					
Air, flexibility	-75	12	No cracking	Syn. rubber w/cotton, linen, fortisan or glass fibers w/wo wire reinforcement, convoluted		1660	Hose, Airduct, Flexible, Aircraft	MIL-H-8796 Class 4
Air, cyclic vibration	600	12	No deterioration					
Flame	-	-	Self burning, 30 sec max					
MIL-J-5624 jet fuel	Ambient	8	No softening or tackiness					
Air, burst test	Ambient	-	400 psi min	Nitrile tube, chloroprene cover, braided reinforcement		4720	Hose Assembly, Rubber, Utility, Gasoline (1/4-inch Inside Diameter)	MIL-H-10868
Low temp. flexibility	-40	0.08	Cover, max 5 fold increase in mod.					
Air, oven aging	212	70	Cover max T change: -40%					
Flame	-	-	Cover, self burning, 60 sec max					
70/30 isooctane/toluene	75	46	Max % vol chg tube +30; cover +65					
Air, burst test	Ambient	-	200 psig min	Nitrile tube, chloroprene cover, cotton or syn. fiber reinforced static wire wound		4720	Hose Assemblies, Rubber, Synthetic, Liquid Petroleum Fuels, Dispensing Collapsible	MIL-H-11588 Type I
Low temp. flexibility	-13	0.08	Tube, max 5 fold increase in mod.					
Low temp. flexibility	-40	0.08	Cover, max 5 fold increase in mod.					
60/40 isooctane/aromatic	75	46	Tube max vol change: +40%					
Air, burst test	Ambient	-	350 psig min	Nitrile tube, chloroprene cover, cotton or syn. fiber reinforced static wire wound		4720	Hose Assemblies, Rubber, Synthetic, Liquid Petroleum Fuels, Dispensing Collapsible	MIL-H-11588 Type II
Low temp. flexibility	-13	0.08	Tube, max 5 fold increase in mod.					
Low temp. flexibility	-40	0.08	Cover, max 5 fold increase in mod.					
60/40 isooctane/aromatic	75	46	Tube, max 5 fold increase in mod.					
Air, burst test	Ambient	-	1" to 4" ID; 400 to 600 psi	Nitrile tube, chloroprene cover, syn. rubber embedded fiber reinforced static wire wound		4720	Hose Assemblies, Rubber, Synthetic, Liquid Petroleum Fuels, Dispensing Collapsible	MIL-H-11588 Types III & IV
Low temp. flexibility	-13	0.08	Tube, max 5 fold increase in mod.					
Low temp. flexibility	-40	0.08	Cover, max 5 fold increase in mod.					
60/40 isooctane/aromatic	75	46	Tube, max vol change: +40%					

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test	Ambient	-	1/8" to 3/4" ID; 2000 to 500 psi	Nitrile tube, chloroprene cover fabric reinforced	Yes	4720	Hose, Rubber: Fuel and Oil	MIL-H-13444 Type I
Air, mandrel bend	-67	70	No cracks or breaks					
Ozone, 50 pphm	100	168	No breaks or cracks					
60/40 isooctane/aromatic	80	48	Max % vol chg: tube +60; cover +110					
Air, burst test	Ambient	-	1/8" to 3/4" ID; 2000 to 500 psi	Nitrile tube material & gasoline & oil cover, cotton & steel wire reinforced	Yes	4720	Hose, Rubber: Fuel and Oil	MIL-H-13444 Type II
Air, mandrel bend	-67	70	No cracks or breaks					
Ozone, 50 pphm	100	168	No breaks or cracks					
Air, burst test	Ambient	-	3/16" to 2" ID; 12000 to 1500 psi	Nitrile tube, chloroprene cover, 1 braid wire reinforcement	Yes	4720	Hose, Rubber and Hose Assembly, Rubber (Hydraulic, Flexible)	MIL-H-13531 Type I
Air, mandrel bend	-67	70	Cover, no cracks					
MIL-H-6083 petroleum oil	158	168	Max % vol chg: tube +30; cover +100					
Ozone, 50 pphm	100	168	No cracks					
Air, burst test	Ambient	-	3/26" to 2" ID; 20000 to 4000 psi	Nitrile tube, chloroprene cover, wire braids or braid & spiral plies of wire reinforcement	Yes	4720	Hose, Rubber and Hose Assembly, Rubber (Hydraulic, Flexible)	MIL-H-13531 Types II & III
Air, mandrel bend	-67	70	Cover, no cracks					
MIL-H-6083 petroleum oil	158	168	Max % vol chg: tube +30; cover +100					
Ozone, 50 pphm	100	168	No cracks					
Air, burst test	Ambient	-	1/8" to 1/4" ID; 5000 to 4500 psi	SBR or chloroprene tube, chloroprene cover, imbedded cotton reinforcement	Yes	2530	Hose Assembly, Rubber; Hydraulic Brake	MIL-H-13719
Air, mandrel bend	-65	72	No cracks, breaks or leakage					
VV-H-910 brake fluid	121	70	Tube vol change: +8% to -3%					
Ozone, 50 pphm	100	168	Cover, no cracks or breaks					
Air, burst test	Ambient	-	900 psi min	Rubber tube, fabric reinforcement, chloroprene cover			Air Brake Hose	SAE J1402 Types A & B
Aging,	212	70	No cracks					
Ozone, 50 pphm	104	70	No cracks					
ASTM #3 oil	212	70	Tube & cover, vol change, max 100%					
Air, burst test	Ambient	-	1/4" to 1/2" hose; 10000 to 7000 psi	Rubber tube, fabric reinforcement, chloroprene cover			Air Brake Hose	SAE J1402 Type C
Aging,	212	70	No cracks					
Ozone, 50 pphm	104	70	No cracks					
ASTM #3 oil	212	70	Tube & cover, vol change, max 100%					
Air, burst test	Ambient	-	3/16" to 5/8" hose; 2000 to 1800 psi	Rubber tube, wire w/wo fabric reinforcement chloroprene cover			Air Brake Hose	SAE J1402 Type D
Aging,	212	70	No cracks					
Ozone, 50 pphm	104	70	No cracks					
ASTM #3 oil	212	70	Tube & cover, vol change, max 100%					
Air, burst test	Ambient	-	3/16" to 5/8" hose, 6000 to 3000 psi	Rubber tube, wire w/wo fabric reinforcement chloroprene cover			Air Brake Hose	SAE J1402 Type E
Aging,	212	70	No cracks					
Ozone, 50 pphm	104	70	No cracks					
ASTM #3 oil	212	70	Tube & cover, vol change, max 100%					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test	Ambient	-	1000 psi	Rubber tube, wire fabric reinforced chloroprene cover			Air Brake Hose	SAE J1402 Type F
Aging,	212	70	No cracks					
Ozone, 50 pphm	104	70	No cracks					
ASTM #3 oil	212	70	Tube & cover, vol change, max 100%					
Air, burst test	Ambient	-	600 psi min	1) Chloroprene tube 2) Frictioned fabric 3) Syn. rubber/wire 4) Frictioned fabric 5) Chloroprene cover		4720	Hose, Rubber, Wire-Reinforced (Oil-and-Gasoline, Suction and Discharge Smooth-Bore)	MIL-H-0015100[1] Class I
Oxygen, aging @ 300 psi	158	46	Tube & cover max T change: ± 25%					
Isooctane	73	46	Tube max vol change: +100%					
Air, burst test	Ambient	-	600 psi min	1) Nitrile tube 2) Frictioned fabric 3) Syn. rubber/wire 4) Frictioned fabric 5) Chloroprene cover		4720	Hose, Rubber, Wire-Reinforced (Oil-and-Gasoline, Suction and Discharge Smooth-Bore)	MIL-H-0015100[1] Class II
Oxygen, aging @ 300 psi	158	46	Tube & cover max T change: ± 25%					
Isooctane	73	46	Tube max vol change: +50%					
Air, burst test	Ambient	-	500 psi min	Chloroprene or nat. rubber tube, chloroprene cover, syn. rubberized fabric reinforcement		4720	Hose, Rubber, Sand-blast	MIL-H-15217
Oxygen, aging @ 300 psi	158	48	Max % T Chg: Tube (nat) 40, (syn) 20					
Oxygen, aging @ 300 psi	158	48	Max T change: cover, 25%					
Air, burst test	Ambient	-	600 psi min	1) CR or NBR tube 2) Frictioned fabric 3) Chloroprene cover		4720	Hose and Hose Assemblies, Rubber, Oil-and-Gasoline-Discharge, Smooth-Bore, Light Weight	MIL-H-15523[2] Types A & B
Oxygen, aging @ 300 psi	158	46	Tube & cover max T change: ±25%					
70/30 isooctane/toluene	75	46	Max % vol chg: tube (NBR) 50, (CR) 100					
70/30 isooctane/toluene	75	46	Max vol change: cover, 100%					
Air, burst test	Ambient	-	1/4" to 4" ID, 600 to 300 psi	Chloroprene or SBR tube chloroprene cover fabric reinforced		4720	Hose and Hose Assemblies, Rubber, Wrapped and Braided, Water Service	MIL-H-15923[3]
Air, oven aging	158	48	Tube & cover max T change: ±25%					
Water	Ambient	24	Tube & cover max vol change: +20%					
Air, burst test	Ambient	-	8000 psi min	SBR, nitrile or chloroprene tube & cover wire, w/wo syn. frictioning reinforcement		4210	Hose, Fire-Extinguisher (Portable, 15-pound Carbon-Dioxide)	MIL-H-16236[4]
Air, oven aging	194	48	Tube & cover max T change: ± 25%					
Air, burst test	Ambient	-	2000 psi min	1) Chloroprene tube 2) Glass yarn 3) Chloroprene/cloth 4) Glass yarn 5) Chloroprene cover		4940	Hose Assembly, Plastic Paint Spraying, Electric-Heating	MIL-H-16711[1]
Air, oven aging	212	70	Tube & cover max T change: ±15%					

[1] Document cancelled without replacement.
[2] Document cancelled. Use MIL-H-22240.
[3] Document cancelled. Use ZZ-H-601.
[4] Document cancelled. Use SAE J517.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst pressure Oxygen, aging @ 300 psi 60/40 diisobutylene/ aromatic	Ambient 158 140	- 46 48	600 psi Tube & cover max T change: ±35% Tube & cover max vol change: +110%	1) Chloroprene tube 2) Syn. rubber/fabric 3) Syn. rubber/duck 4) Syn. rubber/wire 5) Syn. rubber/fabric 6) Chloroprene cover		4720	Hose, and Hose Assembly, Rubber, Oil & Gasoline Suction & Discharge	MIL-H-17505 Class I
Air, burst test Oxygen, aging @ 300 psi 60/40 Issoctane/aromatic 60/40 isooctane/aromatic	Ambient 158 75 75	- 46 46 46	600 psi min Tube & cover max T change: ±25% Tube max % vol chg: (CR) +100 Cover max vol change: +100%	Chloroprene or nitrile (NBR) tube, chloroprene (CR) cover, syn. frictionized fabric reinforced		4720	Hose Assemblies, Rubber, Aircraft, Fueling, Collapsible Type	MIL-H-17902
Air, burst test Isooctane and aromatic 60/40 isooctane/aromatic	Ambient Ambient 75	- 24 -	150 psi min Tube & cover max vol change: +90% Gun fire, self sealing, 2 min max	Reinforced inner tube chloroprene		4720	Hose and Hose Assemblies, Aircraft, Self Fueling, Aromatic Fuel	MIL-H-18288[1]
Air, burst test Oxygen, aging @ 300 psi 60/40 isooctane/aromatic 60/40 isooctane/aromatic	Ambient 158 73 73	- 46 46 46	600 psi min Tube & cover max T change. ±25% Max % vol chg. Tube (CR) 100; (NBR) 5 Max vol chg: Cover +100	Chloroprene (CR) or nitrile (NBR) tube syn,-frictioned fabric reinforcement, chloroprene cover		4720	Hose, Rubber (Oil-and-Gasoline Discharge), Smooth-Bore, Light Weight, Bouyant Type; 6 Inch Size	MIL-H-19091[2]
Air, burst test Oxygen, aging @ 300 psi	Ambient 158	- 48	1/2" ID; 800 psi Max tensile change: -25%	Chloroprene, nitrile or butyl tube, chloroprene cover, syn.-rubberized fabric reinforcement		4720	Hose Assemblies, Rubber, Paint Spray Equipment	MIL-H-19639[3]
Air, burst test MIL-H-5606 mineral oil	Ambient 158	- 168	1/4" to 1" ID, 16000 to 7500 No leakage @ 7000 psi	Chloroprene cover fabric backing, wire reinforcement		4720	Hose Assemblies, Flexible (Pneumatic), High Pressure Oil Resistant	MIL-H-19992[4]
Tensile Strength ASTM #3 oil Ozone, 100 pphm Flexibility	Ambient 212 Ambient 212 -67	- 70 - 70 72	Tube & Cover, min 1400 psi Tube & Cover max -30% T.S change 500 psi min Cover, no cracks No cracks after bending to V-shape	Chloroprene Cover & synthetic tube fiber reinforcement		4720	Hose and Hose Assembly Rubber, Smooth Bore Light-Weight, Sewage Discharge and Oily Waste Discharge	MIL-H-20176 Type I & Type II

[1] Document cancelled. Use MIL-H-7061.

[2] Document cancelled. Use MIL-H-22240

[3] Document cancelled Use ZZ-H-521

[4] Document cancelled without replacement

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test	Ambient	-	1-1/2" to 2-1/2" ID, 600 to 500 psi	Nitrile or chloroprene tube, chloroprene cover fabric braid & wire helix reinforcement		4720	Hose Assemblies for Noncollapsible Aviation Fuel	MIL-H-21291
Air, 180° bend	-22	24	No cracking or failure					
Oxygen, aging @ 300 psi	158	46	Tube & cover max T change. ±25%					
60/40 isooctane/aromatic	73	46	Cover, max vol change: +100%					
60/40 isooctane/aromatic	73	46	(NBR) tube max vol change. +50%					
Air, burst test	Ambient	-	6" to 7" ID, 600 to 500 psi	Chloroprene cover & or tube, nitrile tube syn.-frictioned, fabric reinforcement	Yes	4720	Hose and Hose Assemblies Rubber, Oil-and-Gasoline Gasoline Discharge, Smooth-Bore, Light Weight, Bouyant Type	MIL-H-22240
Oxygen, aging @ 300 psi	158	46	Tube & cover max T change. ±25%					
60/40 isooctane/aromatic	73	46	Cover (CR) max vol change. 100%					
60/40 isooctane/aromatic	73	46	Tube, (NBR), max vol change: 50%					
air, mandrel bend	-20	24	No cracking or failure	Chloroprene tube fabric reinforcement, chloroprene cover, static wire wound		4720	Hose Assemblies, Rubber, Aircraft Fueling Collapsible, By Negative Pressure	MIL-H-22279[1]
Oxygen, aging @ 300 psi	158	46	Tube & cover max T change: ±25%					
60/40 Isooctane/aromatic	73	46	Tube & cover max vol change: +100%					
Air, burst test	Ambient	-	600 psi min	Nitrile tube frictioned fabric & wire helix reinforcement, chloroprene cover		4720 4730	Hose-Line Assembly: 4-inch Fueling, Quick-Coupling Type	MIL-H-22297[2]
Air, 90° bend	-40	24	No cracking or separation					
Air, 90° bend	150	24	No cracking or separation					
ASTM #3 petroleum oil	212	70	Max vol change: tube 40%, cover 120%					
Air, pressure test, 200 psia	Ambient	-	No failure		Yes	4720	Duct, Pneumatic Start, Flexible	MIL-D-22706
Air, bend test	-65	10	No damage					
Air, even aging	130	10	No damage					
Air, Burst Pressure	Ambient	-	Sizes 1/4 to 2 inches, 20,000 psi to 4,500 psi	Tube, synthetic Polyester reinforced cloth	Yes	4720	Hose, Reinforced, Water and Oil Resistant, And End Fittings, Reusable, For Flexible Hose Connections	MIL-H-24135 Classes I, II, III, & IV
Oil immersion, MIL-L-17331 17331	158	76	No leakage					
Flexibility	-40	24	No cracks	Cover, Synthetic				
ASTM D746	-80	-	No cracking			4720	Tubing, Rubber, Silicone, For In Flight Feeding	MIL-T-25458[3]
Air, oven aging	300	24	Max T change: -20%					
Water	212	70	Max vol change ±5%					
Air, burst test	Ambient	-	0.110" to 1.406" ID; 12000 to 4000 psi	Tube w/wire braid reinforcement	Yes	4720	Hose Assembly, Tetrafluoroethylene, High Temperature, Medium Pressure	MIL-H-25579
Air, mandrel bend	-67	24	No cracks					
60/40 isooctane/aromatic	450	24	No leakage at room temp					

1 Document cancelled. Use API 1529 and NFPA 407.
2 Document cancelled. Use MIL-H-370 and MIL-C-27487
3 Document cancelled without repacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, burst test Air, bend test Ozone	Ambient -65 100	- 48 1	400 psig min No damage No cracks	Tube w/wo dacron jacket		4720	Duct, Pneumatic, Flexible	MIL-D-26124
Air, bend test air, oven aging Ozone 120 ppm	-65 158 Ambient	48 48 1	No leakage after exposure No leakage after exposure No leakage after exposure	Rubber tube & cover fabric and wire reinforced		1660	Hose, Oxygen Pressurization, Ozone Resistant	MIL-T-26385 Resistant
Air, burst test Air, 180° bend 70/30 isooctane/toluene	Ambient -67 75	- 72 24	1-1/4" to 4"; 1000 to 700 psi Max force to unbend: 40 lbs Max % vol chg. tube +30; cover +60	syn. tube, chloroprene cover fabric reinforcement	Yes	4930	Hose Assembly, Rubber, Fuel, Collapsible, Low Temperature, With Reattachable Couplings	MIL-H-26521
Air, burst test Air, 180° bend Air, oven aging @ 500 psig	Ambient -297 260	- 0.25 48	2200 psig min No loss of strength No loss of strength	Teflon tube wire braid reinforcement	Yes	1660	Hose Assembly, Tetrafluroethylene, Oxygen	MIL-H-26626
Air, burst test Air, 180° bend	Ambient -65	- 24	12000 psig min No cracking or splitting	Teflon tube, chloroprene or teflon cover wire reinforcement	Yes	1730	Hose Assembly, Polytetrafluoroethylene, Oxygen	MIL-H-26633
Air, burst test Air, 180° bend	Ambient -65	- 24	16000 psig min No cracking or splitting	Polyethylene tube chloroprene cover wire reinforced		1730	Hose Assembly, Pneumatic, High pressure	MIL-H-26666
Air, burst test Air, U bend 70/30 isooctane/toluene	Ambient -67 75	- 72 24	700 psi min No cracking Max % vol chg. tube 30; cover 60	Syn. tube, chloroprene cover fabric & wire helix reinforcement		4930	Hose Assembly, Rubber, Gasoline, Refueling Low Temperature	MIL-H-26894
Air, burst test Air, mandrel bend Air, burst test	Ambient -67 450	- 24 1	0.12" to 1.41" ID, 12000 to 4080 psi No cracking No leakage @ 1000 psi	Teflon tube, wire braid reinforcement	Yes	4720	Hose, Tetrafluoroethylene, High Temperature, Medium Pressure	MIL-H-27267
Air, burst test Air, U bend 60/40 isooctane/aromatic	Ambient -67 75	- 72 24	1-1/2" to 6" ID; 600 to 400 psi No cracks Max % vol chg tube 50; cover 100	Nitrile tube, chloroprene cover, braided reinforcement		4930	Hose Assembly, Rubber GRK-6/E32R-1	MIL-H-27508[1]
Air, burst test Air, U bend 60/40 isooctane/aromatic	Ambient -67 75	- 72 24	1-1/2" to 6" ID; 400 to 240 psi No cracks Max % vol chg: tube 50; cover 100	Nitrile tube, chloroprene cover, wire stiffened woven jacket reinforcement		4930	Hose Assembly, Rubber GRK-7/E32R-1	MIL-H-27516

[1] Document cancelled. Use MIL-H-26521.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, Burst Pressure	Ambient	-	1600 psi minimum	Tube & Cover,			Hose Assembly, Rubber,	MIL-H-28523
Air, Tensile Strength	Ambient	-	Tube 1000 psi min, cover 1800 psi min	Synthetic Rubber		4720	Hydraulic & Pneumatic	
ASTM #3 oil	212	70	Tube T.S. 800 psi min	fabric reinforced			Jetting (400 psi working	
ozone 50 pphm	212	70	Cover, No Cracks				pressure)	
Air, Burst Pressure	Ambient	-	2000 psi minimum	Tube, & Cover		4720	Hose Assemblies, Rubber,	MIL-H-28596
ozone resistance 50 pphm	212	70	Cover, No Cracks	Synthetic Rubber			Wire Reinforced 200 psig	
				Wirebraid & Fabric			Saturated Steam Service	
				reinforcement			(3/4" to 2" I.D.)	
Air Tensile Strength	Ambient	-	1200 psi minimum	Natural Rubber		4720	Tubing, Rubber	MIL-T-36966
Air Aging	212	168	Tensile strength change					
			max - 35%					
Air, Burst Pressure	Ambient	-	16,000 to 12,000 psi	Tube, Synthetic		4720	Hose Assembly Tetrafluoro-	MIL-H-38360[1]
				Reinforced, two or			ethylene, High Temperature	
				more layers stain-			High Pressure, Hydraulic	
				less steel braid			and Pneumatic	
Air, Burst Pressure	Ambient	-	16,000 psig minimum	Tube, Tetrafluro-		4720	Hose Assembly, Tetrafluoro-	MIL-H-38390
				ethylene, two or			ethylene, Pneumatic, High	
				more layers of			Pressure	
				stainless steel				
				braid				
Flexibility 180° Bend	-65	-	No Cracking	Cover-Chloroprene				
Air, @ 25 psi	Ambient	0.05	No deformation or damage			1450	Hose Assembly, Propellant	MIL-H-45704
							Transfer Oxidizer and Fuel	Types I & III
Air, @ 60 psi	Ambient	0.02	No deformation or damage			1450	Hose Assembly, Propellant	MIL-H-45704
							Transfer Oxidizer and Fuel	Types II & IV
Air, Tensile strength	Ambient	-	3000 psi minimum	Tubing-polyurethane		4720	Tubing, Rubber, Urethane,	MIL-T-47046[2]
							High Strength and Abrasion	
							Resistant	
Hardness, Shore A	Ambient	-	85±5 points					
Dielectric strength	Ambient	-	400 volts per mil thickness					

[1] Document cancelled. Use AS604A.
[2] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, Burst Pressure	Ambient	-	2000 psig, min	Cover, chloroprene		4720	Hose, Fuel, Flame, Thrower	MIL-H-51059
Bend Test 7 inch Radius	-65	24	No cracks	Reinforcement, wire braid			M8	
Resistance to 80/20 isooctane-Benzene	Ambient	168	-10% max decrease in I.D.					
Air, Burst Test	Ambient	-	75 psi min	Chloroprene	Yes	2940	Hose, Performed: Semi-Flexible, Reinforced	MIL-H-52079
Air, Mandrel Bend	-65	24	No cracks					
Fungus	82	2160	Resistnt					
Air, Burst Test	Ambient	-	500 psi min	Nitrile tube, chloroprene cover syn. fabric reinforcement		4720	Hose, Assembly, Rubber: Lightweight, Collapsible 4 Inch	MIL-H-52262
Air, S Bend	-15	24	No cracking					
70/30 Isooctane/toluene	74	46	Max % vol chg: tube +40; cover +120					
Flexibility 180° Bend	-40		No cracks					
Air, Burst Pressure	Ambient	-	1/4" to 2" 1,500 to 11,000 psi min	Tube-chloroprene	Yes	4720	Hose and Hose Assembly, Hydraulic Pressure - Type	MIL-H-52471
ASTM #3 Oil	212	70	Vol change + 100% max	Reinforcement-steel Wirebraid				
Ozone, 50 pphm	122	168	No cracks	Cover-chloroprene				
Air, Burst Pressure	Ambient		3/4" to 4" 300 to 1,200 psi min			4720	Hose, Rubber: Oil Suction, Wire-Reinforced	MIL-H-52544
ASTM #3 Oil	250	70	Vol change cover + 100% max	Tube & Cover				
			Tube +60% max	Synthetic Rubber				
Ozone, 50 pphm	122	168	No cracks	Reinforcement-steel wirebraid				
Air, Burst Pressure	Ambient	-	3/8" to 1-1/8", 425 to 375 psi min	Tube, Silicone		4720	Hose, Non-Metallic Silicone, Polyester Reinforced (For Coolant and Heating Systems of Diesel and gasoline Powered Engines	MIL-H-62217
Air, Tensile Strength	Ambient	-	1000 minimum	Reinforcement - Polyester fiber				
ASTM #3 Oil	212	70	T.S , -40% max					
Hardness, Shore A	Ambient	-	50 to 70	Tube & Cover		1660	Hose Assemblies, Breathing Oxygen and Air, General Specification for	MIL-H-81581
Ozone, 50 pphm	122	168	No cracking	synthetic elastomer Reinforcement, polyester braid				

Source: https://assist.dla.mil -- Downloaded: 2026/10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, Burst Pressure Air, Tensile Strength ASTM #3 Oil Ozone, 50 pphm	Ambient Ambient 75 212	- - 48 72	400 psi minimum Tube 1500 psi min Cover: 1800 psi min T.S. Tube - 40% max No Cracks in cover	Tube: Butadiene-acrylonitrile Reinforcement-two layers of synthetic fabric Cover: Nitrile or chloroprene		4720	Hose Assembly, Rubber (Synthetic) Fuel Discharge charge, Lightweight	MIL-H-82127
Air, Burst Pressure	Ambient	-	Size 4 to 10, 16,000 psi to 12,000 psi, min	Tube. Tetra-fluoroethylene	Yes	4720	Hose, Tetrafluorethylene, High Temperature, High Pressure (3000 psi), Hydraulic and Pneumatic	MIL-H-83289[1]
Conductivity, at 1,000 volts	Ambient	-	Tube 12 microampers, min	Reinforcement - corrosion resistant steel				
Air, Burst Pressure Air, Tensile Strength Hardness, Shore A Fuel JP-7	Ambient Ambient Ambient 70	- - 168	3" 800 psi min: 4" - 700 psi min Tube & Cover 1400 psi min Tube 75 ± 5 Tube & Cover T.S. 1200 psi min	Tube: Fluoro-elastomer Reinforcement: Nylon Cloth and Steelwire Helix Cover: Chloroprene		4720	Hose Assembly, Fluoro-elastomer Tube, With Reattachable Couplings for JP-7 Service	MIL-H-83373 Type I
Air, Burst Pressure	Ambient	-	Hose Size 3 to 32: 6,000 psi to 1,200 psi min			4720	Hose Assembly, Rubber, Lightweight, Medium Pressure, General Specification	MIL-H-83796

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

MATS AND FLOOR COVERINGS

SPECIFICATION TEST CONDITIONS				CONSTRUCTION AND ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Oxygen, aging	158	166	No deterioration	Nat. and/or syn. rubber links		7220	Mat, Floor (Link-Type)	ZZ-M-46 Classes 1 & 4
Oxygen, aging	158	166	No deterioration	Piled rubber - fabric links		7220	Mat, Floor (Link-Type)	ZZ-M-46 Class 2
Oxygen, aging	158	166	No deterioration	Metal reinforced rubber links		7220	Mat, Floor (Link-Type)	ZZ-M-46 Class 3
Oxygen, aging	158	166	No deterioration	PVC Links		7220	Mat, Floor (Link-Type)	ZZ-M-46 Class 5
Air, original properties	Ambient	-	T, 400 psi. min; H, 65-90	Fabric reinforced nat. or syn. rubber corrugated		7220	Mats; Floor, (Vehicular, Rubber)	KKK-M-0050[1]
Air, oven aging	212	166	Tensile change, -25% max					
Air, flexibility	Ambient	0.08	No breaks or cracks					
Air, original properties	Ambient	-	T, 700 psi. min; elong, 250% min	Syn. or reclaimed rubber, corrugated		7220	Matting; Rubber and Vinyl	ZZ-M-71
Air, flexibility	Ambient	0.08	No breaks or cracks					
Air, original properties	Ambient	-	T, 400-900 psi; elong, 100-250%	Not specified			Automotive Rubber Mats	SAE J80[1]
Air, oven aging	158	70	Max. change: T, -25%, elong, -35%					
Air, original properties	Ambient	-	T, 1200 psi. min; elong, 250% min	Fabric reinforced syn. with/without reclaimed rubber; corrugated		7220	Matting; Rubber and Plastic (Special, Dielectric)	ZZ-M-81 Class 1
Air, figure 8 bend	32	-	No breaks or cracks					
Flame	-	-	Slight flame or flash					
Sulfuric acid, 20%	158	46	Max. loss. T, 30%, elong, 25%					
15,000 volts	Ambient	0.02	No puncture, warming or weakness					
Air, original properties	Ambient	-	T, 700 psi. min; elong, 250% min	Fabric reinforced syn. with/without reclaimed rubber corrugated		7220	Matting; Rubber and Plastic (Special Dielectric)	ZZ-M-81 Class 2
Air, figure 8 bend	32	-	No breaks or cracks					
Sulfuric acid, 20%	158	46	Max. loss. T, 30%; elong, 25%					
15,000 volts	Ambient	0.02	No puncture, warming or weakness					
Air, original properties	Ambient	-	T, 1600 psi. min, elong, 150% min	Vinyl chloride vinylidene chloride or vinyl acetate knurled back		7220	Matting; Rubber and Plastic (Special Dielectric)	ZZ-M-81 Class 3
Air, figure 8 bend	32	-	No breaks or cracks					
Air, oven volatilization	225	5	Volatile matter loss; 0.5% max					
15,000 volts	Ambient	0.02	No puncture, warming or weakness					
Air, original properties	Ambient	-	T, 700 psi min, elong, 250% min	Fabric reinforced rubber			Rubber Matting For Use Around Electrical Apparatus	ASTM D178
15,000 volts	Ambient	-	No puncture, warming or weakness					

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				CONSTRUCTION AND ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Water absorption	70	24	10% max. wt. change	Top layer - synthetic rubber Bottom layer - sponge rubber (chloroprene)		7220	Matting, Floor, Rubber, Sponge Base, Anti-Fatigue	ZZ-M-0085
Air, original properties	Ambient	-	Modulus @ 10%E, 150 psi. min Hardness, 90 min.	Nat. and/or syn. and/or reclaimed rubber; with/ without fabric		7220	Floor-Covering; Rubber, Sheet	ZZ-F-461[1]
Air, original properties	Ambient	-	T, 1500 psi. min; elong, 200% min	Plastic and/or syn. and/or reclaimed rubber; cellular base & solid cover		7220	Mats, Floor, Standing	MIL-M-910
Air, oven aging	194	46	Change: T, ±20%; elong, ±30%					
Isooctane	74	46	Volume change, 10% max					
Water, absorption	74	22	Wt. change; 10% max					
Air, original properties	Ambient	-	T.S. 1300 psi. min; elong, 300% min	Synthetic rubber		7220	Matting, Floor, Rubber Aperture Surface	ZZ-M-001033
Hardness, Shore A	Ambient	-	65 ± 5 points					
Water absorption	70	24	8% max. wt. increase					
Air, original properties	Ambient	-	T, 1200 psi. min; elong, 300% min	Fabric reinforced syn. and/or reclaimed rubber	Yes	7220	Matting; Floor, Rubber Insulating For High Voltage Application	MIL-M-15562 Application
Flame	-	-	Slight flame or flash					
Oxygen, aging	158	46	Tensile change, -20% max					
Sulfuric acid, 20%	158	46	Tensile change, -30% max					
15,000 volts	Ambient	0.02	No puncture, warming or weakness					
Air, original properties	ambient	-	T, 500 psi. min; elong, 200% min	Fabric reinforced synthetic rubber		7220	Mats, Floor, Synthetic Rubber, Shower Stall Light Gray	MIL-M-19018
Air, bend test	Ambient	0.08	No cracking					

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

O-RINGS

SPECIFICATION TEST CONDITIONS				PERFORMANCE		ELASTOMER			
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	TESTS REQUIRED	QPL ISSUED	COMMONLY USED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Hardness, 70 ± 5; Elong	200-400%	Fatigue	No	Nitrile		
Rubber "O" Rings	SAE J120,								
Air, figure 8 bend	-20	5	No cracks	Flexing @				For Automotive Seal	Class I
Air, oven aging	250	70	Elong. change, -50% max	15% stretch @					
ASTM #1 petroleum oil	300	70	Vol. change, ± 5%	room tempera-					
ASTM #3 petroleum oil	300	70	Vol change, +20% max	ture for 24					
				hrs.					
Air, original properties	Ambient	-	Hardness, 70 ± 5; Elong	150-300%	Fatigue	No	Nitrile		
Rubber "O" Rings	SAE J120,								
Air, figure 8 bend	-40	5	No cracks	Flexing @ 15%				For Automotive Seal	Class II
Air, oven aging	212	70	Elong. change, -50% max	stretch @ room					
Isooctane	Ambient	70	Vol. change, -3 to +5%	temperature					
70/30 isooctane/toluene	Ambient	70	Vol. change, +30% max	for 24 hrs.					
Air, original properties	Ambient	-	Hardness, 90 ± 5; Elong.	100% min	None	No	Nitrile		Hydraulic
"O" Ring	SAE J515,								
Air, ASTM D2137 Method A	-30	5	No cracks					Type 1	
Air, compression set	212	22	25% max						
ASTM #3 petroleum oil	212	70	Vol. change, -10 to +5%						
Air, original properties	Ambient	-	Hardness, 88 ± 5; Elong.	100% min	None	No	Butyl	Hydraulic "O" Ring Type 2	SAE J515,
Air, original properties	Ambient	-	Hardness, 70 + 10	Leakage and	No	Butyl		Packing, O-Ring,	NAS 1613,[1]
Phosphate ester lubricant	158	70	Vol. change, ∓10% max	breakout @ -65°F and +160°F @ 2 and 3000 psig. Chew, abrasion and endurance				Phosphate Ester Resistant	Class I
Air, original properties	Ambient	-	Hardness, 88 ± 5	Installation	No	Butyl		Packing, O-Ring,	NAS 1613,[1]
Air, figure 8 bend	-65	72	No breaks	stretch @				Phosphate Ester	Class II
Phosphate ester lubricant	158	70	Vol. change, +10% max	-20°F Crush extrusion and impulse.				Resistant	
Air, original properties	Ambient	-	Hardness, 80 ± 5; Elong. 200% Min	Crush (5600 lb. load, 80% recovery)	No	Nitrile 5330		Rubber, Synthetic Sheet, Strip and Molded	MIL-R-3533 Grade A
Cooling medium, temp retraction	-10	-	10% recovery @ 50% elong.						
Air, oven aging	158	168	Elong 175% min						
ASTM #1 petroleum oil	158	168	Vol change, ± 8%						

[1] Document cancelled without replacement

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS									
ENVIRONMENT AND TEST	TEMP, °F	TIME, HRS	SPECIFICATION REQUIREMENTS	PERFORMANCE TESTS REQUIRED	QPL ISSUED	ELASTOMER COMMONLY USED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Hardness, 70 ± 5, Elong 300% min	Crush (5600	No	Nitrile	5330	Rubber, Synthetic.	MIL-R-3533
Cooling medium, temp retraction	-20	-	10% recovery @ 50% elong.	lb. load, 80%				Sheet, Strip and	Grade B
Air, oven aging	158	168	Elong 275% min	recovery)				Molded	
ASTM #1 petroleum oil	158	168	Vol. change, ± 8%						
Air, original properties	Ambient	-	Permanent set, 50% max	Leakage @	Yes	Nitrile	5330	Packing, "O" Ring,	MIL-P-5315
70/30 isooctane/toluene	Ambient	72	Vol. change, +50% max	650F cyclic				Hydrocarbon Fuel	
				endurance				Resistant	
Air, original properties	Ambient	-	Hardness, 88 min; Elong. 100% min	Installation	Yes	Nitrile	5330	Packing, Preformed	MIL-P-5510
Air, figure 8 bend	-65	72	No breaks	stretch -20°F				Straight Thread Tube	
Air, oven aged	158	166	Elong. change, -20% max	Crush (5600 lb				Fitting Boss	
MIL-H-5606 hydraulic fluid	158	166	Vol. change, 0 to +6%	load, 75% re-					
				covery) Ex-					
				trusion.					
				Impulse					
Air, original properties	Ambient	-	Hardness, 88 min	Leakage and	Yes	Nitrile	5330	Packing, Preformed	MIL-P-5516
MIL-H-5606 hydraulic fluid	158	168	Vol. change, 0 to +5	breakout @				Petroleum Hydraulic	Class A
				160°F and				Fluid Resistant	
				1500 psi. Leak-				160°F	
				age @ -65°F.					
				Cycling. Corro-					
				sion					
Air, original properties	Ambient	-	Hardness, 68 min	Leakage,	Yes	Nitrile	5330	Packing, Preformed	MIL-P-5516
Cooling medium, temp retraction	-45	-	10% recovery @ 50% elong.	breakout,				Petroleum Hydraulic	Class B
MIL-H-5606 hydraulic fluid	158	168	Vol. change, 0 to +10	crush, fatigue				Fluid Resistant	
				cycling and				160°F	
				corrosion					
Air, original properties	Ambient	-	Hardness, 75 ± 5; Elong. 100% min	None	No	Nitrile		Rings, Packing	AMS 7260
Air, hammer bend	-50	5	No cracking					Synthetic Rubber	
Air, compression set	257	70	75% max (85% for small rings)					Fuel and Low Temper-	
70/30 isooctane/toluene	Ambient	96	Vol. change, +30 to +50					ature (70-80)	
Isooctane	Ambient	96	Positive swell						
Air, original properties	Ambient	-	Hardness, 85-95; Elong. 150% min	None	No	Butyl		Rings, Sealing, Butyl	AMS 7263[1]
Synthetic ester lubricant	-65	5	No cracking					Rubber Phosphate	
Air, oven aging	158	168	Elong. change, -35% max					Ester, Hydraulic Fluid	
Phosphate ester lubricant	158	168	Vol. change, 0 to +10%					Resistant (85-95)	
Air, original properties	Ambient	-	Hardness, 75 ± 5; Elong. 125% min	None	No	Silicone		Rings, Sealing,	AMS 7267
Air, ASTM D746	-85	10	No cracks					Silicone Heat	
Air, oven aging	500	70	Elong. change, -55% max					Resistant-Low Com-	
ASTM #1 petroleum oil	350	70	Vol change, 0 to +15%					pression Set (70-80)	

[1] Document cancelled. Use AMS 7262

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS									
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	PERFORMANCE TESTS REQUIRED	QPL ISSUED	ELASTOMER COMMONLY USED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Hardness, 70 ± 5, Elong. 150% min	None	No	Nitrile		Rings, Sealing, Synthetic Rubber-Fuel Resistant (65-75)	AMS 7270
Isooctane, bend test	-40	5	No cracking						
Air, oven aging	212	70	Elong. change, -40% max						
70/30 isooctane/toluene	Ambient	168	Vol. change, 0 to +40%						
ASTM #3 petroleum oil	302	70	Vol. change, +15 to +35%						
Air, original properties	Ambient	-	Hardness, 65 ± 5; Elong. 200% min	Simulated component leakage test	No	Nitrile		Rings, Sealing, Synthetic Rubber-Fuel and Low Temperature Resistant (60-70)	AMS 7271
Air, hammer bend	-60	5	No cracking						
Air, oven aging	257	70	Elong. change, -50% max						
70/30 isooctane/toluene	Ambient	70	Vol. change, +40 to +70%						
Isooctane	Ambient	70	Positive swell						
Air, original properties	Ambient	-	Hardness, 70 ± 5; Elong. 250% min	None	No	Nitrile		Rings, Sealing, Synthetic Rubber-Synthetic Lubricant Resistant NBR Type (65-75)	AMS 7272
Air, temp retraction	-15	-	10% recovery @ 50% elong.						
Air, oven aging	250	70	Elong. change, -50% max						
Synthetic ester lubricant	302	70	Vol. change, 0 to +15%						
70/30 isooctane/toluene	Ambient	70	Vol. change, 0 to 35%						
Air, original properties	Ambient	-	Hardness, 70 ± 5; Elong. 150% min	None	No	Nitrile		Rings, Sealing, Synthetic Rubber-Oil Resistant (65-75)	AMS 7274
Lubricating oil, bend test	-40	5	No cracking						
Air, oven aging	212	70	Elong. change, -40% max						
ASTM #1 petroleum oil	302	96	Vol change, 0 to 10%						
ASTM #3 petroleum oil	302	70	Vol. change, +25 to 45%						
Air, original properties	Ambient	-	Hardness, 70-85; Elong. 200% min	Low and high pressure cycling, breakout and leakage. Fatigue, chew & endurance	No	Butyl		Rings, Sealing, Synthetic Rubber-Phosphate Ester Hydraulic Fluid Resistant (70-85) (Butyl type)	AMS 7277[1]
Phosphate ester, bend test	-65	5	No cracking						
Air, oven aging	158	168	Elong. change, -35% max						
Phosphate ester lubricant	158	168	Vol. change, 0 to 15%						
Air, original properties	Ambient	-	Hardness, 75 ± 5, Elong. 125% min	None	No	Fluorocarbon		Rings, Sealing, Fluorocarbon Rubber, High-Temperature-Fluid Resistant (70-80)	AMS 7279[2]
Cooling medium, temp retraction	+5	-	10% recovery @ 50% elong.						
Air, oven aging	500	70	Elong. change, -50% max						
70/30 isooctane/toluene	Ambient	70	Vol. change, 0 to +10%						
Synthetic ester lubricant	400	70	Vol. change, 0 to +20%						
Air, original properties	Ambient	-	Hardness, 90 ± 5, Elong. 100% min	None	No	Fluorocarbon		Rings, Sealing, Fluorocarbon Rubber, High-Temperature-Fluid Resistant (85-95) Fluorocarbon Type	AMS 7279[2]
Cooling medium, temp retraction	+5	-	10% recovery @ 50% elong.						
Air, oven aging	500	70	Elong. change, -30% max						
70/30 isooctane/toluene	Ambient	70	Vol. change, 0 to +10%						
Synthetic ester lubricant	400	70	Vol. change, 0 to +15%						

[1] Document cancelled without replacement.
[2] Document cancelled. Use AMS 7259.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS									
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	PERFORMANCE TESTS REQUIRED	QPL ISSUED	ELASTOMER COMMONLY USED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Hardness, 70 ± 5, Elong. 250% min	None	No	Nitrile	9320	Rubber Sheet, Solid Molded, & Extruded Shapes, Synthetic Oil Resistant	MIL-R-7362 Type I
Cooling medium, temp retraction	-40	-	10% recovery @ 50% elong.						
Air, oven aging	275	70	Elong. change, -70% max						
Synthetic ester lubricant	275	70	Vol change, +2 to +15%						
Air, original properties	Ambient	-	Hardness, 75 ± 5; Elong. 150% min	None	No	SBR	5330	Gaskets, "O" Rings, For Rockets	MIL-G-17553
Cooling medium, comp. set	-20	96	Set, 70% max						
Air, oven aging	158	96	Elong. change, -15% max						
Water	158	96	Vol. change, +8% max						
Air, original properties	Ambient	-	Hardness, 65 ± 10; Elong 250% min	None	No	Nitrile	5330	Gaskets, Cylinder Liner Seal O-Ring, Synthetic Rubber	MIL-G-21569 Class I
Air, oven aging	194	336	Tensile retention, 75% min						
ASTM #2 petroleum oil	194	336	Vol. change, 0 to +10%						
Water	194	336	Tensile retention, 75% min						
Air, original properties	Ambient	-	Hardness, 65 ± 10; Elong 120% min	None	No	Silicone	5330	Gaskets, Cylinder Liner Seal O-Ring, Synthetic Rubber	MIL-G-21569 Class II
Air, oven aging	194	336	Tensile retention, 75% min						
ASTM #2 petroleum oil	194	336	Vol. change, 0 to +15%						
Water	194	336	Tensile retention, 65% min						
Air, original properties	Ambient	-	Hardness, 60-75; Elong. 300% min	None	No	Nitrile	5330	Gaskets, Heat Exchanger, Various Cross Section Rings, Synthetic Rubber	MIL-G-21610 Type I
Air, oven aging	212	168	Elong. change, -40% max						
ASTM #1 petroleum oil	230	168	Vol. change, +5% max						
ASTM #3 petroleum oil	230	168	Vol. change, +25% max						
Water	212	168	Vol. change, +10% max						
Steam, 50 psig	-	24	Vol. change, +10% max						
Air, original properties	Ambient	-	Hardness, 60-75, Elong. 150% min	None	No	Silicone	5330	Gaskets, Heat Exchanger, Various Cross Section Rings, Synthetic Rubber	MIL-G-21610 Type II
Air, oven aging	300	168	Elong. change, -20% max						
ASTM #1 petroleum oil	300	168	Vol change, +15% max						
Air, original properties	Ambient	-	Hardness, 70 ± 5; Elong. 150% min	None	No	Fluorocarbon	5330	Gasket and Packing Material Petroleum and Phosphate Ester Fluid Resistant	MIL-G-23652[1] Type I
Air, oven aging	212	70	Elong. change, -15% max						
ASTM #3 petroleum oil	212	70	Vol. change, -0 to +5%						
Synthetic ester lubricant	212	70	Vol. change, -0 to +8%						
Air, original properties	Ambient	-	Hardness, 90 ± 5; Elong. 100% min	None	No	Fluorocarbon	5330	Gasket and Packing Material Petroleum and Phosphate Ester Fluid Resistant	MIL-G-23652[1] Type II
Air, oven aging	212	70	Elong. change, -15% max						
ASTM #3 petroleum oil	212	70	Vol. change, -0 to +5%						
Synthetic ester lubricant	212	70	Vol. change, -0 to +8%						

[1] Document cancelled. Use MIL-R-83248.

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS									
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	PERFORMANCE TESTS REQUIRED	QPL ISSUED	ELASTOMER COMMONLY USED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Hardness, 65 ± 5; Elong. 300% min	None	No	Not known	5330	Gasket and Packing Material, Oil Resistant Rubber Access Hull Applications	MIL-G-23983
Air, oven aged	194	46	Elong. change, -20% max						
ASTM #1 petroleum oil	212	70	Vol. change, 0 to +5%						
Water	212	168	Vol. change, 0 to +10%						
Ozone, 100 pphm	100	168	No cracks						
Air, original properties	Ambient	-	Hardness, 68 min; Elong. 180% min	Leakage, breakout, cycling fatigue and crush	Yes	Nitrile	5330	Packing, Preformed, Petroleum Hydraulic Fluid Resistant, 275°F	MIL-P-25732
Cooling medium, temp retraction	-49	-	10% recovery @ 50% elong						
MIL-H-5606 hydraulic fluid	275	72	Vol. change, 0 to +15%						
Air, original properties	Ambient	-	Hardness, 75 ± 5, Elong. 175% min	None	No	Fluorocarbon	5330-9320	Rubber, Fluorocarbon Elastomer, High-Temperature, Fluid-Resistant	MIL-R-25897[1] Type I Class 1
Air, oven aging	600	70	Elong. change, -45% max						
Stauffer Blend 770	400	72	Vol. change, +1 to +10%						
Synthetic ester lubricant	392	72	Vol. change, +1 to +15%						
70/30 isooctane/toluene	Ambient	72	Vol. change, 0 to +5%						
Air, original properties	Ambient	-	Hardness, 90 ± 5; Elong. 120% min	None	No	Fluorocarbon	5330-9320	Rubber, Fluorocarbon Elastomer, High-Temperature, Fluid-Resistant	MIL-R-25897[1] Type I Class 2
Air, oven aging	600	70	Elong. change, -50% max						
Stauffer Blend 770	400	72	Vol. change, +1 to +10%						
Synthetic ester lubricant	392	72	Vol. change, +1 to +15%						
70/30 isooctane/toluene	Ambient	70	Vol. change, 0 to +5%						
Air, original properties	Ambient	-	T.S. 1400 psi min; Elg. 125% min			Fluorocarbon	5330	Rubber, Fluorocarbon Elastomer, High Temperature Fluid and Compression Set Resistant	MIL-R-83248 Type I Class 1
Air, Hardness Shore A	Ambient		75 ± 5						
Air, oven aging	528	70	T.S. - 35% max						
Stauffer Blend 7700	357	70	T.S. -30% max, Elong. -20% max Vol. change, +20% max						
Air, original properties	Ambient	-	Hardness 75 + 3, Elong. 125% min			Nitrile	5330	Packing Preformed, Petroleum Hydraulic Fluid Resistant, Improved Performance of 275°	MIL-P-83461
Air, oven aging	275	70	Compression 60% max						
Hydraulic Fluid MIL-H-5606	275	70	Vol. change, 10 to 20%						

[1] Document cancelled Use MIL-R-83248.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

PACKINGS AND GASKETS

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, 180° bend Steam	Ambient 417	- 24	No cracks No cracks, distortion or hardening	Nat. or syn. rubber 13%; brass wire-asbestos cloth, 50%		5330	Packing Material, Asbestos, Metallic Cloth and Tape	HH-P-31 Type II
Air, tensile	212	1	1/32" or over, 3500 psi. min, 1/64", 1200 psi min	70% asbestos, 10% nat or syn. rubber		5330	Packing; Asbestos, Sheet, Compressed	HH-P-46
Air, 180° bend Steam	Ambient 410	- 24	No cracks No cracks, distortion or hardening	Nat. or syn. rubber 15%, brass wire-asbestos cloth, 50%		5330	Gaskets, Asbestos, Metallic Cloth	HH-G-76 Types I & II
Air, compressibility ASTM #3 petroleum oil 70/30 Isooctane/toluene	212 330 80	1 5 5	Recovery, 15 to 40% Thickness increase, 0 to 70% Thickness increase, 0 to 45%	Nat. or syn. rubber and asbestos or other mineral (15 grades) fibers			Nonmetallic Gaskets for General Automotive Purposes	SAE J90 Type I
Air, compressibility ASTM #3 petroleum oil Isooctane	Ambient 212 80	- 70 22	Recovery, 70 to 75% Vol. change, -2 to +50% Vol. change, -5 to +35%	Nat. or syn. rubber and cork (11 grades)			Nonmetallic Gaskets for General Automotive Purposes	SAE J90 Type II
Air, compressibility ASTM #3 petroleum oil 70/30 Isooctane/toluene Water	212 330 80 80	1 5 5 22	Recovery, 15 to 40% Thickness increase, 0 to 70% Thickness increase, 0 to 45% Thickness increase, 15 to 50%	Nat. or syn. rubber and cellulose or other organic fibers (24 grades)			Nonmetallic Gaskets for General Automotive Purposes	SAE J90 Type III
Air, original properties Air, 180° bend Air, compression set Air, oven aging	Ambient -13 158 158	- - 22 166	Elong. 400% min, hardness 50 No cracks 25% max Elongation change, -30% max	Nat. or syn. rubber		5330	Gasket; Rubber, Molded or Extruded, for Concrete Non-Pressure Sewer Pipe	HH-G-160[1]
Air, original properties Air, compression set Air, oven aging Water	Ambient 158 158 158	- 22 96 158	Tensile, 1200 psi min; elong. 350% min 25% max Elongation change, -20% max Weight increase, 10% max	Nat. or syn. rubber			Joints for Circular Concrete Sewer and Culvert Pipe, Using Flexible, Watertight Rubber Type Gaskets	ASTM C443/
Air, original properties	Ambient	-	Hardness, 50-80	Nitrile or poly-acrylate			Lathe Cut Seals	SAE J654
Air, original properties Air, compression set Air, compression set Air, oven aging Ozone, 100 pphm	Ambient -35 194 194 104	- 94 46 46 70	Tensile, 1000 psi min; elong. 300% min 75% max 30% max Elongation change, -30% max No cracks	Syn. rubber		5330	Rubber Material, 45 Durometer Hardness	MIL-R-900

[1] Document cancelled. No replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, ASTM D746	-20	94	No cracks	Syn. rubber		5330	Gasket Material, Synthetic Rubber (For Bolted Steel Tanks)	MIL-G-1086 Type I
Air, compression set	-20	94	60% max					
Air, compression set	194	46	40% max					
Isooctane	74	46	Volume change, 10 min					
70/30/Isooctane/toluene	74	46	Volume change, 70% max					
Air, ASTM D746	-20	94	No cracks	Syn. rubber		5330	Gasket Material, Synthetic Rubber (For Bolted Steel Tanks)	MIL-G-1086 Type II
Air, compression set	-20	94	60% max					
Air, compression set	194	46	50% max					
Isooctane	74	46	Volume change, 10 min					
70/30/Isooctane/toluene	74	46	Volume change, 70% max					
Air, original properties	Ambient	-	Tensile, 1000 psi. min; elong, 300% min	Chloroprene, SBR, Butyl or Nitrile		5330	Gasket Materials, Synthetic Rubber, 50 & 60 Durometer Hardness	MIL-G-1149 Type I
Air, flexibility	-20	16	Flexible					
Air, compression set	158	94	75% max					
Air, oven aging	158	94	Elongation change, -35% max					
Air, original properties	Ambient	-	Tensile, 1000 psi. min; elong, 250% min	Chloroprene, SBR, Butyl or Nitrile		5330 9320	Gasket Materials, Synthetic Rubber, 50 & 60 Durometer Hardness	MIL-G-1149 Type II
Air, flexibility	-20	16	Flexible					
Air, compression set	158	94	75% max					
Air, oven aging	158	94	Elongation change, -35% max					
Air, compressibility	Ambient	-	Recovery, 15 to 40%	Nat. or syn rubber and asbestos or other mineral fibers (16 grades)			Nonmetallic Gasket Material for General Automotive and Aeronautical purposes	ASTM F104 Type I
ASTM #3 petroleum oil	300	5	Thickness increase, 0 to 70%					
70/30 Isooctane/toluene	80	5	Thickness increase, 0 to 45%					
Air, compressibility	Ambient	-	Recover, 70 to 75%	Nat. or syn. rubber and cork (11 grades)			Nonmetallic Gasket Material for General Automotive and Aeronautical Purposes	ASTM F104 Type 2
Air, mandrel bend	212	70	No cracks					
ASTM #3 petroleum oil	212	70	Volume change, -2 to +50%					
Isooctane	80	22	Volume change, -5 to +35%					
Air, compressibility	Ambient	-	Recovery, 75% min	Nat. or syn. cellular rubber and cork (3 grades)			Nonmetallic Gasket Material for General Automotive and Aeronautical Purposes	ASTM F104 Type 2
Air, mandrel bend	212	70	No cracks					
ASTM #3 petroleum oil	212	70	Volume change, -2 to +50%					
Isooctane	80	22	Volume change, -10 to +25%					
Air, compressibility	Ambient	-	Recovery, 20 to 55%	Nat. or syn. rubber and cellulose or other organic fibers (18 grades)			Nonmetallic Gasket Material for General Automotive and Aeronautical Purposes	ASTM F104 Type 3
ASTM #3 petroleum oil	80	22	Thickness increase, 5 to 30%					
70/30 Isooctane/toluene	80	22	Thickness increase, 5 to 30%					
Water	80	22	Thickness increase, 15 to 90%					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Tensile, 700 psi min; elong. 150% min	Nat. or syn. rubber			Sheet Rubber Packing	ASTM D1330/ Grade I
Air, oven aging	158	94	Tensile change, -25% max					
Air, compression set	158	22	75% max					
Air, original properties	Ambient	-	Tensile, 400 psi min; elong. 150% min	Nat or syn. rubber			Sheet Rubber Packing	ASTM D1330/ Grade II
Air, oven aging	158	94	Tensile change, -25% max					
Air, compression set	158	22	75% max					
Air, compression set	158	22	16% max	Nat. or syn. rubber			Rubber Ring for Asbestos-Cement Pipe	ASTM D1869/
Cooling medium, ASTM D746	-13	-	No cracks					
Water	212	480	Volume change, 12% max					
ASTM #3 petroleum oil	212	70	Volume change, -1 to +15%					
Air, compression set	194	46	40% max	Syn. rubber		5330	Rubber Sheet, Strip Extruded, and Molded Shapes, Synthetic, Oil Resistant	MIL-R-2765
Air, compression set	-20	94	35% max					
ASTM #3 petroleum oil	158	94	Volume change, 25% max					
Benzene	74	22	No delaminatuon					
Air, original properties	Ambient	-	Hardness, 80 max	40% Syn rubber, 30% graphite		5330	Rubber Sheet, Solid, Unvulcanized, High Graphite, Gasket Use, Symbol 2352	MIL-R-2778
(Test performed on rubber compound only)								
TT-S-735 40% aromatic	74	24	Volume change, 100% max	Syn. rubber cotton sheeting		5330	Joing Sealing Packing	MIL-J-28291
MIL-L-15017 lubricating oil	210	1000	Satisfactory performance @ 1650 psi	12% syn rubber, 40% cotton fabric	Yes	5330	Packing Assembly Hydraulic Conical and V Types	MIL-P-2911 Type I
MIL-L-15017 lubricating oil	210	1000	Satisfactory performance @ 1650 psi	12% syn rubber, 40% cotton, asbestos or wire asbestos fabric	Yes	5330	Packing Assembly Hydraulic Conical and V Types	MIL-P-2911 Type II
Air, original property	Ambient	-	T.S. 1500 psi min	Syn. rubber		5325	Grommets-Rubber, Hot-Oil and Coolant Resistant	MIL-G-3036
Air, impact dropping weight	-40	24	No cracks or deformation					
Air, oven aging	212	70	Breaking strength, 100 lbs. min					
Lubricating Oil	300	72	Volume change, 0 to 15%					
Ethylene glycol	300	72	Volume change, 0 to 25%					
Air, oven aging	200	15	Mandrel bend, no cracks	Nat. or syn. rubber or asbestos fibers			Gasket, Oil Resisting	AMS 32301
Lubricating Oil	250	5	Thickness increase, 40% max					
Gasoline	Ambient	5	Thickness increase, 40% max					

1 Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, oven aging	212	15	Mandrel bend, no cracks	Syn. rubber and asbestos fibers			Gasket, Oil Resisting	AMS 3231[1]
Lubricating Oil	300	5	Thickness increase, 20% max					
Gasoline	80	5	Thickness increase, 25% max					
Air, compressibility	Ambient	-	25% max	Syn. rubber and asbestos fibers			Asbestos and Synthetic Rubber Sheet, Hot Oil Resistant	AMS 3232
Air, oven aging	212	16	Mandrel bend, no cracks					
ASTM #1 petroleum oil	300	5	Thickness increase, 0 to 10%					
Isooctane	80	5	Thickness increase, 0 to 10%					
Air, compression set	158	22	70% max	Syn. rubber and cork			Synthetic Rubber and Cork Composition. General Purpose Soft	AMS 3250
Cooling medium, ASTM D746	-40	-	No cracks					
Air, oven aging	212	70	Mandrel bend, no cracks					
ASTM #1 petroleum oil	212	24	Volume change, ±15%					
Isooctane	80	24	Volume change, -5 to 25%					
Air, compression set	158	22	80% max	Syn. rubber and cork			Synthetic Rubber and Cork Composition. General Purpose Medium	AMS 3251
Cooling medium, ASTM D746	-40	-	No cracks					
Air, oven aging	212	70	Mandrel bend, no cracks					
ASTM #1 petroleum oil	212	24	Volume change, ±10%					
Isooctane	80	24	Volume change, -5 to 25%					
Air, compression set	158	22	80% max	Syn. rubber and cork			Synthetic Rubber and Cork Composition General Purpose Firm	AMS 3252
Cooling medium, ASTM D746	-40	-	No cracks					
Air, oven aging	212	70	Mandrel bend, no cracks					
ASTM #1 petroleum oil	212	24	Volume change, ±10%					
Isooctane	80	24	Volume change, -5 to 25%					
Air, hydrostatic pressure	Ambient	-	180 psi min	Syn. rubber	Yes	1355	Diaphrams, Synthetic-Rubber	MIL-D-3377 Type I
Air, oven aging	158	96	Hydrostatic pressure, 180 psi min					
SAE #30 paraffin oil	80	24	Weight change, ±1%					
Air, hydrostatic pressure	Ambient	-	300 psi min	Syn rubber	Yes	1355	Diaphrams, Synthetic-Rubber	MIL-D-3377 Type II
Air, oven aging	158	96	Hydrostatic pressure, 210 psi min					
SAE #30 paraffin oil	80	24	Weight change, 1 to +3%					
Air, compression set	158	22	10% max	Syn. rubber		5330	Rubber, Synthetic; Sheet, Strip and Molded	MIL-R-3533 Type II
Air, ASTM D736 bent loop	-17	5	No cracks					
ASTM #1 petroleum oil	168	70	Volume change, ±10%					
(Tests performed on rubber compound only)								
Air, compressed set	158	22	40% max	Syn. rubber with or without fabric		1560	Fittings, Tank, Power-plant Fluid, Removable General Specification For	MIL-F-5577 Type I
ASTM #1 petroleum oil	215	70	Volume change, -20 to +10%					
Ozone, 100 PPM	100	1/2	No cracks					

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
(Tests performed on rubber compound only)								
Air, compressed set	212	22	70% max	Syn. rubber with or without fabric		1560	Fittings, Tank, Power-plant Fluid, Removable General Specification For	MIL-F-5577 Type II
ASTM #1 petroleum oil	275	70	Volume change, -20 to +10%					
Ozone, 100 PPM	100	1/2	No cracks					
Air, compression set	158	22	80% max	Syn. rubber and cork		5330	Cork and Rubber Composition Sheet; for Aromatic Fuel and Oil Resistant Gaskets	MIL-C-6183 Type I, Cl, 1, Gr. A (40-55) Gr. B (55-70)
Air, compressibility	140	5	10% min					
ASTM #1 petroleum oil	212	70	Volume change, ±15%					
TT-S-735 40% aromatic	74	24	Volume change, +20% max					
Air, compression set	158	22	55% max	Syn. rubber and cork		5330	Cork and Rubber Composition Sheet; for Aromatic Fuel and Oil Resistant Gaskets	MIL-C-6183 Type I, Cl, 1 Gr. C (70-85)
Air, compressibility	140	5	25% min					
ASTM #1 petroleum oil	212	70	Volume change, ±15%					
TT-S-735 40% aromatic	74	24	Volume change, +20% max					
Air, compression set	158	22	80% max	Syn. rubber and cork		5330	Cork and Rubber Composition Sheet; for Aromatic Fuel and Oil Resistant Gaskets	MIL-C-6183 Type I, Cl.2 Gr. A (40-55) Gr. B (55-70)
Air, compressibility	140	5	25% min					
ASTM #1 petroleum oil	212	70	Volume change, 0 to +10%					
TT-S-735 40% aromatic	74	24	Volume change, +60% max					
Air, compression set	158	22	55% max	Syn. rubber and cork		5330	Cork and Rubber Composition Sheet; for Aromatic Fuel and Oil Resistant Gaskets	MIL-C-6183 Type I, Cl.2 Gr. C (70-85)
Air, compressibility	140	5	25% min					
ASTM #1 petroleum oil	212	70	Volume change, 0 to +10%					
TT-S-735 40% aromatic	74	24	Volume change, +60% max					
Air, compression set	158	22	80% max	Syn. rubber and cork		5330	Cork and Rubber Composition Sheet, for Aromatic Fuel and Oil Resistant Gaskets	MIL-C-6183 Type II, Cl.1 Gr. A (40-55) Gr. B (55-70)
Air, compressibility	140	5	15% min					
ASTM #1 petroleum oil	212	70	Volume change, ±15%					
TT-S-735 40% aromatic	74	24	Volume change, +25% max					
Air, compression set	158	22	55% max	Syn. rubber and cork		5330	Cork and Rubber Composition Sheet; for Aromatic Fuel and Oil Resistant Gaskets	MIL-C-6183 Type II, Cl.1 Gr. C (70-85)
Air, compressibility	140	5	15% min					
ASTM #1 petroleum oil	212	70	Volume change, ±15%					
TT-S-735 40% aromatic	74	24	Volume change, +25% max					
Air, compression set	158	22	80% max	Syn. rubber and cork		5330	Cork and Rubber Composition Sheet; for Aromatic Fuel and Oil Resistant Gaskets	MIL-C-6183 Type II, Cl.2 Gr. A (40-55) Gr. B (55-70)
Air, compressibility	140	5	30% min					
ASTM #1 petroleum oil	212	70	Volume change, - to +10%					
TT-S-735 40% aromatic	74	24	Volume change, +60% max					
Air, compression set	158	22	55% max	Syn. rubber and cork		5330	Cork and Rubber Composition Sheet; for Aromatic Fuel and Oil Resistant Gaskets	MIL-C-6183 Type II, Cl.2 Gr. C (70-85)
Air, compressibility	140	5	30% min					
ASTM #1 petroleum oil	212	70	Volume change, 0 to +10%					
TT-S-735 40% aromatic	74	24	Volume change, +60% max					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, compressibility Air, compressibility 70/30 Isooctane/toluene	Ambient Ambient 74	- - 22	12 ± 5% Recovery, 45% min Thickness change, 0 to 20%	Nat. or syn. rubber, asbestos		5330	Asbestos Sheet, Compressed, For Fuel, Lubricant, Coolant, Water, and High-Temperature Resistant Gaskets	MIL-A-7021 Class 1
Air, compressibility Air, compressibility Water	Ambient Ambient 212	- - 70	12 ± 5% Recovery, 45% min Thickness change, 0 to 10%	Nat. or syn. rubber asbestos fibers		5330	Asbestos Sheet, Compressed, For Fuel, Lubricant, Coolant Water and High Temperature Resistant Gaskets	MIL-A-7021 Class 2
Air, compression set Air, compression set Isooctane ASTM #1 petroleum oil Isooctane	Ambient 212 80 212 80	- 70 5 70 5	15% max 10% max Compression set, 20% max Thickness change, 0 to 10% Thickness change, 0 to 15%	18 cr-8 Ni screen between rubber like gasket			Gaskets, Type XX Engine Accessory Drive. Corrosion Resistant Steel Screen Reinforced Controlled Performance	AMS 7283
Air, original properties	Ambient		T.S. 1200 psi min, elong. 150% min	Synthetic rubber		5330	Rubber Synthetic Solid Sheet Strip and Fabricated Parts Synthetic Oil	MIL-R-7362 Type II
MIL-H-5606 Hydraulic Fluid and nitrogen, endurance	-65 to 200	-	10% max air leakage after cycling	Nat. or syn. rubber		5330	Packings, Gaskets, and Fillers, Performed Rubber or Synthetic Rubber (for Recoil Mechanism)	MIL-P-11501[1]
Air, original properties Air, oven aging Cooling medium, ASTM D1053	Ambient 437 -40	- 70 -	Tensile, 500 psi, min; elong. 75% min Elongation change, 30% max Flexible	Syn. rubber		5330	Packing, Performed; Pneumatic Hose Couplings, Universal	MIL-P-11719
Air, compressibility Air, mandrel bend ASTM #3 petroleum oil 70/30 Isooctane/toluene	Ambient -40 302 78	- 6 5 5	Recovery, 15 to 40% No breaks or cracks Thickness increase 0 to +70% Thickness increase 0 to +45%	Nat. or syn rubber asbestos or other mineral fibers (15 grades)		5330	Gasket Material, Non-Metallic	MIL-G-12803 Type I
Air, compressibility Air, mandrel bend ASTM #3 petroleum oil Isooctane	Ambient -40 212 78	- 6 70 22	Recovery, 76% min No breaks or cracks Volume change, -2 to +50% Volume change, -5 to +15%	Nat. or syn. rubber and cork (9 grades)		5330	Gasket Material, Non-Metallic	MIL-G-12803 Type II
Air compressibility ASTM #3 petroleum oil 70/30 Isooctane/toluene Water	Ambient 78 78 78	- 22 22 22	Recovery, 20 to 55% Thickness increase, +5 to +30% Thickness increase, +5 to 30% Thickness increase, +15 to 90%	Nat. or syn. rubber cellulose or other organic fabric (24 grades)		5330	Gasket Material, Non-Metallic	MIL-G-12803 Type III

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Tensile, 1000 psi min; elong, 400% min	Nat. or syn. rubber		4240	Gaskets, Rubber	MIL-G-13210
Air, compression set	158	22	25% max					
Air, original properties	Ambient	-	Tensile, 1200 psi, min, elong, 300% min	Syn. rubber		5330	Rubber Sheet: Synthetic Medium Soft General - Purpose Gasket Material (For Extreme Climatic Conditions)	MIL-R-14328
Air, compression set	-65	94	60% max					
Air, compression set	194	46	40% max					
Water	74	24	Volume change, -2 to 5%					
(Tests performed on rubber compound only)								
Air, original properties	Ambient	-	Tensile, 1500 psi min; elong 300% min	Syn. rubber with		5330	Packing (Wiper Ring).	MIL-P-14574
Air, compression set	158	22	50% max	6 to 10 piles of			Synthetic Rubber, Cloth	
ASTM #3 petroleum oil	212	70	Volume change, 0 to 120%	cotton duck			Insertion	
(Tests performed on rubber compound only)								
Air, original properties	Ambient	-	Tensile, 1800 psi min; elong, 300% min	Chloroprene		5330	Rubber, Shaft Covering Material, (For Marine Propellar Shafts)	MIL-R-15058[1] Type II
Air, oven aging	158	96	Tensile change, ±20%					
Water	212	96	Volume change, 15% max					
(Tests performed on rubber compound only)								
Air, original properties	Ambient	-	Tensile, 1200 psi min; elong, 250% min	SBR		5330 8030	Rubber, Shaft Covering Material, (For Marine Propellar Shafts)	MIL-R-15058[1] Type III
Air, oven aging	158	96	Tensile change, ±20%					
Water	212	96	Volume change, 15% max					
(Tests performed on rubber compound only)								
Air, original properties	Ambient	-	Tensile, 1200 psi min; elong, 250% min	Nitrile		5330 8030	Rubber, Shaft Covering Material, (For Marine Propellar Shafts)	MIL-R-15058[1] Type IV
Air, oven aging	158	96	Tensile change, ±20%					
Water	212	96	Volume change, 15% max					
Air, original properties	Ambient	-	Tensile, 1500 psi min; elong, 400% min	Class I, Chloro-prene; Class III, Nitrile		5330	Rubber Gasket Material 50 Durometer Hardness (Maximum)	MIL-R-15624 Class I, Class III
Air, flexibility	-20	16	Flexible					
Air, compression set	194	46	30% max					
Air, oven aging	194	46	Elongation change, -30% max					
Water	74	24	Volume change, 5% max					
Air, original properties	Ambient	-	Tensile, 1000 psi min; elong, 300% min	SBR		5330	Rubber Gasket Material 50 Durometer Hardness (Maximum)	MIL-R-15624 Class II
Air, flexibility	-20	16	Flexible					
Air, compression set	194	46	30% max					
Air, oven aging	194	46	Elongation change, -30% max					
Water	74	24	Volume change, 5% max					

1 Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Tensile, 1200 psi min; elong, 300% min	Syn. rubber		9320	Parts, Synthetic Rubber, for Use with Batteries or in Battery Compartments of Submarines	DOD-P-15817
Air, compression set	194	46	40% max					
Air, oven aging	194	46	Elongation change, -30% max					
Sulfuric acid, 60%	158	168	Volume change, 0 to +8%					
Flame	-	-	No burning after flame is removed	Syn. rubber asbestos cloth (2 ply)		5330	Gaskets, Asbestos Metallic Cover, Rubber Core	MIL-G-17927
(Tests performed on rubber compound only)								
Air, original properties	Ambient	-	Tensile, 1000 psi min; elong, 300% min					
Air, compression set	194	46	40% max					
ASTM #3 petroleum oil	158	70	Volume change, -1 to +7%	Syn. rubber	Yes	5330	Packings, Hydraulic High Pressure (For Hydropneumatic Systems)	MIL-P-19152
Mineral oil	-	-	Cycling test, satisfactory performance					
Air, original properties	Ambient	-	Tensile, 2500 psi min; elong, 250% min	Nitrile		9330	Gaskets, Synthetic Rubber, Oil Resistant, Slide Valve (For 21-inch Submerged Torpedo Tubes)	MIL-G-19769
Air, compression set	194	46	40% max					
ASTM #3 petroleum oil	158	94	Volume change, +3% max					
Hardness, Shore A	Ambient	-	75 ± 5					
Air, compressibility	Ambient	-	Recovery, 50% min	Syn. rubber		5330	Packing, V Ring	MIL-P-19918 V packing (85-95)
ASTM #3 petroleum oil	212	70	Volume change, +45% to +65%					
Air, compression set	212	70	30% max	Syn. rubber		5330	Packing, V Ring	MIL-P-19918 Filler Ring (55-65)
ASTM #3 petroleum oil	212	70	Volume change, +30 to +40%					
(Tests performed on rubber compound only)								
Air, original properties	Ambient	-	Tensile, 1000 psi min; elong, 300% min	Syn. rubber		5330	Gaskets, Metal Inserted Rubber, Armored Hatch	MIL-G-20078
Air, compression set	-35	94	40% max					
Air, compression set	194	46	30% max					
Benszene	74	22	No delamination					
Air, compression set	212	70	60% max	Syn rubber		5330	Packing, Vulcanized Asbestos-Metallic (For Small Arms)	MIL-P-20099
ASTM #3 petroleum oil	212	70	Volume change, 0 to +40%					
MIL-H-19457 hydraulic fluid	180	1000	Satisfactory performance @ 3000 psi	Syn rubber with cotton, leather or asbestos	Yes	5330	Packing Assemblies, Hydraulic Concial and V Types, Fire Resistant Type Hydraulic Fluid	MIL-P-21099

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Tensile, 1600 psi min, elong, 70% min	SBR		5330	Rubber Sheet, Solid,	MIL-R-21252
Air, compression set	212	70	65% max				Synthetic, Shipboard	
Water	194	70	Volume change, +25% max				Water Evaporator Gasketing	
(Tests performed on rubber compound only)						5330	Seals, Plain or Plain	MIL-S-21558
MIL-F-17111 hydraulic fluid	150	70	Volume change, -1 to +10%	Syn. rubber			Encased, Oil	Grades A & B Class 1
(Tests performed on rubber compound only)						5330	Seals, Plain or Plain	MIL-S-21558
MIL-F-17111 hydraulic fluid	200	70	Volume change, -1 to +10%	Syn. rubber			Encased, Oil	Grades A & B Class 2
Air, original properties	Ambient	-	T.S. 1800 psi min; elong, 250% min Hardness 60 ± 10	Syn. rubber		5330	Gasket, Cylinder	MIL-G-21569 Class I
Air, oven aging	194	336	T.S. -25% max change Compression set 50% max change					
Oil immersion #2 Oil	194	94	T.S. -25% max change Volume change +10% max					
Air, original properties	Ambient	-	T.S. 500 psi min Elong 120% min Hardness 65 ± 10	Syn. rubber		5330	Gasket Cylinder	MIL-G-21569 Class II
Air, oven aging	194	336	T.S. -25% max change Compression set 50% max change					
Oil immersion #2 Oil	194	94	T.S. -35% max change Volume change +15% max					
Air, original properties	Ambient	-	Tensile, 1200 psi min; elong, 300% min	Nitrile	Yes	5330	Gaskets, Heat Exchanger,	MIL-G-21610
Air, compression set	158	22	35% max				Various Cross Section	Type I
ASTM #3 petroleum oil	230	168	Volume change, +20% max				Ring, Synthetic Rubber	
Steam	280	24	Volume change, 10% max					
Air, original properties	Ambient	-	Tensile, 600 psi min; elong, 150% min	Silicone	Yes	5330	Gaskets, Heat Exchanger,	MIL-G-21610
Air, compression set	158	22	40% max				Various Cross Section	Type II
ASTM #1 petroleum oil	230	168	Volume change, 15% max				Ring, Synthetic Rubber	
Air, original properties	Ambient	-	T.S. 2400 psi min, elong, 25% min Hardness 65 ± 5	Ethylene-Propylene		9320	Gasket & Packing Material Rubber for Use with Polar	MIL-G-22050 Grade 1
Air, aging	280	166	T S. -30% max, elong, -30% max				Fluids, Steam and Air at	
MIL-H-19457 Hydraulic Fluid	212	166	Volume change 0- 10%				Moderately High Temperatures	
Steam	330	166	Volume change +5% max					

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	T.S. 2400 psi min; elong 150% min Hardness 80 ± 5	Ethylene Propylene		9320	Gasket & Packing Material Rubber for Use with Polar Fluids, Steam and Air at Moderately High Temperatures	MIL-G-22050 Grade 2
Air, aging	280	166	T.S. -30% max; elong, -30% max					
MIL-H-19457 Hydraulic fluid	212	166	Volume change 0 - 10%					
Steam	330	166	Volume change +5% max					
Air, original properties	Ambient	-	Tensile, 1600 psi min; elong, 150% min	Syn. rubber		5330	Gasket and Packing Material Petroleum and Phosphate Ester Fluid Resistant	MIL-G-23652[1] Type I
Air, compression set	212	70	25% max					
ASTM #3 petroleum oil	212	70	Volume change, 0 to +5%					
MIL-H-19457 hydraulic fluid	212	70	Volume change, 0 to +8%					
Air, original properties	Ambient	-	Tensile, 1700 psi min; elong, 100% min	Syn. rubber		5330	Gasket and Packing Material Petroleum and Phosphate Ester Fluid Resistant	MIL-G-23652[1] Type II
Air, compression set	212	70	40% max					
ASTM #3 petroleum oil	212	70	Volume change, 0 to +5%					
MIL-H-19457 hydraulic	212	70	Volume change, 0 to +8%					
Air, original properties	Ambient	-	Tensile, 1500 psi min; elong, 300% min	Syn. rubber		5330	Gasket and Packing Material, Oil Resistant Rubber, Access Hull Applications	MIL-G-23983
Air, compression set	194	46	30% max					
ASTM #1 petroleum oil	212	70	Volume change, 9 to +5%					
Ozone, 100 pphm	100	168	No cracks					
Air, original properties	Ambient	-	Specific gravity 2.15 Melting Point 327°C	Polytetra-Fluoroethylene		5330	Packing Material, Braided TFE (Poly-tetrafluoroethylene	MIL-P-24396
Lubricant Content	Ambient	-	15% petroleum oil					
Rubber conforms to MIL-H-5606				Synthetic rubber		5330	Packing, Performed Petroleum Hydraulic Fluid Resistant 275°F	MIL-P-25732
Air, original properties	Ambient		T.S. 200 psi min, elong, 200% min Hardness 50 to 70	Tetrafluoroethylene		5330	Gasket Material, Tetrafluorethylene Resin, Glass-Filled Cryogenic Application	MIL-G-38426[2]
Water absorption	Ambient	336	Wt increase 0.5% max					
MIL-L-10295, lubricating oil	-65	16	Sealing test, no leak during shutdown	Syn. rubber chrome leather	Yes	5330	Seal, Plain, and Seal Plain, Encased: Fluid Radial, Single and Multiple Lip Sealing Member	MIL-S-45005 Class 1
MIL-L-15015, lubricating oil	170	192						
MIL-L-10295, lubricating oil	-65	16	Sealing test, no leak during shutdown	Syn. rubber	Yes	5330	Seal, Plain, and Seal Plain, Encased Fluid Radial, Single and Multiple Lip Sealing Member	MIL-S-45005 Class 2
MIL-L-15015, lubricating oil	200	192						

[1] Document cancelled. Use MIL-R-83248.

[2] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	COMPOSITION	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
MIL-L-10295, lubricating oil	-65	16	Sealing test, no leak during shutdown	Syn. rubber	Yes	5330	Seal, Plain, and Seal Plain, Encased: Fluid Radial, Single and Multiple Lip Sealing Member	MIL-S-45005 Class 3
MIL-L-15015, lubricating oil	300	192						
Rubber conforms to AMS 3222				Chloroprene rubber		5330	Gasket, RF and Pressure	MIL-G-46898
Rubber conforms to ZZ-R-765, Class III, Grade 25				Silicone rubber		5330	Gasket shielding, Electronic-oriented Wires Embedded in Silicone Rubber, Pressure Seal	MIL-G-47197
Air, original properties	Ambient	-	T.S. 100 psi; elong, 500% Hardness 30 to 80	Synthetic rubber		5330	Rubber Synthetic Sheets Strips Molded or Extruded Shapes	MIL-R-6855 Class 1
Air, oven aging	212	70	T.S. -20% max, elong. -50% max					
Oil immersion	212	70	Volume change -30 to +10%					
Air, original properties	Ambient	-	T.S. 1200 to 1500 psi; elong, 300 to 500%; Hardness 30 to 60	Synthetic rubber		5330	Rubber Synthetic Sheets Strips Molded or Extruded Shapes	MIL-R-6855 Class 2
Air, oven aging	212	70	T.S. -20% max; elong. 40% max					
Oil immersion	212	70	Volume change +10%					
Air, original properties	Ambient	-	T.S. 1600 psi min Elongation 100% min Hardness 85 ± 5	Ethylene-Propylene		5330	Rubber, Ethylene-Propylene, Hydrazine Resistant	MIL-R-83412 Type I
Air, oven aging	257	70	T.S. -35% max Elongation -30% max Hardness +5 points					
Oil immersion, Hydrazine	160	96	T.S. -20% max Vol. change +3% max					
Air, original properties	Ambient	-	T.S. 1350 psi min Elongation 125% min Hardness 75 ± 3	Synthetic		5330	Packings, Rubber, Synthetic, Solid Sheet, Strip and Fabrication Parts Synthetic Oil Resistant	MIL-P-83461
Oil immersion Conforming to MIL-H-5606	275	70	T.S. -50% max change Elongation -35% max change Volume Change +20%					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

TIRES, TUBES AND RELATED ITEMS

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP, °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	ELASTOMER	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
(Tests on cured patch)	Ambient	-	T, 2000 psi min; E, 600% min	Natural rubber		2640	Patch, Repair, for Inner Tubes and Tubeless Tire Liners	ZZ-P-112
Air, original properties	Ambient	-	T, psi min, tread 1800; sidewall 1000	Natural or synthetic rubber, Rayon or nylon cord		2610	Tires, Pneumatic, Vehicular (Highway)	ZZ-T-381 Type I
Air, original properties	Ambient	-	T, psi min, tread 1700, sidewall 900	Natural or synthetic rubber, Rayon or nylon cord		2610	Tires, Pneumatic, Vehicle and Portable Equipment	ZZ-T-381 Type II
Air, original properties Air, oven aging	Ambient 158	- 70	T, 2000 psi min; E, 200% min; H, 65±10 Max change, T, -15%; E, -25%, H, +5	Type of rubber not specified		2630	Tire, Solid Rubber, and Wheel, Solid Rubber Tire, (Industrial)	ZZ-T-391 Type I
Air, original properties Air, oven aging Ozone, 50 pphm	Ambient 158 100	- 70 168	T, 2000 psi min; E, 200% min; H, 65±10 Max change, T, -15%, E, -25%, H, +5 No cracks under 7X magnification	Type of rubber not specified		2630	Tire, Solid Rubber, and Wheel, Solid Rubber Tire, (Industrial)	ZZ-T-391 Type II
Air, original properties Methanol, ASTM D746 Air, oven aging	Ambient -65 158	- 0.05 70	T, 3800 psi min; E, 400% min, h, 75±20 No cracks Max change; T, -15%, E, -25%, H, +5	Type of rubber not specified		2630	Tire, Solid Rubber, and Wheel, Solid Rubber Tire (Industrial)	ZZ-T-391 Type III
Air, road service test Air, road service test	Ambient Ambient	- -	Class A; No failure after 1500 miles Class B, No failure after 2500 miles	Tires; natural Tires; natural		2610	Tire, Pneumatic; Inner Tube, Pneumatic Tire; (Bicycle)	ZZ-T-401[1]
Air, original properties	Ambient	-	Tread; T, 1700 psi min; E, 400% min Sidewalls, T, 900 psi min	Tires, natural or synthetic		2610	Tire Pneumatic, Industrial	ZZ-T-410
(Tests on cured materials) Air, tensile strength Cooling medium, ASTM D746	Ambient -65	- 0.05	2000 to 3300 psi, varying with type No cracks	Natural, SBR, butyl or polybutadiene		2640	Tire, Pneumatic: Retread and Repair Materials	ZZ-T-416
(Repair and retread materials covered in ZZ-T-416 Curing bags and tubes covered in MIL-C-14625)						2640	Tire, Pneumatic: Retreaded and Repaired	ZZ-T-441

[1] Document cancelled without replacement

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	ELASTOMER	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength	Ambient	-	Psi min; Butyl, 1200, Natural, 2100	Butyl or natural		2610	Inner Tube, Pneumatic Tire	ZZ-I-550
Air, elongation	Ambient	-	% min, Butyl, 450, Natural 550					
Air, endurance test (Cl B)	-64	168	No cracks or leaks					
Air, tension set	225	5	% max; Butyl 35; Natural, 25					
Air, original properties	Ambient	-	Hardness, Type A, 85 to 95	Type A: Natural or synthetic. Type B: PVC		5670	Treads, Metallic and Nonmetallic, Nonskid	RR-T-650
Air, tensile strength	Ambient	-	Psi min, Butyl, 1400, Natural 2300	Natural or butyl		2610	Tubes, Inner, Vehicle Puncture-Sealing	ZZ-T-766[1]
Air, elongation	Ambient	-	% min; Butyl, 500, Natural, 600					
Air, tension set	225	5	% max, Butyl, 30, Natural, 25					
Air, original properties	Ambient	-	T, 1900 psi min, E, 200% min; H, 70±10	Synthetic rubber type not specified		2630	Wheels, Solid Elastomer Tired, for Track Laying Vehicles	MIL-W-3100
Air, oven aging	158	166	T change, 25% max; E change, 35% max					
Ozone, 50 pphm	100	168	No cracks under 7X magnification					
Air, original properties	Ambient	-	T, 2100 psi min, E, 550% min	type of rubber not specified	Yes	2620	Inner Tube, Pneumatic Tire Aircraft	MIL-I-5014
Cooling medium, ASTM D746	-65	0.05	No cracks					
Air, air retention	Ambient	24	Air pressure loss, 5% max	type of rubber not specified		2620	Tires, Pneummatic, Aircraft	MIL-T-5041
Cooling medium, ASTM D746	-65	0.05	No cracks					
Air, original properties	Ambient	-	Camelback; T,3300 psi min; E,475% min	Natural		2640	Repair and Treading Materials, Aircraft Pneumatic Tire	MIL-R-7725[2]
Air, original properties	Ambient	-	Cushion, T, 2500 psi min; E, 550% min					
Air, original properties	Ambient	-	Padding; T, 2500 psi min, E, 550% min					
Air, original properties	Ambient	-	Tread repair; T, 2200 psi min; E, 500% min					
Air, original properties	Ambient	-	T.S. Tread 1700 psi min; Sidewall, 900 psi min Elongation 400% sidewall, 300% sidewall	Natural or synthetic rubber		2610	Tires, Pneumatic, Low Speed, Off Highway	ZZ-T-1083
Air, tensile strength	Ambient	-	Bushings, 3500 psi min, Shoes, 2900 psi min	Type of rubber not specified	Yes	2530	Track Shoe Assemblies Track Shoe Pads, and Track Shoe Sets, Vehicular: Rubberized	MIL-T-11891
Air, elongation	Ambient	-	Bushings, 500% min, Shoes 400% min					
Cooling medium, ASTM D746	-40	0.05	No cracks (bushings, shoes & pads)					
Air, oven aging	158	70	Change in elong. bushings, -15%, shoes, -25%					
Ozone, 50 pphm	100	168	No cracks under 7X magnification					

1 Document cancelled without replacement.
2 Document cancelled. Use ZZ-T-416.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	ELASTOMER	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength	Ambient	-	Tread, 1700 psi min; sidewall, 900 psi min	Natural or synthetic	Yes	2610	Tire, Pneumatic: For Military Ground Vehicles	MIL-T-12459
Air, elongation	Ambient	-	Tread, 400% min; sidewall, 300% min					
Air, test wheel performance	-64	168	No cracks or breaks					
Ozone, 50 pphm	100	720	Cracking no greater than for control					
Air, curing @ 85 psig	310	6	Type I, class 1; no damage	Natural or butyl		4910	Curing Bags and Curing Tubes Tire Repair, Recapping & Retreading	MIL-C-14625
Air, curing @ 85 psig	310	3	Type I, class 2; no damage					
Air, curing @ 130 to 180 psig	310	6	Type II, classes 1 and 2; no damage					
Air, original properties	Ambient	-	Tread T.S. 1300 psi run, Sidewall TS 900 psi min Elongation, tread 400% min; sidewall 300% min	Natural or synthetic		2610	Tire, Pneumatic, Agricultural	ZZ-T-1619
Air, original properties	Ambient	-	T, 2000 psi min (nat); 1500 psi min (syn)	Natural or synthetic		2530	Wheels, - Cushion Tread (Semi-Pneumatic) For Mobile Ground Support Equipment	MIL-W-21985
Air, original properties	Ambient	-	H, 70 ± 3 (outer shell); 55 ± 3 (core)					
Air, compression set	158	24	20% max					
Air, original properties	Ambient	-	T, E & H, as per approved value	SBR (unvulcanized)		2640	Tread Rubber, Solid Rubber Tire for Track Laying Vehicles	MIL-T-45301
Air, blowout resistance	100	6	No cracking, chunking or blowout					
Rubber properties conforms to MIL-T-3100				Synthetic rubber		2630	Wheels, Solid Rubber Tired, Rebuilt	MIL-W-46759[1]
(Tests on vulcanized bushings)								
Air, original properties	Ambient	-	T, 3500 psi min; E, 500% min; H, 55-68	Pin bushing. Natural or nat/syn blend		2530	Rubber Stock Unvulcanized: For Track Shoes, Pads, and Pin Bushings	MIL-R-46762 Style II
Cooling medium, ASTM D746	-67	0.05	No cracks					
Air, oven aging	158	70	T, 3000 psi min, E, 425% min					
(Tests on vulcanized shoes and pads)								
Air, original properties	Ambient	-	T, 2900 psi min; 400% min; H, 63-73	Block Stock SBR		2530	Rubber Stock Unvulcanized: For Track Shoes, Pads, and Pin Bushings	MIL-R-46762 Style I
Cooling medium, ASTM D746	440	0 05	No cracks					
Air, oven aging	212	70	T, 2500 psi min; E, 300% min					
Ozone, 50 pphm	100	168	No cracks under 7X magnification					

[1] Document cancelled. Use MIL-T-3100

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS								
ENVIRONMENT AND TEST	TEMP, °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	ELASTOMER	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
No specific properties listed				Natural or synthetic rubber		2610	Tire, Pneumatic: Large Size, Off-the-Road, General Specification For	MIL-T-52583[2]
Air, original properties	Ambient	-	T.S. 2500 psi min, Elongation 475% mmin Hardness 62 ± 5	Natural or synthetic rubber		2640	Tread Rubber: Strip Form Stock, for Retreading Pneumatic Tires	MIL-T-62118[3]
Air, original properties	Ambient	-	T.S. 2500 psi min Elongation 500% min	Natural or synthetic natural		2610	Tire, Pneumatic: For Truck, Logistical Goer Type, (Tubeless)	MIL-T-62129
Air, original properties	Ambient	-	Tread T.S. 1700 psi min; sidewall T.S. 1300 psi min Elongation 400% min	Natural or synthetic rubber		2610	Tire: Pneumatic; with Flap, 14.00-20, Run Flat	MIL-T-62157

[2] Document cancelled without replacement.
[3] Document cancelled. Use ZZ-T-416.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

WIRE, CABLE AND RELATED ELECTRICAL ITEMS

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, elongation	Ambient	-	Jkt min %. PVC, 100; CR, 300	Chloroprene or PVC	Chloroprene (CR) or PVC		6145	Cable and Wire, Power, Electrical, Non-metallic Sheathed	J-C-94[1] Types NM, NMC, and UF
Air, mandrel bend	14	5	No cracks, Type NM						
Air, mandrel bend	-4	5	No cracks; Types NMC & UF						
Air, mandrel bend	-40	20	No cracking of elastomer	SBR	Chloroprene		6145	Cable, Telephone, (W-108-B)	J-C-96
Oxygen, @ 300 psi	160	240	Min T: jacket, 1000 psi						
Ozone, 50 pphm	100	168	No cracking of jacket						
Air, tensile strength	Ambient	-	Min psi. ins 500; jkt 1800	Nat and/or SBR	Chloroprene		6145	Cable, Power, Electrical and Wire, Electrical	J-C-103[1] Types R & RW
Oxygen, aging @ 300 psi	158	96	Max % T chg: ins -25; jkt 1800						
ASTM #2 petroleum oil	250	18	Max % T chg jacket -40						
Air, tensile strength	Ambient	-	Min psi: ins 1500, jkt 1800	Chlorosulfonated polyethylene	Chloroprene		6145	Cable, Power, Electrical and Wire, Electrical	J-C-103[1] Type RHW-1
Oxygen, aging @ 300 psi	176	168	Max % T chg: ins -25; jkt -50						
ASTM #2 petroleum oil	250	18	Max % T chg: jacket -40						
Air, tensile strength	Ambient	-	Min psi: ins 1500, jkt 1800	Nat and/or SBR and/or butyl	Chloroprene		6145	Cable, Power, Electrical and Wire, Electrical	J-C-103[1] Type RH & RHW-2
Oxygen, aging @ 300 psi	176	168	Max % T chg. ins -50; jkt -50						
ASTM #2 petroleum oil	250	18	Max % T chg. jacket -40						
Air, tensile strength	Ambient	-	Min psi: ins 700, jkt 1800	Nat and/or SBR and/or butyl	Chloroprene		6145	Cable, Power, Electrical and Wire, Electrical	J-C-103[1] Type RHH
Air, oven aging	260	168	Max % T chg ins -40, jkt -50						
ASTM #2 petroleum oil	250	18	Max % T chg: jacket -40						
Air, tensile strength	Ambient	-	Min psi ins 3000; jkt 1800	Natural	Chloroprene		6145	Cable, Power, Electrical and Wire, Electrical	J-C-103[1] Type RU, & RUW
Oxygen, aging @ 300 psi	158	96	Max % T chg ins -15; jkt -30						
ASTM #2 petroleum oil	250	18	Max % T chg jacket -40						
Air, tensile strength	Ambient	-	Min psi: ins 3000, jkt 1800	Natural	Chloroprene		6145	Cable, Power, Electrical and Wire, Electrical	J-C-103[1] Type RUH
Oxygen, aging @ 300 psi	176	168	Max % T chg ins -20						
Oxygen, aging @ 300 psi	158	96	Max % T chg jkt -30						
ASTM #2 petroleum oil	250	18	Max % T chg. jkt -40						
Air, original properties	Ambient	-	Min T. 800 psi, E 250%	Silicone	Asbestos or glass braid		6145	Cable, Power, Electrical and Wire, Electrical	J-C-103[1] Type SA
Air, oven aging	277	1440	Max % E chg: -35						
Air, mandrel bend	14	5	No cracks	Rubber or plastic	Natural or chloroprene		6145	Cable and Wire, Power, Electrical, (Service-Entrance and Service-Drop)	J-C-115[1] Types SE & USE
Flame	-	-	Self burning 1 min max						

[1] Document cancelled Use J-C-30

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, mandrel bend	14	1	No cracks	Thermoplastic	None		6145	Cable and Wire; Thermo-plastic-Insulated, General Purpose, (0 to 600 Volt Service)	J-C-129[1] Type TW & THW
Air, mandrel bend	250	1	No cracks						
(Tests on rubber only)									
Air, original properties	Ambient	-	Min T: 1400 psi; E 250%		Chloroprene		6145	Cable, Power, Electrical and Wire, Electrical, (Weather-Resistant)	J-C-145[2] Type I
Oxygen, aging @ 300 psi	158	96	Max % chg: T -25; E -35						
ASTM #2 petroleum oil	250	18	Max % chg: T -40, E -40						
(Type I covered by Series S or SJ of J-C-580 Type II covered by MIL-C-3432)				Natural, SBR, PVC	Natural, SBR, PVC or chloroprene		6150	Cable Assembly, Power, Electrical, for 125 Volt Equipment	J-C-175
(Tests on rubber only)									
Air, original properties	Ambient	-	Min T: 1200 psi; E 400%	Natural	Not applicable			Natural Rubber Performance Insulation For Wire and Cable, 60C Operation	ASTM D353
Air, oven aging	158	96	Max E chg: -15%						
Air, tensile strength	Ambient	-	1500 psi min	PVC	None		6145	Cable (Wire), Two-Conductor, Parallel	MIL-C-442 Types I, II & III Class 1
Air, mandrel bend	-65	5	No cracks						
Air, aging @ 1/3 psi	160	48	Not soft or tacky						
Air, tensile strength	Ambient	-	1200 psi min	PVC	None		6145	Cable (Wire), Two-Conductor, Parallel	MIL-C-442 Types I, II & III Class 2
Air, mandrel bend	-40	5	No cracks						
Air, aging @ 1/3 psi	160	48	Not soft or tacky						
Air, tensile strength	Ambient	-	3000 psi min	SBR	None		6145	Cable (Wire), Two-Conductor, Parallel	MIL-C-442 Types I, II & III Class 3
Air, mandrel bend	-65	5	No cracks						
Oxygen, aging @ 300 psi	158	94	Tensile strength: 900 psi min						
Air, tensile strength	Ambient	-	1200 psi min	SBR	None		6145	Cable (Wire), Two-Conductor, Parallel	MIL-C-442 Types IV, V & VI Class 2
Air, mandrel bend	-40	5	No cracks						
Air, aging @ 300 psi	158	94	Tensile strength: 900 psi min						
(Tests on rubber only)									
Air, original properties	Ambient	-	Min T: 1500 psi; E 400%	Natural	Not applicable			Natural Rubber Heat-Resisting Insulation For Wire and Cable, 75C Operation	ASTM D469
Air, oven aging @ 80 psi	260	20	Max E chg. -50%						
(Tests on rubber only)									
Air, original properties	Ambient	-	Min T: 3500 psi, E 500%	Not applicable	Natural			Natural Rubber Jacket For Wire and Cable	ASTM D532
Oxygen, aging @ 300 psi	158	96	Min T 2500 psi; E 400%						

[1] Document cancelled. Use J-C-30.

[2] Document cancelled. Use ANSI C8 35.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, mandrel bend	-30	24	No cracking of jkt	Natural	Synthetic			High Tension Ignition Cable	SAE J557 Types HTLR, HTHR & HTS
Air, oven aging	250	48	No cracking of jkt						
Kerosene	Ambient	18	No damage to ins						
SAE #30 oil	250	-40	No cracking of jkt						
Air, corona 20000 volts	Ambient	2	No failure	Natural	Braid			High Tension Ignition Cable	SAE J557 Type HTB
Air, mandrel bend	-30	24	No cracking of jkt	PVC	None			High Tension Ignition Cable	SAE J557 Types HTT
Air, oven aging	250	48	No cracking of jkt						
Kerosene	Ambient	18	No damage to insulation						
Air, original properties	Ambient	-	Min T: 2300 psi; E 125%	PVC	None			Low Tension Cable	SAE J558[1] Types GPT, HDT & SGT
Kerosene & SAE 10 W oil	122	20	Max OD chg: +15%						
SAE 30 and gasoline	Ambient	24	Max OD chg: +15% (Natural)	Natural or PVC	Braid			Low Tension Cable	SAE J558[1] Types GPB, HDB & HDB-X
Kerosene & SAE 10 W oil	122	20	Max OD chg: +15% (PVC)						
Gasoline and SAE 30 oil	Ambient	24	Max OD chg: +15%	Natural or synthetic	None			Low Tension Cable	SAE J558[1] Type SGR
Air, elongation	Ambient	-	Min. ins 250%; jkt 300%	Not specified	Not specified			Seven Conductor Jacketed Cable For Truck and Trailer Connections	SAE J559
Air, mandrel bend	-20	4	No cracking of jkt						
Oxygen, aging @ 300 psi	158	96	Max E chg. ins & jkt -30%						
ASTM #2 petroleum oil	250	18	Max E chg. jkt -40%						
(Tests on rubber only)									
Air, original properties	Ambient	-	Min T. 450 psi, E 250%	Natural or synthetic	Not applicable			Ozone-Resisting Insulation For Wire and Cable	ASTM D574
Air, oven aging	158	168	Min T 400 psi; E 200%						
Ozone, 10000 to 15000 pphm		3	No cracks						
Air, original properties	Ambient	-	Min: Cl 2; T 500 psi, E 200%	Natural or SBR (Cl 2), PVC (Cl 11), Chloroprene (Cl 13)	Braid or none		6145	Cord, Flexible, and Wire, Fixture, (Electrical 0 to 600 Volt Service)	J-C-580 Types C, K, P, P-2, PD, PO, PO-2, PW & PW-2
Air, original properties	Ambient	-	Min. Cl 11; T 1600 psi, E 200%						
Air, original properties	Ambient	-	Min: Cl 13; T 1200 psi, E 250%						
Oxygen, aging @ 300 psi	158	96	Cl 2, Max E chg. -35%						
Air, oven aging	212	168	Cl 11, Max E chg: -50%						
Air, oven aging	158	168	Cl 13, Max E chg: -40%						

[1] Document cancelled. Use SAE J1127 and J1128.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Min: Cl 2, T 500 psi, E 200%	Natural or SBR (Cl 2), PVC (Cl 11), PVC (Cl 12)	Braid or none		6145	Cord, Flexible, and Wire, Fixture, (Electrical 0 to 600 Volt Service)	J-C-580 Types ET, SPT-2, TF, TFF, SPT-3, HC & HPD
Air, original properties	Ambient	-	Min: Cl 11; T 1600 psi, E 200%						
Air, original properties	Ambient	-	Min. Cl 12; T 1500 psi, E 100%						
Oxygen, aging @ 300 psi	158	96	Cl 2; Max E chg: -35%						
Air, oven aging	212	168	Cl 11; Max E chg: -50%						
Air, oven aging	178	1440	Cl 12; Max E chg: -30%						
Air, original properties	Ambient	-	Min: Cl 2, T 500 psi, E 200%	Natural or SBR (Cl 2, 7), Natural (Cl 5, 9)	None or braid		6145	Cord, Flexible, and Wire, Fixture, (Electrical 0 to 600 Volt Service)	J-C-580 Types RF-2, FF-2, RFH-2 & FFH-2
Air, original properties	Ambient	-	Min: Cl 5; T 3000 psi, E 650%						
Air, original properties	Ambient	-	Min: Cl 7; T 700 psi, E 300%						
Air, original properties	Ambient	-	Min: Cl 9, T 3000 psi, E 650%						
Oxygen, aging @ 300 psi	158	96	Cl 2; Max E chg. -35%						
Oxygen, aging @ 300 psi	158	96	Cl 5; Max E chg: -25%						
Oxygen, aging @ 300 psi	178	168	Cl 7, 9; Max E chg: -50%						
Air, original properties	Ambient	-	Min T: 500 psi; E 100%	Silicone (Cl 22)	Braid		6145	Cord, Flexible, and Wire, Fixture, (Electrical 0 to 600 Volt Service)	J-C-580 Types SF-2 & SFF-2
Air, oven aging	410	1440	Max E chg: -75%						
Air, original properties	Ambient	-	Min: Cl 3, T 600 psi, E 250%	Nat or SBR (Cl 3, 4) chloroprene (Cl 17)	Braid or none		6145	Cord, Flexible, and Wire, Fixtures, (Electrical 0 to 600 Volt Service)	J-C-580 Types HPN, SP-3, E
Air, original properties	Ambient	-	Min: Cl 4; T 1500 psi, E 350%						
Air, original properties	Ambient	-	Min: Cl 17; T 1200 psi, E 250%						
Oxygen, aging @ 300 psi	158	96	Cl 3; Max E chg: -35%						
Oxygen, aging @ 300 psi	158	96	Cl 4; Max E chg. -30%						
Air, oven aging	248	240	Cl 17; Max E chg: -40%						
Air, original properties	Ambient	-	Min: Cl 3; T 600 psi, E 250%	Nat or SBR (Cl 3) PVC (Cl 11)	PVC (Cl 11, 12)		6145	Cord, Flexible, and Wire, Fixtures, (Electrical 0 to 600 Volt Service)	J-C-580 Types SVT, SRDT & SJT
Air, original properties	Ambient	-	Min: Cl 11; T 1600 psi, E 200%						
Air, original properties	Ambient	-	Min: Cl 12; T 1500 psi, E 100%						
Oxygen, aging @ 300 psi	158	96	Cl 3; Max E chg: -35%						
Air, oven aging	212	168	Cl 11; Max E chg: -50%						
Air, oven aging	178	1440	Cl 12; Max E chg: -30%						
Air, original properties	Ambient	-	Min: Cl 3; T 600 psi, E 250%	Nat or SBR (Cl 3) Nat (Cl 5)	Nat or SBR (Cl 6) chloroprene (Cl 15)		6145	Cord, Flexible, and Wire, Fixtures, Electrical 0 to 600 Volt Service)	J-C-580 Types EO, SRD, S, SO, SV
Air, original properties	Ambient	-	Min: Cl 5; T 3000 psi, E 650%						
Air, original properties	Ambient	-	Min: Cl 6; T 1500 psi, E 300%						
Air, original properties	Ambient	-	Min. Cl 15; T 15000 psi, E 300%						
Oxygen, aging @ 300 psi	158	96	Cl 3; Max E chg. -35%						
Oxygen, aging @ 300 psi	158	96	Cl 5; Max E chg· -25%						
Oxygen, aging @ 300 psi	158	96	Cl 6; Max E chg. -30%						

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Min. Cl 2; T 500 psi, E 200%	Nat or SBR (Cl 2) FVC (Cl 11)	Nat or SBR (Cl 6, 10) Chloroprene (Cl 16)		6145	Cord, Flexible, and Wire, Fixtures, Electrical 0 to 600 Volt Service)	J-C-580 Types AFS, HS, HSJ
Air, original properties	Ambient	-	Min. Cl 6; T 1500 psi, E 300%						
Air, original properties	Ambient	-	Min: C l 10; T 1500 psi, E 300%						
Air, original properties	Ambient	-	Min: C l 11, T 1600 psi, E 200%						
Air, original properties	Ambient	-	Min: Cl 16, T 1500 psi, E 300%						
Oxygen, aging @ 300 psi	158	96	Cl 2; Max E chg: -35%						
Oxygen, aging @ 300 psi	158	96	Cl 6, 16, Max E chg: -30%						
Oxygen, aging @ 300 psi	178	168	Cl 10, Max E chg: -50%						
Air, oven aging	212	168	Cl 11; Max E chg: -50%						
Air, original properties	Ambient	-	Min. Cl 3, 8; T 600 psi, E 250%	Nat or SBR (Cl 3, 8) Nat (Cl 5, 9)	Nat or SBR (Cl 6, 10) Chloroprene (Cl 15, 16)		6145	Cord, Flexible, and Wire, Fixtures, Electrical 0 to 600 Volt Service)	J-C-580 Types SJ and SJO
Air, original properties	Ambient	-	Min: Cl 5, 9; T 3000 psi, E 650%						
Air, original properties	Ambient	-	Min: Cl 6, 10, 15, 16; T 1500 psi						
Air, original properties	Ambient	-	Min: Cl 6, 10, 15, 16; E 300%						
Oxygen, aging @ 300 psi	158	96	Cl 3, Max E chg: -35%						
Oxygen, aging @ 300 psi	158	96	Cl 5, Max E chg: -25%						
Oxygen, aging @ 300 psi	158	96	Cl 6, 15, 16, Max E chg· -30%						
Oxygen, aging @ 300 psi	178	168	Cl 9, 10; Max E chg: -50%						
Air, original properties	Ambient	-	Min: Cl 4; T 1500 psi, E 350%	Nat or SBR (Cl 4) Chloroprene (Cl 14)	Nat or SBR (Cl 4) Chloroprene (Cl 14)		6145	Cord, Flexible, and Wire, Fixtures, (Electrical 0 to 600 Volt Service)	J-C-580 Type SP-2
Air, original properties	Ambient	-	Min: Cl 14, T 1500 psi, E 300%						
Oxygen, aging @ 300 psi	158	96	Cl 4, Max E chg: -25%						
Oxygen, aging @ 300 psi	158	168	Cl 14, Max E chg: -30%						
Air, tensile strength	Ambient	-	Min psi: 1800		PVC Tubing	Yes	5970	Insulation, Electrical, Synthetic - Resin Composition	MIL-I-631 Form U Type F, Grade A
Air, ASTM D746	-30	1	No failure						
Air, mandrel bend	212	200	No cracking						
ASTM #3 petroleum oil	122	200	Max vol chg. +15%						
Air, tensile strength	Ambient	-	Min psi. 1450		PVC Tubing	Yes		Insulation, Electrical, Synthetic - Resin Composition Nonrigid	MIL-I-631 Form U Type F, Grade B
Air, ASTM D746	-46	1	No failure						
Air, mandrel bend	212	200	No cracking						
ASTM #3 petroleum oil	122	200	Max vol chg. +15%						
Air, tensile strength	Ambient	-	Min psi. 1800		PVC Tubing	Yes	5970	Insulation, Electrical, Synthetic - Resin Composition Nonrigid	MIL-I-631 Form U Type F, Grade C
Air, ASTM D746	-10	1	No failure						
Air, mandrel bend	212	200	No cracking						
ASTM #3 petroleum oil	122	200	Max vol chg +15%						

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP, °F	TIME, HRS	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Min ins T 1800 psi, E 150%	PVC	Nylon w/wo braid			Wire, Electrical, Insulated, Copper Hook-Up and General Purpose (For 105°C Service)	NAS 702 Types U & S
Air, mandrel bend	-67	4	No cracking						
Air, oven aging	235	1440	Max ins chg: T & E -30%						
MIL-O-6081 jet oil	Ambient	20	No cracking						
(Covered in MIL-I-3930, Type IS-L Insulation and Type JS-L Jacket)				SBR	SBR or natural		6150	Leads, Electrical, Arc-Welding	MIL-L-741
(Tests on rubber only)									
Air, original properties	Ambient	-	Min. T 1800 psi; E 300%	Not applicable	Chloroprene			Heavy-Duty Black Polychloroprene Jacket For Wire and Cable	ASTM D752
Air, aging @ 80 psi	260	20	Max chg. T & E -50%						
ASTM #2 petroleum oil	250	18	Max chg: T & E -40%						
(Tests on rubber only)									
Air, original properties	Ambient	-	Min: T 1500 psi; E 250%	Not applicable	Chloroprene			General Purpose Polychloroprene Jacket For Wire and Cables	ASTM D753
Air, aging @ 80 psi	260	20	Max chg: T & E -50%						
ASTM #2 petroleum oil	250	18	Max chg. T & E -40%						
(Tests on rubber only)									
Air, original properties	Ambient	-	Min: T 700 psi; E 300%	Not known	Not applicable			Synthetic Rubber Insulation For Wire and Cable, 75C Operation	ASTM D754
Air, aging @ 80 psi	260	20	Max chg: T & E -50%						
(Tests on rubber only)									
Air, original properties	Ambient	-	Min· T 700 psi; E 300%	Not known	Not applicable			Synthetic Rubber Insulation For Wire and Cable, 60C Operation	ASTM D755
Oxygen, aging @ 300 psi	158	96	Max chg: T -25%, E -35%						
(Tests on rubber only)									
Air, original properties	Ambient	-	Min T 1800 psi; E 300%	Not applicable	SBR			Styrene-Butadiene (SBR) Synthetic Rubber Jacket For Wire and Cable	ASTM D866
Oxygen, aging @ 300 psi	158	48	Min: T 1400 psi; E 200%						
Air, tensile strength	Ambient	-	Min T psi: ins 600; jkt 1800	Synthetic	Chloroprene	Yes	6145	Cable, Cord and Wire Electrical (Shipboard Use)	MIL-C-915 Types: DSS, TSS, SSF, FSS, MSS, CVSF, MCSC, MCGC, DCOP, TCOP, TRF
Oxygen, aging @ 300 psi	176	168	Max % T chg. ins -50						
Navy Symbol 3100 oil	240	18	Max % T chg: jkt -35						

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength Air, aging @ 80 psi Navy Symbol 3100 oil	Ambient 296 240	- 20 18	Min T psi. ins 600; jkt 1800 Max % T chg. ins -30; jkt -35 Max % T chg: jkt -35	Butyl	Chloroprene	Yes	6145	Cable, Cord and Wire Electrical (Shipboard Use)	MIL-C-915 Types: DSS, JAS, TSS, FSS, MSS, FCSF, SDU, SHOF, DHOF, THOF, FHOF, TRF, CVSF, T3P
Air, tensile strength Air, heat aging @ 80 psi Navy Symbol 3100 lub. oil	Ambient 295 240	- 20 18	Min T psi· jkt 1800 Max % T chg: jkt -35 Max % T chg: jkt -35	Non-elastomeric	Chloroprene	Yes	6145	Cable, Cord and Wire Electrical (Shipboard Use)	MIL-C-915 Types. TRXF, MNOP, MCOS, FCOTF-4
Water, @ 75 psi Air, @ 75 psi		4 4	Impervious Impervious	Non-elastomeric	PVC	Yes	6145	Cable, Cord and Wire Electrical (Shipboard Use)	MIL-C-915 Types. TSP, MHFF, TIOP, MCOS, TTRS
Lubricating oil	240	18	Max % + chg: jkt -35	Natural	Chloroprene	Yes	6145	Cable, Cord and Wire Electrical (Shipboard Use)	MIL-C-915 Type DLT
Air, tensile strength Oxygen, aging @ 300 psi	Ambient 176	- 168	Min T psi. ins 600 Max % T chg: ins -50	Not known	Non-elasto-meric	Yes	6145	Cable, Cord and Wire, Electrical (Shipboard Use)	MIL-C-915 Types: DBSP, TBSP, FBSP
Air, tensile strength Air, heat aging @ 80 psi	Ambient 296	- 20	Min T psi: ins 600 Max % T chg: ins -30	Butyl	Non-elasto-	Yes	6145	Cable, Cord, and Wire, Electrical (Shipboard Use)	MIL-C-915 Types: DBSP, TBSP, FBSP
Air, original properties Air, brittleness ASTM #3 petroleum oil	Ambient -22 158	- 0.05 4	Min: T 2000 psi, E 200% No failure E chg: -20% + 5%	PVC tubing				Non-Rigid Vinyl Chloride Polymer Tubing	ASTM D922 Grade A
Air, original properties Air, brittleness ASTM #3 petroleum oil	Ambient 14 221	- 0.05 4	Min: T 2000 psi, E 200% No failure E chg: -20% + 5%	FVC	None			Non-Rigid Vinyl Chloride Polymer Tubing	ASTM D922 Grade C
(Tests on rubber only) Air, original properties Air, oven aging SAE 20 oil	Ambient 212 158	- 100 4	Min: T 1500 psi, E 100% Max chg: T -20%; E -40% Max chg: T -20%; E -40%	Not applicable	PVC			Poly (Vinylchloride) Jacket for Wire and Cable	ASTM D1047
Air, original properties	Ambient	-	Min: T 1600 psi; E 350%	Synthetic hose				Rubber Insulating Line Hose	ASTM D1050

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
(Tests on rubber only) Air, original properties Air, aging @ 80 psi Ozone, 25000 to 30000 pphm	Ambient 260 Ambient	- 40 3	Min. T 600 psi; E 350% Max chg: T & E -50% No cracking	Butyl	Not applicable			Ozone-Resisting Butyl Rubber Insulation For Wire and Cable	ASTM D1352
Air, original properties Air, mandrel bend Air, oven aging MIL-O-6081 jet oil	Ambient -67 235 Ambient	- 4 1440 20	Min ins: T 1800 psi; E 150% No cracking Max ins chg: T & E -30% No cracking	PVC	Nylon			Wire, Electrical, Insulated, Copper Solid Conductor, Hook-Up and General Purpose (For 105°C Service)	NAS 1391
(Tests on rubber only) Air, original properties Air, aging @ 80 psi	Ambient 260	- 20	Min. T 700 psi; E 300% Max chg: T & E -50%	Not known	Not applicable			Synthetic Rubber Heat-or Moisture-Resisting Insulation For Wire and Cable	ASTM D1520[1]
(Tests on rubber only) Air, original properties Oxygen, aging @ 300 psi	Ambient 158	- 96	Min: T 700 psi; E 300% Max chg: T -25%; E -35%	Not known	Not applicable			Synthetic Rubber Performance, Moisture-Resisting Insulation For Wire and Cable	ASTM D1521[2]
(Tests on rubber only) Air, original properties Air, oven aging	Ambient 250	- 168	Min: T 700 psi; E 300% Max chg: T & E -40%	Not known	Not applicable			Synthetic Rubber Insulation For Wire and Cable, 90C Operation	ASTM D1523
(Tests on rubber only) Air, original properties Oxygen, aging @ 300 psi	Ambient 176	- 168	Min: T 700 psi; E 300% Max chg: T & E -50%	Not known	Not applicable			Synthetic Rubber Heat- and Moisture-Resisting Insulation For Wire and Cable, 75C Operation	ASTM D1679
Air, original properties	Ambient	-	T, 900 psi min; E 250%	Chloroprene Hypolon	SBR Hypolon		1075	Cable and Cable Assemblies, Special Purpose, Electrical, Magnetic Mine Sweeping (Quad Cable)	MIL-C-17694
Air, tensile strength Oxygen, aging @ 300 psi	Ambient 158	- 48	Min T psi: jacket, 800 Max % T chg: jacket, -25	None	SBR			Cable, 1-Conductor Submarine Mine, M6	MIL-C-1892[2]
Air, original properties Air, mandrel bend Air, oven aging	Ambient 14 212	- 1 168	Min: T 1500 psi; E 100% No cracks Max % T & E chg: -35	PVC	None		1390	Wire, Insulated, Submarine Mine Wiring Device	MIL-W-1904[2] Type TW

[1] Document cancelled. Use ASTM D1679.
[2] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient	-	Min: T 1500 psi; E 100%	PVC	Not applicable		1390	Vinyl Chloride Plastic Insulation For Wire and Cable, 60C Operation	ASTM D2219
Air, mandrel bend	14	1	No cracking						
Air, oven aging	212	168	Max % chg. T & E -35%						
ASTM #2 petroleum oil	158	4	Max % chg: T -20; E -40						
Air, original properties	Ambient	-	Min: T 2000 psi; E 150%	PVC	Not applicable			Vinyl Chloride Plastic Insulation For Wire and Cable, 75C Operation	ASTM D2220
Air, mandrel bend	-32	1	No cracks						
Air, oven aging	250	168	Max % chg: T -20; E -25						
ASTM #2 petroleum oil	158	4	Max % chg: T -20; E -40						
(Covered in MIL-I-3930, Type IL, IS-L and JS-L, except that low temperature tests do not apply)									
Air, mandrel bend	-40	20	Ins & jkt; no cracking	SBR	SBR		6145	Cable, Special Purpose, Electrical WM-46/U	MIL-C-2486
Air, mandrel bend	-65	4	No cracking	Nat or syn	Non-elasto-meric		6145	Cable, Electric, Insulated Low-Tension, Single-Conductor	MIL-C-3078[1]
Air, oven aging, 180° bend	250	120	No damage						
Air, tensile strength	Ambient	-	Min T psi; ins 1500	PVC	None		6145	Cable, Telephone Inside Distribution Wiring (WD-15/U, WF-9/U, and WT-3/U)	MIL-C-3093
Air, oven aging	212	120	Max % T chg: ins -15						
Flame	-	0	Max self burning: ins 1 min						
(Covered in MIL-I-3930 ins IS, jkt JS)				SBR	SBR		6145	Cable and Wire, Electrical (Power and Control; Flexible and Extra Flexible, 300 and 600 volts)	MIL-C-3432 Class G
(Covered in MIL-I-3930 ins IS; jkt JN)				SBR	Chloroprene		6145	Cable and Wire, Electrical (Power and Control; Flexible and Extra Flexible, 300 and 600 volts)	MIL-C-3432 Class O
(Covered in MIL-I-3930 ins IS, jkt JS-L)				SBR	SBR		6145	Cable and Wire, Electrical (Power and Control; Flexible and Extra Flexible, 300 to 600 volts)	MIL-C-3432 Class L
(Covered in MIL-I-3930 ins IS; jkt JN-L)				SBR	Chloroprene		6145	Cable and Wire, Electrical (Power and Control; Flexible and Extra Flexible, 300 to 600 volts)	MIL-C-3432 Class D

[1] Document cancelled. Use MIL-C-13486, MIL-W-8777 or MIL-W-7139.

Source: https://assist.dla.mil -- Downloaded: 2026/0-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties Air, mandrel bend Air, oven aging Flame	Ambient -13 265 -	- 4 400 -	Min: T 2000 psi; E 250-450% No cracking Max chg. E ± 35% Self burning 15 sec max	PVC sleeving				Polyvinyl Chloride Tubing, Extruded, High Temperature (Electrical Insulation)	AMS 3629
Air, mandrel bend Air, oven aging MIL-L-6082 petroleum oil	-65 450 195	24 125 40	No cracking or breaking No breakdown No cracking or decomposing	Silicone	Silicone	Yes	6145	Cable, Power, Electrical. Ignition, High-Tension	MIL-C-3702 Grade B
Air, mandrel bend Air, oven aging MIL-L-6082 petroleum oil	-65 250 195	24 125 40	No cracking or breaking No breakdown No cracking or decomposing	Chlorosulfo-nated polyethylene	Hypalon	Yes	6145	Cable, Power, Electrical Ignition, High-Tension	MIL-C-3702 Grade C
Air, mandrel bend Air, oven aging MIL-L-6082 petroleum oil	-65 600 195	24 50 40	No cracking or breaking No breakdown No cracking or decomposition	Silicone	Silicone	Yes	6145	Cable, Power, Electrical: Ignition, High-Tension	MIL-C-3702 Grade D
(Covered in MIL-I-3930)				Elastomeric	Elastomeric		6145	Cord, Electrical (Tinsel)	MIL-C-3849
(Covered in MIL-I-3930)				Elastomeric	Nat, syn or PVC		5995	Cable Assemblies and Cord Assemblies, Electrical (Power, Control, and Audio-Frequency); General Specification for	MIL-C-3885
Air, original properties Air, oven aging	Ambient 212	- 96	Min: ins, T 1800 psi; E 125% Max % E chg. ins -20	PVC	Not applicable		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type IP
Air, tensile strength Oxygen, aging @ 300 psi	Ambient 158	- 95	Min T psi: ins 450 to 600 Max % T chg: ins -25	SBR	Not applicable		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type IS
Air, tensile strength Oxygen, aging @ 300 psi Air, ASTM D746	Ambient 176 -67	- 168 0.08	Min T psi: ins 450 to 600 Max % T chg. ins -50 No cracking	SBR	Not applicable		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type IS-L
Air, tensile strength Oxygen, aging @ 300 psi	Ambient 158	- 95	Min T psi: ins 800 to 1200 Max % T chg ins -25	Natural	Not applicable		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type IR

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength Oxygen, aging @ 300 psi	Ambient 158	- 95	Min T psi: ins 1000 Max % E chg: ins -25	SBR	Not applicable		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type IJ-S
Air, original properties Oxygen, aging @ 300 psi	Ambient 178	- 168	Min: ins, T 25000 psi, E 600% Max % E chg: ins -50	Natural	Not applicable		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type IL-N
Air, original properties Oxygen, aging @ 300 psi	Ambient 158	- 168	Min: ins, T 2500 psi, E 650% Max % E chg: ins -30	Natural	Not applicable		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type IL-RN
Air, original properties Air, oven aging ASTM #2 petroleum oil	Ambient 212 158	- 96 18	Min: jkt, T 1500 psi, E 100% Max % E chg: jkt -40 Max % T chg: jkt -20	Not applicable	PVC		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type JP
Air, original properties Oxygen, aging @ 300 psi Ozone, @ 50 pphm	Ambient 158 100	- 96 168	Min: jkt, T 1600 psi, E 300% Max % E chg: jkt -35 No cracking	Not applicable	SBR		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type JS
Air, original properties Oxygen, aging @ 300 psi Ozone, @ 50 pphm	Ambient 158 100	- 96 168	Min: jkt, T 1500 psi, E 300% Max % E chg: jkt -35 No cracking	Not applicable	SBR		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type JS-L
Air, original properties Oxygen, aging @ 300 psi Ozone, @ 50 pphm	Ambient 158 100	- 96 168	Min: jkt, T 2000 psi, E 350% Max % E chg: jkt -35 No cracking	Not applicable	Natural		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type JR
Air, original properties Oxygen, aging @ 300 psi ASTM #2 petroleum oil Ozone, @ 50 pphm	Ambient 158 158 100	- 96 18 168	Min: jkt, T 1800 psi, E 300% Max % E chg: jkt -25 Max % T chg: -40 No cracking	Not applicable	Chloroprene		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type JN
Air, original properties Air, oven aging ASTM #2 petroleum oil Ozone, @ 50 pphm	Ambient 158 158 100	- 168 18 168	Min: jkt, T 1500 psi, E 300% Max % E chg: -20 Max % T chg: -40 No cracking	Not applicable	Chloroprene		5970	Insulating and Jacketing Compounds, Electrical (For Cables, Cords and Wires)	MIL-I-3930 Type JN-L

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, elongation	Ambient	-	Min elong. ins 75%	PVC	Non-elasto-	Yes	6145	Wire, Electric, Polyvinyl Chloride Insulated, Copper or Copper Alloy	MIL-W-5086 Types. I, II, and III
Air, mandrel bend	-67	1	Ins: no cracks						
Air, oven aging	239	1440	Max % elong chg. ins -30						
MIL-H-5606 hydraulic oil	122	20	No cracks after mandrel bend						
(Covered in MIL-I-3930, Types IS & JN)				SBR	Chloroprene		6145	Cable, Power, Electrical, Polychloroprene Sheathed, Buna Compound Insulated	MIL-C-5136
Air, mandrel bend	-67	48	No cracking	Syn or nat	Syn or nat	Yes	6145	Cable and Wire, Power, Electric, Portable	MIL-C-5756
Air, tensile strength	Ambient	-	Min T psi: ins 800; jkt 1200	Nat or syn	Nat or syn	Yes	5995	Cord: Headset-Microphone CX-1301/AR	MIL-C-6166
Air, mandrel bend	-40	-	No cracking						
Oxygen, aging @ 300 psi	158	94	Jkt: no tackiness						
Air, mandrel bend	-67	4	No cracking	PVC	Non-elasto-meric	Yes	6145	Wire, Electric, 600-Volt, Aluminum, Aircraft, General Specification For	MIL-W-7072
Flame	-	-	Self burning 30 sec max						
Air, mandrel bend	-67	4	No cracking	Braid, plastic or wire	PVC	Yes	6145	Cable, Electric, Aerospace Vehicle, General Specification For	MIL-W-7072
Air, oven aging	248	96	No cracking						
Air, tensile strength	Ambient	-	Min psi: 1800	PVC tubing		Yes	5970	Insulation Sleeving, Electrical, Flexible	MIL-I-7444
Air, ASTM D746	-90	-	No failure						
(Cables covered in MIL-C-5756) (Plugs covered in MIL-I-3930)				Syn. or natural (cables) PVC, SBR, or Natural (Plugs)		Yes	5935-6150	Cable Assemblies and Attachable Plugs, External Electrical Power, Aircraft	MIL-C-7974
(Tests on receptacle only)									
Air, ball impact	-67	24	No cracking	None	Syn	Yes	5935-	Cable Assemblies and Attachable Plugs, External Electrical Power, Aircraft	MIL-C-7974
Air, aging	392	-	No cracking						
Air, tensile strength	Ambient	-	Min psi: ins 800	Silicone	Silicone	Yes	6145	Wire, Electrical, Silicone-Insulated, Copper, 600-Volt, 200°C	MIL-W-8777
Air, cold bend	-67	4	No cracking						
Air, oven aging	450	6	Min T psi: ins 600						
MIL-H-5606 hydraulic oil	Ambient	20	No exudation of insulation						
(Covered in MIL-I-3930)				SBR	SBR		6145-	Cables, Special Purpose, Electrical (Multipair Audio Frequency)	MIL-C-10065

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
(Covered in MIL-I-3930, Types IS & JS)				SBR	SBR		6145	Cables, Special Purpose, Electrical (Miniature)	MIL-C-10392
(Covered in MIL-I-3930)				SBR	SBR		6145	Power and Control Cables, Heavy Duty, Buna S Insulated and Jacketed	MIL-P-10582[1]
(Covered in MIL-I-3930)				SBR	SBR		6145	Cables, Power and Control, Electrical, Shielded, Heavy Duty, Buna S insulated and Jacketed	MIL-C-10769[2]
Air, mandrel bend Ozone, @ 50 pphm	-40 100	20 168	No cracking Jkt: no cracking	SBR	Chloroprene		6145	Cable, Telephone (W-50-A)	MIL-C-11097
Air, original properties Oxygen, aging @ 300 psi	Ambient 158	- 96	Min: jkt; T 1200 psi, E 175% Ins, no cracking; jkt, E 100%	Natural	Natural and/or SBR		5995	Cord Assembly, Electrical CX-2151 ( )/U	MIL-C-11997
Air, compression Air, mandrel bend Ozone, 50 pphm	Ambient -40 100	- 20 168	800 lbs min crush load No cracking Jkt: no cracks	SBR	Chloroprene		6145	Cable, Telephone WD-33/U	MIL-C-12423
(Covered in MIL-I-3930)				SBR	Braid		6145	Wire, Electrical (Wire W-124, W-125, and W-128)	MIL-W-13075
(Covered in MIL-I-3930 Types IS & JS)				SBR	SBR		6145	Cable, Special Purpose, Electrical (Cordage CO-212 and Cable, Special Purpose, Electrical WD-32/U	MIL-C-13077
Air, tensile strength Air, mandrel bend Oxygen, aging @ 300 psi	Ambient -40 158	- 168 94	Ins; 1000 psi min No cracking Max % T chg. ins -25	SBR	None		6145	Wire, Electrical (For Instrument Test Leads)	MIL-W-13169
Air, tensile strength Air, @ 400% extension Oxygen, aging @ 300 psi	Ambient -40 158	- 20 96	Min psi: ins 600; jkt 1200 No cracking Min T psi: ins 450; jkt 1000	SBR or natural	SBR and/or nat		6145-5995	Cord, Electrical (Retractile, 2, 3 and 4 Conductor, WD-9/U, WT-2/U, WF-4/U)	MIL-C-13273
Air, mandrel bend Air, oven aging ASTM #3 petroleum oil	-65 250 160	24 120 20	No cracking Ins. no breakdown Volume change, 20% max	Elastomeric	Chloroprene	Yes	6145	Cable, Special Purpose, Electrical: Low-Tension, Heavy Duty Single Conductor and Multiconductor	MIL-C-13486 Types I and II

1 Document cancelled. Use MIL-C-3432.
2 Document cancelled without replacement

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength	Ambient	-	Min psi: ins 2500, jkt 1800	Natural (60%)	Chloroprene	Yes	6145	Cable, Special Purpose, Electrical: General Specification For	MIL-C-13777 Comp A
Air, mandrel bend	-65	48	No cracking						
Oxygen, aging @ 300 psi	158	94	Min T psi ins 2000; jkt 1600						
ASTM #2 petroleum oil	250	18	Max % T chg. jkt -40						
Ozone, 50 pphm	120	168	Jkt; no cracks						
Air, tensile strength	Ambient	-	Min psi: ins 3000, jkt 1800	Natural (Latex)	Chloroprene	Yes	6145	Cable, Special Purpose, Electrical: General Specification For	MIL-C-13777 Comp B
Air, mandrel bend	-65	48	No cracking						
Oxygen, aging @ 300 psi	158	94	Min T psi: ins 2500; jkt 1600						
ASTM #2 petroleum oil	250	18	Max % T chg: jkt -40						
Ozone, 50 pphm	120	168	Jkt; no cracks						
Air, tensile strength	Ambient	-	Min psi: ins 600, jkt 1800	SBR	Chloroprene	Yes	6145	Cable, Special Purpose, Electrical: General Specification For	MIL-C-13777 Comp D
Air, mandrel bend	-65	48	No cracking						
Oxygen, aging @ 300 psi	158	94	Min T psi: ins 480; jkt 1600						
ASTM #2 petroleum oil	250	18	Max % T chg. jkt -40						
Ozone, 50 pphm	120	168	Jkt; no cracks						
Air, tensile strength	Ambient	-	Min psi: ins 2000; jkt 1800	Natural rubber (40%)	Chloroprene	Yes	6145	Cable, Special Purpose, Electrical: General Specification For	MIL-C-13777 Comp E
Air, mandrel bend	-65	48	No cracking						
Oxygen, aging @ 300 psi	158	94	Min T psi: ins 1800; jkt 1600						
ASTM #2 petroleum oil	250	18	Max % T chg: jkt -40						
Ozone, 50 pphm	120	168	Jkt; no cracks						
Air, tensile strength	Ambient	-	Min psi: jkt 1800	Polyethylene, teflon & fluorinated ethylene propylene	Chloroprene	Yes	6145	Cable, Special Purpose, Electrical: General Specification For	MIL-C-13777 Comps F, G and H
Air, mandrel bend	-65	48	No cracking						
Oxygen, aging @ 300 psi	158	94	Min T psi jkt 1600						
ASTM #2 petroleum oil	250	18	Max % T chg: jkt -40						
Ozone, 50 pphm	120	168	Jkt; no cracks						
Air, tensile strength	Ambient	-	Min psi: ins SBR 450, Nat 3000	SBR or natural	SBR		6145	Cable, Telephone (Flexible) (Cords and Cordage, Multipair)	MIL-C-13892
Air, tensile strength	Ambient	-	Min psi: jkt 1600						
Air, mandrel bend	-40	20	No cracks						
Oxygen, aging @ 300 psi	158	48	Max % T chg. ins SBR -25						
Oxygen, aging @ 300 psi	158	48	Max % T chg. jkt -20						
Oxygen, aging @ 300 psi	158	96	Max % T chg. ins nat -25						
Air, tensile strength	Ambient	-	Min psi: ins 600	SBR	SBR of chloroprene		5935	Cable Assemblies, Power, Electrical, and Extension Lights, Connectors, Adapters, and Dummies	MIL-C-13940
Air, tensile strength	Ambient	-	Min psi. jkt SBR 1500, CR 1800						
Air, ASTM D746	-65	-	No cracking						
Oxygen, aging @ 300 psi	178	168	Max % T chg: ins -50						
Oxygen, aging @ 300 psi	158	96	Max % T chg: jkt SBR 25 CR 10						
ASTM #2 petroleum oil	250	18	Max % T chg. jkt CR -40						

Source: https://assist.dla.mil -- Downloaded: 20260-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, breaking strength	Ambient	-	6400 to 7000 lbs	Polyethylene	PVC		6145	Cable, Special Purpose, (TOW), Electrical, Coaxial, Lead Wrapped, Nylon Covered	MIL-C-15452
(Covered in MIL-C-17 Type I jkt)				Polyethylene	PVC		6145	Cables, Power, Electrical, Submarine, Navy Standard Harbor Defense	MIL-C-1547/9
Air, tensile strength Oxygen, aging @ 300 psi	Ambient 158	- 48	Ins 2500 psi; jkt 3500 psi Min psi T: ins 2000; jkt 2800	Natural	Natural		6145	Cable, Special Purpose, Electrical (Underwater Use)	MIL-C-16839 Types DMU, DNU
(Covered in MIL-C-915)				Butyl	Chloroprene		6145	Cable, Special Purpose, Electrical (Underwater Use)	MIL-C-16839 Types DPU, MSU, MTU & SPU
(See individual specification sheets for tests and requirements)				Not known (See individual specification sheets for acceptable construction)	PVC		6145	Wire, Electrical, Insulated, High Temperature	MIL-W-16878
Air, mandrel bend	5	20	No cracking	PVC	None		6145	Wire, Electrical, Radio Antenna, 7/12, 7/14, 7/16, 7/18, 7/20, 7/22	MIL-W-17211
Air, crush Flame	482 Ambient	168 96	No cracking of silicone Max self burning 45 sec	Glass fiber sleeving, silicone rubber coated			5970	Insulation Sleeving, Electrical, Flexible Glass Fiber, Silicone Rubber Treated	MIL-I-18057[1]
Air, original properties Oxygen, aging @ 300 psi	Ambient 158	- 168	T, 450 psi min; E, 250% min T, 400 psi min; E, 200% min	Syn rubber	Lead		6145	Cable, Power, Electrical, Rubber Insulated, Lead Sheathed, High Voltage	MIL-C-18869[2]
Air, original properties Air, oven aging	Ambient 500	- 24	Min; jkt; T 800 psi, E 250% No exudation at elastomer	Asbestos	Silicone		6145	Cables, Special Purpose, Electrical, (Nuclear Plant)	MIL-C-19381[3]

1 Document cancelled. Use MIL-I-3190 and MIL-I-3190/6.
2 Document cancelled. Use MIL-C-28661.
3 Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
(Jacket covered in MIL-C-17 Type I)				Polyethylene	PVC		6145	Cables, Power, Electrical Submarine, Navy Harbor Defense	MIL-C-19638[1]
Air, tensile strength	Ambient	-	Min: ins 850 psi; jkt 2000 psi	SBR of syn	Chloroprene		6145	Cable, Telephone; Submarine	MIL-C-19654
Air, oven aging	158	96	Max % T chg: ins -30; jkt -25						
Water	Ambient	168	% wt chg: ± 20						
Air, elongation	Ambient	-	Min E: ins 650%; jkt 350%	Natural w/wo chloroprene	Chloroprene		6145	Cable, Electric, Torpedo 65 Conductor (For Torpedo Control, Electric Setting)	MIL-C-19787
Oxygen, aging @ 300 psi	158	96	Min E: ins 600%; jkt 300%						
MIL-L-15016 mineral oil	248	18	Max % E chg: jkt -40						
(Insulation covered in ASTM D734)				PVC	Polyethylene		6145	Cables, Special Purpose, Electrical, For Remote Control Radar Set AN/FPN-28 ( )	MIL-C-19883[1] Types 4, 5, 6
Air, mandrel bend	-32	20	No damage	None	Not known		1440	Cable Assemblies, Electrical	MIL-C-21529
Steam, aging @ 115 psig	325	0.17	No damage						
Fungus	-	-	Resistant						
Air, ASTM D746	5	0.08	No cracking	Glass fiber sleeving, PVC coated		Yes	5970	Insulation Sleeving Electrical, Flexible, Glass Fiber, Vinyl Treated	MIL-I-21557[2]
ASTM #3 petroleum oil	Ambient	24	No cracking						
Air, elongation	Ambient	-	Min: jkt 250% (PVC)	Polyamide	PVC & Polyamide		6145	Cable, Electrical, Shielded, 600-Volt (For Nonflexing Service)	MIL-C-21609
Air, mandrel bend	-40	1	Jkt; no cracks (PVC)						
Air, oven aging	212	120	Max % E chg: jkt -20% (PVC)						
Air, tensile strength	Ambient	-	Min psi: 1800	PVC tubing		Yes	5970	Insulation Tubing, Electrical Nonrigid, Vinyl, Very Low Temperature Grade	MIL-I-22076
Air, ASTM D746	-67	0.08	No cracking						
ASTM #3 petroleum oil	Ambient	24	No cracks						
Requirements in accordance with MIL-R-6855				Synthetic rubber			5995	Cable Assembly, Special Purpose, Electrical CX4832/AR	MIL-C-22442

[1] Document cancelled without replacement.
[2] Document cancelled. Use MIL-I-003190.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, tensile strength	Ambient	-	Min psi: ins 800; jkt 1500	SBR	PVC		1350	Cables, Controlled Mine	MIL-C-22731[1] Types SUR, MU A-7 and SUA
Air, oven aging	212	96	Max % chg: jkt -20						
Air, oven aging	158	166	Max % T chg. ins -25						
SAE 20 oil	158	4	Max % T chg. jkt -20						
Water, dielectric strength	-	-	Ins: no failure at 3000 volts	Polyethylene	PVC		6145	Cable, Electrical, Underwater, Seadrome Lighting	MIL-C-22929[1]
(Covered in MIL-C-17, Type VIII)				Teflon or none	Chloroprene		6145	Cable, Coaxial (For Submarine Use)	MIL-C-23020 Types. RG-293/U, RG-294/U, RG-295/U, RG-317/U
(Covered in MIL-C-17, Type IIa)				None	PVC		6145	Cable, Coaxial (For Submarine Use)	MIL-C-23020 Types: RG-14A/U, RG-17A/U
Air, tensile strength	Ambient	-	Min psi: ins 2000, jkt 15000	PVC	PVC		6145	Cable, Electrical, Shielded Pairs	MIL-C-23437
(Covered in MIL-W-76 or MIL-W-16878)				PVC	PVC		1190	Cable Assemblies, Special Weapons, Electrical, General Requirements For	MIL-C-25200
(PVC covered in MIL-I-631, Type F, Grade B)				Polyamide (See individual specification sheets for acceptable construction)	PVC		6145	Cable, Special Purpose Electrical Multiconductor	MIL-C-27072 Grade B and Style 1
Air, elongation	Ambient	-	Min. jkt 300%	Polyamide (See individual specification sheets for acceptable construction	Chloroprene		6145	Cable, Special Purpose Electrical Multiconductor	MIL-C-27072 Style 3
Oxygen, aging @ 300 psi	158	94	Min: jkt 250%						
ASTM #2 petroleum oil	250	18	Max % E change: JKT-40						
(Insulation covered in MIL-I-3930, Type IP or IL Jacket covered in MIL-I-3930, Type JP or JN)				Natural or PVC	PVC or chloroprene		6145	Cable, Power, Electrical, Airport Lighting Control	MIL-C-27212
Air, mandrel bend	-67	4	jkt. no cracking	Not specified	PVC		6145	Cable Electrical, Shielded and Unshielded, Aerospace	MIL-C-27500 Symbol 1
Air, oven aging	322	96	jkt. no cracking						

[1] Document cancelled without replacement

Source: https://assist.dla.mil -- Downloaded: 202640-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER COMMONLY USED					
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	INSULATION	JACKET	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
(Insulation covered in MIL-W-8777)				Silicone	Not Specified		6145	Cable Electrical, Shielded and Unshielded, Aerospace	MIL-C-27500 Symbol H & F
(Covered in MIL-C-12064)				SBR	Chloroprene		4940	Cable Assemblies, Electrical	MIL-C-45820 Types I & II
(Covered in MIL-C-13486)				Elastomeric	Syn		4940	Cable Assemblies, Electrical	MIL-C-45820 Type III
(Covered in MIL-C-12064)				SBR	Syn		4940	Cable Assmeblies, Electrical	MIL-C-45820 Type IV
(Covered in MIL-C-3432)				SBR	SBR or chloroprene		6150	Cable Assemblies Power, Electrical (With Molded on Terminations)	MIL-C-52286
(Insulation covered in MIL-W-76)									
Air, elongation	Ambient	-	Min: jkt 100%	PVC	PVC		6145	Cables; Twisted Pairs and Triples, Internal Hookup, Shielded and Unshielded	MIL-C-55021 Symbol P & SP
Air, mandrel bend	-40	4	No cracking						
Air, oven aging	212	96	Max E chg: jkt-35%						
Air, elongation	Ambient	-	Min: jkt 250%	Polyethylene	PVC		6145	Cable, Telephone, WM-130 ( )/G	MIL-C-55036
Air, mandrel bend	-67	24	No cracking						
Air, oven aging	212	96	Max E chg: jkt-10%						
(Jacket covered in MIL-I-3930 Type JN-L)				Polyethylene	Chloroprene		6145	Cable, Telephone,	MIL-C-55036
Air, elongation	Ambient	-	Min: ins 250%; jkt 150%	Rubber type not known	Chloroprene		6145	Cable, Special Purpose Electrical (Retractile)	MIL-C-55040
Air, mandrel bend	-40	20	No cracking						
Oxygen, aging @ 300 psi	158	96	Min E: ins 175%; jkt 100%						
Air, tensile strength	Ambient	-	Min psi: jkt 2000	Polyethylene	PVC		6145	Cables, Telephone (Inside)	MIL-C-55134
Air, oven aging	178	336	Max % T chg: jkt -10						
Air, mandrel bend	-65	48	No cracking	Butadiene or Chloroprene	Chloroprene		6145	Cable, Power, Electrical WP-26( )/U	MIL-C-55483
Air, elongation	Ambient	-	Min. (jkt) 175%	Ethylene-Propylene	SBR or EDDM		6145	Cord, Electrical, Audio, Subminiature (Rectractile & Straight)	MIL-C-55668
Air, tension, Low Temp	-55		20% min recovery (jkt)						
Ozone resistance	70	168	No cracks (jkt)						

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

MISCELLANEOUS RUBBER ITEMS

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, hardness	Ambient		Cl A, 95-100; Cl b, 70-80; Cl C, 60-65	Natural or synthetic		4510	Valves, Pump, Rubber	ZZ-V-51[1]
Air, oven aging	270	0.5	No disintegration or blistering					
Steam	400	3	No distintegration (Class A only)					
Air, 90° bend	-40	120	No cracks	Natural or SBR			Rubber Cups for Hydraulic Actuating Cylinders	SAEJ60[2]
Air, oven aging	158	70	Hardness increase, 0 to +5					
Air, original properties	Ambient		T, 3000 psi min; E, 800% min	Natural		6510	Bandages; Rubber	ZZ-B-101[1]
Air, oven aging	158	168	Tensile change, -25% max					
Steam, 15 psi		2	T, 2000 psi min					
Air, breaking strength	Ambient		Warp, 20 lbs min; Filling, 45 lbs min	Cotton yarn and rubber strands. Type rubber not specified		6510	Bandages; Cotton, Elastic (Washable)	JJ-B-102[1] Type II
Air, elasticity	Ambient		Elongation, 120% min					
Air, original properties	Ambient		T, 1400 psi min; E, 250% min	Natural, SBR, chloroprene or butyl		3030	Belting; Conveyor (Rubber and Synthetic Rubber)	ZZ-B-206[3] Types, A, B, & D
Air, oven aging	158	168	Tensile change; -25% max					
Preproduction sample must meet procuring activity requirements				Type I - cotton duck and natural Type II - cotton duck and synthetic rubber		3030	Belting, V, Link, Impregnated Cotton Duck and Metal Studs	ZZ-B-220[1]
Air, original properties	Ambient		T, 600 psi min; E, 300% min	Natural and synthetic		8125	Rings; Jar, Rubber and Synthetic Rubber	ZZ-R-351[1]
Air, oven aging	158	168	T and E change, -25% ma					
Air, original properties	Ambient		T, 1400 psi min; E, 600% min	Natural		1670	Rings; Parachute Vent, Molded Rubber	ZZ-R-371[1]
Air, oven aging	212	70	T change, -30% max; E change, -40% max					
Air, original properties	Ambient		T, 2000 to 2300 psi; E, 50 to 200%	PVC		8135	Plastic Film, Flexible, Vinyl Chloride	L-P-375 Type I
Air, 180° crease	0	1	No cracks					
Air, original properties	Ambient		T, 1600 psi min; E, 50 to 225%	PVC		8135	Plastic Film, Flexible, Vinyl Chloride	L-P-375 Type II
Air, 180° crease	-40	1	No cracks					
Air, original properties	Ambient		T, 2500 psi min; E, 750% min	Natural, butyl, SBR or chloroprene		6515	Tourniquets; Rubber and Synthetic Rubber, Tubular	ZZ-T-606[1]
Air, oven aging	158	168	Tensile strength; 2000 psi min					

1 Document cancelled without replacement
2 Document cancelled. Use SAE J1600 series.
3 Document cancelled. Use MIL-B-52761.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, hardness	Ambient		10 to 95, depending on type	Natural or synthetic		7510	Erasers, Rubber and Rubber Substitute	ZZ-E-661[1]
Air, 90° bend	-42	120	No cracks	Natural		2530	Cups, Hydraulic-Brake, Natural Rubber	ZZ-C-746[2]
Air, oven aging	158	70	Hardness change, 0 to +5					
Brake fluid, VV-H-910	158	120	Volume change, 0 to +20%					
Air, original properties	Ambient		T, 1800 psi min; E, 300%; H, 55± 5	Acrylics		9320	Rubber for Mounting (Unbonded-Spool & Compression Types)	ZZ-R-768
Air, oven aging	194	96	T, 1440 psi min, E, 225%					
Oil immersion, ASTM #3 oil	122	96	Vol. change ± 10%					
Compression set @ 40% defl	194	96	45% max set					
No physical property requirements				Natural		6640	Bulb, Dropping, Pipet	NNN-B-788
Air, inflation @ 3 psi	Ambient		No leakage	Fabric coated with SBR, butyl or chloroprene		6530	Cushions; Ring, Cloth-Inserted	ZZ-C-791[2]
Air, original properties	Ambient		T, 1700 psi min; E, 400% min	Natural or synthetic		6530	Cushions; Ring, Rubber	ZZ-C-796
Air, oven aging	158	166	T change, -20% max; E change, -25% max					
Air, inflation @ 3 psi	Ambient		No leakage					
Air, original properties	Ambient		T, 2500 psi min; E, 500% min	Natural or synthetic			Rubber Insulating Blankets (Without Fabric Reinforcement)	ASTM D1048
Air, oven aging	158	168	Change in T and E, -20% max					
Air, alternating current	Ambient	0.05	No breakdown under 20,000 volts					
Air, original properties	Ambient		T, 2500 psi min; E, 600% min	Natural or synthetic			Rubber Insulating Sleeves	ASTM D1051
Air, oven aging	158	168	Change in T and E, -25% max					
Air, alternating current	Ambient	0.05	No breakdown under 10,000 volts					
Air, original properties	Ambient		Breaking force, 45 lbs min; E, 700% min	Natural latex		1670	Rubber Band, Parachute Suspension Line	MIL-R-1832 Type I
Air, oven aging	158	168	Change in breaking force and E, -25% max					
Air, original properties	Ambient		Breaking force, 50 lbs min; E, 700% min	Chloroprene		1670	Rubber Band, Parachute Suspension Line	MIL-R-1832 Type II
Air, oven aging	158	168	Change in breaking force and E, -25% max					
Air, original properties	Ambient		T, 1400 psi min; E, 250% min	Synthetic rubber		9320	Synthetic Rubber Compound, Acid and Oil Resistant (For Lining Battery Compartments on Submarines)	MIL-S-2912
Oxygen, bomb aging	158	46	Change in T and E, -25% max					
ASTM #3 petroleum oil	Ambient	46	Volume change, +15% max					

[1] Document cancelled. Use A-A-132.
[2] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original proprties	Ambient		T, 250 psi, min; E, 100% min	Silicone			Silicone Rubber Compound, Room Temperature Vulcanizing, 15,000 Centipoises Viscosity (Durometer 35-55)	AMS 3362[1]
Cooling medium, ASTM D746	-67		No cracks					
Air, oven aging	450	24	Change in T and E, -25% max					
Air, compression set	212	22	60% max					
Air, original properties	Ambient		T, 300 psi min; E, 100% min	Silicone			Silicone, Rubber Compound, Room Temperature, Vulcanizing, 50,000 Centipoises Viscosity, Short Pot Life (Durometer 35-55)	AMS 3364[1]
Cooling medium, ASTM D746	-67		No cracks					
Air, oven aging	-50	24	Elongation change, -15% max					
Air, compression set	212	22	35% max					
Air, original properties	Ambient		T, 500 psi min, E, 100% min	Silicone			Silicone Rubber Compound, Room Temperature Vulcanizing, 1,200,000 Centipoises Viscosity (Durometer 55-70)	AMS 3367[1]
Cooling medium, ASTM D746	-67		No cracks					
Air, oven aging	450	24	Change in T and E, -25% max					
Air, compression set	212	22	70% max					
Air, original properties	Ambient		T, 2000 psi min; E, 250% min; H, 70-85	PVC	Yes	9330	Plastic Sheet, Polyvinyl Chloride, Plasticized, Elastomeric	MIL-P-3584[1]
Cooling medium, hand bend	0	0.5	No cracks					
Air, oven aging	158	96	Change in T, E and H, 0% max					
SAE 20 paraffin oil	Ambient	24	Change in T, E and H, 0% max					
Air, original properties	Ambient		T, 1800 psi min, E, 300% min	PVC			Plastic Extrusions, Flexible Polyvinyl Chloride	AMS 3630
Cooling medium, ASTM D746	-40		No cracks					
Air, oven aging	250	2	Lengthwise shrinkage, 10% max					
ASTM #3 petroleum oil	212	8	Lengthwise shrinkage, 10% max					
Air, original properties	Ambient		T, 1800 psi min, E, 250% min	PVC			Plastic Extrusions, Flexible, High Temperature Polyvinyl Chloride	AMS 3631
Cooling medium, ASTM D746	-25		No cracks					
Air, oven aging	265	2	Lengthwise shrinkage, 10% max					
ASTM #3, petroleum oil	212	8	Lengthwise shrinkage, 10% max					
(Rubber covered by Grades 25, 50 or 60, Class III of (ZZ-R-765)				Silicone	Yes	5930	Boots, Dust and Water Seal (For Toggle and Push-button Switches and Rotary-Actuated Parts), General Specification for	MIL-B-5423
(Tests on separator material only)								
Air, mandrel bend	-65	72	No cracks	Nitrile rubber	Yes	1650	Accumulators, Aircraft Hydropneumatic Pressure	MIL-A-5498 Type I
Air, oven aging	158	168	T change, -20% max, E change, -30% max	separator				
Petroleum oil, MIL-H-5606	158	168	Volume change, 0 to +15%					

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
(Tests on 1/2 inch diameter cord)								
Air, breaking strength	Ambient		400 lbs min	Cotton yarn and		8305	Cord; Elastic, Exerciser	MIL-C-5651
Air, elongation	Ambient		140% min	natural or cis-1,4			and Shock Absorber for	Type I
Air, load to stretch 100%	-40	5	50% increase, max, over ambient load	polyisoprene			Aeronautical Use	
Air, oven aging	158	168	Change in breaking strength, -40% max	rubber strands				
Air, original properties	Ambient		T, 700 psi min, E, 200%	Silicone		5975	Nipple; Electrical	MIL-N-6748
			H, 50 ± 5				Terminal	
Air, oven aging	212	70	T, 560 psi min, E, 120%					
			H, ± 10 max change					
Oil immersion, ASTM #3 oil	212	22	Volume change + 15%					
Water immersion,	212	70	Volume change +5%					
Air, original properties	Ambient		T, 3800 psi min, E, 850% min	Natural		5977	Rubber, Anodic	MIL-R-6891[1]
Air, low temp. hardness	-40	4	Increase over orig. hardness, 33% max					
Air, oven aging	158	168	T, 3200 psi min; E, 800% min					
(Rubber covered in AMS 3215)				Nitrile		5340	Clamps, Tube Support, Loop Type	MIL-C-8603 Type II
(Rubber covered in AMS 3209)				Chloroprene		5340	Clamps, Tube Support, Loop Type	MIL-C-8603 Type III
Air, original properties	Ambient		H, 45-75; T, 400 ps. min	Silicone		5340	Clamps, Tube Support,	MIL-C-8603
Air, oven aging	500	24	H change, +20 max; T change, -5% max				Loop Type	Type IV
Air, original properties	Ambient		T, 3000 psi min; E, 700% min	Natural		8465	Bladder, Pneumatic	MIL-B-8743[1]
Air, oven aging	160	72	Change in T, -25% max				B-5 Life Preserver	
Air, original properties	Ambient		T, 5lbs/inch width; E, 15% min	Type of material		9330	Film, Elastomeric,	MIL-F-87992
Air, impact loading	-20	5	No cracks under 10 ft-lb load	not specified			Pigmented, For Use in	
85/15,paint thinner/xylene	Ambient		No visible deterioration				The Manufacture of Aircraft Decalcomanias	
Air, original properties	Ambient		T, 1000 psi min; E, 300% min	Nitrile		4920	Repair Material, For	MIL-$-9208
70/30 isooctane/toluene	Ambient	72	Volume change, +20% max				Sealing Fuel Tanks	
Air, flex test	-65	96	No cracks	Fabric and natural or synthetic rubber		3030	Belt, V; Engine Accessory Drive	MIL-B-11040
Air, resilience	Ambient		65% min	Natural or		5340	Shock Mounts, M-447,	MIL-S-12100
Cooling medium, ASTM D746	-60		No cracks	chloroprene			M-448, M-449 and Bracket FT-512	

[1] Document cancelled without replacement.
[2] Document cancelled. Use MIL-M-43719.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, hardness	Ambient		75 ± 5	Natural		7510	Eraser, Rubber-Pumice (For Testing Coated Optical Elements)	MIL-E-12397
Air, oven aging	158	168	Change in hardness, +10 max					
Air, resilience	122		Impact resilience of 65-75%	Natural or chloroprene		5340	Mounts, Vibration	MIL-M-12863
Air, load deflection	-40	100	300% max increase in stiffness					
Air, hardness	Ambient		50 to 75	SBR		2530	Cup, Hydraulic Brake Cynlinder: Synthetic Rubber (For Master, Wheel and Slave Cylinders)	MIL-C-14055
Air, 90° bend	-40	22	No cracking					
Air, oven aging	212	70	Hardness change, 0 to +5					
Brake fluid, VV-H-910	250	70	Volume change, +5 to +20%					
(Tests on rubber only)								
Air, original properties	Ambient		T,1500 psi min; E, 300%	SBR coated nylon		5430	Tanks, Fabric, Collapsible. Water, Nylon, Rubber-Coated	MIL-T-14398
Air, ASTM D746	-40	168	No cracks					
Air, oven aging	158	166	Change in elongation, -35% max					
(Rubber covered by Grade RS510F$_2$ of MIL-R-3065)				SBR, glass cloth laminate		1055	Guard, Bellows, Rocket Launcher M21	MIL-G-14524[1]
Air, hardness	Ambient		70 ± 5	Natural or synthetic	Yes	1020	Rubber Facing, (For Rammer Heads)	MIL-R-16920
Air, compression @ 75 psi	Ambient	0.05	No permanent set or cutting					
Air, 300-350 ft. lb. impacts	Ambient	2/min	No cutting					
Air, original properties	Ambient		T,1800 psi min; E, 300% min	Nitrile		9320	Rubber Special-Shaped Section; For Mountings	MIL-R-17006[2]
Air, compression set	30	96	15% max					
Air, oven aging	194	96	T change, -20% max; E change, -25% max					
Air, resilience	80		70% max					
Air, original properties	Ambient		T,2200 psi min; E, 650% min; H, 38± 5	Chloroprene or nitrile	Yes	5340	Mounts, Resilient; Portsmouth Bonded Spool Type	MIL-M-17191 Class A
Air, compression set	30	94	40% max					
Air, oven aging	194	46	T,2100 psi min; E, 600% min					
ASTM #3 petroleum oil	Ambient	46	Volume change, +15% max					
Air, original properties	Ambient		T,2500 psi min; E, 600% min; H, 43± 5	Chloroprene or nitrile	Yes	5340	Mounts, Resilient; Portsmouth Bonded Spool Type	MIL-M-17191 Class B
Air, compression set	30	94	37% max					
Air, oven aging	194	46	T,2400 psi min, E, 550% min					
ASTM #3 petroleum oil	Ambient	46	Volume change, +15% max					

[1] Document cancelled without replacement.
[2] Document cancelled. Use ZZ-R-768.

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient		T,2800 psi min; E, 575% min; H, 48± 5	Chloroprene or nitrile	Yes	5340	Mounts, Resilient; Spool Type	MIL-M-17191 Class C
Air, compression set	30	94	34% max					
Air, oven aging	194	46	T,2400 psi min; E, 550% min					
ASTM #3 petroleum oil	Ambient	46	Volume change, +15% max					
Air, original properties	Ambient		T,2900 psi min; E, 550% min; H, 57 ± 5	Chloroprene or nitrile	Yes	5340	Mounts, Resilient; Portsmouth Bonded Spool Type	MIL-M-17191 Class D
Air, compression set	30	94	30% max					
Air, oven aging	194	46	T,2800 psi min; E, 500% min					
ASTM #3 petroleum oil	Ambient	46	Volume change, +15% max					
Air, original properties	Ambient		T,2200 psi min; E, 550% min; H, 35 ± 5	Natural	Yes	5340	Mounts, Resilient; Naval Engineering Station Types 6E2000, 6E900, 7E450, 6E150, and 6E100	MIL-M-17508 Type 6E100
Air, compression set	30	94	20% max					
Air, oven aging	194	46	T,2100 psi min; E, 500% min					
Air, compression set	194	46	30% max					
Air, original properties	Ambient		T,3200 psi min; E, 500% min; H, 42 ± 5	Natural	Yes	5340	Mounts, Resilient; Naval Engineering Station Types 6E2000, 6E900, 7E450, 6E150, and 6E100	MIL-M-17508 Type 6E150
Air, compression set	30	94	20% max					
Air, oven aging	194	46	T,2600 psi min; E, 450% min					
Air, compression set	194	46	35% max					
Air, original properties	Ambient		T,2200 psi min; E, 600% min; H, 38 ± 5	Chloroprene or nitrile	Yes	5340	Mounts, Resilient; Naval Engineering Station Types 6E2000, 6E900, 7E450, 6E150, and 6E100	MIL-M-17508 Type 7E450
Air, compression set	30	94	50% max					
Air, oven aging	194	46	T,2100 psi min; E, 550% min					
ASTM #3 petroleum oil	158	94	Volume change, +15% max					
Air, original properties	Ambient		T,2500 psi min; E, 600% min; H, 43 ± 5	Chloroprene or nitrile	Yes	5340	Mounts, Resilient; Naval Engineering Station Types 6E2000, 6E900, 7E450, 6E150, and 6E100	MIL-M-17508 Type 6E2000 and 6E900
Air, compression set	30	94	60% max					
Air, oven aging	194	46	T,2400 psi min; E, 550% min					
ASTM #3 petroleum oil	158	94	Volume change, +15% max					
Air, original properties	Ambient		T,2000 psi min; E, 75% min; H, 80-90	Type or rubber not known		4820	Disk, Valve, Non-Metallic (Synthetic Rubber): Insert Type	MIL-D-17650
Air, oven aging	212	70	T,1600 psi min; E, 55% min					
Water	212	70	Volume change, 0 to +15%					
(Tests on rubber only)								
Air, original properties	Ambient		T,1500 psi; E, 150% min; H, 65-90	Type of rubber not known	Yes	3130	Bearing Components Bonded Synthetic Rubber, Water Lubricated	MIL-B-17901
Air, oven aging	158	96	T and E change, ± 25% max					
Water	Ambient	168	Volume change, +5% max					

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
(Tests on rubber only)								
Air, oven aging	158	168	Set no greater than that of std. sample	Nylon yarn and natural rubber thread		8305	Webbing, Nylon, Elastic	MIL-W-17965
Air, oven aging	158	168	E no less than that of std. sample					
Air, original properties	Ambient		T,1000 psi min; E, 400%; H, 40 ± 5	Type or rubber not known		6650	Eye Guards, Rubber, For Optical Instruments	MIL-E-18648[1]
Air, compressed under 25 psi	-25	3	No cracks					
Air, oven aging	158	48	T change, -20% max; H change, +20 max					
(Covered in ASTM D1048)				Natural or synthetic		5970	Insulation Blanket, Electrical	MIL-I-19254[2]
Air, original properties	Ambient		T,2200 psi min; E, 650%; H, 38 ± 5	Chloroprene or nitrile		5340	Mounts, Resilient, Mare Island Types 11M15, 11M25 and 10M50	MIL-M-19379 Types 11M15 and 11M25
Air, compression set	30	94	50% max					
Air, oven aging	194	46	T,2100 psi min; E, 650% min					
ASTM #3 petroleum oil	Ambient	46	Volume change, +15% max					
Air, original properties	Ambient		T,2800 psi min; E, 575%; H, 48 ± 5	Chloroprene or nitrile		5340	Mounts, Resilient, Mare Island Types 11M15, 11M25 and 10M50	MIL-M-19379 Type 10M10
Air, compression set	30	94	60% max					
Air, oven aging	194	46	T,2700 psi min; E, 525% min					
ASTM #3 petroleum oil	Ambient	46	Volume change, +15% max					
Air, original properties	Ambient		T,2800 psi min; E, 500% min; H, 50 ± 5	Natural	Yes	5340	Mount Resilient; Type 5B5000-H	MIL-M-19863
Air, compression set	30	94	25% max					
Air, oven aging	194	46	T,2200 psi min; E, 450% min					
Air, breaking strength	Ambient		Warp, 76.5 lbs min; Filling, 78 lbs min	Natural or synthetic rubber coated fabric		8465	Bladders, Flotation	MIL-B-20278
Air, breaking strength	Ambient		269 lbs min	Chloroprene coated nylon cloth		8465	Bladder, Flotation, MK2 Mod 0 and MK2 Mod 1	MIL-B-21160
Air, leakage	28	48	No leakage when bladder inflated					
Air, original properties	Ambient		T,3000 psi min; E, 500% min; H, 45 ± 5	Natural	Yes	5340	Mount, Resilient, Type 5M10,000-H	MIL-M-21649
Air, compression set	30	94	20% max					
Air, oven aging	194	46	T,2500 psi min; E, 450% min					
Air, original properties	Ambient		T,1800 psi min, E, 400% min	Natural or synthetic		5340	Mount, Resilient, Shear (For Use in Shipping Containers)	MIL-M-22322[1] Class A
Air, compression set	194	48	30% max					
Air, oven aging	194	48	T and E change, -20% max					

[1] Document cancelled without replacement.
[2] Document cancelled Use ASTM D1048.

Source: https://assist.dla.mil -- Downloaded: 2026/10-26T13:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION TEST CONDITIONS				ELASTOMER				
ENVIRONMENT AND TEST	TEMP., °F	TIME, HRS.	SPECIFICATION REQUIREMENTS	SPECIFIED OR COMMONLY USED	QPL ISSUED	FSC CLASS	SPECIFICATION TITLE	SPECIFICATION NUMBER
Air, original properties	Ambient		T,1200 psi min; E 400% min	Natural or		5340	Mounts, Resilient	MIL-M-22322[1]
Air, compression set	194	48	30% max	synthetic			Shear (For Use in	Classes B & C
Air, oven aging	194	48	T and E change, -20% max				Shipping Containers)	
Air, original properties	Ambient		T,1400 psi min; E, 350% min; H, 47-57	Chloroprene		9320	Rubber Tile, Rubber-Air-	MIL-R-23074
Air, oven aging	158	166	T and E change, -20% max				Air-Lead-Type (RAL)	
Water	Ambient	46	Volume change, 0 to +12%					
Air, original properties	Ambient		T,1000 psi min; E, 200% min	Natural or		2540	Guards, Splash, Wheel	MIL-G-23621
Ozone resistance	104	168	No cracks					
Air, oven aging	212	16	T,700 psi min					
Low temp	-40		No cracks					
Air, hardness	Ambient		50 to 75	SBR		2530	Boot, Dust and Moisture	MIL-B-45326
Hydraulic fluid, MIL-H-13910	-65	70	No leakage				Seal: Hydraulic Brake Cylinder, Synthetic	
Air, oven aging, 180° bend	250	24	No cracks; hardness change, -5 to +10				Rubber	
Ozone, 50 pphm	100	168	No cracks					
Air, shock attenuation	-39	16	Registered shock of 250, max	Natural		5340	Mount, Shipping Container,	MIL-M-45907
Air, shock attenuation	159	4	Registered shock of 120, max				Resilient; Shock and Vibration Damping	
(No physical property requirements)				Natural			Bulb, Aspirator	MIL-B-50015

[1] Document cancelled without replacement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:46Z
Check the source to verify that this is the current version before use.

ABBREVIATIONS

Break . . . . . breaking
Brk . . . . . breaking
Cell . . . . . cellulose
Chg . . . . . .change
Cl . . . . . class
comp . . . . . compression
Cot . . . . . .cotton
Cr . . . . . chlromium
CR . . . . . chloroprene
D . . . . . .density
defl . . . . . deflection
E . . . . . .elongation
elong . . . . . .elongation
GR . . . . . grade
H . . . . . .hardness, Shore A
humid . . . . . .humidity
in . . . . . inch
indent . . . . . indentation
ins . . . . . .insulation
jkt . . . . . .jacket
lub . . . . . .lubricating
M . . . . . .minutes
max . . . . . .maximum
Mg . . . . . milligrams
min . . . . . .minimum
mm . . . . . millimeters
mod . . . . . .modulus
Nat . . . . . .natural
NBR . . . . . .nitrile
Ni . . . . . .nickel
Orig . . . . . .original
pphm . . parts per hundred million
ppm . . . . . .parts per million
press . . . . . pressure
psi . . . . pounds per square inch
psig pounds per square inch gage
PVC . . . . . polyvinyl chloride
Rel . . . . . relative
sec . . . . . seconds
sep . . . . . separation
Syn . . . . . .synthetic
T . . . . . tensile strength
temp . . . . . temperature
V . . . . . volume
Vol . . . . . volume
W . . . . . weight
wt . . . . . .weight

METRIC UNITS

ENGLISH	MILITARY	EQUAL	METRIC SI UNITS
^{o}F	t ^{o}C = ($t^{o}F$ -32)/1.8	=	^{o}C
PSI	6894.757	=	PASCAL
lbs	0.453924	=	Kg
in^2	6.4516 x E^{-04}	=	M_2
$16/ft^3$	16.01846	=	Kg/M_3

Custodian:
Army - MR

Review:
ME, AR, GL

Preparing activity:
Army - MR

Project 9320-A002

(KBWP# ID-0398A, 0393A, 0400A, 0401A, 0402A, 0403A, 0404A, 0405A, 0406A, 0407A, 0397A, 0399A/DISK 0127A, 0128A. FOR MTL USE ONLY)

☆U.S. GOVERNMENT PRINTING OFFICE 1989 604-033/12227

Source: https://assist.dla.mil -- Downloaded: 2026-0-26T13:46Z
Check the source to verify that this is the current version before use.