MILITARY SPECIFICATION

FILM, PHOTOGRAPHIC, AERIAL, BLACK AND WHITE

This amendment forms a part of Military Specification MIL-F-32G, dated 9 Feb 1973, and is approved for use by all Departments and Agencies of the Department of Defense.

Page 2

TABLE I: TOTAL THICKNESS (MILS) column change 1 1.0 - 1.9 to 1.0 - 2.4 and 2 2.0 - 3.8 to 2 2.5 - 3.8.

Page 7

TABLE III: SLITTING WIDTH (INCHES) column change 2.745 ± 0.002 to 2.754 ± 0.002 and 9.460 ± 0.10 to 9.460 ± 0.01 change last two columns to read: FILM LENGTH (FEET) NOMINAL BASE 7.5 MIL THICK and FILM LENGTH (FEET) NOMINAL BASE 4.5 MIL THICK, respectively.

Page 11

Delete TABLE V and insert new TABLE V.

Page 17

Delete TABLE VIII and insert new TABLE VIII.

Page 21

Paragraph 5.1.2 Level C Package: Delete in its entirety and substitute the following:

"5.1.2 Level C Package -- Each roll of film shall be preserved as specified in paragraph 5.1.1 and packaged in accordance with the manufacturer's commercial practice."

FSC 6750

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T04:26Z
Check the source to verify that this is the current version before use.

CUSTODIANS:
Army - EL
Navy - AS
Air Force - 70

REVIEW ACTIVITIES:
Army -
Navy -
Air Force - 11

USER ACTIVITIES:
Army - AV
Navy - MC

PREPARING ACTIVITY
Navy - AS

Project No. 6750-0328

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T04:26Z
Check the source to verify that this is the current version before use.

TABLE V

SENSITOMETRIC CHARACTERISTICS OF AERIAL NEGATIVE FILM AND DUPLICATING FILM

SENSITOMETRIC DESIGNATOR	RELATIVE SENSITIVITY RANGE METHOD E *	GAMMA	SPECTRAL SENSITIVITY (MAXIMUM) WRATTEN FILTER FACTORS					MAXIMUM FOG	MAX. INCUBATION FOG	DMAX (MINIMUM)	MINIMUM RESOLVING POWER (1/mm)
			25	47	58	70	89B				
53i	200	1.30 - 1.60	6	7	7	--	---	.15	.25	2.55	100
54i	200	1.50 - 1.80	9	7	7	--	---	.15	.45	2.40	100
54j	400	1.35 - 1.85	6	8	10	--	---	.10	.25	2.80	71
63i	200	1.20 - 1.80	5	10	16	20	---	.15	.35	2.90	80
64g	50	2.30 - 2.90	5	10	12	16	---	.05	.25	3.50	180
64h	100	1.95 - 2.20	4	7	12	75	---	.15	.25	3.00	100
64i	200	1.80 - 2.85	6	10	16	25	---	.10	.25	3.20	90
64k	800	1.50 - 2.10	5	10	16	25	---	.20	.40	2.90	63
	METHOD F (INFRARED)										
74f	18 - 35	1.51 - 3.00	2	--	--	--	---	.15	.35	2.30	70
	METHOD B (POSITIVE)										
23c	2.2 - 4.2	1.20 - 1.70	--	--	--	--	---	.05	.15	2.80	180
23d	4.3 - 8.5	0.90 - 1.40	--	--	--	--	---	.05	.10	2.75	140
24a	0.57 - 1.1	1.40 - 1.75	--	--	--	--	---	.05	.10	2.75	285
24d	4.3 - 8.5	1.80 - 2.15	--	--	--	--	---	.05	.10	2.75	135
* Plus or minus 1/2 stop.											

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T04:26Z
Check the source to verify that this is the current version before use.

TABLE VIII

SENSITOMETRIC TEST CONDITION

SENSITOMETRIC DESIGNATOR	ILLUMINANT (FED-STD-170)	EXPOSURE TIME (SECONDS)	DEVELOPER (FED-STD-170)	DEVELOPING TIME (MINUTES)
54i	1	1/40 - 1/120	1	8
54j	1	1/40 - 1/120	1	8
63i	1	1/40 - 1/120	2 *	8
64g	1	1/40 - 1/120	1	8
64h	1	1/40 - 1/120	1	8
64i	1	1/40 - 1/120	1	8
64k	1	1/40 - 1/120	1	12 *
74f	3	1/40 - 1/120	1	8
23c	2	1/5	3	7
23d	2	1/5	3	7
24a	2	1/5	2	4
24d	2	1/5	3	7

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T04:26Z
Check the source to verify that this is the current version before use.