MILITARY SPECIFICATION

STEEL BARS FOR PROJECTILE STOCK

This amendment forms a part of Military Specification MIL-S-43A, dated 31 July 1951, and was approved by the Departments of the Army, the Navy, and the Air Force for use of procurement services of the respective Departments.

Page 2, table III: Delete and substitute:

TABLE III.—*Mechanical properties.*

Diameter	Tensile strength maximum	Yield point minimum	Elongation in 4 X diameter minimum
Inches	*P.s.i.*	*P.s.i.*	*Percent*
1.25 and smaller	118,000	75,000	15
over 1.25 to 2	118,000	70,000	15

Page 4, paragraph 4.4.3: Delete and substitute:

"4.4.3 *Tension test methods.* — Tension tests shall be conducted in accordance with Specification QQ-M-151. Yield point shall be determined by the divider method."

Custodians:
Army—Ordnance Corps
Navy—Bureau of Ordnance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T04:27Z
Check the source to verify that this is the current version before use.

983324—52—(36)