MILITARY SPECIFICATION

SOCKS, MEN'S, CUSHION SOLE, STRETCH TYPE

This Amendment forms a part of Military Specification MIL-S-48K, dated 24 September 1982, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 2

2.1, under "STANDARDS MILITARY": Delete "MIL-STD-1188 - Commercial Packaging of Supplies and Equipment

Add the following paragraph:

"2.1.1 Other publications. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein."

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Chromatic Transference Scale

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal Agencies.)

FSC 8440

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T04:28Z
Check the source to verify that this is the current version before use.

3.3.1: Delete the first sentence and substitute "The color shall match the standard sample when viewed under filtered tungsten lamps which approximate artificial daylight having a correlated color temperature of 7000 ± 500K, with illumination of 100 ± 20 foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300 ± 100K."

3.3.2: Delete the third sentence and substitute "When no standard sample is available, the dyed Black 197 socks shall show "good" fastness to perspiration, "fair" fastness to laundering, and shall show an AATCC Chromatic Transference Scale rating for crocking not less than 1.5 and the dyed Olive Green 408 socks shall show "good" fastness to perspiration and laundering, and shall show an AATCC Chromatic Transference Scale rating for crocking not less than 3.5."

PAGE 17

4.4.3: Delete the third and fourth sentences and substitute "The sample unit shall be one shipping container fully packaged."

PAGE 18

5.1.2: Delete "MIL-STD-1188" and substitute "ASTM D 3951".

PAGE 19

5.2.3, line 2: Delete "MIL-STD-1188" and substitute "ASTM D 3951".

5.3: Delete and substitute:

"5.3 Palletization. When specified (see 6.2), socks, packed as specified in 5.2, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV or type V in accordance with MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern 3 shall be used (see Appendix D of MIL-STD-147). Interlocking of loads shall be effected by reversing the pattern of each course."

5.4, line 3: Delete "MIL-STD-1188" and substitute "ASTM D 3951".

PAGE 20

6.4, line 2: Delete "DAR 7-104.55" and substitute "FAR 52.209".

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T04:28Z
Check the source to verify that this is the current version before use.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - EA, MD
Navy - MC
Air Force - 11, 82
DLA - CT

Preparing activity

Army - GL

Project No. 8440-0167

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T04:28Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T04:28Z
Check the source to verify that this is the current version before use.