INCH-POUND

MIL-DTL-32065
May 11, 2000
SUPERSEDING
C-F-202F
December 31, 1985

DETAIL SPECIFICATION

FELT SHEET (HAIR) AND FELT ROLL (HAIR)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers cattle hair felt as manufactured by the felted and fulled process in sheet and roll form.

1.2 Classification.

1.2.1 Types and classes. The felt will conform to the following types and classes, as specified (see 6.2 and 6.5). The thickness and weight designations will be as required in table 1, as specified (see 6.2):

Type H-26-S
Class U - Untreated
Class N - Neutralized

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Supply Center Philadelphia, Clothing and Textiles Directorate, Attn: DSCP-COTC, 700 Robbins AVE, Philadelphia PA 19111-5096, by using the self addressed Standardization Document Improvement Proposal(DD Form 1426) appearing at the end of this document, or by letter.

AMSC N/A **FSC 8305**

DISTRIBUTION STATEMENT A. ***Approved for public release; distribution is unlimited.***

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

Types and classes continued:

Type H-26-R
Class U - Untreated
Class N - Neutralized

Type H-34-S
Class U- Untreated
Class N- Neutralized

Type H-34-R
Class U- Untreated
Class N- Neutralized

Type H-43-S
Class U - Untreated
Class N - Neutralized

TypeH-43-R
Class U - Untreated
Class N - Neutralized

Type H-56-S
Class U - Untreated
Class N – Neutralized

Type H-56-R
Class U - Untreated
Class N - Neutralized

APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4. This section does not include documents cited in other sections or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements and documents cited in sections 3 and 4, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the Department of Defense Index of Specification and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

Military Specifications

MIL-F-2312 - Felt, Hair or Wool: Mildew Resistant and Moisture Resistant Treatment For

(Unless otherwise indicated, copies of the above specifications, standards, and handbooks are available from the Defense Automated Printing Service , 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

FEDERAL TRADE COMMISSION

Rules and Regulations Under The Textile Fiber Products Identification Act

(Copies may be obtained without charge from the Federal Trade Commission, Washington, DC 20580-0001).

DoDISS - Department of Defense Index of Specifications and Standards.

(Copies of the DoDISS are available on a yearly subscription basis either from the Government Printing Office or the DoDSSP Subscription Services, 700 Robbins Ave., Building 4D. Philadelphia PA 19111-5094.)

2.3 Non-Government publications. The following document(s) form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DoDISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN NATIONAL STANDARDS INSTITUTE (ANSI) / AMERICAN SOCIETY for QUALITY (ASQ)

ANSI/ASQ Z1.4 Sampling Procedures and Tables for Inspection of Attributes.

(Application for copies should be addressed to American Society for Quality Control, P.O. Box 3005, 611 East Wisconsin Ave., Milwaukee, WI 53201-4606)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM) PUBLICATION

ASTM-D-1777 - Thickness of Textile Materials

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

ASTM-D-3776	-	Mass Per Unit Area (Weight) of Fabric
ASTM-D- 3951	-	Standard Practice for Commercial Packaging
ASTM-D-5034	-	Breaking Force and Elongation of Textile Fabrics (Grab Test)

(Application for copies should be addressed to American Society for Testing and Materials, 100 Barr Harbour Drive, West Conshohocken, PA 19428)

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

AATCC – 20A	-	Fiber Analysis Quantitative
AATCC – 81	-	pH of the Water- Extract from Bleached Textiles

(Applications for copies should be addressed to American Association of Textile Chemists and Colorists (AATCC) PO Box 12215, Triangle Park, NC 27709-2215)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified, a sample shall be submitted for first article inspection (see 4.3, 6.2, and 6.3).

3.2 Recycled, recovered, or environmentally preferable materials. Recycled, recovered, or environmentally preferable materials should be used to the maximum extent possible provided that the material meets or exceeds the operational and maintenance requirements, and promotes economically advantageous life cycle costs.

3.3 Material.

3.3.1 Fiber. The felt shall be made predominately from washed cattle hair, Which shall be the main fiber constituent of the felt, but not to the exclusion of other animal hair. The fiber content of all felt shall be not as than 95 percent hair fibers. These requirements shall be tested as specified in 4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

3.3.2 Extractable matter. Chloroform and water extractable matter shall not exceed 16.0 percent by weight, based on the bone - dry weight of the test specimen. These requirements shall be tested as specified in 4.4.

3.3.3 Weight and thickness. The felt shall conform to the requirements for thickness in inches, and weight in pounds pet square yard, as specified in table I, when tested as specified in 4.4.

TABLE I. Thickness and weight of finished hair felt

Types classes U and N)	Thickness of finished felt (inches) Nominal	Min.	Max.	Weight of finished felt (pounds/square yard) Nominal	Mim.	Max.
H-26-S	0.188	0.170	0.206	2.26	2.03	2.49
And	0.250	0.225	0.275	3.00	2.70	3.30
H-26-R	0.313	0.281	0.345	3.75	3.37	4.13
	0.375	0.388	0.412	4.50	4.05	4.95
H-26-S	0.500	0.450	0.550	6.00	5.40	6.60
and	0.625	0.562	0.688	7.50	6.75	8.25
R-26-R	0.750	0.675	0.825	9.00	8.10	9.90
	0.875	0.787	0.963	10.50	9.45	11.55
	1.000	0.900	1.100	12.00	10.80	13.20
	1.250	1.130	1.370	15.00	13.00	17.00
	1.500	1.350	1.650	18.00	16.00	20.00
	1i150	1.600	1.900	21.00	19.00	23.00
	2.000	1.850	2.150	24.00	22.00	26.00
H-34-S	0.125	0.112	0.137	2.00	1.60	2.20
and	0.188	0.170	0.206	3.00	2.70	3.30
H-34-R	0.250	0.225	0.275	4.00	3.60	4.40
	0.313	0.281	0.345	5.00	4.50	5.50
	0.375	0.338	0.412	6.00	5.40	6.60
	0.500	0.650	0.550	8.00	7.20	8.80
	0.625	0.562	0-688	10.00	9.00	11.00
	0.750	0.675	0.825	12.00	10.80	13.20
	0.875	0.787	0.963	14.00	12.60	15.40
	1.000	0.900	1.100	16.00	16.40	17.60
	1.250	1.130	1.370	20.00	18.00	22.00
	1.500	1.350	1.650	24.00	22.00	26.03
	1.750	1.600	1.900	28.00	26.00	30.00
	2.000	1.850	2.150	32.00	30.00	34.00

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

Table I. Thickness and weight of finished hair felt - Continued

Types classes U and N)	Thickness of finished felt (inches) Nominal	Min.	Max.	Weight of finished felt (pounds/square yard) Nominal	Mim.	Max.
H-43-S and H-43-R	0.094	0.082	0.106	1.88	1.69	2.07
	0.125	0.112	0.137	2.50	2.25	2.75
	0.188	0.170	0.206	3.75	3.37	4.13
	0.250	0.225	0.275	5.00	4.50	5.50
	0.313	0.281	0.345	6.25	5.62	6.88
	0.375	0.338	0.412	7.50	6.75	8.25
	0.500	0.450	0.550	10.00	9.00	11.00
H-43-S and H-43-R	0.625	0.562	0.688	12.50	11.25	13.75
	0.750	0.675	0.825	15.00	13.50	16.50
	0.875	0.78?	0.963	17.50	15.75	19.25
	1.000	0.900	L.100	20.00	18.00	22.00
	1.250	1.130	1.370	25.00	23.00	27.00
H-43-S and H-43-R	1.500	1.350	1.650	30.00	28.00	32.00
	1.750	1.600	1.900	35.00	33.00	37.00
	2.000	1.850	2.150	40.00	38.00	42.00
H-56-S and H-56-R	0.094	0.062	0.106	2.44	2.20	2.68
	0.125	0.13.2.	0.137	3.25	2.92	3.58
	0.188	0.170	0.206	4.88	4.39	5.37
	0.250	0.225	0.275	6.50	5.80	7.15
	0.313	0.281	0.345	8.14	7.33	8.95
	0.375	0.338	0.412	9.75	8.77	10.73
	0.500	0.450	0.550	13.00	11.70	14.30
	0.625	0.562	0.688	16.25	14.62	17.88
	0.750	0.675	0.825	19.50	17.55	21.45
	0.875	0.787	0.963	22.75	20.75	24.75
	1.000	0.900	1.100	26.00	24.00	28.00
	1.250	1.130	1.370	32.50	30.50	34.50
	1.500	1.350	1.650	39.00	37.00	41.00
	1.750	1.600	1.900	45.50	43.50	47.50
	2.000	1.850	2.150	52.00	50.00	54.00

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

3.3.4 Roll length and width. Unless otherwise specified (see 6.2), the felt shall be furnished in rolls 48 inches +/- 1 .0 inch in width and in continuous length ranges in accordance with the following thickness schedule:

Thickness (inches)	Length (yards)
5/16 and under	8-17
Over 5/16 and Less than 1/2	5-12
1/2 to 1 inclusive	3-7
1 ¼ to 2	1-3

3.3.5 Sheet length and width. Unless otherwise specified (see 6.2), the felt shall be furnished to sheet form with trimmed edges in the following sizes as specified:

Sheet size,inches (± 1/2 inch in either direction)			
30x24	30x48	36x36	
30x36	36x24	36x48	36x60

3.3.6 Color. Unless otherwise specified (see 6.2), the felt shall be natural; the color resulting from the various shades of brown hair used shall be acceptable.

3.3.7 Organic acidity. When specified (see 6.2 and 6.4), all class "U" felt shall not show an organic acidity greater than 0.2 percent when tested as specified in 4.4.

3.3.8 Alkalinity and mineral acidity. When specified (see 6.2 and 6.4), all class "N" felts shall have a pH of 7.0 ± 1.0 when tested as specified in 4.4.

3.3.9 Mildew treatment. When specified (see 6.2), the felt shall be mildew-resistant treated in accordance with type I of MIL-F-2312. The physical and chemical characteristics of the treated felt shall conform to the requirements specified therein. Organic acidity, alkalinity, and mineral acidity requirements are not applicable to mildew-resistant treated felts.

3.4 Construction. The construction of all types and classes of the felt covered by this specification shall be that of a textile composed wholly of hair fibers physically interlocked by the inherent felting properties of animal hair fibers and produced by a suitable combination of mechanical work, chemical action, moisture, and heat, but with out needle loom weaving, knitting**,** stitching, thermal bonding, or adhesives.

3.4.1 Flexibility. All types and classes of felt covered by this specification shall show no visible sign of cracking when tested as specified in 4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

3.4.2 Splitting resistance. All, types and classes of felt covered by this specification shall have a minimum splitting resistance of 4.0 pounds in each direction when tested as specified in 4.4. This test is not applicable to felt of 1/8 inch and under in thickness. The split sections shall be visually inspected to ensure that needle looming has not been used during manufacture.

3.4.3 Bulk density. The bulk density shall be as follows when tested as specified in 4.4

Types H-26-S and R = 0.26
Types H-34-S and R = 0.34
Types H-43-S and R = 0.43
Types H-56-S and R = 0.56

3.5 Identification. Each roll and sheet shall be identified by the following methods as applicable.

3.5.1. Identification. Each roll shall have a piece ticket (see 6.2*)* (identification tag attached to the edge at the inner end of the felt with not finer than 5-ply cotton string doubled to not less than 8 inches long or a plastic tag hanger of 5-inch minimum length. The piece ticket shall be made of not less than 15-point paper stock, and the finished surface shall not be calendered or pigmented to the degree that would cause the obliteration of printed, stamped, or typed markings. The piece ticket shall have a reinforced eyelet for attaching the typing cord or hanger and shall be legibly printed with water insoluble ink with the markings shown on figure 1. Entries on piece tickets (tags) shall be printed, stamped, or typed. The entries shall be complete and responsive with respect to the information required by the piece ticket legend (see figure 1). Hand lettered entries are permitted, but hand written entries are not permitted.

3.5.2 Labels. Each sheet of felt shall have a label attached to the upper right corner by staple or pin-ticket attachment. The label shall be made of not less than 15-point paper stock, and the color shall be white or light in intensity to permit easy reading of printed markings. The label shall be legibly printed with water insoluble ink with the information specified in 3.5.1, except that gross and net yards are replaced by width and length.

3.5.3 Fiber identification label. Felt manufactured under this specification shall be labeled in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act.

3.6 Workmanship. The finished felt shall conform to the quality established by this specification. The occurrence of defects shall not exceed the applicable quality levels.

4. VERIFICATION

4.1 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Conformance inspection (see 4.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

4.2 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check-test such items to determine the validity of the certification.

4.3 First article inspection. The first article, submitted in accordance with 3.1, shall be inspected for the requirements of Table II.

Table II First article examination and tests

INSPECTION	REQUIREMENT	INSPECTION METHOD
Material Inspection	3.3.1, 3.3.2, 3.3.3, 3.3.4, 3.3.5, 3.3.6, 3.3.7, 3.3.8, 3.3.9, 3.4, 3.4.1, 3.4.2, 3.3.3	4.4.1
Visual Examination	3.5.1, 3.5.2, 3.5.3, 3.6	4.5

4.4 Conformance inspection. Sampling for inspection shall be performed in accordance with ANSI/ASQC Z1.4, for the requirements of Table III, except where otherwise indicated:

Table III Conformance Examination and Tests

INSPECTION	REQUIREMENT	INSPECTION METHOD
Visual Examination	3.5.1, 3.5.2, 3.5.3, 3.6	4.5

4.4.1 End item testing. The cloth shall be tested for the characteristics listed in Table IV. All test reports shall contain the individual values utilized in expressing the final results. The sample unit shall be 1 square yard of rolled felt or one sheet of felt, as applicable. The lot shall be unacceptable if one or more sample units fail to meet any teat requirement specified. All test reports shall contain the individual values utilized in expressing the final result. The sample size (number of sample units) shall be as follows

Lot size (yards)	Sample size (sample units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Table IV. Verification Testing.

Characteristic	**Requirement paragraph**	**Test Method**
Fiber identification	3.3.1	1/
Fiber content	3.3.1	AATCC-20A

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

Table IV. Verification Testing - Continued.

Characteristic	Requirement paragraph	Test Method
Washed	3.3.1	1/
Extractable matter	3.3.2	AATCC-20A 2/
Weight	3.3.3	ASTM-D-3776 3/
Thickness	3.3.3	ASTM-D-1777 4/
Organic acidity	3.3.7	4.4.1
Alkalinity or mineral acidity	3.3.8	AATCC-81
Flexibility	3.4.1	4.4.2 5/
Splitting resistance	3.4.2	4.4.3
Bulk density	3.4.3	4.4.4

1/ Unless otherwise specified a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ Test method AATCC-20A except that the test specimen shall be cut into pieces of approximately 1/8 inch.

3/ Method ASTM-D-3776 Option C, shall be used except the weight shall be calculated as follows:

$$\text{Wt/sq yd (pounds)} = \frac{\text{Weight of specimen (grams) x 36 in/yd x 36 ,in/yd}}{\text{Area of specimens (sq in) x 453.59 (grams/lb)}}$$

4/ A thickness gauge of the dead-weight type equipped with a dial graduated to read directly to.001 inches shall be used. The presser foot shall be circular, with a diameter of 1.129 +/- 0.001 inches and with moving parts weighed to apply a total load of 0.60 +/- 0.03 pounds per square inch to the specimen. The anvil shall be not less than 1.129 inches in diameter. The presser foot and anvil surface shall be planed to within 0.001 inches and shall be parallel to each other within 0.001 inches.

5 / One determination per sample unit and the results reported as “pass” or “fail.”

4.4.1.1 Organic acidity. A specimen totaling 10.0 grains ± 1 gram shall be tested for organic acidity.

4.4.1.2 Procedure. Heat the specimen in an Erlenmeyer flask with 100 milliliters of neutral 95percent ethyl alcohol at a temperature between 50° and 60^{0}C for 15 minutes. The temperature shall maintained by means of a water bath. Filter the solution through filter paper, retaining as much of the specimen as possible in the flask. Repeat the process, then wash the filter paper with a small amount of warm alcohol., all filtrates and washing being caught in the same vessel. Cool the solution to room temperature and titrate with standard alcoholic KOH (in range of O.2N). A blank determination shall be made on all reagents and the necessary correction applied.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

4.4.1.3 Calculations. The method of calculating the organic acidity shall be as follows:

a. Highly ionized acids: use methyl orange as indicator. Shall not indicate presence of acid greater than 0.2 percent.
b. Total acidity: use phenolphthalein as indicator.
c. Organic acids (or slightly ionized acids): (b)- (a) = organic (or slightly ionized) acids.
d. Acidity as acetic acid percent = $\frac{6.CV\ N}{W}$

where V= milliliters of standard KOH corrected for blank determination, required to titrate organic acid only,
N= normality of standard KOH, and
W= grams of sample.

e. Two determinations shall be made on each sample unit and the average reported to the nearest 0.1 percent.

4.4.2 Flexibility. All felt shall be bent 160° over a rod equal In diameter to the thickness of the felt. Any visible sign of cracking of the specimen shall be cause for rejection$_1$

4.4.3 Splitting resistance. The felt shall be tested for splitting resistance as follows,

4.4.3.1 Apparatus. The teat apparatus shall be as specified in method ASTM-D-5034(except that the width of the jaw shall exceed the specimen width by 0.5 inch and that all machine attachments for determining maximum load shall be disengaged during the test.

4.4.3.2 Procedure. Cut eight specimens with a die 2 inches by 6 inches from each sample unit: four specimens shall be cut in the lengthwise direction and four specimens shall be cut in the widthwise direction. The specimens shall be cut in such a manner that the 6-inch dimension is parallel with the direction of the material being tested. Each specimen shall be evenly split in thickness a distance of 2 inches by cutting with a knife or other sharp instrument. The split shall be within the middle third of the thickness of the specimen. Clamp one of the split-ends in one jaw of the testing machine and the other split-end in the other jaw. Record the maximum load in pounds necessary to split the specimen completely apart to the nearest 0.1 pound. Record the three highest peak-load values as read from the recording dial or autographic recording device. These three separate values from the individual specimen shall be averaged and this average recorded as the single determination of the splitting resistance of the specimen and recorded separately.

4.4.3.3 Report. The splitting resistance of each sample unit shall be obtained by averaging the four single determination values obtained in 4.4.3.2 above for the direction being tested and reported to nearest 0.1 pound.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

4.4.4 Bulk density. Bulk density shall be calculated as follows:

$$\text{Bulk density} = \frac{\text{Weight of felt (lb/sq yd)}}{\text{Thickness of felt (Inches)}} \times 0.0214$$

4.5 Examination of the end item. Defects found during the visual examination shall be classified in accordance with 4.5.2 through 4.5.3.

4.5.1 Visual examination. The felt shall be examined on one side only. However, for each successive roll or sheet in the sample, that side shall be alternated. Defects found during this examination shall be classified in accordance with table V. All defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition, in which case only the mote serious defect shall be counted. In rolled felt, a defect extending over more than 1 continuous linear yard shall be counted as one defect for each yard or fraction thereof in which it occurs. the lot size shall be expressed in units of 1 linear yard when rolls are specified and one sheet when sheets are specified. The sample unit shall be 1 linear yard when rolls are specified and one sheet when sheets are specified. The inspection level shall be I. The acceptable quality levels (AQL's) shall be specified in the contract, or acquisition document. The number of rolls from which the sample is to be taken shall be in accordance with tableVI. An approximate equal number of yards shall be examined for each roll.

TABLE V. Classification of visual defects

Defects	Classification	
	Major	**Minor**
Cut, hole or tear - any size	201	
Thin or weak place — any size	202	
felting rub — clearly noticeable but not resulting in a thin or weak place		101
High place or Lump		102
Hardener rib		103
Width (rolls only):		
— more than 1/2 inch over the specified width		104
— more than 1/2 inch less than the specified width	203	
Width and length (sheets only):		
— more than 1/2 inch over the specified width or length		105
— more than 1/2 inch less than the specified width or length	204	
Identification (ticket or labe1)		
— missing, incorrect, incomplete, illegible, or insecurely attached		106

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

4.5.2 Examination for overall defects. The felt shall be examined for the overall defects listed below in Table VI. Each defect shall be counted not more than once in a roll or sheet. The sample unit shall be one roll or sheet. The number of rolls or sheets selected shall be in accordance with Table VII. The lot shall be unacceptable if the defects found exceed the maximum number permitted in Table VII.

TABLE VI Overall defects

Defects	Classification	
	Major	**Minor**
Burrs, shives, or other foreign matter, any protrusion or Accumulation visible from 3 feet		107
Uneven felting		108
Color not natural		109
Wrong type, roll, or sheet		110
Not clean		111

TABLE VII Examination criteria

Lot Size in Yards or sheets	Sample Size		Maximum number of Defects acceptable In sample	
	Roll 1/	**Sheets 1/**	**Rolls**	**Sheets**
Up to 1200	3	7	0	0
1201 up to and including 3200	5	10	0	0
3201 up to and including 10,000	7	15	0	0
10,001 up to and including 35,000	10	25	0	1
35,001 up to and including 150,000	15	35	1	2
150,001 and over	25	50	1	3

1/ If a lot contains fewer than the required number of rolls or sheets,, each roll or sheet in the lot shall be examined.

4.5.3 Length examination (rolls only).

4.5.3.1 Individual rolls. Each roll shall be examined for gross length. Any gross length found to be less than the minimum length specified or more than 1 yard less than the gross length marked on the roll ticket, or not in a continuous length, shall be considered a defect with respect to length. The sample unit shall be one roll. The rolls used for the visual examination shall be used for this examination. The lot shall be unacceptable if one or more defects are found in the sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

4.5.3.2 Examination for total yardage (rolls only). The lot shall be unacceptable if the total of the actual gross lengths in the sample is less than the total of the gross lengths marked on the roll tickets. The rolls used for the visual examination shall be used for this examination.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When actual packaging of material is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activity within the Military Department or Defense Agency, or within the Military Department's System Command. Packaging data retrieval is available from the managing Military, Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The felt (hair) is intended for uses listed below and for similar applications:

H-26-S and H-26-R - For insulation where the temperature will not exceed 120° F for cushioning, packing, padding, and crating of greater than one-time use. Vibration mountings and dust shields.

H-34-S and H-34-R - For cushioning, packing, padding, and shielding where moderate and strength and abrasion resistance are required. Vibration and shock mounts for long-term operation. Ammunition components, when class N. Filter elements.

H-43-S and H-43-R - For cushioning, packing, padding, and shielding where high and strength and abrasion r resistance are required. Vibration end shock mounts for long - term operation and moderate loading. Ammunition components when class N. Polishing blocks, wheels and pads, wiper, applicators, and filter elements.

H-56-S and H-56-R - For cushioning, packing, padding, and shielding where unusual strength, hardness, and abrasion resistance are required. Vibration and shock mounts for heavy loading and high frequency. Ammunition components when class N. Heavy-duty polishing blocks, wheels, and pads. Wipers, applicators, and filters.

6.2 Ordering data. Purchasers should select the preferred option permitted herein and include the following information in procurement documents;

a. Title, number, and date of this specification.
b. Type., class, thickness, and weight required (1.2.1).
c. When a first article is required (see 3.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

d. Length and width or sheet sizes as applicable, if other than specified (see 3.2.4 and 3.2.5).
e. Color, if other than natural (see 3.2.6).
f. Organic acidity when required (see 3.2.7 and 6.4).
g. Alkalinity and mineral acidity when required (see 3.2.8 and 6.4).
h. When mildew-resistant treatment is required (see 3.2.9).
i. When other than ticket is required (see 3.4.1).
j. Packing requirements (see 5.1).

6.3 First article. When a first article is required, it will be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a pre-production sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instruction in all acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Organic acidity, alkalinity, and mineral acidity. If felt is to be used in direct contact with brass, bronze, copper, aluminum, or other materials that might be affected by acid, purchasers should specify that the felt shall be free from organic acidity, alkalinity, and mineral acidity (see 3.2.7 and 3.2.8).

6.5 Hair felt types. The hair felt types covered by this specification are classified by a code letter "H" designating the composition of fibers as predominately washed cattle hair. Final letters designate the general form of manufacture, either 'R" or 'S" for roll or sheet. manufacture, respectively, and the relative condition of residual acidity, either "U" for untreated or "N" for neutralized.

6.6 Subject term (key word) listing.

Wool
Felt
Sheet
Roll
Hair

MILITARY INTERESTS:

Custodians

Army - GL
Navy – NU
Air Force - 99

Review activities

Army – MD
Navy - OS
Air Force – 82

CIVIL AGENCY COORDINATING ACTIVITIES:

GSA — FSS
VA-OSS
HHS - SSA
USDA - AMS
JUS — FPI

PREPARING ACTIVITY;

DLA-CT

Project Number 8305-0782

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7 and send to preparing activity.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	**1. DOCUMENT NUMBER** MIL-DTL-32065	**2. DOCUMENT DATE** ***(YYYYMMDD)*** May 11, 2000

3. DOCUMENT TITLE

FELT SHEET (HAIR) AND FELT ROLL (HAIR)

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME *(Last, First, Middle Initial)*	b. ORGANIZATION	
c. ADDRESS *(Include Zip Code)*	d. TELEPHONE *(Include Area Code)* (1) Commercial (2) DSN *(If applicable)*	7. DATE SUBMITT *(YYYYMMDD)*

8. PREPARING ACTIVITY

a. NAME DEFENSE SUPPLY CENTER PHILADELPHIA DSCP-COCT	b. TELEPHONE *(Include Area Code)* (1) Commercial (2) DSN (215) 737-2418 444-2418
c. ADDRESS *(Include Zip Code)* 700 Robbins Ave (Bldg 6, C&T) PHILADELPHIA, PA 19111-5092	**IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:** Defense Standardization Program Office (DLSC-LM) 8725 John J. Kingman Road, Suite 2533 Fort Belvoir, Virginia 22060-6221 Telephone (703) 767-6888 DSN 427-6888

DD Form 1426, FEB 1999 (EG) PREVIOUS EDITION IS OBSOLETE
WHS/DIOR, Feb 99

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T04:32Z
Check the source to verify that this is the current version before use.