The documentation and process conversion measures necessary to comply with this document shall be completed by 3 January 2023.

INCH-POUND
MIL-PRF-19500/343M
w/AMENDMENT 2
3 October 2022
SUPERSEDING
MIL-PRF-19500/343M
w/AMENDMENT 1
6 December 2017

PERFORMANCE SPECIFICATION SHEET

RF TRANSISTOR, NPN, SILICON, LOW POWER, ENCAPSULATED (THROUGH-HOLE AND SURFACE MOUNT), AND UNENCAPSULATED, RADIATION HARDNESS ASSURANCE, TYPES 2N2857, QUALITY LEVELS JAN, JANTX, JANTXV, JANS, JANHC, AND JANKC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for NPN, silicon, low power, ultra-high frequency transistors. Four levels of product assurance (JAN, JANTX, JANTXV and JANS) are provided for each device type. Two levels of product assurance (JANHC and JANKC) are provided for unencapsulated devices as specified in MIL-PRF-19500. RHA level designators “M”, “D”, “P“, “L”, “R”, “F”, “G”, and “H” are appended to the device prefix to identify devices, which have passed RHA requirements.

1.2 Package outlines and die topography. The device packages for the encapsulated device types are as follows: (2N2857) (TO-72) in accordance with figure 1, 2N2857UB (UB) in accordance with figure 2. The dimensions and topography for JANHC and JANKC unencapsulated die is as follows: “A” version die in accordance with figure 3

1.3 Maximum ratings at T_A = +25°C unless otherwise specified.

	P_T T_A = +25°C	P_T (1) T_C = +25°C	I_C	V_{CBO}	V_{CEO}	V_{EBO}	$R_{\theta JA}$ (2)	$R_{\theta JSP}$ (2)	$R_{\theta JC}$ (2)	T_J and T_{STG}
	mW	mW	mA dc	V dc	V dc	V dc	°C/W	°C/W	°C/W	°C
TO-72	200	300	40	30	15	3	550		300	-65 to +200
UB	200	300	40	30	15	3		210		

(1) Derate linearly 3.33 mW/°C for T_C > +25°C, see figure 4 and figure 5.
(2) For thermal impedance curves, see figure 6, figure 7, and figure 8.

Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A
DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

FSC 5961

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics at T_A = +25°C.

	h_{FE1}	$\lvert h_{fe} \rvert$	C_{cb}	F	G_{pe}	$r_b' C_c$
	V_{CE} = 1 V dc I_C = 3 mA dc	V_{CE} = 6 V dc I_C = 5 mA dc f = 100 MHz	V_{CB} = 10 V dc I_E = 0 f = 100 kHz ≤ f ≤ 1 MHz	V_{CE} = 6 V dc I_C = 1.5 mA dc f = 450 MHz R_g = 50 Ω	V_{CE} = 6 V dc I_C = 1.5 mA dc f = 450 MHz	V_{CB} = 6 V dc I_E = 2 mA dc f = 31.9 MHz
			pf	db	db	ps
Min	30	10			12.5	4
Max	150	21	1.0	4.5	21	15

1.5 Part or Identifying Number (PIN). The PIN is in accordance with MIL-PRF-19500, and as specified herein. See 6.5 for PIN construction example, 6.6 for a list of available PINs.

1.5.1 JAN certification mark and quality level.

1.5.1.1 Quality level designators for encapsulated devices. The quality level designators for encapsulated devices that are applicable for this specification sheet from the lowest to the highest level are as follows: "JAN", "JANTX" “JANTXV”, and "JANS".

1.5.1.2 Quality level designators for unencapsulated devices (die). The quality level designators for unencapsulated devices (die) that are applicable for this specification sheet from the lowest to the highest level are as follows: "JANHC" and "JANKC".

1.5.2 Radiation hardness assurance (RHA) designator. The RHA levels that are applicable for this specification sheet from lowest to highest for JANS, JANHC, and JANKC quality levels are as follows: "M", "D", "P", "L", “R”, “F’, “G”, and “H”. The RHA levels for TXV quality levels are as follows: “R” and “F’.

1.5.3 Device type. The designation system for the device types of transistors covered by this specification sheet are as follows.

1.5.3.1 First number and first letter symbols. The transistors of this specification sheet use the first number and letter symbols "2N".

1.5.3.2 Second number symbols. The second number symbols for the transistors covered by this specification sheet are as follows: "2857".

1.5.4 Suffix symbols. The following suffix letters are incorporated in the PIN in the order listed in the table as applicable:


	A blank first suffix symbol indicates a through hole TO-72 devices (see figure 1).
UB	Indicates a surface mount (2N2857UB) (see figure 2)

1.5.5 Lead finish. The lead finishes applicable to this specification sheet are listed on QML-19500.

1.5.6 Die identifiers for unencapsulated device (manufacturers and critical interface identifiers). The manufacturer die identifier that is applicable for this specification sheet is "A" (see figure 3, 6.5, and 6.6).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

Symbol	Dimensions				Notes
	in	in	mm	mm	
	Min	Max	Min	Max	
CD	.178	.195	4.52	4.95	5
CH	.170	.210	4.32	5.33	
HD	.209	.230	5.31	5.84	5
LC	.100	TP	2.54	TP	7,8
LD	.016	.021	.410	.533	7,8
LL	.500	.750	12.70	19.05	7,8
LU	.016	.019	.41	.48	
L_1		.050		1 .27	
L_2	.250		6.35		
P	.100		2.54		
Q		.040		1.02	5
TL	.028	.048	.71	1.22	
TW	.036	.046	.91	1.17	
r		.007		.18	
α	45° TP				




NOTES:

1. Dimension are in inches.
2. Millimeters are given for general information only.
3. Beyond r (radius) maximum, TW shall be held for a minimum length of .011 (0.28 mm).
4. Dimension TL measured from maximum HD.
5. Body contour optional within zone defined by HD, CD, and Q.
6. Leads at gauge plane .054 +.001 -.000 inch (1.37 +0.03 -0.00 mm) below seating plane shall be within .007 inch (0.18mm) radius of true position (TP) at maximum material condition (MMC) relative to tab at MMC. The device may be measured by direct methods or by the gauge and gauging procedure shown in figure 2.
7. Dimension LU applies between L_1 and L_2. Dimension LD applies between L_2 and LL minimum. Diameter is uncontrolled in L_1 and beyond LL minimum.
8. All four leads.
9. Dimension r (radius) applies to both inside corners of tab.
10. Lead 1 = emitter, lead 2 = base, lead 3 = collector, lead 4 = case (electrically connected).

FIGURE 1. Physical dimensions for 2N2857, (TO-72).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.




Symbol	Dimensions				Note	Symbol	Dimensions				Note
	in	in	mm	mm			in	in	mm	mm	
	Min	Max	Min	Max			Min	Max	Min	Max	
BH	.046	.056	1.17	1.42		LS1	.035	.040	0.89	1.02	
BL	.115	.128	2.92	3.25		LS2	.071	.079	1.80	2.01	
BW	.085	.108	2.16	2.74		LW	.016	.024	0.41	0.61	
CL		.128		3.25		r		.008		0.20	
CW		.108		2.74		r1		.012		0.31	
LL1	.022	.038	0.56	0.96		r2		.022		0.56	
LL2	.017	.035	0.43	0.89							

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Hatched areas on package denote metallized areas.
4. Lid material: Kovar.
5. Pad 1 = base, Pad 2 = emitter, Pad 3 = collector, Pad 4 = shielding connected to the lid.

FIGURE 2. Physical dimensions, surface mount (UB version).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.



Die size --------.016 x .016 inch (0.41 x 0.41 mm).
Die thickness---.008 ±.0016 inch (0.203 ± 0.041 mm).
Base pad--------.0023 x .0023 inch (0.058 x 0.058 mm).
Emitter pad-----.0023 x .0023 inch (0.058 x 0.058 mm).
Back metal:-----Gold, 6,500 ±1,950 Å.
Top metal -------Aluminum, 17,500 ±2,500 Å.
Back side --------Collector.
Glassivation-----SiO_2, 7,500 ±1,500 Å.

FIGURE 3. JANHC and JANKC (A-version) die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Copies of these documents are available online at https://quicksearch.dla.mil)

2.3 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturers list before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

3.4 Interface and physical dimensions. Interface and physical dimensions shall be as specified in MIL-PRF-19500, and on figure 1, figure 2, and figure 3 herein. The device package styles shall be as follows: Four pin metal can (similar to TO-72) in accordance with figure 1, four pad surface mount case outlines (UB) in accordance with figure 2, and unencapsulated die in accordance with figure 3 for device types JANHC and JANKC.

3.4.1 Lead finish. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Pin-out. The pin-out of the device shall be as shown in figure 1. Lead 1 = emitter, lead 2 = base, lead 3 = collector, lead 4 = case (electrically connected).

3.5 Radiation hardness assurance (RHA). Radiation hardness assurance requirements and test levels shall be as defined in MIL-PRF-19500.

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

3.7 Electrical test requirements. The electrical test requirements shall be as specified in table I.

3.8 Marking. Marking shall be in accordance with MIL-PRF-19500. At the option of the manufacturer, marking on the UB package may be omitted from the body, but shall be retained on the initial container.

3.9 Workmanship. Low-power device, transistor, NPN, silicon, low power shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4 and table I, table II, table III, and table IV).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.2.1. JANHC and JANKC qualification. JANHC and JANKC qualification inspection shall be in accordance with MIL-PRF-19500.

4.2.2 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table IV tests, the tests specified in table IV herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

4.3 Screening (JANS, JANTX, and JANTXV only). Screening shall be in accordance with table E-IV of MIL-PRF-19500 and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen	Measurements for JANS level	Measurements for JANTX and JANTXV levels
(1) 3c	Thermal impedance, method 3131 of MIL-STD-750 (see 4.3.1.3).	Thermal impedance, method 3131 of MIL-STD-750 (see 4.3.1.3).
9	I_{CES}, h_{FE1}.	Not applicable.
10	48 hours minimum.	48 hours minimum.
11	I_{CES}, h_{FE1}; ΔI_{CES} = 100 percent of initial value or 5 nA, whichever is greater; Δh_{FE1} = 15 percent.	I_{CES}, h_{FE1}.
12	See 4.3.1.1.	See 4.3.1.1.
13	Subgroups 2 and 3 of table I herein; ΔI_{CES} = 100 percent of initial value or 5 nA dc, whichever is greater; Δh_{FE1} = 15 percent .	Subgroup 2 of table I herein; ΔI_{CES} = 100 percent of initial value or 5 nA dc, whichever is greater; Δh_{FE1} = 15 percent.

(1) Shall be performed anytime after temperature cycling, screen 3a; TX and TXV do not need to be repeated in screening requirements.

4.3.1.1 Power burn-in conditions. Power burn-in conditions are as follows: V_{CB} = 5 - 15 V dc; P_T = 200 mW at, T_A = room ambient as defined in the general requirements of 4.5 of MIL-STD-750. NOTE: No heat sink or forced air cooling on the devices shall be permitted.

4.3.1.2 Screening of unencapsulated die (JANHC and JANKC). Screening of JANHC and JANKC die shall be in accordance with MIL-PRF-19500, “Discrete Semiconductor Die/Chip Lot Acceptance”. Burn-in duration for the JANKC level follows JANS requirements; the JANHC follows JANTX requirements.

4.3.1.3 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3131 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, t_{MD} (and V_C where appropriate). The thermal impedance limit shall comply with the thermal impedance graph on figure 6, figure 7, and figure 8 (less than or equal to the curve value at the same t_H time) and shall be less than the process determined statistical maximum limit as outlined in method 3131 of MIL-STD-750. See table IV, subgroup 4 herein.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500, and as specified herein. If alternate screening is being performed in accordance with E.5.3.1d of MIL-PRF-19500, a sample of screened devices shall be submitted to and pass the requirements of group A1 and A2 inspection only (table E-VIb, group B, subgroup 1 is not required to be performed again if group B has already been satisfied in accordance with 4.4.2).

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500, and table I herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the tests and conditions specified for subgroup testing in table E-VIa (JANS) of MIL-PRF-19500 and 4.4.2.1 herein. See 4.4.2.2 herein for JAN, JANTX, and JANTXV group B testing. Delta measurements shall be in accordance with table III herein.

4.4.2.1 Quality level JANS.

Subgroup	Method	Conditions
B4	1037	V_{CB} = 5 - 15 V dc, 2,000 cycles, t_{ON} = t_{OFF} = 3 minutes, $P_{D(ON)}$ = P_D max rated in accordance with 1.3; $P_{D(OFF)}$ = 0.
B5	1027	V_{CB} = 5 - 15 V dc; 1,000 hours maximum rated power shall be applied and ambient temperature adjusted to achieve T_J = +150°C minimum. n = 45, c = 0.

4.4.2.2 Quality level JAN, JANTX, and JANTXV. Separate samples may be used for each step. In the event of a group B failure, the manufacturer may pull a new sample at double size from either the failed assembly lot or from another assembly lot from the same wafer lot. If the new “assembly lot” option is exercised, the failed assembly lot shall be scrapped.

Step	Method	Conditions
1	1026	1,000 hours at VCB = 5 - 15 V dc; power shall be applied and ambient temperature, T_A, adjusted to achieve T_J = +150°C minimum and a minimum of PD = 100 percent of maximum rated PT as defined in 1.3 n = 45, c = 0. The sample size may be increased and the test time decreased as long as the devices are stressed for a total of 45,000 device hours minimum, and the actual time of test is at least 340 hours.
2	1048	Blocking life: T_A = +150°C, V_{CB} = 80 percent of rated voltage, 48 hours minimum. n = 45 devices, c = 0.
3	1032	High temperature life (non-operating), t = 340 hours; T_A = +200°C. n = 22, c = 0.

4.4.2.3 Group B sample selection. Samples selected from group B inspection shall meet all of the following requirements:

a. For JAN, JANTX, and JANTXV samples shall be selected randomly from a minimum of three wafers (or from each wafer in the lot) from each wafer lot. For JANS, samples shall be selected from each inspection lot. See MIL-PRF-19500.

b. Shall be chosen from an inspection lot that has been submitted to and passed group A conformance inspection. When the final lead finish is solder or any plating prone to oxidation at high temperature, the samples for life test (subgroups B4 and B5 for JANS, and group B for JAN, JANTX, and JANTXV) may be pulled prior to the application of final lead finish.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the tests and conditions specified for subgroup testing in table E-VII of MIL-PRF-19500, and in 4.4.3.1 herein (JANS). See 4.4.3.2 herein for JAN, JANTX, and JANTXV group C testing. Delta measurements shall be in accordance with table III herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

4.4.3.1 Quality level JANS table E-VII of MIL-PRF-19500.

Subgroup	Method	Condition
C2	2036	Test condition E; not applicable for UB devices.
C5	3131	$R_{\theta JA}$ and $R_{\theta JC}$ only, as applicable (see 1.3).
C6	1026	1,000 hours at VCB = 5 - 15 V dc; power shall be applied and ambient temperature T_A, adjusted to achieve TJ = +150°C minimum and a minimum of PD = 100 percent of maximum rated PT as defined in 1.3 n = 45, c = 0. The sample size may be increased and the test time decreased as long as the devices are stressed for a total of 45,000 device hours minimum, and the actual time of test is at least 340 hours.

4.4.3.2 Quality level JAN, JANTX, and JANTXV, table E-VII of MIL-PRF-19500.

Subgroup	Method	Condition
C2	2036	Test condition E; not applicable for UB devices.
C5	3131	$R_{\theta JA}$ and $R_{\theta JC}$ only, as applicable (see 1.3).
C6		Not applicable.

4.4.3.3 Group C sample selection. Samples for subgroups in group C shall be chosen at random from any inspection lot containing the intended package type and lead finish procured to the same specification which is submitted to and passes group A tests for conformance inspection. When the final lead finish is solder or any plating prone to oxidation at high temperature, the samples for C6 life test may be pulled prior to the application of final lead finish. Testing of a subgroup using a single device type enclosed in the intended package type shall be considered as complying with the requirements for that subgroup.

4.4.4 Group D inspection. Conformance inspection for hardness assured JANS and JANTXV types shall include the group D tests specified in table II herein. These tests shall be performed as required in accordance with MIL-PRF-19500 and method 1019 of MIL-STD-750, for total ionizing dose or method 1017 of MIL-STD-750 for neutron fluence as applicable (see 6.2 herein), except group D, subgroup 2 may be performed separate from other subgroups.

4.4.5 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-IX of MIL-PRF-19500 and as specified in table IV herein.

4.5 Method of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

4.5.2 Noise figure. The noise figure shall be measured using commercially available test equipment and its associated standard test procedures (see figure 9 and figure 10).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits	Limits	Unit
	Method	Conditions		Min	Max	
Subgroup 1 2/						
Visual and mechanical examination	2071					
Solderability 3/ 4/	2026	n = 15 leads, c = 0				
Salt atmosphere 4/	1041	(Laser marked devices only) n = 6 devices, c = 0.				
Resistance to solvents 3/ 4/ 5/	1022	n = 15 devices, c = 0				
Temp cycling 3/ 4/	1051	Test condition C, 25 cycles. n = 22 devices, c = 0				
Hermetic seal 4/ 6/ Fine leak Gross leak	1071	n = 22 devices, c = 0				
Electrical measurements 4/		Table I, subgroup 2				
Bond strength 3/ 4/	2037	Precondition T_A = +250°C at t = 24 hrs or T_A = +300°C at t = 2 hrs n = 11 wires, c = 0				
De-cap internal visual	2075	n = 4, c = 0				
Subgroup 2						
Thermal impedance 7/	3131	See 4.3.1.3.	$Z_{\theta JX}$			mV
Breakdown voltage, collector to emitter	3011	Bias condition D; I_C = 3 mA dc	$V_{(BR)CEO}$	15		V dc
Collector to base cutoff current	3036	Bias condition D; V_{CB} = 15 V dc	I_{CBO1}		10	nA dc
Collector to base cutoff current	3036	Bias condition D; V_{CB} = 30 V dc	I_{CBO3}		1	µA dc
Emitter to base cutoff current	3061	Bias condition D; V_{EB} = 3 V dc	I_{EBO1}		10	µA dc

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits	Limits	Unit
	Method	Conditions		Min	Max	
Subgroup 2 - Continued.						
Forward-current transfer ratio	3076	V_{CE} = 1 V dc; I_C = 3 mA dc	h_{FE1}	30	150	
Collector-emitter saturation voltage	3071	I_C = 10 mA dc; I_B = 1 mA dc;	$V_{CE(sat)}$		0.4	V dc
Base-emitter saturation voltage	3066	Test condition A; I_C = 10 mA dc; I_B = 1 mA dc	$V_{BE(sat)}$		1.0	V dc
Collector to emitter cutoff current	3041	Bias condition C; V_{CE} = 16 V dc	I_{CES}		100	nA dc
Subgroup 3						
High temperature operation		T_A = +150°C				
Collector to base cutoff current	3036	Bias condition D; V_{CB} = 15 V dc	I_{CBO2}		1.0	µA dc
Low temperature operation		T_A = -55°C				
Forward-current transfer ratio	3076	V_{CE} = 1 V dc; I_C = 3 mA dc	h_{FE2}	10		
Subgroup 4						
Noise figure	3246	V_{CE} = 6 V dc; I_C = 1.5 mA dc; f = 450 MHz; R_g = 50 Ω (case lead grounded) (see 4.5.2 and figure 9)	F		4.5	dB
Magnitude of common-emitter small-signal short-circuit forward-current transfer ratio	3306	V_{CE} = 6 V dc; I_C = 5 mA dc; f = 100 MHz (case lead grounded)	$\|h_{fe}\|$	10	21	

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits	Limits	Unit
	Method	Conditions		Min	Max	
Subgroup 4 - Continued.						
Small-signal short-circuit forward current transfer ratio	3206	V_{CE} = 6 V dc; I_C = 2 mA dc; (case lead floating)	h_{fe}	50	220	
Collector to base -feedback capacitance		V_{CB} = 10 V dc; I_E = 0 mA dc; 100 kHz ≤ f ≤ 1 MHz (see 4.5.1)	C_{cb}		1.0	pF
* Small-signal power gain	3256	V_{CE} = 6 V dc; Ic = 1.5 mA dc; f = 450 MHz	G_{pe}	12.5	21	dB
Collector-base time constant		V_{CB} = 6 V dc; I_E = 2 mA dc; f = 31.9 MHz (see figure 10)	$r_b' C_c$	4	15	ps
Subgroups 5, 6, and 7						
Not applicable						

1/ For sampling plan (unless otherwise specified), see MIL-PRF-19500.
2/ For resubmission of failed subgroup A1, double the sample size of the failed test or sequence of tests. A failure in group A, subgroup 1 shall not require retest of the entire subgroup. Only the failed test shall be rerun upon submission.
3/ Separate samples may be used.
4/ Not required for JANS devices.
5/ Not required for laser marked devices.
6/ This hermetic seal test is an end-point to temp-cycling in addition to electrical measurements.
* 7/ For end-point measurements, this test is required for the following subgroups:
Group B, step 1 of 4.4.2.2 herein (JAN, JANTX, and JANTXV).
Group B, subgroups 3, 4, and 5 (JANS).
Group C, subgroup 2 and 6.
Group E, subgroup 1 and 2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection.

Inspection 1/ 2/ 3/	MIL-STD-750		Symbol	Limit	Limit	Unit
	Method	Conditions		Min	Max	
Subgroup 1 4/						
Neutron irradiation	1017	Neutron exposure V_{CES} = 0 V				
Breakdown voltage, collector to emitter	3011	Bias condition D; I_C = 3 mA dc	$V_{(BR)CEO}$	15		V dc
Collector to base cutoff current	3036	Bias condition D; V_{CB} = 15 V dc	I_{CBO1}		20	nA dc
Collector to base cutoff current	3036	Bias condition D; V_{CB} = 30 V dc	I_{CBO3}		2	µA dc
Emitter to base cutoff current	3061	Bias condition D; V_{EB} = 3 V dc	I_{EBO1}		20	µA dc
Forward-current transfer ratio	3076	V_{CE} = 1 V dc; I_C = 3 mA dc	[h_{FE1}]	[15]	150	
Collector-emitter saturation voltage	3071	I_C = 10 mA dc; I_B = 1 mA dc;	$V_{CE(sat)}$		0.46	V dc
Base-emitter saturation voltage	3066	Test condition A; I_C = 10 mA dc; I_B = 1 mA dc	$V_{BE(sat)}$		1.15	V dc
Collector to emitter cutoff current	3041	Bias condition C; V_{CE} = 16 V dc	I_{CES}		200	nA dc
Subgroup 2						
Total dose irradiation	1019	Gamma exposure V_{CES} = 12 V Condition A				
Breakdown voltage, collector to emitter	3011	Bias condition D; I_C = 3 mA dc	$V_{(BR)CEO}$	15		V dc
Collector to base cutoff current	3036	Bias condition D; V_{CB} = 15 V dc	I_{CBO1}		20	nA dc
Collector to base cutoff current	3036	Bias condition D; V_{CB} = 30 V dc	I_{CBO3}		2	µA dc

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection - Continued.

Inspection 1/ 2/ 3/	MIL-STD-750		Symbol	Limit	Limit	Unit
	Method	Conditions		Min	Max	
Subgroup 2 - Continued.						
Emitter to base cutoff current	3061	Bias condition D V_{EB} = 3 V dc	I_{EBO1}		20	µA dc
Forward-current transfer ratio	3076	V_{CE} = 1 V dc; I_C = 3 mA dc	[h_{FE1}]	[15]	150	
Collector-emitter saturation voltage	3071	I_C = 10 mA dc; I_B = 1 mA dc;	$V_{CE(sat)}$		0.46	V dc
Base-emitter saturation voltage	3066	Test condition A; I_C = 10 mA dc; I_B = 1 mA dc	$V_{BE(sat)}$		1.15	V dc
Collector to emitter cutoff current	3041	Bias condition C; V_{CE} = 16 V dc	I_{CES}		200	nA dc

1/ Tests to be performed on all devices receiving radiation exposure.
2/ For sampling plan, see MIL-PRF-19500.
3/ Electrical characteristics apply to the corresponding AL, UA, UB, and UBC suffix versions unless otherwise noted.
4/ See 6.2.f herein.
5/ See method 1019 of MIL-STD-750 for how to determine [h_{FE}] by first calculating the delta (1/h_{FE}) from the pre- and post-radiation h_{FE}. The [h_{FE}] is not the same as h_{FE} and cannot be measured directly. The [h_{FE}] value can never exceed the pre-radiation minimum h_{FE} that it is based upon.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

TABLE III. Groups B, C, and E delta measurements. 1/ 2/ 3/ 4/

Step	Inspection	MIL-STD-750		Method	Conditions		Units
					Min	Max	
1.	Collector-base cutoff current	3036	Bias condition D; V_{CB} = 15 V dc	ΔI_{CB01}	100 percent of initial value or 5 nA dc, whichever is greater.		
2.	Forward current transfer ratio	3076	V_{CE} = 1.0 V dc; I_C = 3 mA dc	Δh_{FE1}	±25 percent change from initial value.		
3.	Collector to emitter voltage (saturated)	3071	I_C = 10 mA dc; I_B = 1.0 mA dc	$\Delta V_{CE(sat)}$ 5/	±50 mV dc change from initial value.		


1/ The delta measurements for table E-VIa (JANS) of MIL-PRF-19500 are as follows:
* a. Subgroup 3, see table III herein, step 1.
* b. Subgroups 4 and 5, see table III herein, step 3.
2/ The delta measurements for group B, 4.4.2.2 herein (JAN, JANTX, and JANTXV) are as follows:
* Steps 1, 2, and 3 of 4.4.2.2, see table III herein, all steps.
3/ The delta measurements for table E-VII (JANS) of MIL-PRF-19500 are as follows:
* a. Subgroup 2 and 3, see table III herein, step 1.
* b. Subgroup 6, see table III herein, all steps.
* 4/ The delta measurements for table E-IX of MIL-PRF-19500 are: Subgroups 1 and 2, see table III herein, all steps.
5/ Devices which exceed the group A limits for this test shall not be acceptable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

TABLE IV. Group E inspection (all quality levels) - for qualification or requalification only.

Inspection	MIL-STD-750		Qualification
	Method	Conditions	
Subgroup 1			45 devices c = 0
Temperature cycling (air to air)	1051	Test condition C, 500 cycles.	
Hermetic seal Fine leak Gross leak	1071		
Electrical measurements		See table I, subgroup 2 and table III herein.	
Subgroup 2			45 devices c = 0
Intermittent life	1037	Intermittent operation life: V_{CB} = 10 V dc; 6,000 cycles; $t_{ON} = t_{OFF}$ = 3 minutes, $P_{D(ON)} = P_D$ max rated in accordance with 1.3; $P_{D(OFF)} = 0$.	
Electrical measurements		See table I, subgroup 2 and table III herein.	
Subgroup 4			
Thermal impedance curves		See table E-IX of MIL-PRF-19500, group E, subgroup 4. $R_{\theta JSP}$ for UB devices only, Sample size = 15, c = 0, can be calculated but shall be measured once in the same package with a similar die size to confirm calculations (may apply to multiple specification sheets).	
Subgroup 5			
Not applicable			
Subgroup 6			11 devices
ESD	1020		
Subgroup 8			45 devices c = 0
Reverse stability	1033	Condition B.	

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.




NOTES:

1. This is the true inverse of the worst case thermal resistance value. All devices are capable of operating at ≤ T_J specified on this curve. Any parallel line to this curve will intersect the appropriate power for the desired maximum T_J allowed.
2. Derate design curve constrained by the maximum junction temperatures and power rating specified. (See 1.3 herein.)
3. Derate design curve chosen at T_J ≤ +150°C, where the maximum temperature of electrical test is performed.
4. Derate design curve chosen at T_J ≤ +125°C, and +110°C to show power rating where most users want to limit T_J in their application.

FIGURE 4. Temperature-power derating for 2N2857 (TO-72).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.



NOTES:

1. This is the true inverse of the worst case thermal resistance value. All devices are capable of operating at ≤ T_J specified on this curve. Any parallel line to this curve will intersect the appropriate power for the desired maximum T_J allowed.
2. Derate design curve constrained by the maximum junction temperatures and power rating specified. (See 1.3 herein.)
3. Derate design curve chosen at T_J ≤ +150°C, where the maximum temperature of electrical test is performed.
4. Derate design curve chosen at T_J ≤ +125°C, and +110°C to show power rating where most users want to limit T_J in their application.

* FIGURE 5. Temperature-power derating for 2N2857 (UB).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.




FIGURE 6. Thermal impedance graph ($R_{\theta SP}$) for 2N2857UB.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.




FIGURE 7. Thermal impedance graph TO-72 ($R_{\theta JA}$) for 2N2857.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.




FIGURE 8. Thermal impedance graph TO-72 ($R_{\theta JC}$) for 2N2857.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.





FIGURE 9. Block diagram for noise figure test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.



Procedure:

1. With a short circuit applied between the collector and emitter terminals adjust 31.9 MHz input for 0.5 V RMS at emitter terminal of transistor.
2. After removing the short circuit between the collector and emitter circuit, insert unit to be tested and adjust V_{CC} and V_{EE} for V_{CB} = 6 V dc, I_E = 2 mA dc.
3. Read $r_b'C_C$ on RF voltmeter scale ($r_b'C_C$ in picoseconds = 10 times meter indication in millivolts) (1 millivolt = 10 picoseconds).
4. External interlead shield to isolate the collector lead from the emitter and base lead.

* FIGURE 10. Collector-base time constant test circuit (an equivalent circuit may be used).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.1).

d. The complete PIN, see 1.5 and 6.5.

e. For die acquisition, the JANHC or JANKC letter version shall be specified (see figure 3).

f. For acquisition of RHA designated devices, table II, subgroup 1 testing of group D herein is optional. If subgroup 1 is desired, it should be specified in the contract.

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML-19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land and Maritime, ATTN: VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.dla.mil.


6.4 Suppliers of JANHC and JANKC die. The qualified JANHC and JANKC suppliers with the applicable letter version (example JANHCA2N2857) will be identified on the QML.

	Die ordering information
PIN	Manufacturer
	34156
2N2857	JANHCA2N2857, JANKCA2N2857


Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

6.5 PIN construction example.

6.5.1 Encapsulated devices. The PINs for encapsulated devices are constructed using the following form.



6.5.2 Un-encapsulated devices. The PINs for un-encapsulated devices are constructed using the following form.



* 6.6 List of PINs. The following is a list of possible PINs available on this specification sheet.

PINs for types 2N2857, 2N2857UB		
JAN2N2857	JANTXVR2N2857	JANS#2N2857
JAN2N2857UB	JANTXVR2N2857UB	JANS#2N2857UB
JANTX2N2857	JANTXVF2N2857	JANHCA#2N2857
JANTX2N2857UB	JANTXVF2N2857UB	JANKCA#2N2857

(1) The number sign (#) represent one of eight RHA designators available (M, D, P, L, R, F, G, or H).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.

6.7 Amendment notations. The margins of this specification are marked with asterisks to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the previous issue.

Custodians:
Army - CR
* Navy - SH
Air Force - 85
NASA - NA
DLA - CC

Review activities:
Army - MI, SM
Navy - AS, MC
* Air Force - 19, 71

Preparing activity:
DLA - CC

(Project 5961-2022-044)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:30Z
Check the source to verify that this is the current version before use.