NNN-D-00370(DSA-DM)
13 April 1965

INTERIM FEDERAL SPECIFICATION

DISK FILTER, MEMBRANE, BACTERIOLOGICAL/PARTICULATE

This interim Federal specification was developed by the Defense Medical Supply Center, Third Avenue and 29th Street, Brooklyn, New York 11232, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers microporous membrane filters.

1.2 Classification. Filters shall be of the following types, styles, classes, grades, colors, and sizes as specified (see 6.1):

Types:
- Type I. - Unreinforced.
- Type II.- Reinforced.

Styles:
- Style A. - Plain.
- Style B. - Grid marked.

Classes (Represent nominal pore diameters):
- Class 1. - 8.0 microns.
- Class 2. - 5.0 microns.
- Class 3. - 3.0 microns.
- Class 4. - 1.2 microns.
- Class 5. - 0.8 micron.
- Class 6. - 0.65 micron.
- Class 7. - 0.45 micron.
- Class 8. - 0.30 micron.
- Class 9. - 0.22 micron.
- Class 10. - 0.10 micron.
- Class 11. - 0.05 micron.
- Class 12. - 0.01 micron.

FSC 6640

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

Grades:
Grade A. - Sterile pack.
Grade B. - Autoclavable pack.
Grade C. - Ordinary pack.
Grade D. - Ordinary pack with thick pads.

Colors:
White.
Black.

Sizes:
Size 013.
Size 025.
Size 029
Size 037.
Size 142.
Size 293.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards. The following specifications and standards, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-B-676	Boxes, Set-Up, Paperboard.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D. C., 20402.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-L-10547 Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.

Military Standards:

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials:

ASTM Designation E128-61 Standard Method of Test for Maximum Pore Diameter and Permeability of Rigid Porous Filters for Laboratory Use.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia 3, Pa.)

3. REQUIREMENTS

3.1 Material. Material shall be suitable for the purpose intended and as hereinafter specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

3.2 Construction. Filters shall be constructed in accordance with the requirements of table I, when examined and tested as specified in section 4.

3.2.1 Type I. Type I filters shall be fabricated of cellulose ester polymer.

3.2.2 Type II. Type II filters shall be fabricated of cellulose ester polymer and shall be reinforced by monofilament nylon cloth.

Table I. Design Characteristics

Type	Class	Nominal pore size in microns	Thickness * in microns	Porosity** percent	Refractive*** index	Extractables**** maximum percent	Bubble Point p.s.i.
I	1	8.0	130	74	1.51	6.0	4 ± 1
I	2	5.0	130	84	1.51	6.0	7 ± 1
I	3	3.0	150	83	1.51	6.0	11 ± 1
II	3	3.0	150	45	not applicable	6.0	12 ± 1
I	4	1.2	150	82	1.51	5.0	12 ± 1
I	5	0.8	150	82	1.51	4.0	16 ± 2
I	6	0.65	150	81	1.51	3.0	21 ± 2
I	7	0.45	150	79	1.51	2.5	32 ± 2
II	7	0.45	150	43	not applicable	2.0	40 ± 5
I	8	0.30	150	77	1.51	2.0	40 ± 5
I	9	0.22	135	75	1.51	2.0	55 ± 5
I	10	0.10	130	74	1.50	1.5	100 ± 10
I	11	0.05	130	72	1.50	1.5	150 ± 10
I	12	0.01	130	70	1.50	1.5	200 ± 10

* Tolerance for thickness shall be ± 10 microns.
** Tolerance for porosity shall be ± 2 percent.
*** Tolerance for refractive index shall be ± 0.01. Refractive index shall not apply to black disks.
****Extractables shall not apply to black filters.

3.2.3 Grid marking. A grid of squares shall be imprinted on the surface of each style B filter. Each side of each square shall be 3.0 ± 0.8 mm. long (0.096 square centimeters (cm.) nominal area). The length of a side shall be the distance between the centers of the two intersecting sides at the points of intersection. Grids shall extend throughout the surface and grid marking shall be legible and permanent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

3.3 Pads. Cellulose pads shall be furnished with Grade A, Grade B and Grade D filters.

3.3.1 Grade A and Grade B. Grade A and grade B filter pads shall be of the same diameters (nominal) as the filters and shall be 1/32 inch (nominal) thick.

3.3.1.1 Absorptivity. Grade A and grade B filter pads shall absorb 1.5 ± 0.2 milliliters (ml.) when tested as specified in 4.4.5.

3.3.2 Grade D. Grade D filter pads shall be 34 mm. (nominal) in diameter and shall be 1/16 inch (nominal) thick.

3.4 Performance. Filters shall meet the requirements of table II, when tested as specified in section 4.

3.4.1 Diffusibility. Water shall diffuse uniformly through the filter in 15 seconds and there shall be no dry spots when tested as specified in 4.4.9.

3.4.1.2 Black filters. Black filters shall be black when wet and black, purple or blue when dry.

Table II. Performance Characteristics

Type	Class	Water Flow Rate*	Air Flow Rate**	Autoclavable***	Organism retained
I	1	850 ± 225		Yes	
I	2	540 ± 85		Yes	
I	3	400 ± 50		Yes	
II	3	155 ± 30		No	
I	4	300 ± 40		Yes	Saccharomyces cerevisiae
I	5	212 ± 28		Yes	
I	6	150 ± 14		Yes	Bacillus subtilus var globigie
I	7	64 ± 9		Yes	Serratia marcescens
II	7	55 ± 14		No	
I	8	40 ± 10		Yes	
I	9	21 ± 3		Yes	Vibrio percolans
I	10		0.49 ± 0.12	Yes	
I	11		0.31 ± 0.05	Yes	
I	12		0.22 ± 0.04	Yes	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

* Water flow rates in ml/min/square centimeter.
** Air flow rates in liters/min/square centimeter.
*** Autoclavability shall not apply to black filters.

3.4.2 Toxicity. Type I filters and grades A and B filter pads shall not inhibit bacterial growth when tested as specified in 4.4.10.

3.4.3 Autoclavability. Type I, white filters shall not deteriorate, buckle or deform and shall have the diameters specified in table III when tested as specified in 4.4.11.

Table III. Diameters in millimeters After Autoclaving

Filter Size	013	025	029	037	047	142	293
Class 1	12.5 ± 0.5	24.5 ± 1.0	28.5 ± 1.0	36.0 ± 1.0	46.0 ± 1.0	138.0 ± 3.0	287.0 ± 5.0
Class 2	12.5 ± 0.5	24.5 ± 1.0	28.5 ± 1.0	36.0 ± 1.0	46.0 ± 1.0	138.0 ± 3.0	287.0 ± 5.0
Class 3	12.5 ± 0.5	24.5 ± 1.0	28.5 ± 1.0	36.0 ± 1.0	46.0 ± 1.0	138.0 ± 3.0	287.0 ± 5.0
Class 4	12.5 ± 0.5	24.5 ± 0.5	28.5 ± 1.0	36.5 ± 0.5	46.5 ± 0.5	139.0 ± 2.0	288.0 ± 4.0
Class 5	12.5 ± 0.5	24.5 ± 0.5	28.5 ± 1.0	36.5 ± 0.5	46.5 ± 0.5	139.0 ± 2.0	288.0 ± 4.0
Class 6	12.5 ± 0.5	24.5 ± 0.5	28.5 ± 1.0	36.5 ± 0.5	46.5 ± 0.5	139.0 ± 2.0	288.0 ± 4.0
Class 7	12.5 ± 0.5	24.5 ± 0.5	28.5 ± 1.0	36.5 ± 0.5	46.5 ± 0.5	139.0 ± 2.0	288.0 ± 4.0
Class 8	12.5 ± 0.5	24.5 ± 1.0	28.5 ± 1.0	36.0 ± 1.0	46.0 ± 1.0	138.0 ± 3.0	287.0 ± 5.0
Class 9	12.5 ± 0.5	25.0 ± 0.5	28.5 ± 1.0	36.5 ± 0.5	46.5 ± 0.5	139.0 ± 2.0	288.0 ± 4.0
Class 10	12.5 ± 0.5	24.5 ± 1.0	28.5 ± 1.0	36.0 ± 1.0	46.0 ± 1.0	138.0 ± 3.0	287.0 ± 5.0
Class 11	12.5 ± 0.5	24.5 ± 1.0	28.5 ± 1.0	36.0 ± 1.0	46.0 ± 1.0	138.0 - 3.0	287.0 ± 5.0
Class 12	12.5 ± 0.5	24.5 ± 1.0	28.5 ± 1.0	36.0 ± 1.0	46.0 ± 1.0	138.0 ± 3.0	287.0 ± 5.0

Measurements shall be made at 25° Centigrade (C.) and 40 percent relative humidity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

3.4.4 Resistance to ethylene oxide. Type I filters shall not deteriorate, buckle, or deform when tested as specified in 4.4.12.

3.5 Intermediate unit pack. Grade A and grade B filters shall be wrapped (10 filters and 10 pads) to form an intermediate unit pack. Ten such intermediate unit packs shall constitute one unit of issue.

3.5.1 Grade A. Grade A filters and pads shall be sterile, when tested as specified in 4.4.13.

3.5.2 Grade B. Grade B intermediate unit pack shall have an indicator which shows when sterilization is complete. Each unit of issue and intermediate unit pack shall have instructions for interpreting the indicator. Intermediate unit pack, filters, pads, and wrapping paper shall not deteriorate, buckle, or deform, and indicator shall perform as shown on instructions when tested as specified in 4.4.11.

3.6 Diameters. Diameters of filters shall be as follows when measured at 25° C. and a relative humidity of 40 percent:

Size	Diameter
013	13 ± 0.2 mm.
025	25.4 ± 0.2 mm.
029	29.0 ± 0.5 mm.
037	37 ± 0.2 mm.
047	47 ± 0.2 mm.
142	141.2 ± 1.0 mm.
293	292.1 ± 2.0 mm.

3.7 Workmanship. Workmanship shall be first class throughout. The filters shall be free from defects which detract from their appearance or may impair their serviceability.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual, auditory, etc., investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.2 Certificates of quality. When available, certificates of quality, supplied by the manufacturer of the component or material, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105.

	Unit of Product	Inspection level	AQL (percent defective) *
For visual examination			
Major A defects	Intermediate unit pack	S-1	2.5
Major B defects	Filter	S-1	2.5
Major C defects	Pad	S-1	2.5
For dimensional examination		S-1	2.5

* If the acceptance number for any category is exceeded, the lot may be reexamined for approval in that category at the same A.Q.L. using inspection level II.

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

Component (unit of product)	Characteristic	Requirement	Test procedure	Inspection level	AQL
Filter	Porocity	3.2	4.4.1	S-1	*
Filter	Refractive index	3.2	4.4.2	S-1	*
Filter	Extractables	3.2	4.4.3	S-1	*
Filter	Maximum pore.	3.2	4.4.4	S-1	*
Pad	Absorptivity	3.3.1.1	4.4.5	S-1	*
Filter	Flow rate (water)	3.4	4.4.6	S-1	*
Filter	Flow rate (air)	3.4	4.4.7	S-1	*
Filter	Organism retention.	3.4	4.4.8	S-1	*
Filter	Diffusibility	3.4.1	4.4.9	S-1	*
Filter	Toxicity	3.4.2	4.4.10	S-1	*
Pad	Toxicity	3.4.2	4.4.10	S-1	*
Filter	Autoclavability	3.4.3	4.4.11	S-1	*
Filter	Resistance to ethylene oxide	3.4.4	4.4.12	S-1	*
Filter	Sterility	3.5.1	4.4.13	S-1	*
Intermediate unit pack	Autoclavability	3.5.2	4.4.11	S-1	*

* Acceptance number shall be zero.

4.3 Examination. The pack and components shall be examined to determine compliance with all requirements contained in this specification.

4.3.1 Classification of defects. Examination shall be conducted in accordance with the following classification of defects:

Categories and defects*

Major A

101	Component missing.
102	Indicator missing.
103	Instructions for indicator not complete, correct, or legible.
104	Pack not free of tears.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

Major B.
111. Filter not free of tears.
112. Filter not free of wrinkles.
113. Grid markings not complete, correct, legible, or permanent.

Major C.
121. Pad not free of tears.
122. Pad not free of wrinkles.

*Examination shall not be restricted to the classified possible defects listed above.

4.3.2 Dimensional examination. The filters and pads shall be examined for defects in dimensions. Any dimension not within the tolerance specified herein shall be classified as a defect.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Porosity. Porosity shall be determined by one of the following methods:

(a) Calculate the theoretical weight of a solid filter by multiplying the volume by the density of the cellulose ester polymer and determine the actual weight of the filter.

$$\frac{\text{Theoretical weight of a solid filter} - \text{Actual weight of filter}}{\text{Theoretical weight of a solid filter}} \times 100 = \text{percent porosity}$$

(b) Calculate the volume of the sample filter. Introduce mercury into the pores of the filter.

$$\frac{\text{Volume of mercury introduced}}{\text{Theoretical volume of filter}} \times 100 = \text{percent porosity}$$

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:48Z
Check the source to verify that this is the current version before use.

4.4.2 Refractive index. The following test shall be performed:

Cut a 1 mm. by 5 mm. strip from a filter. Dimensions shall be approximate and cutting shall be done with a sharp instrument so that that smooth edges are obtained. Place strip on a glass slide. Add a drop of oil to the strip and cover strip with a cover glass. Place the prepared slide on the stage of a microscope (magnification 100 times) and position so that the microscope is focused on an edge of the strip (interface of the oil and strip). If the refractive indices of the oil and strip are different, a line called a Becke line will appear at the interface. Move the objective lens up or down so that the Becke line is moving from the strip to the oil. Upward movement of the lens indicates that the refractive index of the oil is greater than that of the strip. Downward movement of the lens indicates that the refractive index of the strip is greater that that of the oil. If the strip and Becke line cannot be brought into focus, the refractive index of the strip and the oil are the same. All oils used shall be within the tolerances of table I and each filter shall be tested with at least two oils, one of greater and one of lesser refractive index than the filter (see 6.2).

4.4.3 Extractables. The following test shall be performed. Weigh filter after it has been dried for 15 minutes at 70° C. and allowed to reach room temperature in a desiccator. Place filter in a minimum of 100 ml. of boiling distilled water for at least 20 minutes. Remove the filter from the water and dry it at 70° C. for 60 minutes. Allow filter to reach room temperature in a desiccator and reweigh. Weighings shall be to the nearest 0.1 milligram.

$$\frac{\text{Original weight} - \text{Weight after extraction}}{\text{Original weight}} = \text{percent extractables.}$$

4.4.4 Bubble point. Bubble point test shall be run in accordance with ASTM Designation E 128-61.

4.4.5 Absorptivity. The following test shall be performed. Place pad in a container which has a diameter slightly larger than that of the pad. Slowly add 1.7 ml. of endo broth (see 6.3) to the center of the pad and allow to stand for 10 minutes. If pad does not absorb all the endo broth, repeat the above procedure with another pad using 1.3 ml. of endo broth. If pad does absorb the entire 1.7 ml. of endo broth, repeat the above procedure with another pad using 1.8 ml. of endo broth.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:48Z
Check the source to verify that this is the current version before use.

4.4.6 Water flow rates. Water flow shall be determined at 25° C. at a pressure differential of 70 cm. of mercury.

4.4.7 Air flow rates. Air flow shall be determined at 25° C. at a pressure differential of 70 cm. of mercury.

4.4.8 Organism retention. The liquid from the following suspensions shall be drawn through the appropriate filters:

Class 4. 100 ml. of sterile saline which contains approximately 1.0×10^3 cells of a 24-hour culture of Saccharomyces cerevisiae per ml.

Class 6. 100 ml. of sterile saline which contains approximately 1.0×10^3 spores of Bacillus Subtilus var globigie per ml.

Classes 7 and 8. 100 ml. of sterile saline which contains 1.0×10^3 cells of a 24-hour culture of Serratia marcescens per ml.

Class 9. 100 ml. of sterile saline which contains 1.0×10^3 cells of an 18-hour culture of Vibrio percolans per ml.

All equipment shall be sterile. Using forceps, a filter shall be placed on the filter support base and the funnel unit shall be placed on the filter and secured by means of the appropriate attachment device. The solution containing the test organism for the appropriate class shall then be drawn through the test filter by applying vacuum to the sterile flask. The filter shall then be rinsed three times with 20 ml. of physiological saline solution. A sterile filter holder shall then be attached to another filtration flask and using aseptic technique, the filtrate from the test filter shall be passed through a reference filter. A reference filter shall be a filter of the same specification designation which has been furnished to the Government and has met the requirements of this specification or it shall be a filter of the same specification designation except for style and class. When the class of the reference filter is different than that of the filter being tested, the pore size of the reference filter shall be smaller than that of the test filter. After filtration, the test filter and reference filter shall be placed on the proper medium in a petri dish and incubated as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

Class	Medium	Temperature	Time
4	Tryptone Glucose Extract Agar	32° C.	48 hours
6	Tryptone Glucose Extract Agar	32° C.	24 hours
7 & 8	Wilson's Peptone Agar (see 6.4)	32° C.	24 hours
9	Tryptone Glucose Extract Agar	32° C.	24 hours

A zero count on the incubated reference filter shall indicate sterility of the filtrate.

4.4.9 Diffusibility. Filter shall be dropped flat on water and diffusion through the filter timed with a stopwatch. (Wet areas will become darker, while dry areas will not change in color intensity.)

4.4.10 Toxicity. The following dilutions of organisms shall be prepared:

Classes 4, 5 and 6. A sterile dilution of a 24-hour culture of Saccharomyces cerevisiae such that 0.1 ml. will contain between 50 and 100 cells.

Classes 1, 2, 3, 7, 8, 9, 10, 11, and 12. A sterile saline dilution of a 24-hour culture of Serratia marcescens such that 0.1 ml. will contain between 50 and 100 cells.

All equipment and filters shall be sterile.

For classes 4, 5, 6, 7, 8, and 9, a test filter shall be placed on the filter support base and funnel unit shall be placed on the filter and made secure by an appropriate attachment device. 20 ± 2 ml. of sterile saline shall be added to the funnel. 0.1 ml. of the appropriate dilution of organisms shall be pipetted into the saline in the funnel. With the same pipet, 0.1 ml. of the same dilution of organisms shall be delivered to each of four agar streak plates. The dilution shall be spread on each plate with a glass streaking rod so that the dilution is evenly distributed over the entire agar surface. The filter shall then be removed and placed on the appropriate medium. Medium for filter and streak plate shall be the same.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:48Z
Check the source to verify that this is the current version before use.

Class	Medium	Temperature	Time
4, 5, and 6	Tryptone Glucose Extract Agar	32° C.	48 hours.
7, 8, and 9	Wilson's Peptone Agar	32° C.	24 hours.

A filter shall be considered nontoxic if the filter grows at least 90 percent of the colonies obtained on the average of the culture streaks. The colonies of the filters of classes 4, 5, and 6 are at least 1.0 mm. in diameter, and the colonies of classes 7, 8, and 9 are at least 0.5 mm. in diameter.

For classes 1, 2, 3, 10, 11, and 12, add 0.5 ml. of the appropriate dilution of organisms to 100 ml. of Wilson's Peptone Agar at 45° C. Pour a thin layer (5 mm.) into a Petri dish (100 mm. diameter) and allow to solidify. Cut the test filter into four sections. Place sterile filter on agar surface and incubate at 32° C. for 24 hours. Filters shall be considered nontoxic if no zone of inhibition appears at the edges of the filter.

4.4.11 Autoclaving. Filters or intermediate unit pack shall be autoclaved for 10 minutes at 121° C.

4.4.12 Resistance to ethylene oxide. The following test shall be performed. Place the filter in 80 percent carbon dioxide and 20 percent ethylene oxide for 4 hours at a pressure of 18 pounds per square inch, a relative humidity of 35 percent, and a temperature of 120° Fahrenheit (F.).

4.4.13 Sterility. The following test shall be performed. Place a pad in a Petri dish, add 1.8 ml. of Tryptone Glucose Extract Broth, and place the filter on the pad. Incubate the Petri dish upside down for 24 hours at 35° C. No growth of bacteria shall indicate sterility.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. One hundred (100) filters, or ten (10) filters, as specified, constitute one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in table IV shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:48Z
Check the source to verify that this is the current version before use.

Table IV. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	12 units	144 units

5.1.2.1 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container, of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Unit package.

5.1.3.1.1 Grades A and B. Filters, packaged as specified in 3.5, shall be packaged in a carton of appropriate size, constructed in accordance with PPP-B-566 or PPP-B-676, except that commercial colors shall be acceptable. Closure of carton shall be adequate to prevent spillage of contents under normal handling. As an alternate, unit package may be a plastic box of appropriate size with a transparent cover. Closure of box shall be adequate to prevent spillage of contents under normal handling.

5.1.3.1.2 Grades C and D. Filters shall be packaged in a carton of appropriate size constructed in accordance with PPP-B-566 or PPP-B-676, except that commercial colors shall be acceptable. Closure of carton shall be adequate to prevent spillage of contents under normal handling. As an alternate, unit package may be a plastic box of appropriate size with a transparent cover. Closure of box shall be adequate to prevent spillage of contents under normal handling.

5.1.3.2 Intermediate package. Intermediate package shall be a carton of appropriate size constructed in accordance with PPP-B-566 or PPP-B-676, except that commercial colors shall be acceptable, or PPP-B-636. Closure shall be adequate to prevent spillage of contents under normal handling.

5.2 Packing.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for type 2 load and constructed in accordance with PPP-B-585, style 3, for class 3 use; PPP-B-601, table II, using type III; class 1 plywood; PPP-B-621, table IV; or PPP-B-636, type CF, class weather-resistant.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

5.2.1.2 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes.

5.2.1.3 Closure. Closure of wood boxes shall be in accordance with appendix of applicable box specification. Closure of each fiberboard box shall be as specified in the appendix of PPP-B-636. In addition, waterproofing shall be in accordance with 30.4.

5.2.1.4 Strapping. Strapping, when required, shall be in accordance with appendix of applicable box specification.

NOTE: Strapping shall not be required for shipments forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall conform to PPP-B-601, table I, using type III, class 1 plywood; or shall be designed for type 2 load, and constructed in accordance with PPP-B-585, style 3, for class 2 use; PPP-B-621, table I; or PPP-B-636, type CF, class domestic. Method I closure shall be utilized for fiberboard boxes.

5.3 Marking.

5.3.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Number and date of this specification.
(b) Type, style, class, grade, color, and size required (see 1.2).
(c) Selection of applicable level of packing (see 5.2).

6.2 Theory of the refractive index test is given in Handbook of Chemical Microscopy, Volume 1 (Chamot and Mason, Third Edition, John Wiley and Sons, New York).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

6.3 Endo broth indicated is Federal stock number 6505-687-8436.

6.4 Wilson's peptone may be obtained from Baltimore Biological Laboratory Inc., Baltimore, Maryland.

6.5 This specification does not include all types, classes, grades, sizes, etc., of the commodity indicated by the title of this specification, or which are commercially available, but is intended to cover the types, etc., which are normally procured to meet Federal Government requirements.

Military custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Review activities:
Army - MD
Navy - MS
Air Force - 03

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

FOLD UNDER

DEFENSE SUPPLY AGENCY
DEFENSE MEDICAL SUPPLY CENTER
3RD AVENUE AND 29TH STREET
BROOKLYN, N.Y., 11232

POSTAGE FEES PAID
DEFENSE SUPPLY AGENCY

OFFICIAL BUSINESS

DEFENSE SUPPLY AGENCY

DEFENSE MEDICAL SUPPLY CENTER

ATTN: DIRECTORATE OF TECHNICAL OPERATIONS (CODE TM5)

3RD AVENUE AND 29TH STREET

BROOKLYN, N.Y., 11232

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

Stc No. 114 0101 807 1.00

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

DISCIFICATION INTERIM FEDERAL SPECIFICATION dated,
FILTER, MEMBRANE, BACTERIOLOGICAL/PARTICULATE NNN-D-00370(DSA-DM) 13 April 1965.

ORGANIZATION *(Of submitter)*	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

FORM 1426

NAVSO P2502

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.