NNN-P-40B
March 13, 1973
SUPERSEDING
Fed. Spec. NNN-P-40A
April 5, 1968 and
MIL-P-13988A(MU)
2 July 1970

FEDERAL SPECIFICATION

PAPER, LENS

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers two types of lens paper used for cleaning and wrapping lenses and other glass or highly polished and coated surfaces.

1.2 Classification.

1.2.1 Types and classes. The lens paper covered by this specification shall be of the following types and classes as specified (see 6.2 and 6.4).

Type I - Cleaning Paper (see 6.3).
Class 1 - Lightweight.
Class 2 - Heavyweight.
Class 3 - Heavyweight, silicone treated.
Class 4 - Heavyweight, wet-strength.
Class 5 - Lightweight, wet-strength.

Type II - Wrapping or covering of coated optical surfaces.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

UU-P-268 - Paper, Kraft, Untreated, Wrapping.
PPP-B-566 - Boxes, Folding, Paperboard.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.

FSC 6640

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

PPP-B-636	-	Boxes, Shipping, Fiberboard.
PPP-B-676	-	Boxes, Setup.
PPP-T-42	-	Tape, Pressure-Sensitive Adhesive; (General Packaging Application).
PPP-T-45	-	Tape, Gummed, Paper, Reinforced and Plain, For Sealing and Securing.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers, at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-L-10547	-	Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof.

Military Standards:

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	-	Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

Technical Association of the Pulp and Paper Industry (TAPPI) Standards:

T 401 - Fiber Analysis of Paper and Paperboard.
T 402 - Standard Conditioning and Testing Atmospheres for Paper, Board, Pulp Handsheets and Related Products.
T 403 - Bursting Strength of Paper.
T 404 - Tensile Breaking Strength of Paper and Paperboard.
T 410 - Weight Per Unit Area (Basis Weight or Substance) of Paper and Paperboard.
T 412 - Moisture in Paper and Paperboard.
T 413 - Ash in Paper.
T 428 - Hot Water Extractable Acidity or Alkalinity of Paper.
T 432 - Water Absorbency of Bibulous Papers.
T 435 - Hydrogen Ion Concentration (pH) of Paper Extracts.
T 444 - Silver-Tarnishing Test of Paper.
T 456 - Wet Tensile Breaking Strength of Paper and Paperboard.
T 468 - Water-Soluble Sulfates and Chlorides in Paper and Paperboard.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, 1 Dunwoody Park, Atlanta, GA 30341.)

Uniform Classification Committee, Agent

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606.)

National Motor Freight Traffic Association, Inc., Agent

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, D.C. 20036.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:48Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Stock and formation.

3.1.1 Type I, cleaning paper.

3.1.1.1 Classes 1 and 4. Classes 1 and 4 paper shall be made from bleached chemical wood pulp, cotton or linen fibers or mixtures of these, and shall not be contaminated with any unbleached or mechanical wood pulp, when tested as specified in 4.3.2. The formation shall be uniform and open.

3.1.1.2 Class 2. Class 2 paper shall be made from 100 percent cotton or linen fibers. The formation shall be uniform and dense.

3.1.1.3 Class 3. Class 3 paper shall be made from 100 percent bleached chemical wood pulp. The formation shall be uniform and dense.

3.1.1.4 Class 5. Class 5 paper shall be made from 1.5 denier viscose rayon at least 0.25 inch long with cellulosic or cellulose derivative binding agents, and shall be free from wood fiber.

3.1.2 Type II, wrapping paper. Type II paper shall be made from either white or unbleached wood pulp, free of ground wood particles, when tested as specified in 4.3.2.

3.2 Physical and chemical properties. The lens papers shall conform to the applicable physical and chemical properties specified in table I when tested as specified in 4.3.2.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:48Z
Check the source to verify that this is the currentversion before use.

TABLE I. Physical and chemical properties

Characteristic	Classes	Type I					Type II
		1	2	3	4	5	
Basis weight, (24 x 36-500), pounds		5.5 ± 0.6	8.5 ± 0.6	11.8 ± 0.7	10.4 ± 0.6	7.0 ± 0.6	11.5 ± 0.7
Bursting strength, pounds/sq. in., minimum		30 1/	—	40 1/	—	—	50 1/
Tensile strength, dry (15 mm. width), grams, minimum							
	Machine direction	—	450	—	1800	700	—
	Cross direction	—	450	—	600	100	—
Tensile strength, wet (15 mm. width), grams, minimum							
	Machine direction	—	—	—	450	150	—
Acidity (pH value)							
	Minimum	5.0	5.0	5.0	4.5	4.5	6.0
	Maximum	7.5	7.5	7.5	7.5	7.5	7.0
Water absorption (0.01 ml)		60	—	—	60	—	—
Maximum (sec.)							
Water absorption (complete)		—	—	—	—	complete	—
(after 1 sec. immersion)		—	—	—	—	absorption	
Free acids or alkali		—	—	—	—	—	0.00
Chlorides and sulfates		—	—	—	—	—	0.00
Ash, percent, maximum		0.5	0.5	1.3 2/	0.5	0.5	—
Silicone content, percent, minimum		—	—	4.0	—	—	—
Tarnish		—	—	—	—	—	none

1/ Requirement is for 10 sheets tested together.

2/ After removal of silicone content.

MIL-P-40

Source: https://assist.dla.mil -- Downloaded: 2026/10-26T12:48Z
Check the source to verify that this is the current version before use.

3.3 Water absorbency (class 5 only). Type I, class 5 paper shall become thoroughly wet within 1 second when immersed in water at a temperature of 18° to 30°C. when tested as specified in 4.3.2.

3.4 Abrasiveness. Lens paper shall be nonabrasive when tested as specified in 4.3.2.

3.5 Tarnish resistance (type II). The tissue paper shall not cause tarnishing of silver surfaces when tested as specified in 4.3.2.

3.6 Sizes. Unless otherwise specified, type I lens paper shall be of the following sizes (see 6.2). Type II lens paper sizes shall be as specified (see 6.2).

3 by 5 inches.
3 by 7 inches.
4 by 6 inches.
4-1/4 by 5 inches.
5 by 5-3/4 inches.
5 by 6-3/4 inches.
7 by 11 inches.
7-1/2 by 11 inches.
20 by 30 inches.

3.6.1 Dimensional tolerances. The following tolerances shall be permitted on the specified sizes (see 3.6).

Dimension	Minus tolerance	Plus tolerance
Less than 6 inches	1/16 inch	1/4 inch
6 to 12 inches inclusive	1/8 inch	1/4 inch
Greater than 12 inches	1/4 inch	1/4 inch

3.7 Form. The lens paper shall be furnished in individual sheets or book form or envelopes, as specified (see 6.2). When furnished in book form, the sheets shall be securely fastened together along one edge and perforated in such a manner that they can be easily and cleanly torn from the book.

3.8 Color.

3.8.1 Type I, classes 1, 2, 4, and 5. Classes 1, 2, 4, and 5 papers shall be white. Class 3 paper shall be lavender.

3.8.2 Type II. Type II paper shall be white or of natural unbleached pulp.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

3.9 Workmanship. The lens paper shall be clean, non-fragile, and free from lint, dust, abrasive materials, tears, cuts, lumps, and stock that is not defibered. The edges shall be clean cut.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to that supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. The end item shall be examined for the defects in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQLs) set forth in 4.3.1.6. A lot shall consist of all material of the same type, class, form, color, and size offered for the inspection at one time from one source of supply. Random supplies shall be drawn from each lot of the end items for examination of visual, dimensional, count, and preparation for delivery defects. The lot size shall be expressed in units of packages, books, envelopes, or reams, as applicable, for examination in 4.3.1.1 through 4.3.1.4, and in units of shipping containers for examination in 4.3.1.5.

4.3.1.1 Examination for visual defects. The sample unit for this examination shall be one sheet. No more than one sheet shall be taken from any package, book, envelope, or ream. Both sides of the sample unit shall be examined.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:48Z
Check the source to verify that this is the currentversion before use.

Examine	Defect
Color (type I, class 1, 2, 4, 5)	Not white.
Color (type I, class 3 only)	Not lavender.
Color (type II)	Not white or of natural unbleached pulp.
Workmanship	Not clean. Presence of lint or dust. Any tears or cuts. Any lumps or hard particles. Not defibered stock. Edges not clean cut (a well formed saw-toothed edge shall be considered clean cut). Too fragile, falls apart in handling.

4.3.1.2 Examination for defects in book form construction. When applicable, the sample unit for this examination shall be one book of lens paper.

Examine	Defect
Construction of book	Sheets loose; not securely fastened. Sheet cannot be torn easily and cleanly from book.

4.3.1.3 Examination for defects in dimensions. The sample unit for this examination shall be one sheet.

Examine	Defect
Length and width	Varies from dimension specified by more than plus 1/4 inch or minus 1/16 inch when dimension is less than 6 inches. Varies from dimension specified by more than plus 1/4 inch or minus 1/8 inch when dimension is 6 to 12 inches. Varies from dimension specified by more than ± 1/4 inch when dimension is more than 12 inches.

4.3.1.4 Examination for count. The sample unit for this examination shall be one package, book, envelope, or ream, as applicable. The lot shall be unacceptable if the average count per sample unit for all sample units examined is less than the specified or indicated quantity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

4.3.1.5 Examination of preparation for delivery requirements. An examination shall be made to determine that the packaging, packing, and marking complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be closed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot.

Examine	Defect
Marking (exterior and interior)	Incorrect; illegible; omitted; of improper size, location, sequence, or method of application.
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components, such as incomplete closure of container flaps, improper taping, inadequate stapling or loose strapping. Bulged or distorted container.
Weight	Weight of contents exceeds requirements.

4.3.1.6 Inspection levels and acceptable quality levels (AQLs) for examination. The inspection levels for the purpose of determining the sample size and acceptable quality levels (AQLs), expressed in defects per one hundred units, shall be as follows:

Examination paragraph	Inspection level	AQL
4.3.1.1	I	2.5
4.3.1.2	S-2	4.0
4.3.1.3	S-2	4.0
4.3.1.4	S-2	N.A.
4.3.1.5	S-1	2.5

4.3.2 Testing of the end item. Before testing, the samples shall be conditioned in accordance with TAPPI T 402. The end item shall be tested for the applicable characteristics in table II. The methods of testing specified in TAPPI test methods, where applicable, and as listed in table II shall be as specified herein. When the end item is to be furnished in the form of sheets less than 7 by 11 inches in size, testing shall be performed on the sheets prior to the cutting and trimming operation. The sample unit shall be expressed in units of 100 square feet of paper of one type. The sample size shall be drawn in accordance with level S-1 of MIL-STD-105. Any failure to meet the sample unit, composite, or lot average requirements shall be cause for rejection of the lot. A composite shall consist of small portions drawn from all sample units and combined in a single sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS FOR TESTING

TABLE II

CHARACTERISTIC	Specification Reference		Requirements Applicable To		Number Determinations Per Unit	Results Reported As		Inspection Level	AQL
	Requirement	Test Method 4/	Individual Unit	Lot Acceptance		Pass or Fail	Numerically to Nearest		
Stock (all types and classes) 1/	3.1	T401	-	-	Average of 2 on composite	-	5 percent		
Atmospheric conditions	4.3.2	T402	All testing						
Basis weight (all types and classes)	3.2	T410	-	X	1	-	pound		
Bursting strength, type I, (classes 1 and 3) 2/	3.2	T403	-	X	Average of 2	-	pounds/ sq. in.		
Tensile strength, dry, (15 mm. width) type I, (classes 2, 4, and 5)									
Machine direction	3.2	T404	-	X	Average of 10	-	gram		
Cross direction	3.2	T404	-	X	Average of 10	-	gram		
Tensile strength, wet, (15 mm. width) 3/ type I, (classes 4 and 5)									
Machine direction	3.2	T456	-	X	Average of 10	-	gram		
Acidity (pH) (all classes)	3.2	T435	-	-	Average of 2 on composite	-	0.1 pH		
Free acids or alkali (type II)	3.2	T428	-	-	Average of 2 on composite	X			
Chlorides and sulfates (type II)	3.2	T468	-	-	Average of 2 on composite	X			
Ash (all types and classes)	3.2	T413	-	-	Average of 2 on composite	-	0.1 percent		
Silicone content, type I, (class 3)	3.2	4.4.1	-	-	Average of 2 on composite	-	0.1 percent		

AMSRE Form 598
8 February 1965

MIL-P-4085

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS FOR TESTING

TABLE II

CHARACTERISTIC	Specification Reference		Requirements Applicable To		Number Determinations Per Unit	Results Reported As		Inspect Level	AQL
	Requirement	Test Method	Individual Unit	Lot Acceptance		Pass or Fail	Numerically to Nearest		
Tarnish resistance (type II)	3.6	T444	-	X	Average of 5 on composite	X			
Water absorption, (0.01 ml) type I, (classes 1 and 4)	3.2	T432	-	X	Average of 10	-	second		
Water absorbency (type I, class 5)	3.2	4.4.3	X	-	1	X			
Abrasiveness (all types and classes)	3.4	4.4.2	X	-	1	X			

1/ The supplier shall furnish a certificate of compliance for this characteristic for type 1, class 5 product.

2/ Bursting strength shall be determined by testing 10 specimens together.

3/ The immersion time shall be 60 seconds.

4/ Cites TAPPI test methods.

AMXRE Form 598
8 February 1965

NNN-P-40B

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

4.4 Test methods.

4.4.1 Silicone content type I, (class 3 only). Ignite a 30 ml. Vycor or equal micro-Kjeldahl flask at 1000° C., cool in a desiccator, and weigh to the nearest 0.1 milligram. Support the flask in a water bath at 75° ± 2° C., with the level of the water about half way up the neck of the flask. Above the flask, suspend a funnel with filter paper to allow maximum free space at the neck and mouth of the flask for vapor dissipation. Adjust the position of the funnel so that the tip rests against the wall of the flask. The effluent should not drip but flow gently down the inner wall of the flask.

Fit a 125 ml. graduated separatory funnel with a Teflon (or equal) plug-cock and attach a spring tension adapter. Cut a 5 gram sample of lens-cleaning tissue into 1/2 inch to 1 inch squares, weigh to the nearest 0.1 milligram and place in the separatory funnel. Cover the tissue with 75 ml. of methylene chloride and agitate for 1 minute. Support the funnel above the filter and after 3 to 5 minutes allow the liquid to flow gradually into the flask at a rate approximately equal to the loss of solvent by volatilization. Repeat to make three extractions of the tissue in fresh solvent. Evaporate the solvent by heating the flask on a steam bath, allow to cool, and add 1.5 ml of fuming sulfuric acid and 10 drops of fuming nitric acid. Heat gently on a digestion rack until the material gels as indicated by no further bubble formation at the bottom of the flask. The heating to expel the acid should be done carefully in a vented hood in such a manner that the material does not spatter. Ignite the flask and residue at 1000°C., to constant weight. Cool and re-weigh to the nearest 0.1 milligram.

To confirm the residue as SiO_2, transfer the major portion to a platinum crucible. Add 3 ml. of concentrated hydrofluoric acid and 3 drops of concentrated sulfuric acid. Carefully expel the acids and ignite. There will be no significant residue if the ash was SiO_2.

Determine the percent moisture content of the paper in accordance with TAPPI Test Method T 412. Then calculate the moisture free weight of the specimen as follows:

$$\text{Wt. paper sample (moisture free)} = \text{Wt. paper sample} - (\text{Wt. paper sample} \times \text{percent moisture})$$

Determine a blank value by analyzing a sample of untreated paper by the same procedure. Blank results are usually in the order of 2.5 mg. SiO_2. Subtract the blank from the weight of SiO_2 and calculate the silicone content of the paper as follows:

$$\text{Percent silicone content} = \frac{(\text{Wt. silica ash} - \text{blank}) \times 1.233\ (SiH(CH_3)_3)}{\text{Wt. paper sample (moisture free)}} \times 100$$

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

4.4.2 Test for abrasiveness. The apparatus shall consist of a methyl methacrylate plate and a rotating roller having a metal surface such that it will hold a strip of paper in close contact with the plastic plate under a pressure of 1 kilogram per centimeter width of the paper. The plastic plate and roller shall be clean and free of dust, and the plate shall have no scratches on its surface. A strip of the paper to be tested shall be drawn slowly through a distance of 10 cm. between the plastic plate and the roller. The plate shall be examined for scratches under a microscope, illuminated from below at an angle of 95°.

4.4.3 Water absorbency, class 5. Immerse a three by five inch specimen in water at a temperature of 18° to 30°C. Withdraw the specimen after one second. To be considered satisfactory, the specimen shall be sufficiently wet so that water can be expelled from the specimen when it is crumpled and squeezed.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Level A. Lens paper of one description only, furnished in the form specified in 3.7, and quantities specified in table III (see 6.2), shall be packaged as hereinafter specified.

TABLE III. Unit packaging

Size (inches)	Forms and quantities (each)
3 by 5	Books of 50 or 100 sheets or envelopes of 100 sheets.
3 by 7	Packages of 800 sheets.
4 by 6	Books of 50 sheets.
4-1/4 by 5	Books of 100, 300, or 1,000 sheets.
5 by 5-3/4	Packages of 400 sheets.
5 by 6-3/4	Packages of 800 sheets.
7 by 11	Packages or envelopes of 100 sheets.
7-1/2 by 11	Reams of 500 sheets.
10 by 15	Reams of 480 sheets.
12 by 18	Reams of 480 sheets.
15 by 20	Reams of 480 sheets.
18 by 24	Reams of 480 sheets.
20 by 30	Packages of 50 sheets or reams of 480 sheets.
24 by 36	Reams of 480 sheets.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

5.1.1.1 Sizes 3 by 5 through 7 by 11. Lens paper of one description only, unit packaged as specified in table III, shall be packaged in a snug-fitting folding paperboard box conforming to PPP-B-566; setup paperboard box conforming to PPP-B-676; or completely wrapped in kraft paper conforming to grade B of UU-P-268. Each paperboard box shall be closed in accordance with the appendix of the applicable box specification. Each paper wrapped package shall be secured with gummed paper tape conforming to type III, grade A or B of PPP-T-45. The weight of contents of each paperboard box or wrapped package shall not exceed 10 pounds.

5.1.1.2 Sizes 7-1/2 by 11 through 24 by 36 inches. Lens paper of one description only, unit packaged as specified in table III, shall be provided with top and bottom paperboard pads of the same size as the lens paper and then be completely wrapped in kraft paper and the wrap secured as specified in 5.1.1.1. Alternatively, the lens paper shall be shrink-packaged in polyvinyl chloride, cellulose acetate or cellulose butyrate; or packaged in a fiberboard box conforming to class domestic or weather-resistant as specified (see 6.2) of PPP-B-636. Each box shall be closed in accordance with the applicable requirements specified in the appendix of PPP-B-636.

5.1.2 Level B.

5.1.2.1 Unit packaging. Lens paper of one description and form (see 3.7) shall be packaged in quantities specified in table III in accordance with 5.1.3.

5.1.2.2 Intermediate packaging. The lens paper shall be intermediately packaged in accordance with 5.1.2.2.1 or 5.1.2.2.2.

5.1.2.2.1 For size 3 by 5 through 7 by 11. Fifty (50) books or envelopes specified in 5.1.2.1 shall be intermediately packaged in a box conforming to PPP-B-566, PPP-B-676 or completely wrapped in paper conforming to UU-P-268. Each box shall be closed in accordance with the applicable box specification. Each wrapped package shall be secured with tape conforming to PPP-T-45 or PPP-T-42. The weight of contents of each box or package shall not exceed 10 pounds.

5.1.2.2.2 For size 7-1/2 by 11 through 20 by 30 inches. The unit packages shall be provided with top and bottom paperboard pads of the same size as the lens tissue and completely wrapped in paper conforming to UU-P-268 and secured with tape conforming to PPP-T-45 or PPP-T-42.

5.1.3 Level C. Lens paper shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:48Z
Check the source to verify that this is the current version before use.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Lens paper of one description only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636 or overseas type, style A or I, grade A or B, type 2 load of PPP-B-601. Each fiberboard container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636. Each wood container shall be waterproofed with a sealed case liner conforming to type I or II, grade C of MIL-L-10547 and be closed and reinforced in accordance with the appendix of PPP-B-601. Shipping containers packed with weather-resistant grade fiberboard boxes need not be waterproofed. The weight of contents of each shipping container shall not exceed 65-pounds for fiberboard containers or 150-pounds for wood containers.

5.2.2 Level B. Lens paper of one description only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II as specified in the appendix of the container specification. The weight of contents of each fiberboard shipping container shall not exceed 65-pounds. Lens paper packaged in fiberboard boxes, as specified in 5.1.1.2 need not be over-packed.

5.2.2.1 When specified (see 6.2), the fiberboard shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of the container specification.

5.2.3 Level C. Lens paper, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Marking.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 Military requirements. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:48Z
Check the source to verify that this is the current version before use.

5.3.3 Special marking.

5.3.3.1 Packages of type I, class 3 lens paper shall be plainly marked with the following:

DO NOT USE ON PRECISION COATED OPTICS OR OPTICAL PLASTICS

5.3.3.2 Packaging type II lens paper shall be plainly marked with the following:

FOR WRAPPING USE ONLY

6. NOTES

6.1 Intended use. Type I lens paper is used for wrapping and cleaning lenses and other glass and highly polished surfaces. Classes 1, 2, and 3 are for dry cleaning applications; classes 4 and 5, for wet cleaning. Type II lens paper is used for wrapping or covering of all coated optics.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type, class, size, and form required (see 1.2, 3.6, and 3.7).
(c) Selection of the applicable levels of packaging and packing (see 5.1 and 5.2).
(d) Quantity of sheets of lens paper in the form required (see 5.1.1).
(e) Whether domestic or weather-resistant grade fiberboard boxes are required for packaging lens paper in specified form (see 5.1.1.2).
(f) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).

6.3 Description of type I, classes. Type I, classes 1, 4 and 5 are low-density kind of paper (formally known as the "Japanese" type of tissue paper). Classes 2 and 3 are thin tissue, with the silicone of class 3 acting as a lubricant.

6.4 Type I, classes 1, 2, 3, 4 and 5 were formerly types 1, 2, 3, 4 and 5 in NNN-P-40A. Type II was the paper, lens, tissue antitarnish, wrapping of MIL-P-13988A(MU).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

MILITARY CUSTODIANS:

Army - GL
Navy - MS
Air Force - 82

Review activities:

Army - MU, MD, ME, WC

User activity:

Army - MI

Preparing activity:

Army - GL

CIVIL AGENCY COORDINATING ACTIVITIES:

GSA-FSS
COM-NBS
HEW-NIH
NASA-JPK
VA-DMS

Project No. 6640-0710

☆U. S. GOVERNMENT PRINTING OFFICE : 1973 O - 514-178 (426)

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 20 cents each.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:48Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.