INCH-POUND

PPP-D-705E
January 3, 1994
SUPERSEDING
PPP-D-705D
August 24, 1974

FEDERAL SPECIFICATION

DRUM, SHIPPING AND STORAGE: STEEL, 16 AND 30 GALLON CAPACITY

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers new straight sided, cylindrical-steel drums of 16 gallon, 30 gallon, and 120 pound grease capacities.

1.2 Classification.

1.2.1 Types. The drums covered by this specification shall be of the following types, as specified (see table I and 6.2):

Type I	-	30 gallon drum, double seamed chimes, tight head (MH2.6)
Type II	-	16 gallon drum, double seamed chimes, tight head (MH2.7)
Type III	-	120 pound grease - Rule 40 or Item 260 drum, double seamed bottom chime, full removable lug cover (MH2.8)
Type IV	-	30 gallon - Rule 40 or Item 260 drum, double seamed bottom chime, full removable head (MH2.12)

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5019 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8110

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

Type V	-	30 gallon drum, double seamed bottom chime, full removable head (MH2.13)
Type VI	-	16 gallon - Rule 40 or Item 260 drum, double seamed bottom chime, full removable head (MH2.14)

2. APPLICABLE DOCUMENTS

2.1 Government documents. The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein:

Federal Specifications:

TT-E-485	-	Enamel, Semi-Gloss, Rust-Inhibiting
VV-L-800	-	Lubricating Oil, General Purpose, Preservative, (Water-Displacing, Low Temperature)
PPP-P-420	-	Plugs and Flanges (For Drum Closures)

Federal Standards:

FED-STD-123	-	Marking for Shipment (Civil Agencies)
FED-STD-141	-	Paint, Varnish, Lacquer and Related Materials: Methods of Inspection, Sampling and Testing
FED-STD-595	-	Colors

(Activities outside the Federal Government may obtain copies of Federal specifications, standards, and Commercial Item Descriptions as outlined under General Information in the Index of Federal Specifications, Standards, and Commercial Item Descriptions. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.)

(Single copies of this specification, and other Federal specifications and Commercial Item Descriptions required by activities outside the Federal Government for bidding purposes are available without charge from the General Services Administration Business Service Centers in Boston, MA; New York, NY; Philadelphia, PA; Washington, DC; Atlanta, GA; Chicago, IL; Kansas City, MO; Fort Worth, TX; Houston, TX; Denver, CO; San Francisco, CA; Los Angeles, CA; and Seattle, WA.)

(Federal Government activities may obtain copies of Federal Standardization documents and the Index of Federal Specifications, Standards, and Commercial Item Descriptions from established distribution points in their agencies.)

Military Specification:

MIL-G-432	-	Gaskets, Nonmetallic, Synthetic Rubber

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

Military Standards:

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage

(Copies of military specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

LAWS AND REGULATIONS

49 CFR 100-199	-	Department of Transportation Rules and Regulations Covering Hazardous Materials

(The code of Federal Regulations (CFR) and the Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402. When indicated, reprints of certain regulations may be obtained from the Federal agency responsible for the issuance thereof.)

2.2 Other publications. The following documents form a part of this document to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

AMERICAN NATIONAL STANDARDS INSTITUTE (ANSI)

MH2.6 ANSI Standard for 30 Gallon Tight-Head Universal Drums

MH2.7 ANSI Standard for 16 Gallon Tight-Head Universal Drum

MH2.8 ANSI Standard for 16 Gallon Full-Removable-Head Lug-Cover Universal Drums (UFC-Rule 40, NMFC - ITEM 260)

MH2.12 ANSI Standard for 30 Gallon Full-Removable-Head Universal Drums (UFC Rule 40, NMFC - ITEM 260)

MH2.13 ANSI Standard for 30 Gallon Full-Removable-Head Universal Drum

MH2.14 ANSI Standard for 16 Gallon Full-Removable-Head Universal Drums (UFC - Rule 40, NMFC - ITEM 260)

(Application for copies should be addressed to the American National Standards Institute, 11 West 42nd Street, New York, NY 10036.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 3951 - Packaging, Commercial
ASTM D 4919 - Testing for Hazardous Materials

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.1.1 Steel sheet and strip, fittings, and seaming compound. Steel sheet and strip, fittings, and seaming compound shall be in accordance with the requirements of 49 CFR 178, Subpart L or ANSI MH2 Standard. Steel sheet tolerances shall be in accordance with the applicable MH2 Standard. Thickness of steel sheet shall be measured at any point on the sheet not less than 3/8 inch from the edge.

3.1.2 Gasket. Gaskets shall be in accordance with MIL-G-432.

3.1.3 Paint. The paint shall conform to TT-E-485 and shall be color No. 27037, 27040, or 24087 of FED-STD-595, as specified (see 6.2).

3.1.4 Plugs and flanges. Plugs and flanges shall be in accordance with PPP-P-420.

3.1.5 Cap seals. Cap seals shall be those commercially available for hand tool application and fit the closure supplied. When specified (see 6.2), the color shall be the same as the drum.

3.2 Design and construction. Type I, II, III, IV, V, and VI drums shall be in accordance with ANSI Standards MH2.6, MH2.7, MH2.8, MH2.12, MH2.13, and MH2.14, respectively. Type I, II, and V drums shall be in accordance with 49 CFR 178, as applicable. Steel gages shall be as specified in table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

TABLE I. Steel gage for drums

Type		Carrier	U.S. Manufacturer's Standard Gage ANSI	Heads	Covers	Bottoms	Bodies	Closing ring
I	2/		MH2.6	19	--	19	19	--
II			MH2.7	20	--	20	20	--
III	1/	Rule 40	MH2.8	--	20	20	20	--
	3/	Item 260						
IV	1/	Rule 40	MH2.12	--	19	19	19	16
V			MH2.13	--	18	18	18	12
VI	1/	Rule 40 Item 260	MH2.14	--	20	20	20	16

1/ Uniform Freight Classification Rule and National Motor Freight Item.

2/ When specified (see 6.2), 20 gage.

3/ When specified (see 6.2), 22 gage (for greases only). (24 gage for intrastate only in California).

3.3 Dimensions and capacity. Dimensions, capacity, tare weight, and tolerances shall be in accordance with the applicable ANSI Standard (see 6.3). In addition, type III drums shall be designed to accommodate 120 pounds of light grade grease. The rated or nominal capacity shall be determined as specified in 4.3.3.

3.4 Lining. Drums used to package materials which would have a deleterious effect on bare drum metal, or vice versa, shall be lined on all internal surfaces with a material that will neither affect nor be affected by the material packaged. A lining material meeting these requirements shall be agreed upon by the contracting officer and supplier. A certificate of compliance of material(s) specified herein shall be provided to the contracting officer (see 4.1.2 and 6.2).

3.5 Fog spray. The interior surfaces of the drum and the gasket seats of threaded flanges, if unplated or uncoated, shall be fog sprayed. Types I, IV, and V drums shall be sprayed with 11 cubic centimeters to 14 cubic centimeters (cc) of oil conforming to VV-L-800. Types II, III, and VI drums shall be sprayed with 6 cc to 8 cc of oil. Dispensing shall be through an accurate metering device. Spraying shall be accomplished immediately after all fabrication operations have been completed, including painting, but before final insertion of plugs or applying of removable head or cover for shipment. The interior surfaces shall be completely wetted with the oil when the fog has settled. There shall be no surplus oil collecting in pools or rings on the bottom. Fog spray shall be applied after drums have cooled to a

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

temperature below 140°F. Air lines of fogging equipment shall contain moisture traps to prevent introducing water vapor into the drums. Closure plugs shall be inserted, wrench tight, immediately after fog spray. Removable head or removable cover drums shall have the head, or cover, fogged before attaching to the drum.

3.5.1 Unlined drums for materials susceptible to contamination. Unlined drums to be used for products required to be of extremely high purity (i.e., super clean products) shall not have fog spray as specified in 3.5, or other surface treatment at time of filling. Drums used for such material will be thoroughly washed and rinsed prior to use.

3.6 Closures. Closure shall be in accordance with 49 CFR and ANSI MH2 Standard. The vent and bung closure flanges for type I and II drums shall not move when tested as specified in 4.3.2. Gaskets specified in 3.1.2 shall be provided for each bung of type I and II drums. A tubular, synthetic, cellular, rubber, flowed-in or sponge rubber gasket shall be provided with each removable cover of types III, IV, V, and VI drums. Type III drums shall have the cover lugs crimped around and under the false wire or curl when closed. The types IV and VI drums shall be provided with a bolted or lever-lock type closing ring. The type V drum shall be provided with a locking ring having forged lugs, one of which shall be threaded, and have a 3/8 inch minimum bolt and locking nut.

3.6.1 Cap seals. When specified (see 6.2), each closure for types I and II drums shall have cap seals applied that prevent removing the plug without destroying the seal. The seal shall be so constructed that the seals may be applied by hand tools. The cap seals shall be suitable for the closures supplied. The cap seals shall pass the air test specified in 4.3.6, without leakage.

3.7 Finish.

3.7.1 Cleaning. Prior to painting, the interior and exterior of the drums shall be free of rust, loose scale, metal particles, foreign matter, and oily and greasy substances. Sharp edges and metal splinters shall be removed.

3.7.2 Painting. The surface that will be the drum exterior shall be coated with paint specified in 3.1.3. Drums which were coated in the flat shall, after welding, have the unpainted side seam painted. All closure plugs shall be in place during final painting operations. After application to the drum and curing, the enamel shall show good adhesion, shall be difficult to furrow, and shall not flake off or show jagged edges when subjected to the knife test specified in 4.3.4. The coating on all surfaces shall be properly dried or baked, as specified, and have a dried film thickness of not less than 0.8 mil, when tested as specified in 4.3.5.

3.8 Performance requirements. Types I, II, and V drums shall be subjected to performance oriented packaging (POP) tests cited in 49 CFR 178, Subpart M.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:50Z
Check the source to verify that this is the current version before use.

Unless otherwise specified in Rule 40 or Item 260, type III, IV and VI drums are not required to pass POP testing.

3.9 Identification marking. Marking of drums shall be in accordance with 49 CFR 178, Subpart L, for the material to be carried or applicable Rule 40 or Item 260. When empty drums are procured by the Government, each drum shall be embossed with "US". The "US" may be omitted when drums are procured incident to procurement of the product contained therein. When specified (see 6.2), containers shall be marked on the lower one third of the side wall in letters at least 1/4 inch in height as follows: Container Conforms to PPP-D-705, Type ____.

3.10 Workmanship. Finished drums shall be clean, free from rust, loose slag, or leaks. Components and linings, when required, shall be free from defects of application that make them leak or may contaminate the product being packed. Welds shall be free of burrs, splatter, cracks, or incomplete fusion. Spot welds, if used, shall be free from flash or burn through. Solder shall not be used to repair leaks. There shall be no excess seaming compound on either the inside or outside of the drum. Painted surfaces shall be adherent, free of blisters, imbedded foreign matter, or crinkles. Threaded areas shall not have threads missing, stripped, or fractured. The two ends of the bolt ring shall be at least 1/4 inch apart when the ring is tightened to close and seal the drum. There shall be no evidence of leaking when the drum is filled and closed. Markings shall be complete and legible.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

4.1.2 Certificate of compliance. Where certificates of compliance are submitted to determine compliance with 3.4, the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Quality conformance inspection. Unless otherwise specified, all items shall undergo quality conformance inspections and examinations.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.2.2 In-process inspection. Inspection of subassemblies shall be made to ascertain that construction details which cannot be examined in the finished product are in accordance with specified requirements. The Government reserves the right to exclude from consideration for acceptance, any material or service for which in-process inspection has indicated nonconformance.

4.2.3 End item visual examination. The end items shall be examined for the defects listed in table II. The lot size shall be expressed in units of drums of one type. The sample unit shall be one drum. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 1.5 for major defects and 6.5 for total (major and minor combined) defects.

TABLE II. End item visual defects

Examine	Defect	Classification Major	Minor
Material:			
Steel	Sharp crease	101	
Gaskets	Not type specified		201
	Not sufficient thickness to provide tight seal		202
	Missing	102	
	Damaged	103	
	Not uniformly distributed		203
Construction:			
Rolling hoops	Not provided as specified	104	
Side seams	Not continuous	105	
	Not electric welded		204
	Repairs over 3 inches long	106	
Seaming compound	Evidence of hardening		205

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

TABLE II. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Construction: (cont'd)			
Linings	Missing, when required	107	
	Exposed internal surfaces not completely covered when lining is specified	108	
Closures:			
Types I and II drums	Less than two openings per drum	109	
	Size of openings not as specified	110	
	Location not as specified		206
	Less than three full threads per flange	111	
	Less than three full threads engaging on plug when gasket is in place and plug seated tightly	112	
	Missing	113	
	Seat not smooth		207
Cap seal	Removal of plug does not destroy seal	114	
	Incorrect color (when required)		208
	Not suitable for closure supplied	115	
Type III drum	Less than 20 lugs per cover	116	
	Gasket missing from cover	117	
	Lugs not sufficient length to make tight seal when crimped around drum top		209
Types IV, V, and VI drums	Gasket missing	118	
	Locking ring not of gage specified		210
	Bolt not size specified		211
	Jam nut missing (when required)		212
	Cover does not fit over false wire	119	
	Locking ring clearance not as specified		213
Finish:			
Cleaning	Evidence of rust, loose scale, metal particles, foreign matter, and oily and greasy substances on interior or exterior	120	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

TABLE II. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Finish: (cont'd)			
Paint	Incorrect color and sheen	121	
	Poor adhesion, bubbles, or runs	122	
	Tacky, not properly dried		214
	Plugs not coated (when required)		215
Fog spray in unlined drums	Evidence of incomplete wetting		216
	Accumulation of oil in bottom of drums		217
	Evidence of water condensate in drum	123	
	Loose closure plugs after fogging		218
	When fog spray is not required	124	
Identification marking	Omitted, incomplete, incorrect or illegible	125	
	Location, size or sequence not as specified		219
	Not embossed, when specified	126	
Workmanship	Not clean and free from rust, loose slag or dents		220
	Improper application of linings	127	
	Burrs, flash, or splatter in weld areas		221
	Cracks or incomplete fusion of welds	128	
	Spot welds burned through	129	
	Solder used for repairs	130	
	Seaming compound protrudes		222
	Excess oil		223
	Paint does not adhere, blistered, covers imbedded materials, wrinkled, or crazed		224
	Threads stripped, missing, or cracked	131	
	Bungs closer than 1/2 inch from edge	132	
	Type III, IV, and VI drums leak when filled	133	
	Marking not legible	134	

4.2.4 End item dimensional examination. The end items shall be examined for the conformance to the dimensions specified. Any dimension not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of drums of one type. The sample unit shall be one drum. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:50Z
Check the source to verify that this is the current version before use.

4.2.5 End item testing. Unless otherwise specified herein, the end item shall be tested for the characteristics listed in table III and POP testing cited in 49 CFR 178, Subpart M. The lot size shall be expressed in units of drums of one type. The sample unit shall be one drum.

TABLE III. Testing of end item

Characteristics	Requirement paragraph	Test paragraph	Results reported as
Hydrostatic 1/	3.8	4.3.1	Pass or fail
Drop 1/	3.8	4.3.1	Pass or fail
Leakpoofness 1/	3.8	4.3.1	Pass or fail
Stacking 1/	3.8	4.3.1	Pass or fail
Vibration 1/	3.8	4.3.1	Pass or fail
Closure	3.6	4.3.2	Pass or fail
Capacity	3.3	4.3.3	Pass or fail
Knife test	3.7.2	4.3.4	Pass or fail
Paint thickness	3.7.2	4.3.5	Pass or fail
Cap seal	3.6.1	4.3.6	Pass or fail

1/ Test parameters and criteria must meet the requirements of 49 CFR 178.

4.2.6 Packaging examination. The packed end items shall be examined for the defects listed below. The lot size shall be expressed in units of drums. The sample unit shall be one drum marked for delivery. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

Examine	Defect
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

4.3 Methods of inspection.

4.3.1 Performance oriented packaging (POP) testing. Type I, II and V drums shall be tested for hydrostatic pressure, drop, leakproofness, stacking, vibration and any other criteria cited in 49 CFR 178, Subpart M and the procedures cited in ASTM D 4919.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

4.3.2 Closure test (types I and II). A drum shall be selected at random from the drum manufacturer's production line and the following torques applied to the inserted plug, as applicable: 3/4 inch size - 15 foot-pounds; 2 inch size - 30 foot-pounds. If flanges do not remain firmly anchored under these tests, it shall be cause for rejection and production stopped until the flange insertion die adjustments have been made that will ensure satisfactory test results. If plug gaskets are damaged during torque tests, the plugs shall be removed and new gaskets applied before the drums are accepted for shipment.

4.3.3 Capacity test. The capacity of the drum shall be determined by pouring a measured volume of fresh water into the specimen until the specified filled level is attained. The total volume poured in shall be recorded.

To determine the filled level of the specimen, pour a measured volume of fresh water equal to the specified capacity into the specimen. Observe and record the position of the liquid level.

To determine the outage, measure the additional volume of water (Vo) required to completely fill the specimen after it is filled to liquid capacity. Calculate the outage using the following formula:

$$\text{Outage in percent of liquid capacity} = \frac{100 \times Vo}{\text{liquid capacity.}}$$

Failure to comply with the requirement in 3.3 shall constitute failure of the test.

4.3.4 Knife test. The knife test shall be conducted on a drum selected at random from each lot by cutting a narrow ribbon of the film loose by means of a knife blade. The blade shall be held at an angle of about 30°. Tests may be conducted on any part of the drum.

4.3.5 Paint thickness test. Paint thickness on heads and sides shall be measured in accordance with method 6181 of FED-STD-141.

4.3.6 Cap seal tests (types I and II). One of the drums selected for the hydrostatic test or the drop test may first be used for the cap seal tests. When cap seals are required to be air tight, a drum shall be selected from each lot and the cap seal shall withstand without leakage a minimum dry air test of 5 psi without the plug in place. The 2 inch opening shall first have a cap seal applied without the plug in place while the air pressure is inserted through the 3/4 inch opening. If this test is satisfactory, the 3/4 inch opening shall have a cap seal applied without the plug in place while the air pressure is inserted through the 2 inch opening (see 3.6).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packing. Packing shall be commercial.

5.1.1 Commercial packing. Drums shall be packed in accordance with ASTM D 3951.

5.2 Marking.

5.2.1 Civil agencies. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the requirements of FED-STD-123 and ASTM D 3951, as applicable.

5.2.2 Military requirement. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the requirements of MIL-STD-129.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. Drums covered by this specification are intended for use by the Government or for the shipment of commodities purchased by the Government when prescribed in the applicable commodity specifications. These drums are single trip containers and may be used for level A, B, or C shipments of non-regulated materials. Drums, when used for shipment of regulated materials must meet the requirements of 49 CFR 170-180.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Type of drum and gage material permitted (see 1.2.1 and table I).
c. Color of paint required (see 3.1.3).
d. When cap seal is to be the same color as drum (see 3.1.5).
e. When certificate of compliance is acceptable for the lining material (see 3.4).
f. When cap seal is required (see 3.6.1).
g. When specification marking is required (see 3.9)
h. Shipment markings required (see 5.2).

6.3 Drum dimensions. The dimensions shown in table IV are partial only and are from the applicable ANSI Standards for cataloging purposes only. Tolerances for depth and height are ± 1/8 inch and for diameters ± 1/16 inch.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:50Z
Check the source to verify that this is the current version before use.

TABLE IV. ANSI dimensions

Type	ANSI Std	Depth inside	Height outside	Diameter inside	Diameter outside	Carrier or Former DOT Designation
I	MH2.6	27-3/8	28-7/8	18-1/4	19-3/16	DOT 17E
II	MH2.7	25-1/2	26-7/8	13-15/16	14-7/8	DOT 17E
III	MH2.8	25-15/16	26-3/4	13-15/16	14-3/4	Rule 40 or Item 260
IV	MH2.12	28-3/8	29	18-1/4	19-19/32	Rule 40 or Item 260
V	MH2.13	28-3/8	29-1/8	18-1/4	19-19/32	DOT 17E
VI	MH2.14	25-15/16	26-7/8	13-15/16	14-7/8	Rule 40 or Item 260

6.4 Subject term (key word) listing.

Barrel
Container

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

MILITARY INTERESTS:

Custodians

Army - GL
Navy - SA
Air Force - 69

Review Activities

Army - MI, EA, AR
Navy - AS, SH
DLA - GS

User Activities

Army - CR
Navy - MC, YD
Air Force - 82

CIVIL AGENCY COORDINATING ACTIVITIES:

GSA - FSS
USDA - APS

PREPARING ACTIVITY:

Army - GL

(Project No. 8110-0302)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	PPP-D-705E	1994 January 3

3. DOCUMENT TITLE

DRUM, SHIPPING AND STORAGE: STEEL, 16 AND 30 GALLON CAPACITY

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON/DSN
U.S. Army Natick RD&E Center	508-651-4532	256-4532
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: SATNC-IR Natick, MA 01760-5019	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 NATICK OP2 JUL 91 *Previous editions are obsolete.* 198

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.