PPP-D-732D
April 14, 1976
SUPERSEDING
Fed. Spec. PPP-D-732C
June 15, 1969

FEDERAL SPECIFICATION

DRUMS, METAL, 55-GALLON RECONDITIONED (FOR SHIPMENT OF NONCORROSIVE MATERIAL)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers reconditioned 55-gallon metal drums.

1.2 Classification. Fifty-five gallon drums shall be furnished in the following types and classes of nonphosphated coated exterior containers, as specified (see 6.2).

1.2.1 Types and classes.

Type I - Reconditioned DOT-5B drums - straight side with two rolling hoops, cylindrical drum; double seamed chimes, tight head, with chime reinforcement

Type II - Reconditioned DOT-17E drums - straight side with two rolling hoops, cylindrical drum; double seamed chimes, tight head, without chime reinforcements

Type III - Reconditioned UFC, Rule 40 and NMFC Item 260 drums - straight side with two rolling hoops, cylindrical drum; double seamed chimes, without chime reinforcement

Class A - Tight head
Class B - Open head provided with removable cover and bolted type lock ring

FSC 8110

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

Type IV - Reconditioned DOT-17H drums - straight side with three rolling hoops, cylindrical drum; double seamed bottom chime, without chime reinforcement, full removable cover, provided with removable bolted type locking ring

Type V - Reconditioned DOT-17C drums - 16 gage with three rolled or swedged in rolling hoops, 12 gage bolted ring with forged lugs and 5/8 inch bolt and nut, welded body seams and double seamed bottom chime

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

TT-E-485	-	Enamel, Semi-gloss, Rust-Inhibiting
TT-E-515	-	Enamel, Alkyd, Lusterless, Quick-Drying
TT-E-516	-	Enamel, Lusterless, Quick-Drying Styrenated Alkyd Type
VV-L-800	-	Lubricating Oil, General Purpose, Preservative (Water-Displacing, Low Temperature)
PPP-D-711	-	Drum: Metal, Shipping, Steel, Lightweight (55 Gallon)
PPP-D-729	-	Drums, Shipping and Storage, Steel, 55-Gallon
PPP-D-736	-	Drums, Shipping Steel, DOT 6A, DOT 6B and DOT 17C
PPP-P-420	-	Plugs and Flanges (For Drum Closures)

Federal Standards:

FED-STD-123	-	Marking for Shipment (Civil Agencies)
FED-STD-595	-	Colors

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-G-432 - Gaskets-Nonmetallic, Synthetic Rubber

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspec Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Laws and Regulations:

U.S. Department of Transportation:

49CFR 178 - Rules and Regulations of Shipping Containers for Transportation of Explosives and Other Dangerous Articles.

(Copies of the Code of Federal Regulations may be obtained upon application to the Superintendent of Documents, U.S. Goverement Printing Office, Washington, DC 20402. Prices may be obtained from the Superintendent of Documents.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

National Motor Freight Traffic Association, Inc., Agent

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Materials.

3.1.1 Drums. Drums for reconditioning shall be used drums that originally conformed to PPP-D-711, PPP-D-729 and PPP-D-736, as applicable, and so designated by DOT or other markings.

3.1.2 Paint. Paint shall conform to TT-E-485, TT-E-515, or TT-E-516.

3.2 Process and physical characteristics. Drums selected for reconditioning shall have been constructed in accordance with the applicable requirements of PPP-D-711, PPP-D-729 or PPP-D-736, as applicable, for the comparable type and class of 1.2 as specified (see 6.2). The reconditioning process shall be that normally used by the reconditioner except that cleaning by the burning method shall not be used on tight head drums. Open head drums may be cleaned by the burning method provided the temperature does not exceed 1400°F and the interval of burning of each drum does not exceed 10 minutes. Drums which show evidence of visible pitting, creases, reduction in metal thickness from rust, corrosion, or cleaning processes; or metal fatigue shall not qualify for reuse.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

3.2.1 Dimensions. The dimensions of each reconditioned drum shall be in accordance with PPP-D-711, PPP-D-729 or PPP-D-736, as applicable, except that tight head drums converted to open head drums may be 34 inches plus or minus 1/4 inch in height.

3.2.2 Capacity. The rated capacity of each reconditioned drum shall be 55 gallons. Actual capacity, including the convex heads, shall be not less than 57.20 gallons nor greater than 57.75 gallons when tested as specified in 4.3.1. Tight head drums converted to open head drums and reconditioned shall have a capacity of not less than 54.41 gallons.

3.2.3 Contour. Drums shall be structurally sound and conform to the original contour as specified for each type and class of PPP-D-711, PPP-D-729 or PPP-D-736, as applicable, and as specified in 3.2.1. The curl or false wire shall be as specified in 3.2.4.7.

3.2.4 Heads.

3.2.4.1 Top heads or covers. The top heads or covers shall be free of dents and protrusions, bulges, or creases which will interfere with marking of the drum.

3.2.4.2 Flanges. Flanges shall be free of worn or damaged threads. Threads shall be clean and face of flange shall be smooth, capable of providing a leak-proof closure. Closure shall permit sealing. Flanges shall have three or more complete threads and shall not move under torques of 15 foot-pounds and 30 foot-pounds applied to the vent and filler plugs respectively, when tested as specified in 4.3.3.

3.2.4.3 Gaskets. All gaskets shall be new. Plug gaskets shall be in accordance with MIL-G-432. Alternatively, commercial gaskets may be used for products other than hydrocarbons. Gaskets for removable head drums shall be tubular or solid rubber, flowed-in or sponge type rubber or synthetic material uniformly distributed about the circumference of the cover. The gasket material shall be of sufficient thickness to provide an adequate seal and not leak when tested (see 4.3.2) and not affect or be affected by the product being packaged. A gasket material meeting the requirements of this specification shall be furnished by the supplier and a certificate of compliance shall be provided upon request from the contracting officer or as required in the contract or order (see 4.1.1 and 6.2).

3.2.4.4 Plugs. The plugs shall be either new or used at the option of the supplier. The new plugs shall conform to PPP-P-420 and match the flange, except that the minimum zinc plating thickness shall not include the threaded surfaces and the salt spray test shall be for 32 hours in lieu of 96 hours specified. Used plugs shall be clean, free of worn or damaged threads, equipped with new gaskets and capable of providing a leak-proof closure.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

3.2.4.5 Covers. Covers for open head drums shall be of thickness and contour specified for the type and class drum of PPP-D-711, PPP-D-729 or PPP-D-736, as applicable, for which the covers are intended. The cover shall fit over the false wire of the body and, with the gasket in place, provide a tight seal (see 3.2.4.7). Covers shall be convexed a minimum of 3/8 inch deep, shall be sealed with a gasket as specified in 3.2.4.3, and secured to the false wire by a locking ring as specified in 3.2.4.6.

3.2.4.6 Locking rings. Locking rings for open head drums shall be bolted type, fabricated from 16 gage steel (nominal 0.0598-inch) for type III and 12 gage (nominal 0.1046) for type IV drums. The lugs for holding the bolt shall be no less than the thickness of the ring. The locking ring for the type IV drum shall have one lug threaded. The lugs shall be dropped forged or bar stock. Bolts shall be 5/16-inch diameter minimum for type III and 5/8-inch diameter minimum for type IV drums and sufficiently long to insure engagement of both lugs and to hold the ring tight. When specified (see 6.2), bolts for type IV drums shall be provided with commercially approved jam nuts. Used rings shall be structurally sound and of original contour. All threaded areas shall be clean and free of nicks, dents, or missing thread that will impair their use.

3.2.4.7 False wire. The false wire of open head drums shall conform to the contour of the type and class drum it is intended to represent and shall be free of dents, nicks, fractures, open side seams, or cracks which will prevent making a complete seal.

3.2.4.8 Bottom heads. The bottom heads of tight head drums shall be free of sharp dents, sharp bulges, radial stress marks, and welds. The bottom heads of open head drums shall be free of sharp dents, sharp bulges, radial stress marks, and welds.

3.2.5 Body or shell. Bodies shall be cylindrical and conform to original contour. Slight dents that do not detract from appearance or weaken the drum shall be permitted. There shall be not more than 6 dents of 1/4-inch in depth or 3-inches in length and there shall be no dents permitted that exceed 1/4-inch in depth and 3-inches in length.

3.2.6 Rolling hoops. Rolling hoops shall be of original contour, and free of sharp dents, sharp creases, or pitting which will weaken the drum.

3.2.7 Chimes. Chimes and chime reinforcements as applicable shall be rolled tight, shall be free of fractures and cracks, and shall conform to the original contour.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

3.3 Repairs. Repairs shall be made by welding as specified herein. Chime welding shall not be permitted. No welds shall be permitted on the bottom heads. One side seam weld not over 3-inches long shall be permitted. The number of top head and body repair welds shall not exceed two within any square foot area with no weld exceeding 1/2-inch in length. Repairs made with solder are not acceptable.

3.4 Finish.

3.4.1 Cleaning. All interior and exterior surfaces of the drums and closures shall be clean and free of all loose paint, rust, rattlers (welding beads, chips, et cetera) or odor of previous contents, previous content, lining material, or other foreign matter. The requirement for no moisture, previous contents, exterior paint runs inside the drum, or odor of previous content may be waived (see 6.2) when they do not affect the product being packed. Blasted drums shall not contain evidence of grit used in the process. Variations in surface appearance due to cleaning are permitted. Care shall be taken not to harm the seaming compounds. Cleaning of interior or exterior of the tight head drum by the burning method shall not be permitted (see 3.2). All sharp edges and metal splinters shall be removed.

3.4.2 Painting. Unless otherwise specified after cleaning (see 6.2), the exterior surface of each drum shall be coated with paint specified in 3.1.2 and unless otherwise specified (see 6.2), the color shall be No. 24087 of FED-STD-595. The coating on all surfaces of the drum shall be dried hard. The dried coating shall be 0.8 mils minimum (see 4.3.4). The finished surface of each drum shall be free of hand and glove marks. When specified (see 6.2), the interior of open head drums shall be coated with paint as specified for the exterior and shall be the same color as exterior unless otherwise specified (see 6.2). The dried coating shall be not less than 0.8 mil. Closing rings and covers shall be painted separately.

3.4.3 Lining. Drums used to package corrosive materials that have a harmful effect on the drum, or vice versa, shall be lined on all internal surfaces, including removable head when applicable, with a material that will neither affect nor be affected by the material packaged. A suitable lining material, meeting the requirements of this specification shall be furnished by the supplier and a certificate of compliance of material(s) specified herein shall be provided upon request from the contracting officer or as required in the contract or order (see 4.1.1 and 6.2).

3.4.4 Fog spray for unlined drums. When specified (see 6.2), drums that have no interior coatings or lining shall be fog sprayed inside and gasket seats, if unplated or uncoated, shall be coated with rust preventive oil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

The spraying shall be done on a completely dried surface, after exterior painting has been completed and prior to the final insertion of plugs or removable head closures. The fog spray shall consist of between 20 cc (cubic centimeters) to 25 cc of rust preventive oil dispensed through an accurate metering device. The preservative oil shall conform to VV-L-800 except that the machine gun test is not required. The interior drum surface shall be completely wetted with the specified oil and there shall be no surplus oil collected in pools or rings in the bottom of the drum. The fog spray shall be applied in drums at temperature not exceeding 140°F. Air lines used for fogging shall have moisture traps to prevent condensate entering the drums. Closure plug shall be inserted immediately after fogging. Removable head closures shall be fogged prior to being attached to the drum.

3.5 Performance. Each reconditioned drum shall not leak when tested as specified in 4.3.2. Drums repaired after initial tests shall be retested. Repairs by welding shall be limited to the areas authorized herein.

3.6 Marking. Each reconditioned drum shall be legibly and durably marked with the applicable marking requirements of CFR 49 for reconditioned drums. The markings or symbols shall not be affected by water, gasoline, alcohol or by the product being packaged. Marking supplied by labels shall not come loose or become illegible when subjected to water, sun, or other shipping hazards. The marking shall be applied on the body within 10 inches of the top head. Other markings shall be in accordance with the provisions of the applicable regulations or rules of DOT, UFC, NMFC or CFR 49.

3.7 Qualification. In the event of any conflict between the requirements of this specification and DOT regulations, Rule 40 of Uniform Freight Classification or Item 260 of the National Motor Freight Classification for the type of drum ordered, the supplier, filler, or the reconditioner shall give the purchasing officer a statement in writing relating to the conflict and obtain instructions before proceeding with the supplying or filling of the drums, or submit to the contracting officer proof of a permit obtained from the Bureau of Explosives when the reconditioned drum is used for regulated products.

3.8 Workmanship. Reconditioned drums shall conform to the quality established by this specification. Drums that leak at the flanges or chimes shall be rejected. Drums that leak at the side seams shall be rejected or repaired by welding and retested.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

4 QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to test such items to determine the validity of certificates.

4.2 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except as specified herein.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced specifications, drawings, and standards, unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.2.2 In-process inspection.

4.2.2.1 Direct procurements. When reconditioned drums are procured by the Government as an end item of supply or when drums are reconditioned by the filler of a product procured by the Government, the drums shall be examined for conformance to this specification in accordance with 4.2.2.1.1 through 4.2.2.1.3. Whenever a nonconformance is noted, correction shall be made to the affected item and the process.

4.2.2.1.1 In-process examination of cleaning tight head drums. Prior to coating of the interior or exterior, three cleaned drums shall be selected at random during each 4 hours of production to determine compliance with 3.2. Evidence of cleaning tight head drums by the burning method shall be cause for rejection of that 4 hours of production.

4.2.2.1.2 In-process examination of dents, bulges, radial stress marks, and welds. Prior to coating, drums shall be inspected for compliance with 3.2, 3.2.4.7, 3.2.4.8, 3.2.5, 3.2.6, 3.2.7, and 3.3. Any nonconformance shall constitute a defect and the drum shall be rejected or repaired and retested except drums with radial stress marks on the bottom head shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

The inspection level shall be S-2 with an AQL 4.0 expressed in terms of defects per hundred units.

4.2.2.1.3 In-process testing of flanges. Prior to coating, drums shall be tested as specified in 4.3.3 for compliance with 3.2.4.2. Any nonconformance shall constitute a defect and the drum rejected, repaired or retested. The inspection level shall be S-2 with an AQL of 4.0 expressed in terms of defects per hundred units.

4.2.2.2 Indirect procurements. When reconditioned drums are used for the packing of a commodity being procured by the Government and the filler is not the reconditioner, the drums shall be examined in-process for conformance to this specification in accordance with 4.2.2.2.1 and tested in accordance with 4.2.2.2.2.

4.2.2.2.1 In-process examination of commodity drums. Prior to filling, the interior of drums shall be examined for compliance with 3.2. Evidence of nonconformance shall constitute a defect and the drum rejected. Tight head drums cleaned by the burning method shall cause rejection of the lot. The inspection level shall be S-2 with an AQL of 4.0 expressed in terms of defects per hundred units. One drum constitutes a unit.

4.2.2.2.2 In-process testing of commodity drums. Prior to filling, the drums selected in accordance with table II, shall be tested as specified in 4.3.1, 4.3.2, and 4.3.3. A certificate of compliance may be submitted as proof of passing these tests.

4.2.3 Examination of the end item. Drums selected in accordance with 4.2 shall be examined in accordance with acceptable quality levels (AQLs) and in table I. The lot size shall be expressed in units of drums. The sample unit for this examination shall be one drum. Any drum in the sample containing one or more defects shall be rejected and if the number of defective drums in any sample exceeds the acceptance numbers of that sample, the lot represented by the sample shall be rejected. Rejected lots may be offered again for Government inspection provided the supplier has removed all nonconforming drums. The inspection level shall be S-3 and the AQL shall be 1.5 major and 6.5 total expressed in terms of defects per hundred units

Examination paragraph	Inspection level	AQL	
		Major	Minor
4.2.3	S-3	1.5	6.5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

TABLE I. Examination of th end item

Examine	Defect	Classification Major	Classification Minor
Type or class	Not type or class specified	X	
Contour	Not contour of applicable type or class	X	
Heads:			
Top, head and cover	Welds in excess of 1/2 inch	X	
	Do not permit sealing	X	
	More than 2 welds within a square foot	X	
	Dents, protrusions, creases or bulges interfere with marking	X	
	Cover with gasket does not fit or provide a tight seal	X	
Flanges	Threads worn or damaged	X	
	Not clean		X
	Face not smooth	X	
Gaskets	Not new	X	
	Not as specified	X	
	Not thickness required to provide adequate seal	X	
Plugs	Not clean		X
	Not as specified	X	
	Worn or damaged threads	X	
	Ring lug not as specified	X	
Locking rings	Not as specified	X	
	Used rings not clean or free of defects that impair use	X	
False wire	Dents, nicks, fracture, cracks, open side seam or distortion that does not permit sealing	X	
Bottom heads	Sharp dents, sharp bulges radial stress marks, or welds	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

TABLE I. Examination of end item (cont'd)

Examine	Defect	Classification Major	Minor
Body or shell	Dents over 1/4 inch deep	X	
	Dents over 3 inches long	X	
	Dents that distract from appearance		X
	More than 6 dents per drum having dimensions of 1/4 inch deep and 3 inches long	X	
	Body welds over 1/2 inch	X	
	More than 2 body welds within a square foot	X	
	Repairs made with solder	X	
	Side seam repairs by welding over 3 inches	X	
Rolling hoops	Sharp dents, sharp creases, or excess pitting which weakens the drum	X	
Chimes	Not rolled tight	X	
	Fractured or cracked	X	
	Welded	X	
Finish:			
Cleaning	Gasket does not provide adequate seal	X	
	Loose rust or paint	X	
	Scale rust	X	
	Rattlers	X	
	Evidence of previous contents (odor) when objectionable	X	
	Foreign matter	X	
	Cleaning compound	X	
	Moisture or water when objectionable to the product being packed	X	
	Sharp edges and metal splinters	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

TABLE . Examination of end item (cont'd)

Examine	Defect	Classification Major	Classification Minor
Painting	Color, exterior and interior, when required, not as specified		X
	Not as specified	X	
	Blisters	X	
	Hand or glove marks		X
	Not dry to the touch		X
Linings	Not as specified	X	
Fog spray	Not as specified	X	
	Closure not inserted as specified	X	
Marking	Omitted, incomplete, incorrect, illegible	X	
	New identification missing when applicable	X	
	Marking not on body within 10 inches of top head		X
	Not durably marked	X	
	Affected by water, gasoline, alcohol or product being packed	X	
	Labels, when used, come loose or illegible when subjected to sun, water or shipping hazards	X	
	Not as specified for DOT, UFC, NMFC or CFR when applicable	X	

4.2.3.2 Dimensional examination. Inspection shall be made to determine compliance with specified dimensions of 3.2, PPP-D-729 and PPP-D-711 for the applicable type and class, as specified. Any deviation from specified dimensions shall constitute a defect. The inspection level shall be S-1 with an AQL of 2.5 expressed in terms of defects per hundred units.

4.2.3.3 Testing of the end item. The reconditioned drum shall be tested as specified in table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

TABLE II. End item testing

Test	Reference paragraph	Test results	Inspection level and AQL
Capacity	4.3.1	Fail or pass	S-1 and AQL of 2.5 defects per hundred units
Leaks	4.3.2	Fail or pass	Each drum shall be tested for leaks
Torque	4.3.3	Fail or pass	S-1 and AQL of 2.5 defects per hundred units
Paint	4.3.4	Fail or pass	S-1 and AQL of 2.5 defects per hundred units

4.2.4 Examination of preparation for delivery. The marking for shipment shall be examined for conformance to the requirements of section 5 of this specification.

4.3 Tests.

4.3.1 Capacity test. The total internal capacity of the drum, including volume of the convex head, shall be measured to determine compliance with 3.2.2.

4.3.2 Leakage test. All types I and V reconditioned drums shall be tested by internal pressure of 15 pounds per square inch (psi) and 7(psi) shall be applied to all other type drums for at least 5 seconds, while the drum is submerged in water in a lighted tank or other methods approved by the Department of Transportation, and inspected for leaks in accordance with 3.5. Leaking drums shall be rejected. Rejected leaking drums may be repaired and submitted for reinspection and test. Open head drums shall be tested without the top cover in place.

4.3.3 Torque test. The torque specified in 3.2.4.2 shall be applied to the inserted plugs and the flanges then checked to determine compliance with 3.2.4.2.

4.3.4 Paint thickness test. Paint thickness shall be measured on the head and side and not on the chime reinforcing ring or rolling hoops by a suitable instrument (see 6.3) to determine compliance with 3.4.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packing, level C. Drums shall be prepared in a manner to insure carrier acceptance and safe delivery to destination at the lowest transportation rate for such supplies Shipment shall be in accordance with National Motor Freight Classification or Uniform Freight Classification.

5.2 Marking.

5.2.1 Civil agencies. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with MIL-STD-123.

5.2.2 Military agencies. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the requirements of MIL-STD-129.

6. NOTES

6.1 Intended use. Reconditioned drums are intended for use by Government for shipment of noncorrosive material. The 20/18 or lighter gage drums should not be used for packing products having a melting point of less than 75°F.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type of drum required (see 1.2 and 3.2).
(c) Class drum required when type III is specified (see 1.2 and 3.2).
(d) Certification of gasket material required (see 3.2.4.3).
(e) When jam nuts are required (see 3.2.4.6).
(f) When requirement is to be waived (see 3.4.1).
(g) When painting is not required (see 3.4.2).
(h) When color other than specified is required (see 3.4.2).
(i) When painted interior is required and color if other than that of exterior (see 3.4.2).
(j) When lining and certificate of compliance for materials are required (see 3.4.3).
(k) When fog spray of unlined drums is required (see 3.4.4)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.

6.3 The following instruments may be used for measuring paint thickness

(1) Amico-Brenner Mag-Gage
American Instrument Company
Silver Spring, MD

(2) Elecometer
Henry Gardner Laboratory, Incorporated
Bethesda, MD

(3) G. R. Gage
General Electric Company
Schenectady, NY

(4) Lea Gage
Lea Manufacturing Company
Waterbury, CT

Custodians:

Army - GL
Navy - SA
Air Force - 69

Review activities:

Army - ME, AT
Navy - SH
Air Force - 68, 71, 84

User activities:

Army - CE
Navy - MC, YD

Preparing activity:

Army - GL

Civil Agency Coordinating Activities:

GSA-FSS
USDA-APS

Project No. 8110-0233

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 40 cents each

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:50Z
Check the source to verify that this is the current version before use.