
MILITARY SPECIFICATION SHEET

CAPACITORS, FIXED, CERAMIC DIELECTRIC (GENERAL PURPOSE),
STYLE CK62

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the capacitors described herein shall consist of this document and the latest issue of Specification MIL-C-11015.




| INCHES | MM |
|---|---|
| .001 | .03 |
| .004 | .10 |
| .025 | .64 |
| .040 | 1.02 |
| .060 | 1.52 |
| .120 | 3.05 |
| .375 | 9.53 |
| .550 | 13.97 |
| 1.250 | 31.75 |

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only and are based upon 1.00 inch = 25.4 mm.
3. Insulating coating shall not extend more than .125 (3.18 mm) along lead wires measured from a tangent to the coating surface drawn perpendicular to the lead wires.

FIGURE 1. Dimensions and configuration.

(E) denotes changes.



FSC 5910

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:55Z
Check the source to verify that this is the current version before use.

TABLE I. Style CK62 characteristics.

| Ⓔ Type designation 1/ | Rated voltage | Rated temperature and voltage-temperature limits | Capacitance | Capacitance tolerance |
|---|---|---|---|---|
| | Volts, dc | | pF | |
| CK62AY220M- | 1,500 | AY | 22 | M |
| CK62AY470M- | 1,500 | AY | 47 | M |
| CK62AY101M- | 1,500 | AY | 100 | M |
| CK62AY221M- | 1,500 | AY | 220 | M |
| CK62AY471M- | 1,500 | AY | 470 | M |
| CK62BX821K- | 500 | BX | 820 | K |
| CK62BX102-- | 500 | BX | 1,000 | K, M |
| CK62BX152-- | 500 | BX | 1,500 | K, M |
| CK62AX222-- | 500 | AX | 2,200 | K, M |
| CK62AW332M- | 500 | AW | 3,300 | M |
| CK62AW472M- | 500 | AW | 4,700 | M |
| CK62AW682M- | 500 | AW | 6,800 | M |

Ⓔ 1/ Where applicable, the complete type designation will include an additional symbol to indicate capacitance tolerance. The type designation will also include the letter "E" to indicate an epoxy coated capacitor (when applicable) or "-" will be deleted for wax impregnated case.

REQUIREMENTS

Design and construction:

Dimensions and configuration - See figure 1.

Ⓔ Case type - Disk, wax impregnated or epoxy coated (E).

Capacitance value - See table I.

Capacitance tolerance - ±10 percent (K) or ±20 percent (M) as shown in table I.

Rated temperature - -55° to +85°C (A) or -55° to +125°C (B) as shown in table I.

Dielectric withstanding voltage:

Dielectric (DWV): Method 301 of MIL-STD-202.

Test voltage - 250 percent of rated voltage for voltage-temperature limits W and X, or 200 percent of rated voltage for voltage-temperature limit Y.

Body insulation: In accordance with MIL-C-11015.

Test potential - 1,300 volts dc.

Barometric pressure (reduced): Method 105 of MIL-STD-202, condition B (50,000 ft) for voltage-temperature limit Y, or 0.82 inch of mercury (80,000 ft) for voltage-temperature limits W and X.

Test potential - 150 percent of rated voltage or 1,550 volts dc, whichever is less.

Insulation resistance (IR): Method 302 of MIL-STD-202, condition B. 200,000 megohms, minimum.



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:55Z
Check the source to verify that this is the current version before use.

Capacitance (Cap.): Method 305 of MIL-STD-202.

Test frequency:
100 pF or less - 1 MHz ±1 kHz.
Over 100 pF - 1 kHz ±100 Hz.

Test voltage - 1.0 ±0.2 volt rms.

Dissipation factor (DF): 1.5 percent, maximum (voltage-temperature limit X) or 2.0 percent, maximum (voltage-temperature limits W and Y).

Shock, medium impact: Method 205 of MIL-STD-202, condition C (50 G's).

Vibration, high frequency: Method 204 of MIL-STD-202, condition D (20 G's).

(E) Thermal shock and immersion:

Thermal shock: Method 107 of MIL-STD-202, condition A, except step 3 shall be at high test temperature.

Immersion: Method 104 of MIL-STD-202, condition B.

DWV - 250 percent of rated voltage for voltage-temperature limits W and X, or 200 percent of rated voltage for voltage-temperature limit Y.

IR - 150,000 megohms, minimum.

Salt spray (corrosion): Not applicable.

Terminal strength: In accordance with MIL-C-11015, 5 pounds applied.

Moisture resistance: Method 106 of MIL-STD-202.

DWV - 250 percent of rated voltage for voltage-temperature limits W and X, or 200 percent of rated voltage for voltage-temperature limit Y.

IR - 150,000 megohms, minimum.

Cap. - Within tolerance of table I value.

Solderability: Method 208 of MIL-STD-202. 2 terminals.

Resistance to soldering heat: Method 210 of MIL-STD-202, condition B.

IR - 200,000 megohms, minimum.

ΔCap. - ±5 percent of initial measurement.

ΔDF - 0.5 percent, maximum.

Voltage-temperature limits: In accordance with MIL-C-11015.

Life (at elevated ambient temperature): Method 108 of MIL-STD-202. 2,000 hours (for qualification); 250 hours (performance check); 1,750 hours (continuation test).

Test potential - 200 percent of rated voltage.

DWV - 250 percent of rated voltage for voltage-temperature limits W and X, or 200 percent of rated voltage for voltage-temperature limit Y (at 25°C).

IR - 100,000 megohms, minimum (at high temperature and 25°C).

Cap. - Within tolerance of table I value (at 25°C).

DF - 1.5 percent, maximum (voltage-temperature limit X) or 2.0 percent, maximum (voltage-temperature limits W and Y) (at 25°C).



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:55Z
Check the source to verify that this is the current version before use.

Marking: In accordance with MIL-C-11015.

Custodians:
Army - ER
Navy - EC
Air Force - 85

Review activities:
Army - MI
Navy - AS, OS, SH
Air Force - 11, 17
DLA - ES

User activities:
Navy - MC
Air Force - 19

Preparing activity:
Navy - EC

Agent:
DLA - ES

(Project 5910-1340-3)



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:55Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY
NAVAL ELECTRONIC SYSTEMS COMMAND
WASHINGTON, D.C. 20360

POSTAGE AND FEES PAID
NAVY DEPARTMENT
DOD 316

OFFICAL BUSINESS

COMMANDER
NAVAL ELECTRONIC SYSTEMS COMMAND
DEFENSE STANDARDIZATION PROGRAM BRANCH
DEPARTMENT OF THE NAVY
WASHINGTON, D. C. 20360

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:55Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS. The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

MIL C 11693/ME

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:55Z
Check the source to verify that this is the current version before use.