
MILITARY SPECIFICATION SHEET

CAPACITORS, FIXED, CERAMIC DIELECTRIC (GENERAL PURPOSE), STYLE CK60

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the capacitors described herein shall consist of this document and the latest issue of Specification MIL-C-11015.



INCHES	MM
.001	.03
.004	.10
.025	.64
.030	.76
.040	1.02
.060	1.52
.120	3.05
.250	6.35
.280	7.11
1.250	31.75

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only and are based upon 1.00 inch = 25.4 mm.
3. Insulating coating shall not extend more than .125 (3.18 mm) along lead wires measured from a tangent to the coating surface drawn perpendicular to the lead wires.

FIGURE 1. Dimensions and configuration.

(E) denotes changes.

FSC 5910

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:54Z
Check the source to verify that this is the current version before use.

TABLE I. Style CK60 characteristics.

Ⓔ Type designation 1/	Rated voltage	Rated temperature and voltage-temperature limits	Capacitance	Capacitance tolerance
	Volts, dc		pF	
CK60BX2R2K-	1,000	BX	2.2	K
CK60BX3R3K-	1,000	BX	3.3	K
CK60BX4R7K-	1,000	BX	4.7	K
CK60BX6R8K-	1,000	BX	6.8	K
CK60BX100K-	1,000	BX	10	K
CK60BX150K-	1,000	BX	15	K
CK60BX220K-	1,000	BX	22	K
CK60BX330--	1,000	BX	33	K, M
CK60BX470--	1,000	BX	47	K, M
CK60BX680--	1,000	BX	68	K, M
CK60BX101--	1,000	BX	100	K, M
CK60BX151--	500	BX	150	K, M
CK60AX221--	1,000	AX	220	K, M
CK60AX331--	500	AX	330	K, M
CK60AX471--	500	AX	470	K, M
CK60AW471M-	1,000	AW	470	M
CK60AW681M-	1,000	AW	680	M
CK60AW102M-	1,000	AW	1,000	M
CK60AW152M-	500	AW	1,500	M

Ⓔ 1/ Where applicable, the complete type designation will include an additional symbol to indicate capacitance tolerance. The type designation will also include the letter "E" to indicate an epoxy coated capacitor (when applicable) or "-" will be deleted for wax impregnated case.

REQUIREMENTS

Design and construction:

Dimensions and configuration - See figure 1.

Ⓔ Case type - Disk, wax impregnated or epoxy coated (E).

Capacitance value - See table I.

Capacitance tolerance - ±10 percent (K) or ±20 percent (M) as shown in table I.

Rated temperature - -55° to +85°C (A) or -55° to +125°C (B) as shown in table I.

Dielectric withstanding voltage:

Dielectric (DWV): Method 301 of MIL-STD-202.

Test voltage - 250 percent of rated voltage.

Body insulation: In accordance with MIL-C-11015.

Test potential - 1,300 volts dc.

Barometric pressure (reduced): Method 105 of MIL-STD-202. 0.82 inch of mercury (80,000 ft).

Test potential - 150 percent of rated voltage or 1,300 volts dc whichever is less.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:54Z
Check the source to verify that this is the current version before use.

Insulation resistance (IR): Method 302 of MIL-STD-202, condition B. 200,000 megohms, minimum.

Capacitance (Cap.): Method 305 of MIL-STD-202.

Test frequency:
100 pF or less - 1 MHz ±1 kHz.
Over 100 pF - 1 kHz ±100 Hz.

Test voltage - 1.0 ±0.2 volt rms.

Dissipation factor (DF): 1.5 percent, maximum (voltage-temperature limit X) or 2.0 percent, maximum (voltage-temperature limit W).

Shock, medium impact: Method 205 of MIL-STD-202, condition C (50 G's).

Vibration, high frequency: Method 204 of MIL-STD-202, condition D (20 G's).

(E) Thermal shock and immersion:

Thermal shock: Method 107 of MIL-STD-202, condition A, except step 3 shall be at high test temperature.

Immersion: Method 104 of MIL-STD-202, condition B.

DWV - 250 percent of rated voltage.

IR - 150,000 megohms, minimum.

Salt spray (corrosion): Not applicable.

Terminal strength: In accordance with MIL-C-11015, 5 pounds applied.

Moisture resistance: Method 106 of MIL-STD-202.

DWV - 250 percent of rated voltage.

IR - 150,000 megohms, minimum.

Cap. - Within tolerance of table I value.

Solderability: Method 208 of MIL-STD-202. 2 terminals.

Resistance to soldering heat: Method 210 of MIL-STD-202, condition B.

IR - 200,000 megohms, minimum.

ΔCap. - ±5 percent of initial measurement.

ΔDF - 0.5 percent, maximum.

Voltage-temperature limits: In accordance with MIL-C-11015.

Life (at elevated ambient temperature): Method 108 of MIL-STD-202. 2,000 hours (for qualification); 250 hours (performance check); 1,750 hours (continuation test).

Test potential - 200 percent of rated voltage.

DWV - 250 percent of rated voltage (at 25°C).

IR - 100,000 megohms, minimum (at high temperature and 25°C).

Cap. - Within tolerance of table I value (at 25°C).

DF - 1.5 percent, maximum (voltage-temperature limit X) or 2.0 percent, maximum (voltage-temperature limit W) (at 25°C).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:54Z
Check the source to verify that this is the current version before use.

Marking: In accordance witn MIL-C-11015.

Custodians:
Army - ER
Navy - EC
Air Force - 85

Review activities:
Army - MI
Navy - AS, OS, SH
Air Force - 11, 17
DLA - ES

User activities:
Navy - MC
Air Force - 19

Preparing activity:
Navy - EC

Agent:
DLA - ES

(Project 5910-1346-1)

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:54Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE
MIL-C-11015/9E

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*	TELEPHONE NO.
	DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 202610-17T14:54Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY
NAVAL ELECTRONIC SYSTEMS COMMAND
WASHINGTON, D.C. 20360

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
NAVY DEPARTMENT
DOD 316

U.S. MAIL

COMMANDER
NAVAL ELECTRONIC SYSTEMS COMMAND
DEFENSE STANDARDIZATION PROGRAM BRANCH
DEPARTMENT OF THE NAVY
WASHINGTON, D.C. 20360

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:54Z
Check the source to verify that this is the current version before use.