INCH-POUND
MIL-PRF-11015/10H
3 February 2023
SUPERSEDING
MIL-C-11015/10G
29 March 2013

PERFORMANCE SPECIFICATION SHEET


CAPACITOR, FIXED, CERAMIC DIELECTRIC (GENERAL PURPOSE),

STYLE CK61

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-C-11015.

INACTIVE FOR NEW DESIGN AFTER 31 MARCH 1999.
FOR REPLACEMENT PURPOSES ONLY.



Inches	mm
.001	0.03
.004	0.10
.025	0.64
.035	0.89
.040	1.02
.060	1.52
.120	3.05
.250	6.35
.350	8.89
1.250	31.75

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are in millimeters and are given for general information only.
3. Insulating coating shall not extend more than .125 inch (3.18 mm) along lead wires measured from a tangent to the coating surface drawn perpendicular to the lead wires.

FIGURE 1. Dimensions and configuration.

AMSC N/A
FSC 5910
DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:54Z
Check the source to verify that this is the current version before use.

TABLE I. Style CK61 characteristics.

Part or Indentifying Number (PIN) 1/	Rated Voltage (Volts, dc)	Rated temperature and voltage-temperature limits	Capacitance (pF)	Capacitance tolerance
CK61CZ2R2--	500	CZ	2.2	K, M
CK61CZ3R3--	500	CZ	3.3	K, M
CK61CZ4R7--	500	CZ	4.7	K, M
CK61CZ6R8--	500	CZ	6.8	K, M
CK61CZ100--	500	CZ	10	K, M
CK61CZ150--	500	CZ	15	K, M
CK61CZ220--	500	CZ	22	K, M
CK61CZ330--	500	CZ	33	K, M
CK61CZ470--	500	CZ	47	K, M
CK61CZ680--	500	CZ	68	K, M
CK61CZ101--	500	CZ	100	K, M
CK61CZ151--	500	CZ	150	K, M
CK61BX221--	500	BX	220	K, M
CK61CZ221--	500	CZ	220	K, M
CK61BX331--	500	BX	330	K, M
CK61CZ331--	500	CZ	330	K, M
CK61BX471--	500	BX	470	K, M
CK61CZ471--	500	CZ	470	K, M
CK61BX681--	500	BX	680	K, M
CK61AW222M-	500	AW	2,200	M

1/ Where applicable, the complete PIN will include an additional symbol to indicate capacitance tolerance. The PIN will also include the letter “E” to indicate an epoxy coated capacitor (when applicable) or “-“ will be deleted for wax impregnated case.

REQUIREMENTS

Dimensions and configuration: See figure 1.

Case type: Disk, wax impregnated or epoxy coated (E).

Capacitance value: See table I.

Capacitance tolerance: ± 10 percent (K) or ± 20 percent (M) as shown in table I.

Rated temperature: -55°C to +85°C (A), or -55°C to +125°C (B), or -55°C to +150°C (C), as shown in table I.

Dielectric withstanding voltage(DWV): In accordance with MIL-C-11015.

Dielectric:

Test voltage: 250 percent of rated voltage.

Body insulation:

Test potential: 1,300 volts dc.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:54Z
Check the source to verify that this is the current version before use.

Barometric pressure (reduced): In accordance with MIL-C-11015 and MIL-STD-202-105, .82 inch of mercury (80,000 ft).

Test potential: 150 percent of rated voltage.

Insulation resistance (IR): In accordance with MIL-C-11015 and MIL-STD-202-302, condition B. 200,000 megohms, minimum.

Dissipation factor (DF): 2.0 percent maximum.

Vibration, high frequency: In accordance with MIL-C-11015 and MIL-STD-202-204, condition D (20 g's).

Thermal shock and immersion: In accordance with MIL-C-11015.

DWV: 250 percent of rated voltage.

IR: 150,000 megohms, minimum.

Salt atmosphere (corrosion): Not applicable.

Terminal strength: In accordance with MIL-C-11015.

Moisture resistance: In accordance with MIL-C-11015.

DWV: 250 percent of rated voltage.

IR: 150,000 megohms, minimum.

Cap.: Within tolerance of table I value.

Solderability: In accordance with MIL-C-11015. 2 terminals.

Resistance to soldering heat: In accordance with MIL-C-11015.

IR: 200,000 megohms, minimum.

ΔCap.: $\pm$ 5 percent of initial measurement.

ΔDF: 0.5 percent, maximum.

Voltage-temperature limits: In accordance with MIL-C-11015.

Life (at elevated ambient temperature): In accordance MIL-C-11015.

Test potential: 200 percent of rated voltage.

DWV: 250 percent of rated voltage. (at +25°C).

IR: 100,000 megohms, minimum (at high temperature and +25°C).

Cap.: Within tolerance of table I value (at +25°C).

DF: 2.0 percent, maximum.

Marking: In accordance with MIL-C-11015.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:54Z
Check the source to verify that this is the current version before use.

Referenced documents: In addition to MIL-C-11015, this specification sheet references the following:

MIL-STD-202-105
MIL-STD-202-204
MIL-STD-202-302

Changes from previous issue: The margins of this specification sheet are marked with vertical lines to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements on this document on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
Navy - EC
Air Force – 85
DLA - CC

Preparing activity:
DLA - CC

(Project 5910-2023-011)

Review activities:
Army - MI
Navy – AS, OS, SH
Air Force – 19

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:54Z
Check the source to verify that this is the current version before use.