MIL-H-18911A (OS)
27 February 1974
SUPERSEDING
MIL-H-18911 (NOrd)
3 August 1955

See Section 6

MILITARY SPECIFICATION

HEADS AND MOTORS, ROCKET, INERT PARTS, PAINTING AND MARKING

This specification is approved for use by all departments and agencies of the Department of Defense

1. SCOPE

1.1 This specification covers the painting and marking of all types of rocket heads and motors by the manufacturer of inert parts. (See 6.1.)

2. APPLICABLE DOCUMENTS

* 2.1 The following documents of the issues in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein.

SPECIFICATIONS

Federal

TT-C-490	Cleaning Method and Pretreatment of Ferrous Surfaces for Organic Coatings
TT-I-558	Ink, Marking Stencil, Opaque, for Nonporous Surfaces (Metals, Glass, etc.)
TT-L-32	Lacquer, Cellulose Nitrate, Gloss, for Aircraft Use
TT-P-1757	Primer Coating, Zinc Chromate Low Moisture-Sensitivity

FSC 1340

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

Military

MIL-C-450	Coating-Compound, Bituminous Solvent Type, Black (For Ammunition)
MIL-P-3420	Packaging Materials, Volatile Corrosion Inhibitor, Treated, Opaque
MIL-C-5541	Chemical Conversion Coatings on Aluminum and Aluminum Alloys
MIL-I-8574	Inhibitors, Corrosion, Volatile, Utilization of
MIL-A-8625	Anodic Coatings, For Aluminum and Aluminum Alloys
MIL-P-15024	Plate, Tags and Bands for Identification of Equipment
MIL-C-16173	Corrosion Preventive Compound, Solvent Cutback, Cold-Application
MIL-P-16594	Projectiles, Bombs, Rockets, and Guided Missile Warheads, Inert Parts, Manufacture of
MIL-E-16663	Enamel, Semi-Gloss (For Metal Surfaces of Ammunition and Ammunition Containers)
MIL-H-19050	Heads, Rocket, Penetrative, Manufacture and Inspection of
MIL-P-22332	Paint, Priming, Exterior and Interior (For Ammunition)
MIL-G-81322	Grease, Aircraft, General Purpose Wide Temperature Range

STANDARDS

Federal

FED-STD-595	Colors

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-130	Identification Marking of U. S. Military Property

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

MS 603	Formula for Fuze Thread Luting (For Special Ammunition Use)
MIL-STD-709	Ammunition Color Coding

(Copies of specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 General.

* 3.1.1 All surfaces protected. All surfaces of rocket head and rocket motor components shall have either paint or rust preventive coatings applied except those surfaces specifically exempted by applicable paragraphs of this specification or by the applicable drawings. See requirements of MIL-P-16594 regarding discrepancies.

* 3.1.2 Dimensions of painted components. The dimensions and tolerances of all rocket components required to be painted shall apply prior to the application of the paint coatings.

* 3.2 Material. All material used shall comply strictly with the specifications and requirements listed herein and with the specifications and requirements shown on the applicable drawings prior to their use.

* 3.3 Surfaces to be painted. The surfaces to be painted shall be those specified in this specification or as indicated on the applicable drawings. Care shall be exercised in controlling the limits of painted areas in order to prevent the impingement of paint on any surface which may be specified, either herein or on the applicable drawings, to remain unpainted.

* 3.4 Surfaces not to be painted. Threads, electrical contact and electrical insulation surfaces, seating surfaces, bearing surfaces, bourrelets, retaining grooves, and such other surfaces as may be specified on the applicable drawings shall not be painted. The final protective treatment of unpainted surfaces shall be as specified in 3.6 and 3.8.2. Unless otherwise specified plated surfaces shall not be painted.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

3.5 Preparation of surfaces to be painted.

* 3.5.1 Steel surfaces. The surfaces of steel parts requiring painting shall be cleaned and otherwise prepared for painting in strict accordance with the requirements of TT-C-490.

* 3.5.1.1 Not-go gaging of steel threaded surfaces. Unless otherwise specified, steel threaded surfaces of parts which are to be prepared in accordance with TT-C-490 shall comply with not-go thread gaging requirements before application of phosphate coating in accordance with TT-C-490 and shall comply with all thread gaging requirements after application of phosphate coating. Prior to use of not-go gages, care shall be exercised that threads are clean and free from rust, chips, or other foreign matter.

* 3.5.2 Aluminum surfaces. Surfaces of aluminum parts shall be anodized in strict accordance with MIL-A-8625 and immediately thereafter painted as specified in the applicable portions of this specification. For aluminum rocket motor tubes which are required to be anodized, the inspection specimen for determination of compliance with MIL-A-8625 shall be a suitable portion of a motor tube which has been anodized. Upon specific approval of the procuring activity, chemical coating in accordance with MIL-C-5541 may be applied to aluminum parts to be painted.

3.5.3 Nonferrous metallic surfaces (other than aluminum). Surfaces of nonferrous (other than aluminum) metal parts shall be prepared for painting as directed by the procuring activity or as specified on the applicable drawing.

3.6 Preparation and treatment of unpainted surfaces.

* 3.6.1 Threaded, bearing, and seating surfaces of metallic components. All threaded, bearing, and seating surfaces of metallic components shall be cleaned and prepared for protective treatment the same as specified in 3.5 for surfaces to be painted. Unless otherwise specified in the applicable drawings, protective treatment in accordance with 3.6.1.1, 3.6.1.2, or 3.6.1.3, as applicable, shall then be applied. The applicable detail requirements for cleanliness of ferrous surfaces of TT-C-490 shall be met prior to application of protective treatment.

* 3.6.1.1 Permanent assemblies. The mating threaded, bearing, and seating surfaces of metallic components which are to be permanently assembled by the contractor, as indicated on the applicable drawings, shall, prior to assembly, be coated with fuze thread luting compound in

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

accordance with MIL-STD-603. After assembly, care shall be taken that the detail requirements of TT-C-490 for cleanliness of adjacent surfaces which are to be painted subsequent to assembly are complied with.

* 3.6.1.2 Semipermanent assemblies. The mating threaded, bearing, and seating surfaces of metallic components of semipermanent assemblies, as indicated on the applicable drawings, shall, prior to assembly, be coated with grease conforming to MIL-G-81322. A thin, even, continuous film shall be applied, covering all applicable surfaces. (Semipermanent assemblies are assemblies made by the contractor which are disassembled at ammunition depots or in the field).

CAUTION: Threaded and other surfaces of rocket heads and components thereof which are required to be coated with grease and which are adjacent to the interior cavity paint coated surfaces of the rocket heads (see para 3.8.1) shall be sparingly coated with a thin, even, continuous film of bearing grease, MIL-G-81322, avoiding contact with the cavity paint coating.

* 3.6.1.3 Components not assembled with mating components. Threaded, bearing, and seating surfaces of components not assembled by the contractor with mating components shall be coated with bearing grease, MIL-G-81322. A thin, even, continuous film shall be applied, covering all applicable surfaces.

* 3.6.2 Metallic surfaces other than threaded, bearing, and seating surfaces. Electrical contact, bourrelet, retaining groove surfaces, and the like of metallic components required to remain unpainted shall be cleaned and prepared for protective treatment the same as specified in 3.5 for surfaces to be painted. Unless otherwise specified, a thin, even, continuous film of rust preventive compound conforming to MIL-C-16173, grade 2, shall then be applied, covering all applicable surfaces. The applicable detail requirements for cleanliness of ferrous surfaces of TT-C-490 shall be met prior to application of rust preventive compound.

3.6.3 Nonmetallic surfaces. Surfaces of nonmetallic components, except those surfaces intended to be in contact with high explosives, shall not be painted or otherwise treated. See 3.8.3 for treatment of nonmetallic surfaces intended to be in contact with high explosives.

* 3.7 Preparation and treatment of nonthreaded permanent steel-aluminum assemblies. Mating surfaces of permanent nonthreaded assemblies involving

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

steel in contact with aluminum shall, prior to assembly, be cleaned and prepared in strict accordance with 3.5.1 for steel surfaces and 3.5.2 for aluminum surfaces. After preparation, the steel and aluminum mating surfaces shall be coated with primer, TT-P-1757; see 3.9 or 3.10, as applicable. On assembly, unbacked zinc chromate tape of sufficient width to assure complete separation of steel from aluminum surfaces shall be applied between the mating steel and aluminum surfaces. The final cover coating shall be applied, after assembly, as specified in this specification for the applicable surfaces.

3.8 Rocket heads and component parts thereof, interior surfaces.

* 3.8.1 Metallic surfaces in contact with high-explosive fillers. After cleaning and preparation of surfaces in strict accordance with the applicable portions of this specification, all interior metallic surfaces of each rocket head assembly, including the head cavity wall, and the applicable surfaces of base plugs, fuze adapters, and fuze liners, which will be in contact with high explosives after the head is loaded, as indicated on the applicable drawings, shall be completely covered (as evidenced by a dense black appearance on all areas so specified to be covered) with acid-proof black paint (cavity paint) conforming to MIL-C-450 or MIL-P-22332. Special precautions shall also be taken that internal cavities of rocket heads are thoroughly purged of all solvent vapors from the cavity paint and that the paint film (MIL-C-450 or MIL-P-22332) is thoroughly dry and hard (see 3.16) before the cavity is sealed for shipment as specified on the applicable drawings.

3.8.2 Metallic surfaces in contact with fillers other than high explosives. Unless otherwise specified, the interior metallic surfaces of rocket head assembles, including the head cavity wall, and the applicable surfaces of base plugs, fuze adapters, and fuze liners intended to be in contact with special purpose fillers other than high explosives shall not be painted.

3.8.2.1 Steel surfaces. Immediately after cleaning and surface preparation, the applicable steel surfaces shall be protected against subsequent corrosion by inserting a 4-ply tube of material conforming to MIL-P-3420 and immediately sealing the cavity securely by means of the plugs or other closures as specified in the applicable drawings. Unless otherwise specified, the tube shall be 0.750 ± 0.0625 inch O.D. and 0.012 inch minimum wall thickness, with length as specified in the applicable drawings. Except as specified above, the general requirements of MIL-I-8574 shall be complied with.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

3.8.2.2 Metallic surfaces other than steel. The applicable metallic surfaces other than steel shall be treated as specified in the applicable drawings or as specified by the procuring activity.

3.8.3 Nonmetallic surfaces. Surfaces of nonmetallic components intended to be in contact with high explosives after the head is filled shall be painted as specified for metallic surfaces in 3.8.1.

3.9 Painting of rocket heads and component parts thereof, exterior surfaces.

* 3.9.1 Metallic surfaces. Exterior metallic surfaces of rocket head assemblies and accessories, such as shipping plug and thread protectors, required to be painted as indicated on the applicable drawings, after having been cleaned and prepared for painting in accordance with the applicable portions of this specification, shall be painted with one coat of zinc chromate primer conforming to TT-P-1757 followed by one cover coat of semi-gloss enamel conforming to MIL-E-16663. Dry-film thickness of the primer shall be not less than 0.0003 inch and not more than 0.0007 inch. Dry-film thickness of the enamel shall be not less than 0.001 inch.

3.9.1.1 Exterior surfaces of rocket heads to contain explosive. For rocket heads which are to be used with high explosive fillers only, i.e., for those rocket heads in which the interior surfaces are coated with cavity paint in accordance with 3.8.1, the exterior surfaces of the detail piece which has the cavity paint coating shall, unless otherwise specified by the procuring activity, be coated with primer only in accordance with 3.9.1, omitting the final enamel cover coat. The exterior surfaces of accessories for these heads, such as shipping plugs and thread protectors, shall, unless otherwise specified, be completely painted with primer and cover coat in accordance with 3.9.1.

CAUTION: Since the rocket heads are to be painted subsequently with the final cover coat by the loading depot, after high explosive loading, special precaution shall be taken that the prime coated surfaces of the rocket heads are free from grease, dirt, or any other contamination which would prevent firm adhesion of the final cover coat to the prime coated surfaces.

* 3.9.2 Color of final coating. The color of the final coating shall be in accordance with MIL-STD-709.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

* 3.10 Painting of rocket motors.

* 3.10.1 Painting of rocket motors and component parts thereof, interior surfaces. Interior surfaces of rocket motors required to be painted shall, after cleaning and preparation for painting in accordance with this specification, be coated with one coat of zinc chromate primer, conforming to TT-P-1757. Dry-film thickness shall be not less than 0.0003 inch nor more than 0.001 inch.

* 3.10.2 Painting of rocket motors and component parts thereof, exterior surfaces. Exterior surfaces of rocket motor assemblies and all surfaces of accessories, such as thread protectors, shipping plugs, and caps required to be painted, after cleaning and preparation in strict accordance with this specification, shall be painted with one coat of zinc chromate primer conforming to TT-P-1757, followed by one coat of semigloss enamel, conforming to MIL-E-16663 or TT-L-32. Dry-film thickness of the primer shall be not less than 0.0003 inch and not more than 0.0007 inch. Dry-film thickness of the enamel shall be not less than 0.001 inch.

* 3.10.2.1 Aircraft rocket motors shall be treated with chemical film in accordance with MIL-C-5541 followed by final color coat specified on the applicable drawing.

* 3.10.3 Color of final coating.

* 3.10.3.1 Blue gray. The color of the final coating of rocket motors shall match the blue gray color 26231 of FED-STD-595. Aircraft rocket motors shall be painted gloss white color 17875 of FED-STD-595.

* 3.10.3.2 Blue. The color of the final covering coating of all dummy or inert loaded rocket motors intended for use as the rocket motor portion of dummy rocket round assemblies shall match the blue color 35109 of FED-STD-595.

* 3.11 Stencilled identifying legend marking of inert parts assemblies.

3.11.1 Use. For rocket heads which have the exterior surfaces coated with primer only, in accordance with paragraph 3.9.1.1, the stencilled identification legend shall be omitted. The stencilled identification legend shall be applied by the manufacturer of inert parts to all rocket heads which are coated with the final cover coat and to all rocket motors.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

* 3.11.2 Characters. Arabic numerals and upper case letters shall be used. Periods after abbreviations shall be omitted, but decimal points in fractional quantities and hyphens in compound words or abbreviations shall be shown. Unless otherwise specified on the applicable drawings, the size of the characters shall comply with the following:

Nominal diameter of rocket head or motor	Size of characters
2.5 inches less	3/16 inch
Above 2.5 inches to and including 3.5 inches	3/8 inch
Above 3.5 inches	1/2 inch
Spacing between all lines	1/4 inch

* 3.11.3 Orientation. The identifying legend shall be located as indicated on the applicable drawings with the markings reading parallel to the longitudinal axis of the rocket and with the left-hand edge of the legend toward the nose end of the rocket. Where circumferential marking is specified, the top edge of the legend shall be toward the nose end of the rocket.

* 3.11.4 Identifying legend. The legend shall consist of the following data:

(1) IN ROCKET (2) MK (3) MOD (4)

(5)

CONT NO (6) LOT (7)

(8) (9)

Key to insertions: (omit parentheses)

For insertion number:

(1) Insert nominal caliber of item (inches), in accordance with the applicable drawing.

(2) Insert "HEAD" or "MOTOR" as applicable.

(3) & (4) Insert applicable mark and mod numbers, in accordance with the applicable drawings.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

(5) Insert drawing number and revision letter of applicable inert parts assembly.

(6) Insert applicable contract number as defined in the contract.

(7) Insert lot number. Lot numbers shall run consecutively beginning with number 1 for the first lot of any modification manufactured by a contractor (see 4.3).

(8) Insert contractor's initials or approved contractor's identifying symbol.

(9) Insert inspector's Department of Defense acceptance stamp.

* 3.11.5 Application. Marking shall be applied by stencilling, by rubber stamping, or by such other processes as may be approved by the procuring activity. Marking ink conforming to TT-I-558 shall be used for the stencilling or rubber stamping processes.

* 3.11.6 Color. The color of the marking ink shall be in accordance with MIL-STD-709.

3.12 Indented manufacturer's code symbol identification marking of inert parts assemblies (see 4.4.4).

* 3.12.1 Characters. Arabic numerals and upper case letters shall be used. Periods after abbreviations shall be omitted, but decimal points in fractional quantities and hyphens in compound words or abbreviations shall be shown. Unless otherwise specified on the applicable drawings, the size of the characters shall comply with the following:

Nominal diameter of rocket head or motor	Size of characters
2.5 inches and less	3/32 inch
Above 2.5 inches to and including 3.5 inches	1/8 inch
Above 3.5 inches	1/4 inch

* 3.12.2 Location and orientation. The indented manufacturer's code symbol shall be located as indicated on the applicable drawings. Where marking reading parallel to the longitudinal axis of the rocket is speci-

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

fied, the left hand edge of the marking shall be toward the nose end of the rocket. Where circumferential marking is specified, the top edge of the marking shall be toward the nose end of the rocket.

* 3.12.3 Manufacturer's code symbol. The indented manufacturer's code symbol shall consist of the following data (it should be noted that caliber is omitted):

MK (1) - (2) LOT (3) (4) (5)

Key to insertions: (Omit parenthesis)

For insertion number:

(1) and (2) Insert applicable Mark and Mod numbers, in accordance with the applicable drawings.

(3) The insertion for (3) shall be the code number designating the type of inert parts assembly in accordance with the following:

Inert parts assembly	Code number
Rocket Head	3
Rocket motor	4

(4) Insertion shall be a symbol which will usually be a letter symbol which will be assigned to each manufacturer and which shall apply to all inert parts assemblies of any one particular type manufactured by the particular contractor.

(5) Insert same lot number as in stencilled or rubber stamped identifying legend as specified in insertion (7) of 3.12.4.

* 3.12.4 Typical manufacturer's code symbol identification. A typical manufacturer's code symbol identification would be MK 17-2 LOT 4A157 which would indicate Lot 157 of Rocket Motor Mk 17 Mod 2 manufactured by a contractor identified by the symbol A.

* 3.12.5 Application. The manufacturer's code symbol identification shall be stamped or otherwise suitably indented into the proper surfaces in the location specified on the applicable drawings. The marking shall be readily legible and arranged in an orderly manner. Burrs raised by stamping shall be removed (see 4.4.4). It should be expressly noted that when application of marking is specified on thin-walled rocket motor tubes, precautions should be taken, by use of plugs or equivalent support on the inside diameter, to prevent deformation of the inside diameter surfaces of the motor tube during application of the marking. (See 4.4.4.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

* 3.13 Identification of rocket motor components and accessories. Identification markings in accordance with MIL-STD-130 and MIL-P-15024 shall be placed on components of rocket motor assemblies and accessories as specified on the applicable drawings. (See 4.4.4.)

* 3.14 Identification of rocket head components and accessories. Identification markings in accordance with MIL-STD-130 and MIL-P-15024 shall be placed on components of rocket head assemblies and accessories as specified on the applicable drawings. (See 4.4.4.)

* 3.15 Workmanship. All workmanship shall be first class in every respect. Every precaution shall be taken that surfaces are cleaned and prepared for painting or application of other preservatives in strict accordance with the provisions of this specification. All surfaces shall be dry upon application of paint or other preservative. Paint shall be evenly applied, and in general the thickness of each coat shall be limited to the minimum necessary to comply with all requirements in the applicable specifications. The paint film on all painted surfaces shall completely cover those surfaces which are intended to be coated with paint and shall be hard, tough, adherent, smooth, continuous unbroken, and shall be thoroughly dry prior to packaging for shipment. When both a primer coat and final coat are applied, the final coat shall completely hide the primer coat. Preservatives, such as bearing grease and rust preventive compound, shall be applied in such a manner that the applicable surfaces are completely, uniformly, continuously, and adequately covered. Care shall be exercised in handling and in packaging for shipment that preservative coatings remain continuous and unbroken.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 The supplier shall be responsible for assuring that the dimensions and tolerances of all rocket components required to be painted conform to the requirements of the applicable drawings before painting.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

* 4.2 Quality conformance inspection. Rocket heads and motors shall, during the process of manufacture and assembly, be subject to such sampling, inspection, and testing as specified herein to determine that all cleaning, painting, preservative, and marking processes, procedures, and workmanship are in accordance with the applicable drawings, specifications, and terms of the contract order or requisition.

* 4.2.1 Sampling. Unless otherwise specified, the sampling plans and procedures used in the determination of the acceptability of products submitted by a supplier shall be in accordance with the provisions of MIL-STD-105. (See 6.2d.)

* 4.3 Production lot. Unless otherwise specified in the contract or order, the lot size of rocket heads (except penetrative heads) and rocket motors 5.0-inch caliber and less shall consist of 2000 rocket heads and motor respectively. Lot size of penetrative heads shall be as defined in MIL-M-19050. Lot size of rocket heads and motors larger than 5.0-inch caliber shall be as specified in the contract or order.

* 4.4 Inspection.

* 4.4.1 Visual examination. The heads and motors shall be examined visually at each step in the painting process as necessary to ensure that the finished product conforms to the requirements of this specification. The defects shall be classified as follows:

Examine	Defect
All surfaces	Absence of protective coating (paint or rust preventive compound) on any surface except those specifically exempted (see 3.1.1).
Unpainted surfaces	Impingement of paint or other surface treatment on any surface specified to remain unpainted (see 3.3, 3.4, 3.6.3, and 3.8.2).
	Rust preventive compound not applied to metallic surfaces as specified (see 3.6.2).
Mating surfaces - steel to aluminum	Primer coating not applied as specified (see 3.7).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

	Zinc chromate tape not applied as specified (see 3.7).
Metallic surfaces in contact with high explosive fillers	Black coating compound not applied as specified, not dry, not hard.
	Presence of solvent vapors.
Interior steel surfaces	Volatile corrosion inhibitor treated material not applied as specified (see 3.8.2.1).
Painted surfaces	Absence of primer coating or enamel on any surface specified to be painted.
	Paint unevenly applied.
	Paint thicker than necessary.
	Paint not hard, tough, adherent, smooth, continuous, unbroken, or thoroughly dry.
	Final coat does not completely cover primer coat.
	Color not as specified (see 3.9.2, 3.10.3.1, and 3.10.3.2).
Marking	Not clear.
	Not legible.
	Not specified size.
	Not in conformance to code specified herein.

* 4.4.2 Inspection of preparation of surfaces to be painted.

* 4.4.2.1 Steel surfaces. Steel surfaces shall be inspected before painting in accordance with TT-C-490 to ensure that they have been cleaned and otherwise prepared for painting in conformance to all applicable requirements. Threaded steel surfaces shall be not-go gaged before and after application of phosphate coating in accordance with TT-C-490 (see 3.5.1 and 3.5.1.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

* 4.4.2.2 Aluminum surfaces. Aluminum surfaces to be anodized or coated in accordance with MIL-A-8625 or MIL-C-5541 shall be inspected before painting to ensure that the treatments conform to this specification and the applicable referenced specifications. For aluminum rocket motor tubes which are required to be anodized, the inspection specimen for determination of compliance with MIL-A-8625 shall be a suitable portion of a motor tube which has been anodized (see 3.5.2).

* 4.4.2.3 Nonferrous metallic surfaces (other than aluminum). Nonferrous metallic surfaces (other than aluminum) shall be inspected to determine conformance to the applicable drawing or to the directions of the Naval Ordnance Systems Command (see 3.5.3).

* 4.4.3 Inspection of threaded, bearing, and seating surfaces of metallic components..

4.4.3.1 Permanent assemblies. The threaded, bearing, and seating surfaces of permanent assemblies shall be inspected to ensure that fuze thread luting compound has been applied in conformance to MS 603. Adjacent surfaces which are to be painted subsequent to assembly shall be inspected to determine conformance to the cleanliness requirements of TT-C-490 (see 3.6.1.1).

* 4.4.3.2 Semipermanent assemblies and components not assembled with mating components. Semipermanent assemblies and components not assembled with mating components shall be inspected to ensure that a thin, even, continuous film of general purpose aircraft grease, MIL-G-81322, has been applied as specified (see 3.6.1.2 and 3.6.1.3).

* 4.4.3.2.1 Contact with black coating compound. All surfaces coated with grease which are adjacent to surfaces coated with black coating compound shall be inspected to ensure that there is no contact between the grease and the coating compound (see 3.6.1.2).

* 4.4.4 Burrs and deformation caused by stamping. Failure to gage after stamping of manufacturer's code symbol or component identification marks shall be considered sufficient cause for rejection. In addition, failure to comply with requirements for inside diameter of thin motor tube surfaces after stamping, due to deformation of these surfaces, shall be considered sufficient cause for rejection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 This section is not applicable to this specification.

6. NOTES

6.1 Intended use. The purpose of this specification is to standardize the painting and marking of all rocket heads and motors manufactured for, and used by, the U. S. Navy.

* 6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Color of final coating and band(s) marking.
(c) Designation of rocket heads and motors to be painted and marked and listing of applicable drawings.
(d) AQL's to be applied to the defect classification.

* 6.3 Supersession data. This specification includes the requirements of MIL-H-18911 (NOrd) dated 3 August 1955 and NAVORD OS 3378 dated 10 September 1954. When drawings, etc., refer to these superseded documents, this specification applies.

* 6.4 The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian:
Navy - OS

Preparing activity:
Navy - OS
(Project No. 1340-N388)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION MIL-H-18911A (OS), Heads and Motors, Rocket, Inert Parts, Painting and Marking

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

S/N-0102-014-1801 C-25254

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:05Z
Check the source to verify that this is the current version before use.