INCH-POUND


MIL-DTL-32480/2A
28 May 2020
SUPERSEDING
MIL-DTL-32480/2
29 August 2014

DETAIL SPECIFICATION SHEET

FITTING, ADAPTER, 45 DEGREE ELBOW, HYDRAULIC AND PNEUMATIC, FLARELESS MALE TO ORFS MALE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-32480.



Dash size	Tube OD nom. inches (mm)	T ORFS SAE J1453-1	TT Flareless SAE AS8879	L inches (mm) ±.04 (1.0)	M inches (mm) ±.04 (1.0)
-4	.2500 (6.350)	0.5625-18UNF-2A	.4375-20 UNJF-3A	.630 (16.00)	.720 (18.29)
-6	.3750 (9.525)	0.6875-16UN-2A	.5625-20 UNJF-3A	.750 (19.00)	.830 (21.08)
-8	.5000 (12.700)	0.8125-16UN-2A	.7500-16 UNJF-3A	.809 (20.50)	.980 (24.89)
-10	.6250 (15.875)	1.0000-14UN-2A	.8750-14 UNJF-3A	.925 (23.50)	1.110 (28.19)
-12	.7500 (19.050)	1.1875-12UN-2A	1.0625-12 UNJ-3A	1.023 (26.00)	1.280 (32.51)
-16	1.0000 (25.400)	1.4375-12UN-2A	1.3125-12 UNJ-3A	1.181 (30.00)	1.470 (37.34)
-20	1.2500 (31.750)	1.6875-12UN-2A	1.6250-12 UNJ-3A	1.260 (32.00)	1.590 (40.39)
-24	1.5000 (38.100)	2.0000-12UN-2A	1.8750-12 UNJ-3A	1.467 (37.00)	1.780 (45.21)

See notes at end of figure.

FIGURE 1. 45° elbow, flareless to ORFS adapter.

AMSC N/A

FSC 4730

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:34Z
Check the source to verify that this is the current version before use.

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for information only.
3. Break all sharp edges and remove all burrs and slivers.
4. Dimensions and tolerances not shown shall be in accordance with the following:
   a. SAE AS4375 style G for flareless end.
   b. SAE J1453-3*520801* for ORFS male end.
   c. SAE J514*080302* for body.

FIGURE 1. 45° elbow, flareless to ORFS adapter - Continued.

REQUIREMENTS:

Fittings shall be as specified on figure 1 and in table I.

Materials and finishes shall be in accordance with MIL-DTL-32480.

Dimensions. All dimensions not specified on figure 1 shall be in accordance with SAE AS4375 for the flareless end, SAE J1453-3 for the ORFS end and SAE J514 for the body.

Across flat widths. Across flat widths shall fit standard wrench openings, see ASME B18.2.2, size shall be in accordance with SAE J514 for the body, SAE AS4375 for the flareless end, and SAE J1453-3 for the ORFS end.

Inside diameter. The inside diameter shall be in accordance with SAE AS4375 for the flareless end and in SAE J1545-3 for the ORFS end, drill depth shall be optional with manufacturer.

Wall thickness. Wall thickness shall be in accordance with SAE AS4375 for the flareless end and SAE J1453-3 for the ORFS end.

Body thickness. The radius and body thickness shall conform to SAE J514.

Material and finish designators. Material and finish designators shall be as specified in table I.

Plating's. Unless otherwise specified, all plating's shall be capable of meeting a minimum of 96 hours salt spray test in accordance with ASTM B117. The fittings shall show no evidence of red corrosion after 96 hours of salt spray. Fluid passages, other openings, and internal threads shall not be subject to the plating thickness requirement and may have bare areas provided they are protected with a light film of oil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:34Z
Check the source to verify that this is the current version before use.

TABLE I. Material and finish identification codes.

PIN code material/plating finish	Material	Plating finish
Blank	Steel	Cadmium plating in accordance with SAE-AMS-C-81562, type II, class 2 or SAE-AMS-QQ-P-416, type II, class 2. 1/ 5/ 7/
H	Steel	Zinc-aluminum in accordance with ASTM F1136/F1136M, grade 3, NC.
J	Steel	Zinc-nickel in accordance with SAE-AMS2417, type 2, grade B. 2/
KA	Steel 4130 or 4140	Zinc Nickel Electroplate, MIL-PRF-32647, Type K20 torque/tension modifier. 3/ 4/ 9/
KB	Steel 4130 or 4140	Zinc Nickel Electroplate, MIL-PRF-32647, Type K16 torque/tension modifier. 3/ 4/ 9/
M	Nickel-copper alloy UNS N04400	No additional finish.
N	High-chromium nickel alloy UNS N06690	No additional finish.
P	Steel	Zinc phosphate finish in accordance MIL-DTL-16232 type Z, class 1. 4/
R	Steel	Zinc plating in accordance with ASTM B633, type V, Fe/Zn 8. 4/
S	Corrosion resistant steel	No additional finish. Passivation in accordance with SAE-AMS2700, method 1, type 6 or 7.
T	Titanium	Anodize in accordance with SAE-AMS2488 type 2. 6/ 8/
TF	Titanium	Fluoride phosphate in accordance with SAE-AMS2486. 6/ 8/
Z	Steel	Zinc plating in accordance with ASTM B695, type II, class 8. 4/ 5/
ZC	Steel	Zinc may be any zinc plating from PIN codes J and R with a colored chromate coating. 4/ 5/
ZF	Steel	Zinc plating in accordance with ASTM B633, type VI, class 8. 4/

1/ Embrittlement test need not be run.
2/ The zinc-nickel alloy plate shall contain 12% to 16% nickel. The coating thickness shall be 315µ inches (8µm) minimum.
3/ Corrosion requirements shall be in accordance with MIL-PRF-32647.
4/ Not for use in aircraft. Requires approval from the Program Office for all applications. Zinc-plated materials should be avoided in hydraulic systems with water-glycol fluids. Reference ASTM MNL37 - Fuels and Lubricants Handbook.
5/ These finishes have a chromate conversion coating which includes hexavalent chromium and are not recommended for Army ground systems. The use of coatings depositing hexavalent chromium for Army hexavalent chromium ground vehicles is prohibited unless otherwise explicitly stated in the contract as a requirement. For new designs PIN codes Blank, P, Z, and ZC are not to be supplied to Army and Marine ground forces.
6/ A pretreatment, a modification of the fluoride treatment, or a post treatment shall be applied so the final color of the fittings shall be similar to SAE-AMS-STD-595 colors 36076 through 36293.
7/ Cadmium shall not be used in oxygen or potable water systems. Cadmium is prohibited from use in NAVSEA-owned shipboard systems in accordance with the requirements of T9070-AL-DPC-020/077-2, unless otherwise approved by NAVSEA. The use of cadmium plating for Army and Marine ground vehicles is prohibited unless otherwise explicitly stated in the contract as a requirement. Pin code J or KB may be substituted for cadmium (blank PIN code) for Army ground vehicle applications.


Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:34Z
Check the source to verify that this is the current version before use.

8/ Army and Marine ground vehicle applications. MIL-PRF-32647 Type KA is intended as a hazardous free plating material and is a direct replacement for zinc plating with hexavalent chromium conversion coating. Type KB is a hazardous free plating material and is a direct replacement for cadmium plating. KA and KB plating's have equivalent torque/tension behavior as the plating they replace.

9/ Titanium shall not be used in oxygen or potable water systems.

Maximum operating pressure. Maximum operating pressure shall be in accordance with MIL-DTL-32480.

Part or Identifying Number (PIN): The PIN consists of the letter M, the basic specification number, the specification sheet number, fitting dash size, and a letter for the material finish designator.



PIN example: M32480 /2-10KB indicates a male 45° elbow adapter, .6250 inch (15.875 mm), steel with zinc nickel electroplate finish.

O-ring is not supplied. Order separately, see MIL-DTL-25988.

Cadmium is not recommended. To the users of this document, it is recommended that the use of carbon steel material with cadmium plating be used only when other materials and finishes specified in this document cannot meet performance requirements.

Cadmium is prohibited from use in NAVSEA owned shipboard systems in accordance with the requirements of T9070-AL-DPC-020/077-2.

For new designs PIN codes Blank, P, Z, and ZC are not to be supplied to Army and Marine ground vehicles.

Class I and II ODS shall not be used in MIL-DTL-32480/2 or any referenced procedures.

Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue, due to the extent of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:34Z
Check the source to verify that this is the current version before use.

Referenced documents. In addition to MIL-DTL-32480, this document references the following:

MIL-DTL-16232	SAE-AMS-STD-595/36081	SAE-AMS-STD-595/36293
MIL-DTL-25988	SAE-AMS-STD-595/36099	SAE-AMS2417
MIL-PRF-32647	SAE-AMS-STD-595/36118	SAE-AMS2486
ASME B18.2.2	SAE-AMS-STD-595/36134	SAE-AMS2488
ASTM B117	SAE-AMS-STD-595/36152	SAE-AMS2700
ASTM B633	SAE-AMS-STD-595/36170	SAE-AS4375
ASTM B695	SAE-AMS-STD-595/36173	SAE AS8879
ASTM F1136/F1136M	SAE-AMS-STD-595/36176	SAE-J514
ASTM MNL37	SAE-AMS-STD-595/36231	SAE J515
SAE-AMS-C-81562	SAE-AMS-STD-595/36251	SAE J1453-1
SAE-AMS-QQ-P-416	SAE-AMS-STD-595/36270	SAE J1453-3
SAE-AMS-STD-595/36076	SAE-AMS-STD-595/36280	T9070-AL-DPC-020/077-2

CONCLUDING MATERIAL

Custodians:
Army - AT
Navy - AS
Air Force - 71
DLA - CC

Preparing activity:
DLA - CC

(Project 4730-2020-045)

Review activities:
Army - AR
Navy - CG, MC, SA, SH

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:34Z
Check the source to verify that this is the current version before use.