AMENDMENT

TO

INTERIM FEDERAL SPECIFICATION

COATING, CLEAR (SATIN-FINISH), POLYURETHANE, LATEX, FOR INTERIOR USE

This amendment was developed by the General Services Administration, Federal Supply Service, Washington, DC 20406, based upon currently available technical information. The General Services Administration has authorized the use of this amendment as a valid exception to Interim Federal Specification TT-C-001951, dated March 16, 1976.

PAGE 2

Under "American Society for Testing and Materials (ASTM) Standards", delete "D 3335 - Determination of Low Concentrations of Lead by Atomic Absorption Spectroscopy".

PAGE 3

Table I, last line, change the maximum requirement for lead content from "0.5" to "0.06".

Table II, line 8, delete "D 3335" under ASTM.

PAGE 5

Paragraph 4.3.12, delete in its entirety and substitute the following:

4.3.12 Lead content.

4.3.12.1 Sample preparation. Using a 0.006-inch film applicator and a mechanical applicator plate, duplicate drawdowns for each sample of well-mixed paint shall be made on a standard paint penetration chart and dried for 24 hours. The drawdown shall be at least 10 inches long on the sealed portion of the penetration chart. The drawdown shall be cut into discs of appropriate size to fit the sample holder of a fluorescence X-ray spectrometer.

4.3.12.2 Procedure. Lead content shall be determined using an X-ray fluorescence spectrometer capable of determining lead content at a minimum level of 0.03 percent by weight of the total nonvolatile. The settings for a wavelength dispersive fluorescence spectrometer shall be as follows: (1)

Element	Analytical Line	Angle	Crystal	Detection	Collimeter	X-ray tube (MO)
Pb	L	33.93	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Pb (backgrd I)		33.00	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Pb (backgrd II)		35.50	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Mo	K	20.33	LiF(200)	Flow S.C.	Fine	60Kv 45Ma

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

Pulse height selection shall be used in all measurements, and counting time shall be 100 seconds. Place the sample disc in the wavelength dispersive unit. Measure the count rates of lead, lead background, and the Molybdenum Compton scattered background from the X-ray tube.

4.3.12.3 Calculation.

$$R = \frac{I_{Pb} - \frac{I_{Pb}\ (\text{Background I}) + I_{Pb}\ (\text{Background II})}{2}}{I_{Mo}}$$

where I equals gross intensity. These results shall be compared to those obtained using a 0.06 percent lead standard made up from the same type of paint sample, and evaluated for compliance with the requirement in table I.

(1) Energy dispersive fluorescence spectrometers shall be set up according to the manufacturer's manual.

GSA DC 77-7803

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:19Z
Check the source to verify that this is the current version before use.