TT-P-1728A
AMENDMENT-1
June 23, 1977

FEDERAL SPECIFICATION

PAINT, LATEX BASE, INTERIOR, FLAT, DEEP-TONE

This amendment, which forms a part of Federal Specification TT-P-1728A, dated February 4, 1974, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 1

Under Federal Specification, change "TT-P-143" to "PPP-P-1892".

PAGE 2

Under American Society for Testing and Materials (ASTM) Standards:

Delete:

D 2088 - Determination of Low Concentrations of Lead in Paint.

and add the following:

D 562 - Test for Consistency of Paints Using the Stormer Viscosimeter.
D 1210 - Test for Fineness of Dispersion of Pigment-Vehicle Systems.
D 1296 - Test for Odor of Volatile Solvents and Diluents.
D 2369 - Test for Volatile Content of Paints.
E 97 - Test for 45-Deg, 0-Deg Directional Reflectance of Opaque Specimens by Filter Photometry.

Table I, last line, under maximum. Change "0.5" to "0.06".

Paragraph 4.4 and table III. Delete and substitute:

4.4 Test procedures. The paint shall be tested as indicated in table III and as hereinafter specified.

TABLE III. Index

Characteristics	Requirement Reference	Test Method		Paragraph Reference
		Fed. Test Method Std. No. 141	ASTM Method	
Condition in container	3.3.1	3011	----	4.4.1
Consistency	Table I	----	D 562	-----
Nonvolatile	Table I	----	D 2369	-----
Dry hard time	Table I	4061 1/	----	-----
Opacity, dry	Tables I and II	5121 2/	----	-----
Opacity, wet	Tables I and II	----	----	4.4.12
85° specular gloss (sheen)	Table I	6103	----	-----
Fineness of grind	Table I	----	D 1210	-----
Lead content	Table I	----	----	4.4.14
Color	3.3.2	4250	----	4.4.2
Flexiblity	3.3.3	6221	----	4.4.3
Working properties	3.3.4	----	----	4.4.4
Appearance	3.3.5	----	----	4.4.5
Odor	3.3.6	----	D 1296	-----
Self-lifting properties	3.3.7	----	----	4.4.4
Streaking	3.3.8	----	----	4.4.7
Scrubbability	3.3.9	6142	----	-----
Washability	3.3.10	----	----	4.4.8
Storage stability	3.3.11	----	----	4.4.9

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:18Z
Check the source to verify that this is the current version before use.

PAGE 2 (con.)

TABLE III. Index (con.)

Characteristics	Requirement Reference	Test Method Fed. Test Method Std. No. 141	Test Method ASTM Method	Paragraph Reference
Water resistance	3.3.12	----	----	4.4.10
Alkali resistance	3.3.13	----	----	4.4.11
Fungus resistance	3.3.14	----	D 3273	-----
Resistance to reflectance variation	3.3.15	----	----	4.4.6
Anchorage	3.3.16	----	----	4.4.13

1/ Apply a film of the paint with a 0.0025-inch (approximately 0.005-inch gap clearance) Bird film applicator or any other doctor blade which produces a film of the same thickness.
2/ Procedure B, Method A.

PAGE 5

Paragraph 4.4.4. Delete 10th sentence and substitute: "After a 24 hour drying period, obtain gloss readings in accordance with Method 6103 of Fed. Test Method Std. No. 141, and reflectance readings in accordance with ASTM Method E 97, on the roller-coated and brushed surfaces for a total of eight different readings each.

Paragraph 4.4.6, line 5. Delete "Method 6121 of Fed. Test Method Std. No. 141" and substitute "ASTM Method E97".

PAGE 6

Paragraph 4.4.14 and 4.4.14.1. Delete and substitute.

4.4.14 Lead content.

4.4.14.1 Sample preparation. Using a 0.006-inch film applicator and a mechanical applicator plate, duplicate drawdowns for each sample of well-mixed paint shall be made on a standard paint penetration chart and dried for 24 hours. The drawdown shall be at least 10 inches long on the sealed portion of the penetration chart. The drawdown shall be cut into discs of appropriate size to fit the sample holder of a fluorescence XXray spectrometer.

4.4.14.2 Procedure. Lead content shall be determined using an X-ray fluorescence spectrometer capable of determining lead content at a minimum level of 0.03 percent by weight of the total nonvolatile. The settings for a wavelength dispersive fluorescence spectrometer shall be as follows: (1)

Element	Analytical Line	Angle	Crystal	Detection	Collimeter	X-ray tube (MO)
Pb	L	33.93	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Pb (backgrd I)		33.00	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Pb (backgrd II)		35.50	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Mo	K	20.33	LiF(200)	Flow S.C.	Fine	60Kv 45Ma

Pulse height selection shall be used in all measurements and counting time shall be 100 seconds. Place the sample disc in the wavelength dispersive unit. Measure the count rates of lead, lead background, and the Molybdenum Compton scattered background from the X-ray tube.

4.4.14.3 Calculation.

$$R = \frac{I_{Pb} - \frac{I_{Pb\ (Background\ I)} + I_{Pb\ (Background\ II)}}{2}}{I_{Mo}}$$

(1) Energy dispersive fluorescence spectrometers shall be set up according to the manufacturer's manual.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:18Z
Check the source to verify that this is the currentversion before use.

where I equals gross intensity. These results shall be compared to those obtained with a 0.06 percent lead standard made up from the same type of paint sample and evaluated for compliance with table I.

Paragraph 4.5, line 2. Delete "TT-P-143" and substitute "PPP-P-1892".

Paragraph 5.1, line 2. Delete "TT-P-143" and substitute "PPP-P-1892".

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:18Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:18Z
Check the source to verify that this is the current version before use.