AMENDMENT

TO

INTERIM FEDERAL SPECIFICATION

PAD, DESK, BLOTTER

This amendment was developed by the General Services Administration, Federal Supply Service, Washington, DC 20406, based upon currently available technical information. The General Services Administration has authorized this amendment as a part of Interim Federal Specification UU-P-0016B(GSA-FSS), dated August 6, 1970.

PAGE 2

Paragraph 3.1.2, delete in its entirety and substitute the following:

"3.1.2 Linoleum (type III pad). Linoleum shall conform to the requirements of LLL-F-1238, type I, class 1 or 2, grade B, except the indenting load for the class 2 residual indentation requirement and test shall be 80 pounds in lieu of 140 pounds. The color shall be as specified (see 6.2)."

Paragraph 3.1.3.1, delete in its entirety and substitute the following:

"3.1.3.1 Artificial leather for type I pads. The artificial leather for type I pads shall conform to the following physical requirements (see 4.1.1.1.2):

Total weight of finished artificial leather, minimum	6-3/4 ounces per square yard

The artificial leather shall not contain linseed oil, rubber or rubber substitutes, and it shall be even and smooth on the outside and be free from holes, cracks, or other defects and free from objectionable odor. The finish shall be that of simulated top grain leather, smooth to the touch. The color shall be brown. The finish shall show no signs of cracking or flaking when tested as specified in 4.1.1.1.3."

PAGE 4

Paragraph 4.1.1.1.2, delete in its entirety and substitute the following:

"4.1.1.1.2 Determination of total weight of finished artificial leather. The total weight of artificial leather shall be determined in accordance with method 5041 of Fed. Test Method Std. No. 191 (see 3.1.3.1)."

Paragraph 4.1.1.1.3, delete in its entirety and substitute the following:

"4.1.1.1.3 Test for cracking, artificial leather. One specimen, 8 by 8 inches, shall be taken from each 100 linear yards of artificial leather. Each specimen shall be tested as follows: Crease the specimen to form a crease parallel to either edge of the specimen. A 10 pound metal roller approximately 5-1/2 inches in diameter and 2 inches in width with a suitable handle shall be rolled one time over the coated cloth specimen while the specimen rests on a hard surface. It shall then be folded in the same position, but the opposite direction and the weight again applied. The specimen shall then be visually examined for cracking or flaking which, if evident, shall be cause for rejection (see 3.1.3.1)."

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:19Z
Check the source to verify that this is the currentversion before use.