[METRIC]

A-A-2192A
March 30, 1994
SUPERSEDING
A-A-2192
September 23, 1983

COMMERCIAL ITEM DESCRIPTION

PAPER, BLOTTING

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification UU-P-63.

This Commercial Item Description covers blotting paper for use in desk blotters.

CLASSIFICATION

Blotting paper covered by this specification shall be of the following sizes and colors.

Size A - 483 mm X 610 mm (19 X 24 inches).
Size B - 610 mm X 925 mm (24 X 38 inches).

Color 1 - Chocolate Brown.
Color 2 - Moss Green.
Color 3 - Light Green.

1. SALIENT CHARACTERISTICS

A. Paper: The blotting paper shall be made from fibrous, cellulosic material with a basis weight of 308 g/m^2 (100 lbs. 19 X 24-500) +/- 5%, when tested in accordance with TAPPI test method T410. The blotting paper shall have an average bursting strength of 170 kPa (25 psi), minimum, when tested in accordance with TAPPI test method T403. The blotting paper shall have a plain finish.

B. Construction: The Blotting paper sheets shall be 483 mm X 610 mm (19 X 24 inches) or 610 mm X 925 mm (24 X 38 inches), as specified in the contract or order. A tolerance of -0, + 3.17 mm (-0, + 1/8 inch) is permitted on each dimension.

Beneficial comments, recommendations, additions, deletions, clarification's, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, NY 10278

Distribution Statement A:
Approved for public release; Distribution is unlimited.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:20Z
Check the source to verify that this is the current version before use.

C. Colors: The blotting papers shall be produced by pulp dyeing and furnished in chocolate brown, moss green, or light green, as specified.

Workmanship: The blotting paper shall be uniform in color and shall be clean and free from lint, dust, spots, scorches, folds, wrinkles, holes and any other defects which may affect the serviceability, durability, or appearance. Sheets shall be flat trimmed square on all sides, with clean and smooth edges.

2. REGULATORY REQUIREMENTS:

The contractor shall certify that the minimum content standard shall be no less than 50% percent recovered materials, including 20% post consumer materials in accordance with Executive Order 12873, section 504 (b), dated October 20, 1993 (See definitions of post consumer materials and recovered materials in sections 203 and 205). As an alternative to meeting the standards of section 504(a) for all printing and writing papers, the minimum content standard shall be no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

3. TABLES AND TESTS:

Table 1. Physical requirements for blotting paper.

	Requirement	Test Method
Basis Weight	308 g/m^2 (100 lbs. 19 X 24-500) +/-5%	T410
Burst	170 kPa (25 psi) average, min.	T403

4. QUALITY ASSURANCE:

Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:20Z
Check the source to verify that this is the current version before use.

The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, and quality assurance practices. The government reserves the right to require proof of conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Each lot of Blotting paper shall be inspected for conformance to the requirements herein. Sampling for inspection shall be in accordance with MIL-STD-105 using the plans specified below.

A. Visual and Dimensional characteristics - Inspection Level II with an Acceptable Quality Level (AQL) of 4.0 percent defective. The sample unit shall be one sheet.

B. Component testing - The paper stock shall be tested in accordance with referenced TAPPI test methods. Characteristics of the component paper stock tested for conformance to the requirements in Section 1 do not have to be retested under end item testing. A certified test report is evidence that the paper has passed the required test.

5. **PREPARATION FOR DELIVERY:**

Packaging, packing and marking shall be as specified in the contract or purchase order.

6. **REFERENCED DOCUMENTS:** The issue of each document in effect on the date of the solicitation shall be used to determine compliance with these requirements.

TAPPI test methods are available from:

Technical Association of the Pulp and Paper Industry
Technology Park/Atlanta, P.O. Box 105113
Atlanta, GA 30348
(404) 446-1400

MIL-STD-105 is available from:

STANDARDIZATION DOCUMENTS ORDER DESK
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:20Z
Check the source to verify that this is the current version before use.

Copies of Executive Order 12873, dated October 20, 1993 may be obtained from:

The White House Publications Office
New Executive Office Building
White House
Att: Publications
Washington, DC. 20500
(202) 395-7332

7. **NOTES:**

A. Ordering Data:

Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(1) Dimensions.
(2) Color.
(3) Specific packaging, packing, palletization and, marking requirements.

B. **Item Identifiers/Reference Part Number System (For Cataloging Use Only)**

AA2192 - A1: This example describes a 483 X 610 mm blotting pad in chocolate brown.

Color 1 - Chocolate Brown.
2 - Moss Green.
3 - Light Green.

SIZE A - 403 mm X 610 mm (19 X 24 inches).
B - 610 mm X 925 mm (24 X 38 inches).

Military custodians:

NONE

Preparing activity:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:20Z
Check the source to verify that this is the current version before use.