INCH-POUND

MIL-L-11075G
30 December 1988
SUPERSEDING
MIL-L-11075F
27 December 1984

MILITARY SPECIFICATION

LOOPS, STRAP FASTENER

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers metal loop fasteners.

1.2 Classification. Strap loops shall be of the following types and styles as specified (see 6.2).

Type I - Brass

Style A	-	1-1/16 by 1/2 inch-Cast
Style B	-	1-1/16 by 1/2 inch-Wire
Style C	-	11/16 by 1/4 inch-Wire
Style D	-	2-1/16 by 1/4 inch-Wire
Style E	-	2-1/16 by 1/4 inch-Wire
Style F	-	1-1/32 by 5/8 inch-Wire
Style G	-	1-1/8 by 3/16 inch-Wire
Style H	-	13/16 by 1/2 inch-Cast
Style S	-	1-1/6 by 1-1/16 inch-Cast
Style JJ	-	13/16 by 5/8 inch-Wire
Style KK	-	15/16 by 1/4 inch-Wire
Style LL	-	1-1/16 by 1/4 inch-Wire

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

Type II - Malleable iron

Style A	-	1-1/16 by 1/2 inch-Cast
Style H	-	13/16 by 1/2 inch-Cast
Style Q	-	1-1/2 by 11/16 inch-Cast
Style HH	-	3-3/8 by 1-5/8 by 1-1/8 inch-Cast

Type III - Steel

Style B	-	1-1/16 by 1/2 inch-Wire
Style C	-	11/16 by 1/4 inch-Wire
Style D	-	2-1/16 by 1/4 inch-Wire
Style E	-	2-1/16 by 1/4 inch-Wire
Style F	-	1-1/32 by 5/8 inch-Wire
Style G	-	1-1/8 by 3/16 inch-Wire
Style J	-	2-1/16 by 7/8 inch-Wire
Style K	-	1-3/8 by 9/16 inch-Wire
Style L	-	1-3/8 by 1-3/8 inch-Wire
Style M	-	2-1/16 inch, 5 sided-Wire
Style N	-	2-1/16 by 1-1/4 inch-Wire
Style P	-	1-1/16 by 1/2 inch-Wire
Style Q	-	1-1/2 by 11/16 inch-Wire
Style R	-	1-5/16 by 11/32 inch-Wire
Style T	-	1-5/16 by 5/16 inch-Wire
Style W	-	1-1/2 by 5/8 inch-Wire
Style Y	-	1-5/16 by 5/16 inch-Wire
Style Z	-	1-3/8 by 3/8 inch-Wire
Style AA	-	4 by 1-1/4 inch-Wire
Style BB	-	1-5/8 by 1-3/8 by 1 inch-Wire
Style CC	-	1-3/8 by 1-1/2 by 1 inch-Wire
Style DD	-	3-1/4 by 1-1/2 by 1 inch-Wire
Style EE	-	3-1/8 by 1-1/2 by 1-3/8 inch-Wire
Style FF	-	3-1/4 by 1-7/16 by 1-3/16 inch-Wire
Style GG	-	4-3/8 by 1-1/2 by 1 inch-Wire
Style MM	-	3/4 by 5/16 inch-Wire

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

QQ-B-637	-	Brass, Naval: Rod, Wire, Shapes, Forgings, and Flat Products with Finished Edges (Bar, Flat Wire, and Strip)
QQ-C-390	-	Copper Alloy Castings (Including Cast Bar)
QQ-W-321	-	Wire, Copper Alloy
QQ-W-461	-	Wire, Steel, Carbon, (Round, Bare and Coated)
TT-C-490	-	Cleaning Methods of Ferrous Surfaces and Pretreatments for Organic Coatings
TT-E-529	-	Enamel, Alkyd, Semigloss
PPP-B-566	-	Boxes, Folding, Paperboard
* PPP-B-601	-	Boxes, Wood, Cleated, Plywood
PPP-B-636	-	Boxes, Shipping, Fiberboard
PPP-B-676	-	Boxes, Setup

MILITARY

MIL-F-495	-	Finish, Chemical, Black, for Copper Alloys
MIL-B-7883	-	Brazing of Steels, Copper, Copper Alloys, Nickel Alloys, Aluminum and Aluminum alloys

STANDARDS

FEDERAL

FED-STD-595	-	Colors

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage
MIL-STD-147	-	Palletized Unit Loads

* (Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Naval Publications and Forms Center, (ATTN: NPODS), 5801 Tabor Avenue, Philadelphia, PA 19120-5099.)

* 2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

DRAWINGS

* U.S. ARMY NATICK RESEARCH, DEVELOPMENT AND ENGINEERING CENTER

4-1-90	-	Loop, Strap Fastener
4-1-437	-	Loop, Strap Fastener

* (Copies of drawings, are available from the U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014).

* 2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

A 47	-	Ferritic Malleable Iron Castings
B 281	-	Preparation of Copper and Copper-Base Alloys for Electroplating and Conversion Coatings
B 322	-	Cleaning Metals Prior to Electroplating
B 633	-	Electrodeposited Coatings of Zinc on Iron and Steel
D 3951	-	Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

* (Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

* 3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3), in accordance with 4.3.

* 3.3 Material. Materials shall be as specified herein. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

3.2.1 Castings, brass. Brass castings shall conform to type I, condition as cast, alloy A3 of QQ-C-390.

3.2.2 Wire, brass. Brass wire shall conform to alloy 270, quarter hard of QQ-W-321, or alloy 462, or 464, half-hard, or light annealed of QQ-B-637.

3.2.3 Castings, malleable iron. Malleable iron castings shall conform to grade 32510 or 35018 of ASTM A 47.

3.2.4 Wire, steel. Steel wire shall conform to AISI numbers 1006, 1008, 1010, or 1015, finish 1, annealed of QQ-W-461.

3.2.5 Enamel. The enamel shall conform to type II, of TT-E-529. The color shall be semi-gloss black, No. 27038 of FED-STD-595.

3.3 Construction. The construction and forming of loops shall conform to the style and requirements as shown on Drawings 4-1-90 and 4-1-437.

3.3.1 Castings. Brass and malleable iron castings shall have no porosity, blowholes, blemishes, slag or other casting imperfections. All sharp edges and burrs shall be removed and finished smooth.

* 3.3.2 Type I loops. Type I loops when fabricated of brass wire, and formed to shape, shall when required be joined by butt resistance welding or brazing, type I-V, grade B conforming to MIL-B-7883. The butt resistance welding or brazed joints shall be sound and smooth. Styles A, H, and S shall be cast of brass as specified in 3.2.1. Styles B, C, D, E, F, G, JJ, KK, and LL shall be formed of brass wire as specified in 3.2.2.

3.3.3 Type II loops. Type II loops, styles A, H, Q, and HH shall be cast of malleable iron as specified in 3.2.3.

3.3.4 Type III loops. Type III loops, styles B, C, D, E, F, G, J, K, L, M, N, P, Q, R, T, W, Y, Z, AA, BB, CC, DD, EE, FF, GG, and MM shall be formed of steel wire as specified in 3.2.4. The ends of the wire, after being formed to shape, shall be joined by welding or brazing at the option of the contractor. The welding or brazing shall be sound and smooth with the welding conforming to good commercial practices and brazing as specified in 3.3.2.

3.4 Finish. Prior to finish application, all burrs, flashing, scale, sharp edges, and welding flux shall be removed. Type I loops shall be cleaned as specified in ASTM B 281 and ASTM B 322. Type II and III loops shall be cleaned in accordance with method I, II, or V of TT-C-490.

3.4.1 Type I loop. After fabrication and cleaning, the type I loops shall be given a black chemical finish, 0.00005 to 0.0002 inch thick, conforming to MIL-F-495. The color shall be semi-gloss black, No. 27038, conforming to FED-STD-595.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

3.4.2 Type II and III loops. The finish for type II and III loops shall consist of phosphate treated zinc coating, conforming to type III, SC3 of ASTM B 633, followed by baked enameling as specified in 3.2.5. The enamel shall dry to a smooth and uniform film, free from runs, wrinkles, orange peel or areas of no film.

* 3.5 Workmanship. The finished loops shall be cleaned in accordance with good commercial practice and be free of sharp edges, burrs, flashing, cracks, bends, flux or incomplete fusion of material. The loops shall conform to the quality of product established by this specification and the occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

* 4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

* 4.3 First article inspection. When a first article inspection is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4. The presence of any defect shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

* 4.4.2 In-process inspection. Inspection of the type II and III loops shall be made to ascertain that the loops have been given a phosphate treated zinc coating conforming to ASTM B 633 as specified in 3.4.2. Whenever nonconformance is noted, correction shall be made to the items affected and to the operation. Items which cannot be corrected shall be removed from production.

4.4.3 End item visual examination. The end items shall be examined for the defects listed in table I. The lot size shall be expressed in units of loops. The sample unit shall be one loop. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5 for major defects and 10.0 for total (major and minor combined) defects.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Minor
Finish (general)	Not finished or finish not as specified	101	
	Evidence of corrosion		201
Black chemical	Color not as specified	102	
	Finish not clean and uniform		202
Black enamel	Area of no film or color not as specified	103	
	Separation of color, or finish rough (i.e. lint, dust, dirt or other foreign matter embedded in finish)		203
	Finish not continuous, smooth, and adherent (i.e. orange peel, wrinkles, drops, streaks)		204

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Construction and workmanship	Wrong type or style	104	
	Sharp edges, burrs, slivers, or projections cracked, broken, bent, malformed, or damaged	105	
	Pronounced tool or forming marks		205
	Casting miscast, incomplete, or contains blowholes, or evidence of porosity	106	
Workmanship welds or brazing	Welds or brazing missing	107	
	Completely broken or not fused	108	
	Cracked, partially broken, incomplete, or evidence of poor fusion or burn through		206
	Evidence that the weld contains gas pockets or flux or spatter that has not been removed		207

* 4.4.4 End item dimensional examination. The end item shall be examined for conformance to the dimensions specified on the drawings that can be determined on the end items without damaging or disassembling the end items. The lot size shall be expressed in units of loops. The sample unit shall be one loop. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

* 4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. Any dimension not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping or inadequate stapling Bulged or distorted container
Content	Number per container is more or less than required

* 4.4.6 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1, and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Unless otherwise specified (see 6.2), loops of one type and style only shall be unit packed in the quantities specified in table II, in a snug-fitting fiberboard shipping box conforming to style RSC, type CF, variety SW, or type SF, class domestic, grade 200 of PPP-B-636. Each box shall be agitated from time to time to assure a compact and well filled box. When quantities are other than those specified in table II, loops of one type and style only shall be unit packed in boxes conforming to PPP-B-566, PPP-B-636 or PPP-B-676. The weight of contents shall not exceed the weight limitations of the applicable box specification. Each box shall be closed in accordance with the appendix of the applicable box specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

TABLE II. Quantity of loops per unit pack and shipping container

Type and style	Quantity per fiberboard box	Quanity per shipping container
Type I - brass:		
Style A	650	3,900
Style B	1,500	9,000
Style C	3,750	22,500
Style D	2,000	12,000
Style E	1,800	10,800
Style F	550	3,300
Style G	1,600	9,600
Style H	1,000	6,000
Style S	500	3,000
Style JJ	1,600	9,600
Style KK	1,500	9,000
Style LL	1,700	10,200
Type II - Malleable iron:		
Style A	550	3,300
Style H	1,100	6,600
Style Q	1,000	6,000
Style HH	175	1,050
Type III - Steel:		
Style B	1,800	10,800
Style C	3,750	22,500
Style D	2,000	12,000
Style E	1,800	10,800
Style F	600	3,600
Style G	2,000	12,000
Style J	1,000	6,000
Style K	600	3,600
Style L	350	2,100
Style M	250	1,500
Style N	350	2,100
Style P	675	4,050
Style Q	1,800	10,800
Style R	675	4,050
Style T	1,500	9,000
Style W	600	3,600
Style Y	675	4,050
Style Z	1,000	6,000
Style AA	275	1,650

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

TABLE II. Quantity of loops per unit pack and shipping container (cont'd)

Type and style	Quantity per fiberboard box	Quantity per shipping container
Type III - Steel (cont'd)		
Style BB	475	2,850
Style CC	525	3,150
Style DD	300	1,800
Style EE	300	1,800
Style FF	375	2,250
Style GG	250	1,500
Style MM	3,750	22,000

5.1.2 Commercial. The loops shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing. Unless otherwise specified (see 6.2), loops of one type and style only, preserved as specified in 5.1, shall be packed in the quantities as specified in table II, in a snug-fitting cleated-plywood box conforming to overseas type, type style options of PPP-B-601. Each shipping container shall be closed and reinforced in accordance with PPP-B-601.

5.2.2 Level B packing. Unless otherwise specified (see 6.2), loops of one type and style only, preserved as specified in 5.1, shall be packed in the quantities as specified in table II, in a snug-fitting fiberboard shipping container conforming to style FTC, type CF, variety DW, class domestic, grade 350 of PPP-B-636. Each shipping container shall be closed and reinforced in accordance with PPP-B-636.

5.2.2.1 Weather-resistant shipping containers. When specified (see 6.2), the shipping container shall be grade V3c, V3s or V4s fiberboard box fabricated and closed in accordance with PPP-B-636.

5.2.3 Commercial packing. Loops, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

* 5.3 Palletization. When specified (see 6.2), loops, packed as specified in 5.2, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with the bonding means K and L or film bonding O or P. Pallet patterns shall be in accordance with the appendix of MIL-STD-147.

5.4 Marking. In addition to any special marking required by the contract or purchase order, unit packs, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

* (This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The loops are intended to fasten the end of a strap or a belt to itself, to another belt or strap, or to an object or structure.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Type and style required (see 1.2).
c. When a first article is required (see 3.1).
d. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
e. When quantity per unit pack and shipping container is other than specified (see 5.1.1, 5.2.1 and 5.2.2).
f. When weather-resistant grade fiberboard shipping containers are required for level B shipment (see 5.2.2.1).
g. When palletization is required (see 5.3).

* 6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in all acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

* 6.4 Subject term (key word) listing.

Belt
Clamp
Fastener
Hardware
Secure

* 6.5 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content, irrespective of the marginal notations and relationship to the previous issue.

Custodians:

Army - GL
Air Force - 99

Review activities:

* Army - MI, MD, AR
Air Force - 82
DLA - IS

User activities:

Army - MD, ME
Navy - MC

Preparing activity:

Army - GL

(Project 5340-1899)

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-L-11075G	LOOPS, STRAP FASTENER

3a. NAME OF SUBMITTING ORGANIZATION

b. ADDRESS *(Street, City, State, ZIP Code)*

4. TYPE OF ORGANIZATION *(Mark one)*

- ☐ VENDOR
- ☐ USER
- ☐ MANUFACTURER
- ☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK/OP, 20 Nov 84

Source: https://assist.dla.mil/online/start/ Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

US ARMY NATICK RESEARCH
and DEVELOPMENT CENTER
ATTN STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research
and Development Center
ATTN STRNC-ES
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:04Z
Check the source to verify that this is the current version before use.