

TABLE I. DASH NUMBERS.

DASH NO	A	HEAT TREATMENT	FORMING PROCESS (SEE REQT 3)	ADDITIONAL REQUIREMENT (SEE REQT 4)
001	.187	NORMALIZED	C	
003	.250	ANNEALED	C	
005	.250	NORMALIZED	C	
007	.312	ANNEALED	C	
009	.312	NORMALIZED AND TEMPERED	C	
011	.312	NORMALIZED	C	

REQUIREMENTS:

1. MATERIAL. ALLOY STEEL 4130 (UNS G41300), AS SPECIFIED IN PROCUREMENT DOCUMENT.
2. LENGTH. STANDARD LENGTH OF HEXAGON WIRE IS 10 FEET MINIMUM, 12 FEET MAXIMUM.
3. FORMING PROCESS. COLD DRAWN - CODE "C"
4. ADDITIONAL REQUIREMENTS.
5. PART NUMBER. THE PART NUMBER CONSISTS OF THE BASIC MS NUMBER, PLUS A FORMING PROCESS CODE, PLUS A DASH NUMBER FROM TABLE I.

   EXAMPLE: MS14293C001

   - C001 — DASH NUMBER FROM TABLE I
   - C — COLD DRAWN (SEE REQUIREMENT 3)
   - MS14293 — BASIC MS NUMBER

6. MARKING. IRON AND STEEL PRODUCTS SHALL BE MARKED IN ACCORDANCE WITH FED-STD-183 WITH THE EXCEPTION THAT A PART NUMBER FROM THIS MILITARY STANDARD SHALL BE INCLUDED AS PART OF THE IDENTIFICATION MARKING.

NOTES:

1. ALL DIMENSIONS ARE IN INCHES.
2. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATIONS FOR BIDS, OR REQUEST FOR PROPOSAL, EXCEPT THE REFERENCED ADOPTED INDUSTRY DOCUMENTS SHALL GIVE THE DATE OF THE ISSUE ADOPTED.
3. FOR DESIGN FEATURE PURPOSES THIS STANDARD TAKES PRECEDENCE OVER PROCUREMENT DOCUMENTS REFERENCED HEREIN.

APPROVED 9 October 1984 REVISED

USER ACTIVITIES:
NAVY - MC, OS

REVIEWER ACTIVITIES:
AIR FORCE - 84
DLA-IS

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document when applicable.

P.A.	INTERNATIONAL INTEREST	TITLE	MILITARY STANDARD
AS		WIRE, NONELECTRICAL, HEXAGON, ALLOY STEEL 4130 CHROME-MOLYBDENUM (AIRCRAFT QUALITY)	MS14293
Other Cust MR 99			
PROCUREMENT SPECIFICATION: MIL-S-6758	SUPERSEDES:		PAGE 1 OF 1

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:39Z
Check the source to verify that this is the current version before use.