MILITARY SPECIFICATION

CLOTH, GABARDINE: WOOL, POLYESTER AND WOOL

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers wool, polyester and wool gabardine cloths.

* 1.2 Classification. The cloth shall be of the following types and classes as specified (see 6.2).

Type I - Wool

Class 3	-	11.0 ounce
Class 5	-	14.5 ounce
Class 7	-	16.0 ounce
Class 8	-	13.0 ounce

Type II - Polyester and wool blend

Class 1	-	10.5 ounce
Class 8	-	9.5 ounce
Class 9	-	10.8 ounce
Class 10	-	13.0 ounce
Class 11	-	11.2 ounce

2. APPLICABLE DOCUMENTS

* 2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

PPP-P-1132 - Packaging and Packing of Woolen, Worsted and Wool Blend (Synthetic Fiber; Cotton) Fabrics

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-C-43665 - Cloth, Wool: Mothproofing Treatment of

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-655 - Provisions for Evaluating Quality of Cloth, Wool and Wool Blends

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

LAWS AND REGULATIONS

U.S. Department of Agriculture

Methods of Test for Grades of Wool Top

(Application for copies should be addressed to the U.S. Department of Agriculture, Agricultural Marketing Service, Washington, DC 20402.)

Rules and Regulations Under the Wool Products Labeling Act of 1939

(Application for copies should be addressed to the Superintendent of Documents, Government Printing Office, Washington, DC 20402.)

3. REQUIREMENTS

3.1 Standard sample. The finished cloth shall match the standard sample for shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

* 3.2 First article. When specified (see 6.2), the supplier shall furnish a sample for first article inspection and approval (see 4.3 and 6.7).

3.3 Material.

3.3.1 Stock.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

* 3.3.1.1 Grade. The wool for the cloth shall be not lower in grade than the U.S. Standard grades specified below for the applicable class, when tested as specified in 4.4.1.1.

Class 1 62's U.S. Standard

Class 3 62's U.S. Standard

Class 5 64's U.S. Standard

Class 7 62's U.S. Standard

Class 8 64's U.S. Standard

Class 9 64's U.S. Standard

Class 10 64's U.S. Standard

Class 11 64's U.S. Standard

3.3.1.2 Type I cloth. The wool top for type I cloth shall be fleece or pulled wool, or both, not lower in grade than that specified for the applicable class (see 1.2 and 3.3.1.1). The use of wool top made from laps, noils, or any other wool manufacturing by-products is prohibited. The finished cloth shall contain not less than 95 percent wool based on the dry weight of the specimen when tested as specified in 4.5.

3.3.1.3 Type II cloth. The blend shall consist of fleece or pulled wool or both not lower in grade than that specified for the applicable class in 3.3.1.1 and polyester fiber in top or cut tow form in such proportion that the finished cloth shall contain not less than 40 percent wool and not less than 55 percent or more than 60 percent polyester fiber based on the oven-dry weight of the specimen when tested as specified in 4.5. The use of wool top produced from laps, noils or any other wool manufacturing by-product is prohibited. The polyester fiber shall be semi-dull polyester fiber made from polyethylene glycol terephthalate either homopolymer or modified polymer as appropriate (see 4.4.1 and 6.6). The minimum average polyester fiber length shall be 3 inches when tested as specified in 4.4.1 and suitable denier to blend adequately with the 62's or 64's Grade wool. The use of polyester fiber waste is prohibited.

3.3.2 Yarn. The yarn for the warp and filling shall be spun from combed top on either the Bradford, French or American system. The warp and filling yarn for all types and classes shall be 2-ply (see 4.5). For type II cloth, the yarns for both warp and filling shall be a blend of the two fibers (see 6.6).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

NOTE: Selvage yarn. To prevent edges of all types of cloth from building up when rolled, 2-ply yarns used in the selvages may be made of a finer count than those used in the body of the cloth.

3.4 Color. The color shall be as specified (see 6.2 and 6.4) and shall match the standard sample. The color of type I cloth shall be obtained by blending stock or top dyed wools; the color of type II cloth shall be obtained by blending top dyed wool with stock, top or tow dyed polyester fibers, with the wool and polyester fibers dyed separately and then blended (see 6.5).

3.4.1 Mothproofing. Mothproofing of the wool material, in accordance with MIL-C-43665, shall be accomplished during stock or top dyeing as applicable.

3.4.2 Matching. The color of the finished cloth shall match the standard sample under natural (north sky) daylight, or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin.

3.4.3 Colorfastness. The finished cloth shall show fastness to crocking, perspiration, wet drycleaning and light equal to or better than the standard sample. When no standard sample has been established or designated as applicable to colorfastness, the finished cloth shall show "good" fastness to perspiration, wet drycleaning and light and shall show a Munsell Value for crocking not lower than 8.5. For Air Force Blue 1549 and Army Green 44 the light exposure time for "good" fastness shall be 60 standard fading hours. Tests shall be made as specified in 4.5.

* 3.5 Physical requirements. The finished cloth shall conform to the requirements specified in table I when tested as specified in 4.5.

* TABLE I. Physical requirements

Type	Class	Weight per linear yard 56 in. width basis (ozs.) minimum	Yarns per inch minimum		Breaking strength (pounds) minimum		Shrinkage percent maximum	
			Warp	Filling	Warp	Filling	Warp	Filling
I	3	11.0	86	48	80	42	4.0	3.0
I	5	14.5	112	56	115	65	6.0	3.0
I	7	16.0	120	60	120	55	4.0	3.0
I	8	13.0	98	52	130	55	5.0	3.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

* TABLE I. Physical requirements (cont'd)

Type	Class	Weight per linear yard 56 in. width basis (ozs.) minimum	Yarns per inch minimum		Breaking strength (pounds) minimum		Shrinkage percent maximum	
			Warp	Filling	Warp	Filling	Warp	Filling
II	1	10.5	84	48	190	110	3.0	2.5
II	8	9.5	114	56	160	70	3.0	2.0
II	9	10.8	122	62	160	80	2.0	1.5
II	10	13.0	98	50	120	80	3.0	1.0
II	11	11.2	90	53	120	70	3.0	1.0

3.5.1 Width. The width of all types and classes of finished cloth shall be a minimum of 60 inches exclusive of the selvage.

* 3.6 Weave. The weave for the types and classes specified shall be as follows (see 4.5):

Type	Class	Weave
I	3	2/1 right twill
I	5	2/2 right twill
I	7	2/2 right twill
I	8	2/2 right twill
II	1	2/1 right twill
II	8	2/2 right twill
II	9	2/2 right twill
II	10	2/1 right twill
II	11	2/1 right twill

3.7 Finish. The cloth shall be scoured, brushed, sheared, pressed and decated so as to provided a finish equal to that of the standard sample.

3.7.1 Pilling. The type II cloth shall be singed and finished to show no more pilling than the standard sample when tested as specified in 4.5 (see 6.6.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

3.7.2 pH. The pH value of the water extract of the finished cloth shall be no less than 5.5 nor more than 8.5 when tested as specified in 4.5.

3.8 Selvages. The selvages shall be no thicker than thirty percent more than the body of the cloth when tested as specified in 4.5.

3.9 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 50 yards. The cloth shall be put up on full width rolls as specified in PPP-P-1132.

3.10 Wool content label. Cloth manufactured under this specification shall be labeled in accordance with the Wool Products Labeling Act of 1939 (see 2.1).

3.11 Marking. The back of the cloth shall be marked "Back" at both ends of each roll with letters not less than 1/2 inch in height (see 4.4.2.3). The marking shall be clearly legible in any indelible marking medium used commercially.

* 3.12 Workmanship. The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards when calculated as specified in section 4 shall not exceed the established maximum point value. Each defect shall be marked with a 1 to 1-1/2 inch long string. The string shall be sewn into the selvage near the defect. A red string shall represent a three or four point defect and a white string shall represent a one or two point defect (see 4.4.2.5).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

* 4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When required (see 6.2), the preproduction sample submitted in accordance with 3.2 shall be visually inspected for appearance, color and finish, and shall be tested in accordance with the methods specified in 4.5.

4.4 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-655, except where otherwise indicated hereinafter.

4.4.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document.

TABLE II. Component test methods

Characteristic	Requirement paragraph	Test method
Polyester identification	3.3.1.3	1/
Length of fiber	3.3.1.3	Visual 1/

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirements.

4.4.1.1 Wool. The wool shall be examined for grade (see 3.3.1.1) in undyed top form by comparison with the applicable U.S. Standard (see 2.1). In the event of a dispute, the wool grade shall be determined by the width method (wedge). The sample unit shall be 1 yard of top, prior to dyeing and to blending with polyester fibers. The sample size (number of sample units) shall be as shown in the table below. The lot size shall be expressed in units of one pound. The results from each sample unit shall be reported separately. The lot shall be unacceptable if a single sample unit fails to meet the required grade.

Lot size (pounds)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

4.4.1.2 In-process inspection. Inspection shall be made at any point or during any phase of the manufacturing process to assure that no noils or wool top made from laps and only approved wools and polyester fibers, in the amount specified are used, and that the dyeing and singeing requirements have been adhered to (see 3.4 and 3.7.1). The Government reserves the right to exclude from consideration for acceptance any material for which in-process inspection has indicated nonconformance.

4.4.2 Examination of the end item. Examination of the end item shall be in accordance with 4.4.2.1 through 4.4.2.5.

* 4.4.2.1 Yard-by-yard examination. The yard-by-yard examination shall be as specified in MIL-STD-655. The fabric quality for all shades except Tan 3729 shall be Quality Level 10. For Tan 3729 the fabric quality shall be Quality Level 12. The yardage examined shall also be given a through-lighting inspection from the back of the cloth towards a light source for holes and thin areas not previously scored on the face side of the cloth. Slight open places resulting from the removal of burrs, shives, sisal or broken yarns not previously scored on the face side shall not be scored in through-lighting inspection.

* 4.4.2.2 Examination for length. The examination for length shall be as specified in MIL-STD-655.

* 4.4.2.3 Examination for back marking and compliance with the Wool Products Labeling Act. The examination for back marking and compliance with the Wool Products Labeling Act shall be as specified in MIL-STD-655.

4.4.2.4 Examination for shade and finish, individual rolls. Each roll in the lot shall be examined visually for shade match (see 3.4.2) and finish (see 3.7). A roll shall be unacceptable if it fails to meet the requirements for shade match and finish. The sample unit shall be a 4-inch by 20-inch swatch of the cloth. A sample unit shall be drawn from each roll in the lot.

* 4.4.2.5 Examination for defect marking (stringing of defects). The examination for defect marking shall be as specified in MIL-STD-655.

4.4.3 Examination of preparation for delivery requirements. Examination shall be made in accordance with the provisions of PPP-P-1132 to determine that packaging, packing and marking comply with the section 5 requirements.

4.5 Tests. The methods of testing specified in FED-STD-191 wherever applicable and as listed in table III shall be followed. The physical and chemical values specified in section 3 apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 3 continuous yards, full width

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

of the finished cloth. The lot size shall be expressed in units of 1 yard. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. All test reports shall contain the individual value utilized in expressing the final results. The sample size (number of sample units) shall be in accordance with the following:

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE III. Test method

Characteristic	Requirement paragraph	Test method
Fiber percentage:		
Type I	3.3.1.2	2101
Type II	3.3.1.3	2102
Yarns ply:		
Warp	3.3.2	Visual 1/
Filling	3.3.2	Visual 1/
Colorfastness:		
Wet drycleaning	3.4.3	5622
Crocking	3.4.3	5651
Light	3.4.3	5660
Perspiration	3.4.3	5680
Weight	3.5	5041
Yarns per inch		
Warp	3.5	5050
Filling	3.5	5050
Breaking strength:		
Warp	3.5	5100
Filling	3.5	5100

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

TABLE III. Test method (cont'd)

Characteristic	Requirement paragraph	Test method
Shrinkage:		
Warp	3.5	5558
Filling	3.5	5558
Weave	3.6	Visual 1/
Pilling (type II)	3.7.1	5320 2/
pH	3.7.2	2811
Selvages thickness	3.8	5030

1/ One determination per sample unit and the results reported as "pass" or "fail".

2/ The pilling test shall be conducted in accordance with Method 5320 except that five specimens of the test cloth and one specimen of the standard sample shall be used concurrently. The pilling of the test specimens shall be evaluated against that exhibited by the standard sample and all specimens shall be equal to or better than the standard sample. Failure of any one of the test specimens shall be cause for rejection.

5. PREPARATION FOR DELIVERY

5.1 Put-up and packaging. Put-up and packaging shall be level A or C as specified (see 6.2).

5.1.1 Levels A and C. The cloth shall be put up and packaged in accordance with the applicable requirements of PPP-P-1132.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Levels A, B and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1132.

5.3 Marking. In addition to any special marking required in the contract or order, shipments shall be marked in accordance with the requirements of PPP-P-1132.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The cloth is intended for use in the manufacture of clothing items for personnel of the Department of Defense.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Type and class of cloth required (see 1.2).
(c) When a first article is required (see 3.2, 4.3 and 6.7).
(d) Color (see 3.4).
(e) Minimum length if other than specified (see 3.9).
(f) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 Standard sample. For access to standard sample, address the procuring office issuing the invitation for bids.

6.4 A suggested but not mandatory dyestuff formulation for Army Green 44, Army Green 344, Shade Tan 3729, Army Blue 150, Army Blue 151, Taupe 79, Dark Blue 2316, Light Blue 2317, Army Blue 450 and Army Blue 451 is as follows:

Wool components, Army Green 44 or 344

Acid Green 58
Acid Green 70
Acid Orange 85
Acid Orange 86

The ratio of Acid Green 58 to Acid Green 70 shall be approximately 1 to 1.

Polyester component Army Green 344

#1	or	#2
Disperse Blue 62		Disperse Blue 27, CI 60767
Disperse Yellow CI 26072		Disperse Yellow 42, CI 10338
Disperse Red 59		Disperse Red 4, CI 60755
Disperse Violet 18		Disperse Yellow 23, CI 26074

Wool component Tan 3729

Acid yellow 128
Neutral Premetallized Olive Green B
Acid Brown 45
Acid Red 182

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

Polyester component Tan 3729

Disperse Yellow CI 26072
Disperse Blue 64
Disperse Blue GR
Disperse Red 4, CI 60755

Army Blue 150

Slate primary:

Mordant Blue 9, CI 14855
Mordant Blue 13, CI 16680
Acid Black 48, CI 65005

Red-Blue Primary:

Mordant Blue 9, CI 14855
Mordant Blue 13, CI 16680
Acid Black 48, CI 65005
Mordant Orange 8

Blue Primary:

Mordant Blue 13, CI 16680
Acid Black 48, CI 65005

Army Blue 151

Red Primary:

Acid Blue 80, CI 61585
Acid Blue 81, CI 64515
Mordant Red 7, CI 18760

Blue Primary:

Acid Blue 80, CI 61585
Mordant Blue 7, CI 17940
Mordant Blue 13, CI 16680

Green Primary:

Sol. Vat Blue 1, CI 73002
Sol. Vat Violet 2, CI 73386

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

Taupe 79

Acid Black 60
Acid Brown 36
Acid Black 138
Acid Orange 85
Acid Brown 28

It is suggested, but not mandatory, that Chrome dyes be used when Dark Blue 2316 is specified and a combination of Vat, Indigo and Chrome dyes be used for Light Blue 2317.

Wool-Polyester-Army Blue 450

Wool Components
Slate Primary:

Mordant Blue 9, CI 14855
Mordant Blue 13, CE 16680
Acid Black 48, CI 65005

Red-Blue Primary:

Mordant Blue 9, CI 14855
Mordant Blue 13, CI 16680
Acid Black 48, CI 65005
Mordant Orange 8

Blue Primary:

Mordant Blue 13, CI 16680
Acid Black 48, CI 65005

Polyester Components

Disperse Developed Black DC
Disperse Developed Blue 64
Disperse Developed Blue BL
Disperse Developed Orange 3, CI 11005

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

Wool-Polyester-Army Blue 451

Wool Components
Red Primary:

Acid Blue 80, CI 61585
Acid Blue 81, CI 64515
Mordant Red 7, CI 18760
Mordant Orange 8

Blue Primary:

Acid Blue 80, CI 61585
Mordant Blue 7, CI 17940
Mordant Blue 13, CI 16680

Green Primary:

Sol. Vat Blue 1, CI 73002
Sol. Vat Violet 2, CI 73386

Polyester Components

Disperse Blue 59
Disperse Blue 63
Disperse Blue 60
Disperse Orange 21

6.5 The dyeing of the wool and the polyester fibers together in a single operation is undesirable because of the tendency to lower colorfastness and the chance that the degree of colorfastness exhibited by the standard sample cannot be met (see 3.4).

6.6 Notes of caution to manufacturers.

6.6.1 Polyester fiber type. The choice of the polyester fiber type should be made by the supplier for a minimum pilling tendency and the fiber which will meet the colorfastness level of the specification (see 3.3.1.3 and 3.4.3).

6.6.2 Staple length. The longest staple length commensurate with the staple of the wool, with proper twist multipliers to prevent pilling, should be used in the manufacture of this cloth (see 3.3.1.3).

6.6.3 Twist in the yarns. The twist in the yarns for both the singles and the ply shall be such that the polyester fibers shall be so locked within the yarn structure that migration in subsequent processing and the weaving of the cloth will not form pills (see 3.3.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

6.6.4 Pilling, type II. The cloth should be closely singed in order to minimize the amount of pilling (see 3.7.1).

* 6.7 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of ASPR 7-104.55. The first article should be a preproduction sample consisting of 3 continuous yards of the finished cloth. The contracting officer should include specific instructions in all procurement instruments regarding arrangements for inspection and approval of the first article.

6.8 Marginal notations. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and suppliers are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - SA
Air Force - 11

Review activities:

Army - MD
Navy - MC
Air Force - 45, 82

User activity:

Navy - CG

Preparing activity:

Army - GL

Project No. 8305-0143

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

Cloth, Gabardine: Wool, Polyester and Wool MIL-C-10176H

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.