MIL-C-10176H
AMENDMENT-2
4 August 1981

SUPERSEDING
Amendment-1
19 February 1976

MILITARY SPECIFICATION

CLOTH, GABARDINE; WOOL, POLYESTER AND WOOL

This amendment forms a part of Military Specification MIL-C-10176H, dated 27 September 1974, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

1.2 under "Type II - Polyester and Wool blend": Add "Class 12 - 10.6 ounce".

PAGE 2

2.1 under "STANDARDS FEDERAL": Add "FED-STD-4 - Glossary of Fabric Imperfections".

PAGE 3

3.3.1.1 under "Class 11": Add "Class 12 64's U.S. Standard".

PAGE 4

3.4.2 Delete and substitute:

* "3.4.2 Matching. The color of the dyed cloth shall match the standard sample under artificial daylight having a color temperature of 7000 ± 500 kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2850 ± 100 kelvin."

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

PAGE 5

Table I, add the following under their respective columns:

Type	Class	Weight per linear yard 56 in. width basis (ozs.) Minimum	Yarns per inch minimum Warp	Yarns per inch minimum Filling	Breaking strength (pounds) minimum Warp	Breaking strength (pounds) minimum Filling	Shrinkage percent maximum Warp	Shrinkage percent maximum Filling
"II	12	10.6	108	58	140	72	3.0	2.0"

3.6 Add the following under their respective columns:

Type	Class	Weave
"II	12	2/2 right twill"

PAGE 6

* 3.8 Delete and substitute:

"3.8 Selvages. The selvages shall be so constructed that in the finished cloth they shall lie flat when the material is laid out for cutting."

PAGE 8

4.4.2.1: Delete the fourth and fifth sentences.

Add new paragraph as follows:

* "4.4.2.1.1 Limits of slubs and knots. Only slubs and knots which exceed "D" for slubs and "C" for knots on the Sears Fabric Defect Scale (see 6.10) shall be scored."

PAGE 10

* Table III: Delete selvages thickness and all its applicable data.

Add the following in their respective column:

"Mothproofing	3.4.1	3/"

Below table III, add the following footnote:

"3/ The test for percent mothproofing compound shall be as specified in MIL-C-43665. For type II cloth, the percent mothproofing compound shall be determined and calculated using the procedure for specimens containing 100 percent wool."

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.

Add the following paragraphs:

* 6.10 Sears Fabric Defect Scales are available from Sears Roebuck and Company, Department 733Q, "Sears Defect Replica Kit", Sears Tower, Chicago, IL 60684."

6.11 Changes from previous issue. The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - NU
Air Force - 11

Preparing activity:

Army - GL

Project No. 8305-0802

Review activities:

Army - MD
Navy - MC
Air Force - 45, 99

User activity:

Navy - CG

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:39Z
Check the source to verify that this is the current version before use.