MILITARY SPECIFICATION
BARIUM NITRATE

This interim amendment is issued for use by U.S Army Armament Research and Development Command, with Military Specification MIL-B-162D, dated 7 February 1968.

Page 1

Add the following Preamble underneath the title: "This specification is approved by U.S. Army Armament Research and Development Command and is available for use by all Departments and Agencies of the Department of Defense."

Page 3

3.2 Table I, Class I: Delete "Heavy metals...None," and substitute "Heavy metals, max...0.05."

Page 13

4.3.9: Delete in its entirety and substitute the following: Heavy metals (applicable to Class 1 only).-Dissolve 500 grams of the sample in distilled water. Add a few drops of hydrochloric acid and then pass in hydrogen sulfide for two or three minutes. (Since it is imperative that no elemental sulfur be introduced into the sample solution from the hydrogen sulfide generator, suitable precautions must be taken.) Inspect for the formation of a precipitate. Render the solution ammoniacal and allow to stand for three hours. Again inspect for the formation of a precipitate. If a precipitate is present, filter the material through a tared, fine porosity, fritted glass crucible. Wash the precipitate with ammoniacal water (3 or 4 washings of 10 ml. each). Dry the crucible at $100^{\circ} \pm 5^{\circ}C$ for 1 hour. Cool in a dessicator, and weigh. Calculate percent heavy metals.

$$\% \text{ H.M.} = \frac{\text{wt. of residue}}{\text{wt. of sample.}}$$

Custodians:
Army-(AR)

Preparing Activity:
Army-(AR)

Project No. 6810-AB21

Source: https://assist.dla.mil -- Downloaded: 2020-10-16 05:29 GMT
Check the source to verify that this is the current version before use.