MIL-B-162D (AR)
INT. AMENDMENT 2
7 March 1986
SUPERSEDING
INT. AMENDMENT 1
17 April 1981

MILITARY SPECIFICATION

BARIUM NITRATE

This Interim Amendment is approved for use within the US Army Armament Munitions and Chemical Command with MIL-B-162D, dated 7 February 1968.

PAGE 1

Add the following preamble underneath the title: "This Specification is approved for use by all Departments and Agencies of the Department of Defense."

PAGE 3

3.2 Table I, Class I: Delete "Heavy metals....None," and substitute "Heavy metals, max...0.05". For "Barium nitrate, min", delete "99.7" and substitute "99.0".

PAGE 13

4.3.9: Delete in its entirety and substitute the following:

"4.3.9 Heavy metals (applicable to Class I only).-Dissolve 500 grams of the sample in distilled water. Add a few drops of hydrochloric acid and then pass in hydrogen sulfide for two or three minutes. (Since it is imperative that no elemental sulfur be introduced into the sample solution from the hydrogen sulfide generator, suitable precautions must be taken.) Inspect for the formation of a precipitate. Render the solution ammoniacal and allow to stand for three hours. Again inspect for the formation of precipitate. If a precipitate is present, filter the material through a tared, fine porosity, fritted glass crucible. Wash the precipitate with ammoniacal water (3 or 4 washings of 10 ml. each). Dry the crucible at 100° ± 5°C for 1 hour. Cool in a dessicator, and weigh. Calculate percent heavy metals.

$$\% \text{ H.M.} = \frac{\text{wt. of residue}}{\text{wt. of sample}} \times 100$$

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 6810-AB51)

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T05:22Z
Check the source to verify that this is the current version before use.