METRIC
A-A-59974
June 17, 2016

COMMERCIAL ITEM DESCRIPTION

POLISH, METAL

The General Services Administration has authorized the use of this commercial item description for all federal agencies.

1. SCOPE. This commercial item description (CID) covers metal polish cleaners suitable for polishing and as a tarnish preventive for aluminum, brass and related alloys, bronze, chrome, copper, nickel, stainless steel, sterling silver, or silver-plated articles.

2. SALIENT CHARACTERISTICS.

2.1 General. The polish shall contain suitable cleaning agents and finely divided abrasives. The polish shall be a uniform liquid and shall not contain any sediment that cannot readily be put into suspension by thorough shaking.

2.2 Prohibited materials. The polish shall not contain any materials above the threshold for trace amount that have a severity category of either catastrophic or critical in the prohibited and restricted chemicals tables in the NAVSEA List of Targeted Chemicals (N-LTC) appendix of T9070-AL-DPC-020/077-2, NAVSEA Hazardous Material Avoidance Process. The threshold for trace amount is defined as less than 1 percent for non-carcinogenic compounds and less than 0.1 percent for carcinogenic compounds. Furthermore, the polish shall not contain any percentage of linseed oil due to its ability to spontaneously combust.

2.3 Volatile organic compound (VOC) levels. VOC levels of the polish shall be stated as a percent of VOCs by weight, when prepared in the dilution ratio as directed on the manufacturer's label, and shall not exceed the California Air Resources Board (CARB) 17 CCR § 94509 VOC standard for metal polish or cleanser.

2.4 pH. The pH of a 1 percent aqueous solution shall be a minimum of 8.0 and a maximum of 11.0 when tested in accordance with ASTM E70.

2.5 Flash point. The flash point shall be greater than 93.3 °C (200 °F) when tested in accordance with ASTM D56.

2.6 Eutrophication and phosphate. The polish shall comply with the U.S. Environmental Protection Agency (EPA) Safer Choice Standard eutrophication and phosphate criteria.

2.7 Aquatic toxicity. The polish, when used as directed on the label in a use-dilution solution, shall not be toxic to aquatic life in accordance with the United Nations Economic Commission for Europe (UNECE) Globally Harmonized System of Classification and Labelling of Chemicals (GHS) criteria for acute and chronic aquatic toxicity. More specifically, the polish at use-dilution shall not have an acute toxicity within GHS Categories 1 and 2 for short-term (acute) aquatic hazard, and shall not have a chronic toxicity within GHS Categories 1 and 2 for long-term aquatic hazard.

2.8 Cleaning efficiency. The polish shall have a cleaning efficiency greater than 85 percent when tested as follows, or following other equivalent or comparable test methods:

a. Tarnish two metal panels by immersion for 5 minutes in a tarnishing solution (ammonium chloride and cupric sulfate for brass, potassium sulfide for silver). Rinse the panels with tap water and wipe dry with a clean, soft cloth.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard DC 20376-5160 or emailed to CommandStandards@navy.mil, with the subject line "Document Comment". Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

FSC 7930

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:32Z
Check the source to verify that this is the current version before use.

b. Apply 8 milliliters of polishing solution on one tarnished panel and stroke 2 minutes. Repeat one more time with panel two. Visually inspect the panels and estimate percent tarnish removed. Calculate average percent of tarnish removed.

c. Report average cleaning efficiency results for the polish.

3. REGULATORY REQUIREMENTS. The offeror/contractor is encouraged to use recovered materials or biobased materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

4. PRODUCT CONFORMANCE PROVISIONS. The products provided shall meet the salient characteristics of this CID, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

5. PACKAGING. Preservation, packing, and marking shall be as specified in the contract or order.

6. NOTES.

6.1 Source of documents.

6.1.1 ASTM International. ASTM standards are available from ASTM International, 100 Barr Harbor Dr., P.O. Box C700, West Conshohocken, PA 19428-2959 or online at www.astm.org.

6.1.2 California Code of Regulations (CCR). The CCR may be obtained online at http://www.oal.ca.gov/CCR.htm.

6.1.3 EPA. The U.S. EPA Safer Choice may be obtained from the Environmental Protection Agency, Ariel Rios Building, 1200 Pennsylvania Avenue, N.W., Washington, DC 20460 or online at https://www.epa.gov/saferchoice/standard.

6.1.4 FAR. The FAR may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402 or online at https://www.acquisition.gov/far.

6.1.5 GHS. The UNECE GHS may be obtained online at http://www.unece.org/trans/danger/publi/ghs/ghs_rev06/06files_e.html.

6.1.6 Naval Sea Systems Command (NAVSEA) Publications. Copies of T9070-AL-DPC-020/077-2 are available online via Technical Data Management Information System (TDMIS) at https://mercury.tdmis.navy.mil/ by searching for the document number without the suffix. Refer questions, inquiries, or problems to: DSN 296-0669, Commercial (805) 228-0669. T9070-AL-DPC-020/077-2 is available for ordering (hard copy) via the Naval Logistics Library https://nll.ahf.nmci.navy.mil. For questions regarding the NLL, contact the NLL Customer Service at nllhelpdesk@navy.mil, (866) 817-3130, or (215) 697-2626/DSN 442-2626.

6.2 Ordering data. The contract or order should specify the following:

a. CID document number and revision letter.

b. Quantity required.

c. Product conformance provisions.

d. Packaging requirements.

6.3 Key words.

Tarnish preventive

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:32Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians:
Army – MI
Navy – SH

Review Activities:
Army – AV, GL
Navy – AS, CG, MC

CIVIL AGENCY COORDINATING ACTIVITY:
GSA – FAS

Preparing Activity:
Navy – SH
(Project 7930-2015-012)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:32Z
Check the source to verify that this is the current version before use.