MILITARY SPECIFICATION SHEET

CHAFF PACKAGE (TYPE RR-152A/AL)

This specification is approved for use by the Naval Air Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the chaff package described herein shall consist of this document and the latest issue of specification MIL-C-85002.

APPLICABLE DOCUMENTS:

Military:

MIL-R-60346 — Roving, Glass, Fibrous

REQUIREMENTS:

Item description: Metalized glass rope materials (stringballs).

Detail requirements:

Components:

Stringballs: Rope element wound on a core such that the core increases the deployment rate of the rope element.

Rope element: Twenty glass fibers drawn from Type E glass marbles made from composition similar to that specified in MIL-R-60346.

Coating: 10 + 2 - 0 fibers shall be coated the entire length with 99 percent (minimum) pure aluminum at .9 mil diameter (nominal). Remaining 10 + 0 - 2 uncoated fibers shall be .5 mil diameter (nominal).

Temper: Stringball rope temper determined by glass fiber composition specified in MIL-R-60346.

Weight of stringball rope: 3.5 ± .5 grams per 1000 feet of length taken as an average of ten 1000 ft samples.

FSC 5865

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:58Z
Check the source to verify that this is the current version before use.

Length of stringball rope element: 200 ± 20 feet.

Processing solution: Applied to rope material at time of manufacture.

Solution properties: A sizing material, a lubricant and an anti-foam agent. Solution shall not prevent deployment of the stringball rope during extreme environmental conditions.

Core: Provide additional weight to aid in unwinding rope element.

Weight of core: 3.75 ± .5 grams.

Dimensions of core: The dimensions of the core shall be such that the stringball assembly shall fit in unit partition, not unwind during storage, but deploy from partition when dispensed.

Material: Optional to meet other requirements.

Winding: Continuous throughout with no loose ends, would with each turn and layer free from entanglement and not tether to the core.

Chaff package: Consists of outer sleeve containing eighteen stringballs and non-chaff components such as vibration protectors and partitions in accordance with DL 1050AS132.

Tape marking: Red ink in accordance with DL 1050AS113.

Assembly:

Chaff package: Eighteen stringballs assembled in chaff package (outer sleeve) with non-chaff components in accordance with DL 1050AS132. Package shall separate as individual stringballs and shall not unravel prior to dispensing, but shall allow free and total dispersion upon deployment.

Vibration protector: Conform to DL 1050AS132.

Dimensions: Permitted to vary to provide a tight assembled package.

Inner packs: Conform to DL 1050AS132.

Foam springs: Conform to DL 1050AS132.

Quality assurance provisions:

Radar requirements: UHF radar with 1.5 - 2 degrees beamwidth horizontally polarized antenna.

Frequency: 435 ± 21.75 MHz

PRF: 320 ± 32 pps

Pulsewidth: 1.0 us

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:58Z
Check the source to verify that this is the current version before use.

Radar cross-section test procedures:

Aircraft operation: In accordance with figure 3 of MIL-C-85002 and flight profile data of table I.

TABLE I. Flight profile test data.

Flight requirement	Value
Aspect Angle	5° - 20°
Aircraft	180 kts. TAS
Altitude	10,000 feet
Dispense Command	35,000 yards
Standby Command	36,000 yards

Data gathering: For acceptable data in gates 12 through 15, range in yards divided by sine of aspect angle shall be equal to or greater than 211,053.

Standby command: See table I.

Dispense command: See table I.

Data from gates 1 through 15: Spaced 1,000 nanoseconds in time.

Full scale value: $10m^2$.

Data processing:

Radar resolution cells: 1000 to 6500 feet behind the aircraft.

Data selection:

Running average: 400 consecutive pulse-to-pulse RCS values.

Correction factors:

Aspect angle: Use ℓ/D ratio of 10 and dipole density of 20 dipoles per meter squared.

Antenna gain: Antenna pattern as specified in MIL-STD-2071 or fourth order polynominal.

Fourth order polynominal for UHF radar:
$.0249023X^4 + .168213X^3 - .666504X^2 + .0185547X + .999268$
(where x = angle off boresite in degrees)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:58Z
Check the source to verify that this is the current version before use.

Radar cross-section (RCS): Measured 1000 through 6500 feet behind aircraft shall meet or exceed .30 square meter per gate.

Average of 10 or more units: Must equal or exceed .50 square meter per gate.

Preparing Activity
Navy - AS
(Project 5865-N030-2)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:58Z
Check the source to verify that this is the current version before use.