The documentation and process conversion measures necessary to comply with this revision shall be completed by 19 March 2012.

INCH-POUND
MIL-PRF-19500/444M
19 December 2011
SUPERSEDING
MIL-PRF-19500/444L
w/AMENDMENT 2
25 January 2010

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, DIODE, SILICON, SWITCHING, SCHOTTKY, TYPES 1N5711-1, 1N5711UR-1, 1N5711UB, 1N5711UBCA, 1N5711UBD, 1N5711UBCC, 1N5712-1, 1N5712UR-1, 1N5712UB, 1N5712UBCA, 1N5712UBD, 1N5712UBCC, 1N6857-1, 1N6857UR-1, 1N6858-1, AND 1N6858UR-1, JAN, JANTX, JANTXV, JANS, JANHC, AND JANKC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for Schottky barrier diodes. Four levels of product assurance are provided for each encapsulated device type as specified in MIL-PRF-19500. Two levels of product assurance are provided for each unencapsulated device type.

1.2 Physical dimensions. See figure 1, DO-35, figure 2, DO-213AA, figure 3 (UB), and figure 4.

1.3 Maximum ratings. Unless otherwise specified T_A = +25°C.

Type	V_{RWM}	I_{O1}	I_{O2} (1)	T_{STG} and T_J	$R_{\Theta JL}$ L = .375 inch (9.52 mm) (2)	$R_{\Theta JEC}$ (UR)	$R_{\Theta JSP}$ (UB)	ESDS class
	V(pk)	mA dc	mA dc		(leaded)	(UR)	(UB)	
1N5711-1	50	33 (3)	5	-65°C to +150°C	250			1
1N5711UR-1	50	33 (4)	5			100		1
1N5711UB	50	33 (4)	5				100	1
1N5711UBCA	50	33 (4)	5				100	1
1N5711UBCC	50	33 (4)	5				100	1
1N5711UBD	50	33 (4)	5				100	1
1N6858-1	50	75 (5)	10		250			1
1N6858UR-1	50	75 (6)	10			100		1
1N5712-1	16	75 (5)	20		250			1
1N5712UR-1	16	75 (6)	20			100		1
1N5712UB	16	75 (6)	20				100	1
1N5712UBCA	16	75 (6)	20				100	1
1N5712UBCC	16	75 (6)	20				100	1
1N5712UBD	16	75 (6)	20				100	1
1N6857-1	16	150 (7)	50		250			1
1N6857UR-1	16	150 (8)	50			100		1

See notes on next page.

* Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to semiconductor@dla.mil . Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.daps.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

1.3 Maximum ratings – Continued.

(1) Maximum I_O rating to ensure τ_{CL} compliance (< 100 ps).
(2) Lead length = .375 inch (9.52 mm).
(3) At T_L = +130°C and L = .375 inch, derate I_O to 0 at +150°C.
(4) At T_{EC} and T_{SP} = +140°C, derate I_O to 0 at +150°C.
(5) At T_L = +110°C and L = .375 inch, derate I_O to 0 at +150°C.
(6) At T_{EC} and T_{SP} = +130°C, derate I_O to 0 at +150°C.
(7) At T_L = +70°C and L = .375 inch, derate I_O to 0 at +150°C.
(8) At T_{EC} and T_{SP} = +110°C, derate I_O to 0 at +150°C.


1.4 Primary electrical characteristics.

Type (1)	$V_{(BR)1}$ I_R = 10 µA dc (min)	V_{F1} I_F = 1 mA dc (max)	V_{F2} I_F = 15 mA dc (max)	I_{R1} V_R = 50 V dc (max)	C V_R = 0, f = 1 MHz V_{sig} = 50 m V(pk) (max)	τ_{CL} (max)		$Z_{\Theta JX}$ (max)
	V dc	V dc	V dc	nA dc	pF	ps	mA	°C/W
1N5711-1	70	0.410	1.0	200	2.0	100	5	40
1N6858-1	70	0.360	0.65	200	4.5	100	10	40

Type (1)	$V_{(BR)1}$ I_R = 10 µA dc (min)	V_{F1} I_F = 1 mA dc (max)	V_{F2} I_F = 35 mA dc (max)	I_{R1} V_R = 16 V dc (max)	C V_R = 0, f = 1 MHz V_{sig} = 50 mv(pk) (max)	τ_{CL} (max)		$Z_{\Theta JX}$ (max)
	V dc	V dc	V dc	nA dc	pF	ps	mA	°C/W
1N5712-1	20	0.410	1.0	150	2.0	100	20	40
1N6857-1	20	0.350	0.75	150	4.5	100	50	40

(1) Electrical characteristics are for all package styles.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.




Symbol	Dimensions				Notes
	Inches		Millimeters		
	Min	Max	Min	Max	
BD	.068	.076	1.73	1.93	2, 3
BL	.125	.170	3.18	4.32	2
LD	.014	.022	0.36	0.56	
LL	1.000	1.500	25.40	38.10	

NOTES:
1. Dimensions are in inches. Millimeters are given for general information only.
2. Dimensions BL and LD include all components of the diode periphery except the sections of the leads over which the diameter is controlled.
3. Dimension BD shall be measured at the largest diameter.
4. In accordance with ASME Y14.5M, diameters are equivalent to Φx symbology.

1N5711-1, 1N5712-1, 1N6857-1, and 1N6858-1

FIGURE 1. Physical dimensions, (DO-35).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.




Symbol	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
BD	.063	.067	1.60	1.70
BL	.130	.146	3.30	3.71
ECT	.016	.022	0.41	0.55
S	.001 Min		0.03 Min	

NOTES:
1. Dimensions are in inches. Millimeters are given for general information only.
2. In accordance with ASME Y14.5M, diameters are equivalent to Φx symbology.

1N5711UR-1, 1N5712UR-1, 1N6857UR-1, and 1N6858UR-1


FIGURE 2. Physical dimensions, (DO-213AA).


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.



Symbol	Dimensions				Symbol	Dimensions			
	Inches		Millimeters			Inches		Millimeters	
	Min	Max	Min	Max		Min	Max	Min	Max
BH	.046	.056	1.17	1.42	LS_1	.035	.040	0.89	1.02
BL	.115	.128	2.92	3.25	LS_2	.071	.079	1.81	2.01
BW	.085	.108	2.16	2.74	LW	.016	.024	0.41	0.61
CL		.128		3.25	r		.008		0.20
CW		.108		2.74	r1		.012		0.31
LL1	.022	.038	0.56	0.96	r2		.022		0.56
LL2	.017	.035	0.43	0.89					


1N5711UBCA
1N5712UBCA






1N5711UB
1N5712UB

1N5711UBD
1N5712UBD






1N5711UBCC
1N5712UBCC

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Hatched areas on package denote metallized areas.
4. Pad 4 = Shielding connected to the lid.
5. In accordance with ASME Y14.5M, diameters are equivalent to Φx symbology.

* FIGURE 3. Physical dimensions, surface mount (UB version).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.



BACKSIDE IS CATHODE

Ltr	Inches		Millimeters	
	Min	Max	Min	Max
A	.004	.005	0.102	0.127
B	.0130	.0170	0.330	0.432

Ltr	Inches		Millimeters	
	Min	Max	Min	Max
A	.0029	.0035	0.074	0.089
B	.0130	.0170	0.330	0.432

Ltr	Inches		Millimeters	
	Min	Max	Min	Max
A	.0055	.0065	0.140	0.165
B	.0130	.0170	0.330	0.432

NOTES:
1. Dimensions are in inches. Millimeters are given for general information only.
2. Element evaluation accomplished utilizing TO-5 package.
3. The physical characteristics of the die are:
   Metallization:
   Top (anode): Al.
   Back (cathode): Au.
   Al thickness: 25,000 Å minimum.
   Gold thickness: 4,000 Å minimum.
   Chip thickness: .010 inch (0.25 mm) ±.002 inch (±0.05 mm).
4. In accordance with ASME Y14.5M, diameters are equivalent to Φx symbology.

FIGURE 4. Physical dimensions, die.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Copies of these documents are available online at https://assist.daps.dla.mil/quicksearch/ or https://assist.daps.dla.mil or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DRAWING

DEFENSE ELECTRONICS SUPPLY CENTER (DESC)

C68001 - Test Fixture for Effective Minority Carrier Lifetime.

(Copies of DESC Drawing C68001 are available from Defense Supply Center, Columbus, ATTN: DSCC-VAC, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail Semiconductor@dla.mil .)

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500 and as follows.

EC	End-cap.
τ_{CL}	Effective carrier lifetime.
UR	Surface mount case outline, round end-cap.

3.4 Interface and physical dimensions. Interface and physical dimensions shall be as specified in MIL-PRF-19500 and figures 1, 2, 3, and 4 herein.

3.4.1 Lead finish. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Diode construction. All devices (except UB version) shall be metallurgically bonded, double plug construction in accordance with the requirements of MIL-PRF-19500. All glass diodes shall be designed with sufficient thermal compensation in the axial direction to optimize tensile and compressive stresses. Dimensional analysis is required of all materials used to achieve axial thermal compensation. Dimensional tolerances and corresponding coefficient of thermal expansion (CTE) shall be documented on the DSCC Design and Construction Form 36D and shall be approved by the qualifying activity to maintain qualification. Dimensional tolerances shall be sufficiently tight enough to prevent excessive stresses due to the inherent CTE mismatch. The UB devices shall be eutectically mounted and wire bonded in a ceramic package.

3.5 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4 and table I.

3.6 Electrical test requirements. The electrical test requirements shall be table I as specified herein.

3.7 Marking. Marking shall be in accordance with MIL-PRF-19500. Manufacturer's identification and date code shall be marked on the devices. Initial container package marking shall be in accordance with MIL-PRF-19500. The polarity shall be indicated with a contrasting color band to denote the cathode end. The prefixes JAN, JANTX, JANTXV, and JANS can be abbreviated as J, JX, JV, or JS, respectively. The part number may be reduced to J5711, JX5711, JV5711, or JS5711. No color coding shall be permitted for part numbering.

3.7.1 Polarity. The polarity of axial leaded devices shall be indicated with a contrasting color band to denote the cathode end. No color coding will be permitted for the part number.

3.7.1.1 UB devices. 'UB' devices do not require polarity marking.

3.7.2 UR devices. For 'UR' version devices only, all marking, except polarity may be omitted from the body, but shall be retained on the initial container. Polarity marking of 'UR' devices shall consist, as a minimum, a band or three contrasting dots spaced equally around the periphery of the cathode.

3.8 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

4.1.1 Sampling inspection. Sampling inspection shall be in accordance with MIL-PRF-19500.

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.2.1 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not require the performance of table II tests, the tests specified in table II herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.

4.2.2 JANHC and JANKC devices. Qualification shall be in accordance with MIL-PRF-19500.

4.3 Screening. Screening shall be in accordance with table E-IV of MIL-PRF-19500 and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table E-IV of MIL-PRF-19500)	Measurement	
	JANS	JANTXV and JANTX level
1a	Required	Not required
1b	Required	Required (JANTXV only)
2	Not required	Not required
3a 3b (1) 3c	Required Not applicable Required (see 4.3.3)	Required Not applicable Required (see 4.3.3)
4	Required for UB	Not applicable
5	Required for UB	Not applicable
6	Not applicable	Not applicable
8	Required	Not required
9 and 10	Not applicable	Not applicable
11	Required I_{R1} and V_{F1}	Required I_{R1} and V_{F1}
12	Required, see 4.3.1	Required. See 4.3.1, t = 48 hours
(2) 13	Required. Subgroup 2 and 3 of table I herein; $\Delta I_{R1} \leq 100$ percent of initial reading or 25 nA whichever is greater; $\Delta V_{F1} \leq \pm 20$ mV dc.	Subgroup 2 of table I herein; $\Delta I_{R1} \leq 100$ percent of initial reading or 50 nA whichever is greater; $\Delta V_{F1} \leq \pm 40$ mV dc.

(1) Thermal impedance shall be performed any time after sealing provided temperature cycling is performed in accordance with table E-IV of MIL-PRF-19500, JANTX and JANTXV levels do not need to be repeated in screening requirements.
(2) Test within 24 hours after removal from test.

4.3.1 Burn-in conditions. Burn-in conditions are as follows: High temperature reverse bias (HTRB), method 1038 of MIL-STD-750, test condition A, V_R = 40 V; T_A = +150°C (min) for 1N5711 and 1N6858. V_R = 12.8 V, T_A = +150°C (min) for 1N5712 and 1N6857.

4.3.2 Screening (JANHC or JANKC). Screening of JANC die shall be in accordance with MIL-PRF-19500, “Discrete Semiconductor Die/Chip Lot Acceptance”. Burn-in duration for the JANKC level follows JANS requirements; the JANHC follows JANTX requirements.

4.3.3 Thermal impedance measurements. The thermal impedance measurements shall be performed in accordance with method 3101 or 4081 of MIL-STD-750, as applicable, using the guidelines in that method for determining I_H and I_M. t_{MD} shall be 70 µs maximum, t_H shall be 10 ms maximum. See group B inspection, subgroup 6, paragraph 4.4.2.1, group C inspection, subgroup 5, paragraph 4.4.3, and group E, subgroup 4 of table II herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

4.3.4 JAN testing. JAN level product will have temperature cycling and thermal impedance testing performed in accordance with MIL-PRF-19500, JANTX level screening level requirements.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500 and table I herein.

4.4.2 Group B inspection . Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VIa (for JANS) and table E-VIb (for JAN, JANTX, and JANTXV) of MIL-PRF-19500, and as follows. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

4.4.2.1 Group B inspection, table E-VIa (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
B3	1051	Required for UB.
B3	See 4.5.5	Preconditioning for temperature cycling.
B4	1037	I_{O1} at rated V_{RWM}; f = 60 Hz; T_A = room ambient as defined in 4.5 of MIL-STD-750; $t_{on} = t_{off}$ = 3 minutes minimum for 2,000 cycles.
B5	1038	HTRB in accordance with 4.3.1.
B6	4081	$R_{\Theta JL}$ = 250°C/W .375 inch (9.52 mm) lead length (non-surface mount).

4.4.2.2 Group B inspection, table E-VIb (JAN, JANTX and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Condition
B2	See 4.5.5	Preconditioning for temperature cycling.
B2	1056	0°C to +100°C, 10 cycles (glass diodes only), n = 22, c = 0.
B2	1051	-55°C to +150°C, 25 cycles, n = 22, c = 0.
B3	1038	HTRB, in accordance with 4.3.1.
B4	2101	See 4.5.4. (Scribe and break not applicable for UB)
B4	2075	See 4.5.4.1. (Scribe and break not applicable to UB.)
B6	1032	T_A = +150°C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

* 4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500, and as follows. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

Subgroup	Method	Condition
C2	See 4.5.5	Preconditioning for temperature cycling.
C2	1056	0°C to +100°C, 15 cycles, n = 22, c = 0.
C2	1051	-55°C to +150°C, 20 cycles, n = 22, c = 0.
C2	2036	(Not applicable to surface mount devices); lead fatigue conditions: Test condition E; .062 inch (1.57 mm) lead restriction from case. Tension conditions: Test condition A; 10 pounds, 15 seconds.
C5	4081	$R_{\Theta JEC}$ = 100°C/W (maximum) +25°C ≤ T_R ≤ +35°C, at T_H ≥ 25 seconds in still air. (See 4.3.3.)
C5	4081	$R_{\Theta JL}$ = 250°C/W (maximum) at .375 inch (9.52 mm) lead length, +25°C ≤ T_R ≤ +35°C, at T_H ≥ 25 seconds in still air. (See 4.3.3.)
C6	1038	HTRB in accordance with 4.3.1.

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the tests and conditions specified for subgroup testing in table E-IX of MIL-PRF-19500, and table II herein. Electrical measurements (end-points) shall be as specified in table II.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Steady-state operation life. This test shall be conducted with a half-sine wave of the specified peak voltage impressed across the diode in the reverse direction followed by a half-sine waveform of the specified average rectified current. The forward conduction angle of the rectified current shall not be greater than 180 degrees nor less than 150 degrees.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

* 4.5.2 Effective carrier lifetime (τ_{CL}). This test shall be measured with the device installed in the test fixture, DESC Drawing C68001 or equivalent, using the test set up shown on figure 5 herein. Adjust the signal generator to 54 MHz. Adjust the sensitivity of the oscilloscope to 5 mV/cm (1N5711), 10 mV/cm (1N6858), 20 mV/cm (1N5712), and 50 mV/cm (1N6857). With the device in the test fixture, adjust the output of the amplifier or VHF oscillator until the peak amplitude of the forward current is 5 cm as seen on the oscilloscope (5 mA (1N5711), 10 mA (1N6858), 20 mA (1N5712), and 50 mA (1N6857)).




FIGURE 5. Test setup for diode effective lifetime measurement.

Change the sensitivity of scope to 2 mV/cm (1N5711, 1N6858), 5 mV/cm (1N5712), or 10 mV/cm (1N6857). Under these conditions, the effective carrier lifetime is related to the amplitude designated as "τ_{CL} " shown on figure 6. This amplitude has the calibration of 200 ps/cm (1N5711), 100 ps/cm (1N6858), 125 ps/cm (1N5712), and 100 ps/cm (1N6857).




FIGURE 6. Oscilloscope display in diode effective lifetime measurement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

4.5.4 Decap analysis (for glass packages only). Scribe and break (scribe and break not applicable to UB packages). Scratch glass at cavity area with diamond scribe. Carefully snap open. Using 30X magnification, examine the area where die (or bonding material) is in contact with the plugs, verify metallurgical bonding area.

4.5.4.1 Decap analysis (for UB packages only). Decap the package. Carefully remove the lid. Using 30X magnification, examine the area where die (or bonding material) is in mounted to the header, verify wire bond area.

4.5.5 Preconditioning for temperature cycling (not applicable to UB packages).

a. Read and record I_{R1}, V_{F2}, and $Z_{\Theta JX}$. Maintain device serialization throughout testing.

b. Immerse device terminations into any suitable flux. Flux is used to prevent solder bridging across the terminations of device and to provide for a suitable contact needed for post electrical testing.

c. Immerse device terminations into solder. The devices terminations shall be immersed instantly and not gradually, and held completely immersed in the solder for 5 +2, -0 seconds. No dwell time over the solder pot shall be permitted. Maintain solder temperature to +260°C ±5°C.

d. The device shall be allowed to return to ambient prior to cleaning. Remove residue flux from the terminations by dipping the parts in isopropyl alcohol or other suitable solvent.

e. Test devices to method 1056 and 1051 of MIL-STD-750 and in accordance with MIL-PRF-19500.

f. Read and record I_{R1}, V_{F2}, and $Z_{\Theta JX}$, test subgroup 2 of table 1 herein.

g. Failure criteria: Subgroup 2 of table 1 herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limit		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical examination	2071					
Subgroup 2						
1N5711-1, all packages						
Thermal impedance	3101	See 4.3.3	$Z_{\Theta JX}$		40	°C/W
Forward voltage	4011	I_F = 1 mA dc	V_{F1}		.410	V dc
Forward voltage	4011	I_F = 15 mA dc	V_{F2}		1.0	V dc
Reverse current	4016	DC method; V_R = 50 Vdc	I_{R1}		200	nA dc
Breakdown voltage	4021	I_R = 10 μA dc	$V_{(BR)1}$	70		V dc
1N5712-1, all packages						
Thermal impedance	3101	See 4.3.3	$Z_{\Theta JX}$		40	°C/W
Forward voltage	4011	I_F = 1 mA dc	V_{F1}		.410	V dc
Forward voltage	4011	I_F = 35 mA dc	V_{F2}		1.0	V dc
Reverse current	4016	DC method; V_R = 16 Vdc	I_{R1}		150	nA dc
Breakdown voltage	4021	I_R = 10 μA dc	$V_{(BR)1}$	20		V dc
1N6857-1, UR-1						
Thermal impedance	3101	See 4.3.3	$Z_{\Theta JX}$		40	°C/W
Forward voltage	4011	I_F = 1 mA dc	V_{F1}		.350	V dc
Forward voltage	4011	I_F = 35 mA dc	V_{F2}		.75	V dc
Reverse current	4016	DC method; V_R = 16 Vdc	I_{R1}		150	nA dc
Breakdown voltage	4021	I_R = 10 μA dc	$V_{(BR)1}$	20		V dc
1N6858-1, UR-1						
Thermal impedance	3101	See 4.3.3	$Z_{\Theta JX}$		40	°C/W
Forward voltage	4011	I_F = 1 mA dc	V_{F1}		.360	V dc
Forward voltage	4011	I_F = 15 mA dc	V_{F2}		.65	V dc
Reverse current	4016	DC method; V_R = 50 Vdc	I_{R1}		200	nA dc
Breakdown voltage	4021	I_R = 10 μA dc	$V_{(BR)1}$	70		V dc
Subgroup 3						
1N5711-1, all packages High temperature operation		T_A = +150°C				
Reverse current	4016	DC method; V_R = 50 Vdc	I_{R2}		200	μA dc
Low temperature operation		T_A = -55°C				
Forward voltage	4011	I_F = 1 mA dc	V_{F3}		.55	V dc
Forward voltage	4011	I_F = 15 mA dc	V_{F4}		1.0	V dc
Breakdown voltage	4021	I_R = 10 μA dc	$V_{(BR)2}$	70		V dc

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limit		Unit
	Method	Conditions		Min	Max	
Subgroup 3 - Continued.						
1N5712-1, all packages High temperature operation		T_A = +150°C				
Reverse current	4016	DC method; V_R = 16 V dc	I_{R2}		150	µA dc
Low temperature operation		T_A = -55°C				
Forward voltage	4011	I_F = 1 mA dc	V_{F3}		0.55	V dc
Forward voltage	4011	I_F = 35 mA dc	V_{F4}		1.0	V dc
Breakdown voltage	4021	I_R = 10 µA dc	$V_{(BR)2}$	20		V dc
1N6857-1, UR-1 High temperature operation		T_A = +150°C				
Reverse current	4016	DC method; V_R = 16 V dc	I_{R2}		300	µA dc
Low temperature operation		T_A = -55°C				
Forward voltage	4011	I_F = 1 mA dc	V_{F3}		.55	V dc
Forward voltage	4011	I_F = 35 mA dc	V_{F4}		1.0	V dc
Breakdown voltage	4021	I_R = 10 µA dc	$V_{(BR)2}$	20		V dc
1N6858-1, UR-1 High temperature operation		T_A = +150°C				
Reverse current	4016	DC method; V_R = 50 V dc	I_{R2}		400	µA dc
Low temperature operation		T_A = -55°C				
Forward voltage	4011	I_F = 1 mA dc	V_{F3}		.55	V dc
Forward voltage	4011	I_F = 15 mA dc	V_{F4}		1.0	V dc
Breakdown voltage	4021	I_R = 10 µA dc	$V_{(BR)2}$	70		V dc
Subgroup 4						
Capacitance 1N5711-1, 1N5712-1, and UB and UR	4001	V_r = 0V dc; f = 1 MHz;	C		2.0	pF
1N6857-1, 1N6858-1, and UR		V_{sig} = 50 mV(pk) maximum			4.5	pF
Effective carrier lifetime (see 4.5.2) 2/		(See DESC drawing C68001)	τ_{CL}		100	ps
Subgroups 5, 6, and 7						
Not applicable						

1/ For sampling plan, see MIL-PRF-19500.
2/ Effective carrier lifetime needs to be performed only one time for each wafer lot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

* TABLE II. Group E inspection (all quality levels) - for qualification and requalification.

Inspection 1/	MIL-STD-750		Qualification
	Method	Conditions	
Subgroup 1			45 devices c = 0
Thermal shock	1056	100 cycles, -55°C to 100°C (glass diodes only)	
Temperature cycling (air to air)	1051	500 cycles, -55°C to 150°C	
Hermetic seal	1071		
Fine leak Gross leak			
Electrical measurements		See table I, subgroup 2 (V_{F1}, I_{R1} and thermal impedance)	
Subgroup 2			45 devices c = 0
Steady-state dc blocking life	1048	See 4.5.1, 1,000 hrs	
Electrical measurements		See table I, subgroup 2 (V_{F1} and I_{R1})	
Subgroup 4			
Thermal resistance	3131	$R_{\Theta JSP}$ can be calculated but shall be measured once in the same package with a similar die size to confirm calculations (may apply to multiple specification sheets).	n = 15, c = 0
Thermal impedance curves		See MIL-PRF-19500, table E-IX, group E, subgroup 4.	Sample size N/A
Subgroup 5			
Not applicable			
Subgroup 6			11 devices c = 0
ESD testing	1020		
Subgroup 7			
UB devices only			
Subgroup 9			45 devices
Resistance to glass cracking	1057	Test until failure occurs or to a maximum of 25 cycles, whichever comes first. Not applicable for UB device.	

1/ For sampling plan, see MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.1).

d. Product assurance level and type designator.

* 6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land and Maritime, ATTN: VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil . An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.daps.dla.mil .

6.4 Suppliers of die. The qualified die suppliers with the applicable letter version (e.g., JANHCA1N5711) will be identified on the QML.

JANC ordering information	
PIN	Manufacturer
	43611
1N5711-1 1N5712-1 1N6857-1 1N6858-1	JANHCA1N5711, JANKCA1N5711 JANHCA1N5712, JANKCA1N5712 JANHCA1N6857, JANKCA1N6857 JANHCA1N6858, JANKCA1N6858

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.

6.5 Substitutability of dash one parts. Non-dash-one devices have been deleted from this specification. Dash-one devices are a direct substitute for non dash-one devices and are preferred. The following table shows the direct substitutability.

Superseded part number	Superseding part number
1N5711	1N5711-1
1N5711UR	1N5711UR-1
1N5712	1N5712-1

* 6.6 Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
Navy - EC
Air Force - 85
NASA - NA
DLA - CC

Review activities:
Army - AR, MI, SM
Navy - AS, MC
Air Force - 19

Preparing activity:
DLA - CC

(Project 5961-2011-032)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.daps.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T01:58Z
Check the source to verify that this is the current version before use.