The documentation and process conversion measures necessary to comply with this document shall be completed by 10 February 2014.

INCH-POUND

MIL-PRF-19500/633D
10 December 2013
SUPERSEDING
MIL-PRF-19500/633C
3 June 2008

PERFORMANCE SPECIFICATION SHEET

* SEMICONDUCTOR DEVICE, FIELD EFFECT RADIATION HARDENED
TRANSISTORS, P-CHANNEL SILICON,
TYPES 2N7403 AND 2N7404, JANSD AND JANSR

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for a P-channel, enhancement-mode, MOSFET, radiation hardened (total dose and single event characterization), power transistor. One level of product assurance is provided for each device type as specified in MIL-PRF-19500.

1.2 Physical dimensions. See figure 1 (similar to TO-254).

1.3 Maximum ratings. T_A = +25°C, unless otherwise specified.

Type	P_T (1) T_C = +25°C	P_T T_A = +25°C	V_{DS}	V_{DG}	V_{GS}	$R_{\theta JC}$ Max	I_{D1} (2) (3) T_C =+25°C	I_{D2} T_C = +100°C	I_S (2)	I_{DM}	T_J and T_{STG}
	W	W	V dc	V dc	V dc	°C/W	A dc	A dc	A dc	A (pk)	°C
2N7403	125	50	-100	-100	±20	1.00	22	14	22	66	-55 to
2N7404			-200	-200	±20	1.00	15	9	15	45	+150


(1) Derate linearly 1.0 W/°C for T_C > +25°C;
(2) The following formula derives the maximum theoretical I_D limit. I_D is limited by package and internal wires and may be limited by pin diameter:

$$I_D = \sqrt{\frac{T_{JM} - T_C}{(R_{\theta JC}) \times (R_{DS}(on) \text{ at } T_{JM})}}$$

(3) See figure 2, maximum drain current graphs.

* Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.



Ltr	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
BL	.530	.550	13.46	13.97
CH	.249	.260	6.32	6.60
LD	.035	.045	0.89	1.14
LL	.510	.570	12.95	14.48
LO	.150 BSC		3.81 BSC	
LS	.150 TYP		3.81 TYP	
MHD	.139	.149	3.53	3.78
MHO	.665	.685	16.89	17.40
TL	.790	.800	20.07	20.32
TT	.040	.050	1.02	1.27
TW	.535	.545	13.59	13.84
Term 1	Drain			
Term 2	Source			
Term 3	Gate			

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. All terminals are isolated from case.
4. Die to base is BeO isolated, terminals to case ceramic (AL_2O_3) isolated.
5. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 1. Physical dimensions (similar to TO-254).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics at T_C = +25°C.

Type	Min $V_{(BR)DSS}$ V_{GS} = 0 I_D = 1.0 mA dc	$V_{GS(TH)1}$ $V_{DS} \geq V_{GS}$ I_D = 1.0 mA dc	Max I_{DSS1} V_{GS} = 0 V_{GS} = 80 percent of rated V_{DS}	Max $r_{DS(on)}$ (1) V_{GS} = -12 V		$I_{AS} = I_{DM}$
				T_J = 25°C at I_{D2}	T_J = 125°C at I_{D2}	
	V dc	V dc Min Max	µA dc	Ω	Ω	A (pk)
2N7403	-100	-2.0 -6.0	25	0.140	0.217	66
2N7404	-200			0.290	0.513	45

(1) Pulsed (see 4.5.1).

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

* (Copies of these documents are available online at http://quicksearch.dla.mil/ or https://www.assist.dla.mil/ or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturers list before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500 and as follows.

nC .....nano coulomb.
I_{AS} .....Rated avalanche current, non-repetitive.

3.4 Interface and physical dimensions. Interface and physical dimensions shall be as specified in MIL-PRF-19500, and on figure 1 (similar to TO-254) herein.

3.4.1 Lead finish and material. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document. Lead material shall be Kovar or Alloy 52; a copper core or plated core is permitted (see 6.2).

* 3.4.2 Internal construction. Multiple chip construction shall not be permitted.

3.5 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in paragraph 1.3, 1.4, and table I.

3.6 Electrical test requirements. The electrical test requirements shall be as specified in table I.

3.7 Electrostatic discharge protection. The devices covered by this specification require electrostatic discharge protection.

3.7.1 Handling. MOS devices must be handled with certain precautions to avoid damage due to the accumulation of static charge. However, the following handling practices are recommended (see 3.5).

a. Devices should be handled on benches with conductive handling devices.

b. Ground test equipment, tools and personnel handling devices.

c. Do not handle devices by the leads.

d. Store devices in conductive foam or carriers.

e. Avoid use of plastic, rubber or silk in MOS areas.

f. Maintain relative humidity above 50 percent if practical.

g. Care should be exercised during test and troubleshooting to apply not more than maximum rated voltage to any lead.

h. Gate must be terminated to source, $R \leq$ or 100 kΩ, whenever bias voltage is applied drain to source.

3.8 Marking. Marking shall be in accordance with MIL-PRF-19500. At the option of the manufacturer, marking of the country of origin may be omitted from the body of the transistor but shall be retained on the initial container.

3.9 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Classification of Inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4 and tables I, II, and III).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500. Alternate flow is allowed for qualification inspection in accordance with MIL-PRF-19500.

4.2.1 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table III tests, the tests specified in table III herein shall be performed on the first inspection lot of this revision to maintain qualification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

* 4.3 Screening (JANS only). Screening shall be in accordance with table E-IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table E-IV of MIL-PRF-19500) (1) (2)	Measurement
	JANS
(3)	Gate stress test (see 4.3.1)
(3)	Method 3470 of MIL-STD-750, (see 4.3.2)
(3) 3c	Method 3161 of MIL-STD-750, (see 4.3.3)
7	Optional.
9	I_{GSSF1}, I_{GSSR1}, I_{DSS1}, subgroup 2 of table I herein.
10	Method 1042 of MIL-STD-750, test condition B
11	I_{GSSF1}, I_{GSSR1}, I_{DSS1}, $r_{DS(ON)1}$, $V_{GS(TH)1}$ Subgroup 2 of table I herein. ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ±25 μA dc or ±100 percent of initial value, whichever is greater.
12	Method 1042 of MIL-STD-750, test condition A
13	Subgroups 2 and 3 of table I herein ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ±25 μA dc or ±100 percent of initial value, whichever is greater. $\Delta r_{DS(ON)1}$ = ±20 percent of initial value. $\Delta V_{GS(TH)1}$ = ±20 percent of initial value.
14	Required.
* 17	For TO-254 packages: Method 1081 of MIL-STD-750 (see 4.3.4), Endpoints: Subgroup 2 of table I herein.

(1) At the end of the test program, I_{GSSF1}, I_{GSSR1} and I_{DSS1}, are measured.
(2) An out-of-family program to characterize I_{GSSF1}, I_{GSSR1}, I_{DSS1}, and $V_{GS(th)1}$ shall be invoked.
(3) Shall be performed anytime before screen 9.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

4.3.1 Gate stress test. Apply V_{GS} = -30 V minimum for t = 250 µs minimum.

4.3.2 Single pulse avalanche energy (E_{AS}).

a. $I_{AS} = I_{DM.}$

b. L = 0.1 mH.

c. $E_{AS} = 1/2\ LI_{AS}^2$.

d. V_{DD} = -50 V to -150 V dc.

e. Initial junction temperature = 25°C, -5°C, +10°C.

4.3.3 Thermal impedance (ΔV_{SD} measurement). The delta V_{SD} measurement shall be performed in accordance with method 3161 of MIL-STD-750. The delta V_{SD} conditions (I_H and V_H) and maximum limit shall be derived by each vendor from the thermal response curves (see figure 3) and shall be specified in the certificate of conformance prior to qualification. The following parameter measurements shall apply:

a. Measuring current (I_M)	10 mA
b. Drain heating current (I_H)	4 A
c. Heating time (t_H)	100 ms
d. Drain-source heating voltage (V_H)	-25 V
e. Measurement time delay (t_{MD})	30 - 60 µs
f. Sample window time (t_{SW})	10 µs maximum

* 4.3.4 Dielectric withstanding voltage.

a. Magnitude of test voltage……..900 V dc.

b. Duration of application of test voltage……..15 seconds (min).

c. Points of application of test voltage…….....All leads to case (bunch connection).

d. Method of connection……..Mechanical.

e. Kilovolt-ampere rating of high voltage source…….1,200 V/1.0 mA (min).

f. Maximum leakage current……...1.0 mA.

g. Voltage ramp up time.....500 V/second.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with table E-V of MIL-PRF-19500 and table I herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VIa (JANS) of MIL-PRF-19500, and as follows. End-point electrical measurements shall be in accordance with the applicable steps of table IV herein.

Subgroup	Method	Condition
B3	1051	Test condition G, 100 cycles
B3	2077	SEM
B4	1042	Intermittent operation life, condition D. No heat sink nor or forced-air Cooling on the device shall be permitted during the on cycle. t_{ON} = 30 seconds minimum.
B5	1042	Accelerated steady-state reverse bias, condition A, V_{DS} = rated; T_A = +175°C; t = 120 hours, minimum.
B5	1042	Accelerated steady-state gate bias, condition B, V_{GS} = rated; T_A = +175°C; t = 24 hours.
B5	2037	Bond strength, test condition A
B6	3161	Thermal resistance, see 4.5.2.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500 and as follows. Electrical measurements (end-points) and delta requirements shall be in accordance with the applicable steps of table IV herein.

Subgroup	Method	Condition
C2	2036	Terminal strength, test condition A, weight = 10 lbs., t = 15 sec.
C5	3161	See 4.5.2.
C6	1042	Test condition D; 1 cycle = 30 sec. min.

4.4.4 Group D inspection. Group D inspection shall be conducted in accordance with table E-VIII of MIL-PRF-19500 and table II herein.

4.4.4.1 Design parameters. Not tested on a per lot basis. Design shall be such that the devices shall be capable of meeting the requirements herein.

4.4.5 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-IX of MIL-PRF-19500 and as specified in table III herein. Electrical measurements (end-points) and delta requirements shall be in accordance with the applicable steps of table IV herein.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

4.5.2 Thermal resistance. Thermal resistance measurements shall be performed in accordance with method 3161 of MIL-STD-750. The maximum limit of $R_{\theta JC}$ = 1.0°C/W. The following parameters shall apply:

a. Measuring current(I_M) ..... 10 mA.

b. Drain heating current (I_H) ..... 4 A.

c. Heating time (t_H) ..... Steady-state (see method 3161 of MIL-STD-750).

d. Drain-source heating voltage (V_H) ..... -25 V.

e. Measurement time delay (t_{MD}) ..... 30 to 60 μs.

f. Sample window time (t_{SW}) ..... 10 μs maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Condition		Min	Max	
Subgroup 1						
Visual and mechanical inspection	2071					
Subgroup 2						
Thermal impedance	3161	See 4.3.2	$Z_{\theta JX}$			
Breakdown voltage, drain to source	3407	Bias condition C V_{GS} = 0 V, I_D = 1.0 mA dc	$V_{(BR)DSS}$			
2N7403				-100		V dc
2N7404				-200		V dc
Gate to source voltage (threshold)	3403	$V_{DG} \geq V_{GS}$,	$V_{GS(th)1}$	-2.0	-6.0	V dc
Gate current	3411	Bias condition C, V_{GS} = +20 V dc, V_{DS} = 0	I_{GSSF1}		+100	nA dc
Gate current	3411	Bias condition C, V_{GS} = -20 V dc, V_{DS} = 0	I_{GSSR1}		-100	nA dc
Drain current	3413	Bias condition C, V_{GS} = 0 V dc, V_{DS} = 80 percent of rated V_{DS}	I_{DSS1}		25	µA dc
Static drain to source on-state resistance	3421	Bias condition A, V_{GS} = -12 V dc, I_D = I_{D2}, pulsed (see 4.5.1)	$r_{DS(ON)1}$			
2N7403					0.14	Ω
2N7404					0.29	Ω
Static drain to source on-state voltage	3405	Bias condition A, V_{GS} = -12 V dc, I_D = I_{D2}, pulsed (see 4.5.1)	$V_{DS(ON)1}$			
2N7403					-3.23	V dc
2N7404					-4.57	V dc
Forward voltage	4011	Pulsed (see 4.5.1), I_D = I_{D1} V_{GS} = 0 V dc	V_{SD}	-0.6	-1.8	V dc
Subgroup 3						
High temperature operation:		T_C = T_J = +125°C				
Gate current	3411	Bias condition C, V_{GS} = ±20 V dc, V_{DS} = 0 V dc,	I_{GSS2}		±200	nA dc
Drain current	3413	Bias condition C, V_{GS} = 0 V dc, V_{DS} = 80 percent of rated V_{DS}	I_{DSS2}		0.25	mA dc

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Condition		Min	Max	
Subgroup 3 - Continued						
* Static drain to source on-state resistance	3421	Condition A. V_{GS} = -12 V dc, pulsed (see 4.5.1), I_D = rated I_{D2}	$r_{DS(on)2}$			
2N7403					0.217	Ω
2N7404					0.513	Ω
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 1 mA	$V_{GS(th)2}$	-1.0		V dc
Low temperature operation:		$T_C = T_J$ = -55°C				
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 1 mA	$V_{GS(th)3}$		-7.0	V dc
Subgroup 4						
Switching time test	3472	I_D = rated I_{D1}; V_{GS} = -12 V dc; R_G = 4.7 Ω; V_{DD} = 50 percent of rated V_{DS}				
Turn-on delay time			$t_{d(on)}$			
2N7403					110	ns
2N7404					120	ns
Rise time			t_r			
2N7403					390	ns
2N7404					160	ns
Turn-off delay time			$t_{d(off)}$			
2N7403					300	ns
2N7404					280	ns
Fall time			t_f			
2N7403					170	ns
2N7404					120	ns

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

	Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
		Method	Condition		Min	Max	
	Subgroup 5						
	Safe operating area test (high voltage)	3474	See figure 4, t_p = 10 ms, V_{DS} = 80 percent of rated V_{DS}, $V_{DS} \leq$200 V dc max.				
	Electrical measurements		See table IV, steps 1, 2, 3, 4, 5, 6, and 7				
	Subgroup 6						
	Not applicable						
	Subgroup 7						
	Gate charge	3471	Condition B				
	On-state gate charge			$Q_{g(on)}$			
	2N7403					160	nC
	2N7404					150	nC
	Gate to source charge			Q_{gs}			
	2N7403					29	nC
	2N7404					32	nC
	Gate to drain charge			Q_{gd}			
	2N7403					65	nC
	2N7404					67	nC
*	Reverse recovery time	3473	Condition A. $d_i/d_t \leq$ 100 A/µs, $V_{DD} \leq$ 30 V,	t_{rr}			
	2N7403					270	ns
	2N7404					300	ns

1/ For sampling plan, see MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection.

Inspection 1/ 2/ 3/ 4/	MIL-STD-750		Symbol	Pre-irradiation limits		Post irradiation limits		Units
	Method	Conditions		Min.	Max.	Min.	Max.	
Subgroup 1								
Not applicable								
Subgroup 2		T_C = +25°C						
Steady state total dose Irradiation (V_{GS} bias)	1019	V_{GS} = -12 V, V_{DS} = 0 V						
Steady state total dose irradiation (V_{DS} bias)	1019	V_{GS} = 0 V, V_{DS} = 80 percent of rated V_{DS}						
Breakdown voltage drain to source	3407	V_{GS} = 0 V, I_D = 1 mA dc, bias condition C	$V_{(BR)DSS}$					
2N7403				-100		-100		V dc
2N7404				-200		-200		V dc
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 1 mA dc	$V_{GS(TH)1}$	-2.0	-6.0	-2.0	-6.0	V dc
Gate current	3411	V_{GS} = ±20 V dc, V_{DS} = 0 V, bias condition C	I_{GSS1}		±100		±100	
Drain current	3413	V_{GS} = 0V, V_{DS} = 80 percent of rated V_{DS}, bias condition C	I_{DSS1}		25		25	µA dc
Static drain to source on-state resistance	3421	V_{GS} =12V dc, condition A, pulsed (see4.5.1), I_D = I_{D2}	$r_{DS(ON)1}$					
2N7403					0.14		0.14	Ω
2N7404					0.29		0.29	Ω
Static drain to source on-state voltage	3405	V_{GS} = -12V dc, condition A, pulsed (see 4.5.1), I_D = I_{D1}	$V_{DS(ON)}$					
2N7403					-3.23		-3.23	V dc
2N7404					-4.57		-4.57	V dc

1/ For sampling plan see MIL-PRF-19500.
2/ Electrical specifications are for 'D' and 'R' rad levels.
3/ Group D qualification may be performed prior to lot formation. Wafers qualified to these group D QCI requirements may be used for any other specification utilizing the same die design.
4/ At the manufacturers option, group D samples need not be subjected to all the screening tests, but shall be assembled in its qualified package or in any qualified package that the manufacturer has data to correlate the performance to the designated package.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

* TABLE III. Group E inspection (all quality levels) for qualification or re-qualification only.

Inspection 1/ 2/ 3/ 4/	MIL-STD-750		Qualification and large lot conformance inspection.
	Method	Conditions	
Subgroup 1			12 devices c = 0
Temperature cycle	1051	Condition G, 500 cycles	
Hermetic seal Fine leak Gross leak	1071		
Electrical measurements		See table IV, steps 1, 2, 3, 4, 5, 6, 7, and 8	
Subgroup 2 1/			45 devices c = 0
Steady-state reverse bias	1042	Condition A, 1,000 hours	
Electrical measurements		See table IV, steps 1, 2, 3, 4, 5, 6, and 7	
Steady-state gate bias	1042	Condition B, 1,000 hours	
Electrical measurements		See table IV, steps 1, 2, 3, 4, 5, 6, and 7	
Subgroup 4			Sample size N/A
Thermal impedance curves		See MIL-PRF-19500.	
Subgroup 5			
Not applicable			
Subgroup 6			
ESD	1020		
Subgroup 8			22 devices c = 0
Commutating diode for safe operating area test procedure for measuring dv/dt during reverse recovery of power MOSFET transistors or insulated gate bipolar transistors	3476		

1/ A separate sample for each test may be pulled.
2/ Group E qualification of single event effect testing may be performed prior to lot formation. Wafers qualified to these group E QCI requirements may be used for any other specification utilizing the same die design.
3/ As a minimum, gate to source leakage and drain to source leakage are to be examined to verify the electrical performance of the DUT prior to and after test. At the manufacturer's option, the remaining static tests in table IV, with the exception of step 8, may be performed.
4/ This sampling plan applies to each bias condition defined.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

TABLE IV. Group A, B, C and E electrical and delta measurements


Step	Inspection 1/ 2/ 3/	MIL-STD-750		Symbol	Limits		Units
		Method	Conditions		Min	Max	
1.	Breakdown voltage drain to source 2N7403 2N7404	3407	Bias condition C, V_{GS} = 0 V, I_D = 1 mA dc	$V_{(BR)DSS}$	 -100 -200		 V dc V dc
2.	Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 1 mA dc	$V_{GS(TH)1}$	-2.0	-6.0	V dc
3.	Gate current	3411	V_{GS} = +20 V and -20 V dc, Bias condition C, V_{DS} = 0 V	I_{GSS1}		±100	nA dc
4.	Drain current	3413	Bias condition C, V_{GS} = 0 V dc, V_{DS} = 80 percent of rated V_{DS}	I_{DSS1}		25	µA dc
5.	Static drain to source on-state resistance 2N7403 2N7404	3421	V_{GS} = -12 V dc, condition A, pulsed (see 4.5.1), $I_D = I_{D2}$	$r_{DS(ON)1}$		 0.14 0.29	 Ω Ω
6.	Static drain to source on-state voltage 2N7403 2N7404	3405	Pulsed (see 4.5.1), V_{GS} = -12 V dc, condition A, $I_D = I_{D1}$	$V_{DS(ON)}$		 -3.23 -4.57	 V dc V dc
7.	Forward voltage	4011	V_{GS} = 0 V dc, condition A, pulsed (see 4.5.1), $I_D = I_{D1}$	V_{SD}	-0.6	-1.8	V dc
8.	Thermal impedance	3161	See 4.3.3	ΔV_{SD}		136	mV

1/ The electrical measurements for table VIa (JANS) of MIL-PRF-19500 are as follows:
   a. Subgroup 3, see table IV herein, steps 1, 2, 3, 4, 5, 6, and 7.
   b. Subgroup 4, see table IV herein, steps 1, 2, 3, 4, 5, 6, 7, and 8.
   c. Subgroup 5, see table IV herein, steps 1, 2, 3, 4, 5, 6, and 7.


2/ The electrical measurements for table VII of MIL-PRF-19500 are as follows:
   a. Subgroup 2 and 3, see table IV herein, steps 1, 2, 3, 4, 5, 6, and 7.
   b. Subgroup 6, see table IV herein, steps 1, 2, 3, 4, 5, 6, 7, and 8.

3/ The electrical measurements for table IX of MIL-PRF-19500 are as follows:
   a. Subgroup 1, see table IV herein, steps 1, 2, 3, 4, 5, 6, 7, and 8.
   b. Subgroup 2, see table IV herein, steps 1, 2, 3, 4, 5, 6, and 7.
   c. Subgroup 8, see table IV herein, steps 3 and 4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.



2N7403



2N7404

FIGURE 2. Maximum drain current vs case temperature graphs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.




FIGURE 3. Thermal response curves.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.




FIGURE 4. Safe operating area graphs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.




FIGURE 4. Safe operating area graphs - Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Lead material and finish (see 3.4.1).

c. Type designation and product assurance level.

d. Packaging requirements (see 5.1).

* e. For acquisition of RHA designated devices, table II, subgroup 1 testing of group D herein is optional. If subgroup 1 is desired, it should be specified in the contract or order.

* f. If SEE testing data is desired, it should be specified in the contract or order.

* g. If specific SEE characterization conditions are desired (see section 6.5 and table IV), manufacturer's cage code should be specified in the contract or order

* 6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land and Maritime, ATTN: VQE, P.O. Box 3990, Columbus, OH 43216-5000 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.dla.mil.

6.4 Substitution information. Devices covered by this specification are substitutable for the manufacturer's and user's Part or Identifying Number (PIN). This information in no way implies that manufacturer's PINs are subitable for the military PIN.

Generic PIN	Military PIN
SF9150	2N7403
SF9250	2N7404

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.

* 6.5 Application data.

* 6.5.1 Manufacturer specific irradiation data. Each manufacturer qualified to this slash sheet has characterized its devices to the requirements of MIL-STD-750 method 1080 and as specified herein. Since each manufacturer's characterization conditions can be different and can vary by the version of method 1080 qualified to, the MIL-STD-750 method 1080 revision version date and conditions used by each manufacturer for characterization have been listed here (see table V) for information only. SEE conditions and figures listed in section 6 are current as of the date of this specification sheet, please contact the manufacturer for the most recent conditions.

* TABLE V. Manufacturers characterization conditions - Continued.

Manufactures cage	Inspection	MIL-STD-750		Sample plan
		Method	Conditions	
Upon qualification, all manufacturers should provide the verification test conditions to be added to this table.				

6.6 Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
Navy - EC
Air Force - 85
NASA - NA
DLA - CC

Preparing activity:
DLA - CC

(Project 5961-2013-114)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:23Z
Check the source to verify that this is the current version before use.