The documentation and process conversion measures necessary to comply with this revision shall be completed by 6 September 2011.

INCH-POUND

MIL-PRF-19500/662D
6 June 2011
SUPERSEDING
MIL-PRF-19500/662C
22 October 2008

PERFORMANCE SPECIFICATION SHEET

# SEMICONDUCTOR DEVICE, TRANSISTOR, FIELD EFFECT RADIATION HARDENED (TOTAL DOSE ONLY), P-CHANNEL, SILICON, TYPES 2N7422, 2N7422U, 2N7423, AND 2N7423U, JANTXVR AND F AND JANSR AND F

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

## 1. SCOPE

1.1 Scope. This specification covers the performance requirements for a P-channel, enhancement-mode, MOSFET, radiation hardened (total dose only), power transistor. Two levels of product assurance are provided for each device type as specified in MIL-PRF-19500, with avalanche energy maximum rating ($E_{AS}$) and maximum avalanche current ($I_{AS}$). See 6.5 for JANHC and JANKC die versions.

1.2 Physical dimensions. See figure 1, (TO-254AA), and figure 2, (surface mount, TO-276AC).

1.3 Maximum ratings. Unless otherwise specified, $T_A$ = +25°C.

| Type (1) | $P_T$ (2) $T_C$ = +25°C | $P_T$ $T_A$ = +25°C | $R_{\theta JC}$ (3) | $V_{DS}$ | $V_{DG}$ | $V_{GS}$ | $I_{D1}$ (4) (5) $T_C$ =+25°C | $I_{D2}$ (4) (5) $T_C$ = +100°C | $I_S$ | $I_{DM}$ (6) | $T_J$ and $T_{STG}$ |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | W | W | °C/W | V dc | V dc | V dc | A dc | A dc | A dc | A (pk) | °C |
| 2N7422 | 150 | 4.0 | 0.83 | -100 | -100 | ±20 | -22.0 | -14.0 | -22.0 | -88 | -55 |
| 2N7423 | 150 | 4.0 | 0.83 | -200 | -200 | ±20 | -14.0 | -9.0 | -14.0 | -56 | to +150 |

(1) Unless otherwise noted, electrical characteristics, ratings, and conditions for “U” suffix devices (surface mount) are identical to the corresponding non-"U" suffix devices.
(2) Derate linearly by 1.2 W/°C for $T_C$ > +25°C.
(3) See figure 3, thermal impedance curves.
(4) The following formula derives the maximum theoretical $I_D$ limit. $I_D$ is limited by package and internal construction.

$$I_D = \sqrt{\frac{T_{JM} - T_C}{(R_{\theta JC}) \times (R_{DS}(on) \text{ at } T_{JM})}}$$

(5) See figure 4, maximum drain current graphs.
(6) $I_{DM}$ = 4 X $I_{D1}$ as calculated in note (4).

* Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.daps.dla.mil/.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics at $T_C$ = +25°C.

| Type (1) | Min $V_{(BR)DSS}$ $V_{GS}$ = 0 $I_D$ = -1.0 mA dc | $V_{GS(TH)1}$ $V_{DS} \geq V_{GS}$ $I_D$ = -1.0 mA dc | | Max $I_{DSS1}$ $V_{GS}$ = 0 $V_{DS}$ = 80 percent of rated $V_{DS}$ | Max $r_{DS(on)}$ (2) $V_{GS}$ = -12V $I_D = I_{D2}$ | | $E_{AS}$ at $I_{D1}$ | $I_{AS}$ |
|---|---|---|---|---|---|---|---|---|
| | | | | | $T_J$ = 25°C | $T_J$ = 150°C | | |
| | V dc | V dc | | µA dc | Ω | Ω | mJ | A |
| | | Min | Max | | | | | |
| 2N7422 | -100 | -2.0 | -4.0 | -25 | 0.080 | 0.200 | 500 | -22 |
| 2N7423 | -200 | -2.0 | -4.0 | -25 | 0.315 | 0.708 | 500 | -14 |

(1) Unless otherwise noted, electrical characteristics, ratings, and conditions for “U” suffix devices (surface mount) are identical to the corresponding non-"U" suffix devices.
(2) Pulsed (see 4.5.1).

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS


MIL-STD-750 - Test Methods for Semiconductor Devices.

* (Copies of these documents are available online at https://assist.daps.dla.mil/quicksearch/ or https://assist.daps.dla.mil/ or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.





| Ltr | Dimensions | | | |
|---|---|---|---|---|
| | Inches | | Millimeters | |
| | Min | Max | Min | Max |
| BL | .535 | .545 | 13.59 | 13.84 |
| CH | .249 | .260 | 6.32 | 6.60 |
| LD | .035 | .045 | 0.89 | 1.14 |
| LL | .510 | .570 | 12.95 | 14.48 |
| LO | .150 BSC | | 3.81 BSC | |
| LS | .150 BSC | | 3.81 BSC | |
| MHD | .139 | .149 | 3.53 | 3.78 |
| MHO | .665 | .685 | 16.89 | 17.40 |
| TL | .790 | .800 | 20.07 | 20.32 |
| TT | .040 | .050 | 1.02 | 1.27 |
| TW | .535 | .545 | 13.59 | 13.84 |
| Term 1 | Drain | | | |
| Term 2 | Source | | | |
| Term 3 | Gate | | | |

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.
4. All terminals are isolated from case.

FIGURE 1. Physical dimensions for TO-254AA.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.




| Dimensions | | | | |
|---|---|---|---|---|
| Symbol | Inches | | Millimeters | |
| | Min | Max | Min | Max |
| BL | .620 | .630 | 15.75 | 16.00 |
| BW | .445 | .455 | 11.30 | 11.56 |
| CH | | .142 | | 3.61 |
| LH | .010 | .020 | 0.25 | 0.51 |
| $LL_1$ | .410 | .420 | 10.41 | 10.67 |
| $LL_2$ | .152 | .162 | 3.86 | 4.11 |
| $LS_1$ | .210 BSC | | 5.33 BSC | |
| $LS_2$ | .105 BSC | | 2.67 BSC | |
| $LW_1$ | .370 | .380 | 9.40 | 9.65 |
| $LW_2$ | .135 | .145 | 3.43 | 3.68 |
| $Q_1$ | .030 | | 0.76 | |
| $Q_2$ | .035 | | 0.89 | |
| Term 1 | Drain | | | |
| Term 2 | Gate | | | |
| Term 3 | Source | | | |

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. The lid shall be electrically isolated from the drain, gate, and source.
4. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 2. Dimensions and configuration of surface mount package outline, TO-276AC.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500 and as follows:

$I_{AS}$ ..... Rated avalanche current, nonrepetitive
nC ..... nano Coulomb.

3.4 Interface and physical dimensions. The interface and physical dimensions shall be as specified in MIL-PRF-19500 and on figures 1 and 2 herein. Methods used for electrical isolation of the terminals shall employ materials that contain a minimum of 90 percent $Al_2O_3$ (ceramic). Examples of such construction techniques are metallized ceramic eyelets, or ceramic walled packages.

3.4.1 Lead material and finish. Lead material shall be kovar or Alloy 52; a copper core or plated core is permitted. Surface mount terminals shall be copper tungsten. Lead finish shall be solderable as defined in MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of terminal finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Internal construction: Multiple chip construction shall not be permitted to meet the requirements of this specification.

3.5 Marking. Marking shall be in accordance with MIL-PRF-19500. At the option of the manufacturer, marking of the country of origin may be omitted from the body of the transistor but shall be retained on the initial container.

3.6 Electrostatic discharge protection. The devices covered by this specification require electrostatic discharge protection.

3.6.1 Handling. MOS devices must be handled with certain precautions to avoid damage due to the accumulation of static charge. However, the following handling practices are recommended (see 3.6).

a. Devices should be handled on benches with conductive handling devices.

b. Ground test equipment, tools, and personnel handling devices.

c. Do not handle devices by the leads.

d. Store devices in conductive foam or carriers.

e. Avoid use of plastic, rubber, or silk in MOS areas.

f. Maintain relative humidity above 50 percent if practical.

g. Care should be exercised during test and troubleshooting to apply not more than maximum rated voltage to any lead.

h. Gate must be terminated to source, $R \leq$ or 100 kΩ, whenever bias voltage is applied drain to source.

3.7 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I herein.

3.8 Electrical test requirements. The electrical test requirements shall be as specified in table I.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

3.9 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4 and tables I and II).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500.

4.2.1 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table III tests, the tests specified in table III herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

* 4.3 Screening (JANS and JANTXV levels only). Screening shall be in accordance with table E-IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

| Screen (see table E-IV of MIL-PRF-19500) (1) (2) | Measurement | |
|---|---|---|
| | JANS | JANTXV |
| (3) | Gate stress test (see 4.3.1) | Gate stress test (see 4.3.1) |
| (3) | Method 3470 of MIL-STD-750, $E_{AS}$ test (see 4.3.2) | Method 3470 of MIL-STD-750, $E_{AS}$ test (see 4.3.2) |
| (3) 3c | Method 3161 of MIL-STD-750, thermal impedance (see 4.3.3) | Method 3161 of MIL-STD-750, thermal impedance (see 4.3.3) |
| 9 | $I_{GSSF1}$, $I_{GSSR1}$, $I_{DSS1}$, subgroup 2 of table I herein | Not applicable |
| 10 | Method 1042 of MIL-STD-750, test condition B | Method 1042 of MIL-STD-750, test condition B |
| 11 | $I_{GSSF1}$, $I_{GSSR1}$, $I_{DSS1}$, $r_{DS(ON)1}$, $V_{GS(TH)1}$ , Subgroup 2 of table I herein.<br>$\Delta I_{GSSF1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{GSSR1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{DSS1}$ = ±10 μA dc or ±100 percent of initial value, whichever is greater. | $I_{GSSF1}$, $I_{GSSR1}$, $I_{DSS1}$, $r_{DS(ON)1}$, $V_{GS(TH)1}$ , Subgroup 2 of table I herein. |
| 12 | Method 1042 of MIL-STD-750, test condition A | Method 1042 of MIL-STD-750, test condition A |
| * 13 | Subgroups 2 and 3 of table I herein.<br>$\Delta I_{GSSF1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{GSSR1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{DSS1}$ = ±10 μA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta r_{DS(ON)1}$ = ±20 percent of initial value.<br>$\Delta V_{GS(TH)1}$ = ±20 percent of initial value. | Subgroups 2 of table I herein.<br>$\Delta I_{GSSF1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{GSSR1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{DSS1}$ = ±10 μA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta r_{DS(ON)1}$ = ±20 percent of initial value.<br>$\Delta V_{GS(TH)1}$ = ±20 percent of initial value. |

(1) At the end of the test program, $I_{GSSF1}$, $I_{GSSR1}$, and $I_{DSS1}$ are measured.
(2) An out-of-family program to characterize $I_{GSSF1}$, $I_{GSSR1}$, $I_{DSS1}$ and $V_{GS(th)1}$ shall be invoked.
* (3) Shall be performed anytime after temperature cycling, screen 3a; JANTXV level does not need to be repeated in screening requirements.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

4.3.1 Gate stress test. Apply $V_{GS}$ = -30 V minimum for t = 250 µs minimum.

4.3.2 Single pulse avalanche energy ($E_{AS}$).

a. Peak current, $I_{AS} = I_{D1}$

b. Inductance, $L = (2*E_{AS}/(I_{D1})^2)*((V_{BR}-V_{DD})/V_{BR})$ mH minimum.

c. Gate to source resistor, $R_{GS}$: $25 \leq R_{GS} \leq 200\ \Omega$.

d. Supply voltage, $V_{DD}$ = -25 V dc, except $V_{DD}$ = -50 V dc for 2N7423.

e. Initial case temperature, $T_C$ = +25° C, -5° C, +10 °C.

f. Gate voltage, $V_{GS}$ = -12 V dc.

g. Number of pulses to be applied: 1 pulse minimum.

4.3.3 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3161 of MIL-STD-750 using the guidelines in that method for determining $I_M$, $I_H$, $t_H$, $t_{SW}$, (and $V_H$ where appropriate). Measurement delay time ($t_{MD}$) = 70 µs max. See table III, group E, subgroup 4 herein.

* 4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with table E-V of MIL-PRF-19500 and table I herein. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VIA (JANS) and table E-VIB (JANTXV) of MIL-PRF-19500 and as follows. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

4.4.1 Group B inspection, table E-VIA (JANS) of MIL-PRF-19500.

| Subgroup | Method | Condition |
|---|---|---|
| B3 | 1051 | Test condition G, 100 cycles. |
| B3 | 2075 | See 3.4.2. |
| B3 | 2077 | SEM qualification may be performed anytime prior to lot formation. |
| B4 | 1042 | Intermittent operation life, condition D, 2,000 cycles. No heat sink or forced-air cooling on the device shall be permitted during the on cycle. $t_{on}$ = 30 seconds minimum. |
| B5 | 1042 | Accelerated steady-state gate bias, condition B, $V_{GS}$ = rated; $T_A$ = +175°C, t = 24 hours minimum, or $T_A$ = +150°C, t = 48 hours minimum. |
| B5 | 1042 | Accelerated steady-state reverse bias, condition A, $V_{DS}$ = rated; $T_A$ = +175°C, t = 120 hours minimum; or $T_A$ = +150°C, t = 240 hours minimum. |
| B5 | 2037 | Bond strength, test condition D. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

4.4.2.2 Group B inspection, table E-VIB (JANTXV) of MIL-PRF-19500.

| Subgroup | Method | Condition |
|---|---|---|
| B2 | 1051 | Test condition G, 25 cycles. |
| B3 | 1042 | Intermittent operation life, condition D, 2,000 cycles. No heat sink or forced-air cooling on the device shall be permitted during the on cycle. $t_{on}$ = 30 seconds minimum. |

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500 and as follows. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

| Subgroup | Method | Condition |
|---|---|---|
| C2 | 2036 | Test condition A; weight = 10 pounds; t = 15 seconds (applicable to TO-254AA only). |
| C5 | 3161 | See 4.3.3, $R_{\theta JC}$ = 0.83 °C/W. |
| C6 | 1042 | Intermittent operation life, condition D, 6,000 cycles. No heat sink or forced-air cooling on the device shall be permitted during the on cycle. $t_{on}$ = 30 seconds minimum. |

4.4.4 Group D inspection. Group D inspection shall be conducted in accordance with table E-VIII of MIL-PRF-19500 and table II herein.

4.4.5 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-IX of MIL-PRF-19500 and as specified in table III herein. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection

| Inspection 1/ | MIL-STD-750 | | Symbol | Limits | | Unit |
|---|---|---|---|---|---|---|
| | Method | Condition | | Min | Max | |
| Subgroup 1 | | | | | | |
| Visual and mechanical inspection | 2071 | | | | | |
| Subgroup 2 | | | | | | |
| Thermal impedance 2/ | 3161 | See 4.3.3 | $Z_{\theta JC}$ | | | °C/W |
| Breakdown voltage drain to source | 3407 | Bias condition C, $V_{GS}$ = 0 V, $I_D$ = -1 mA dc, | $V_{(BR)DSS}$ | | | |
| 2N7422, 2N7422U | | | | -100 | | V dc |
| 2N7423, 2N7423U | | | | -200 | | V dc |
| Gate to source voltage (threshold) | 3403 | $V_{DS} \geq V_{GS}$, $I_D$ = -1 mA dc | $V_{GS(TH)1}$ | -2.0 | -4.0 | V dc |
| Gate current | 3411 | Bias condition C, $V_{GS}$ = -20 V dc, $V_{DS}$ = 0 V | $I_{GSSF1}$ | | -100 | nA dc |
| Gate current | 3411 | Bias condition C, $V_{GS}$ = 20 V dc, $V_{DS}$ = 0 V | $I_{GSSR1}$ | | 100 | nA dc |
| Drain current | 3413 | Bias condition C, $V_{GS}$ = 0 V dc, $V_{DS}$ = 80 percent of rated $V_{DS}$, | $I_{DSS1}$ | | -25 | µA dc |
| Static drain to source on-state resistance | 3421 | $V_{GS}$ = -12 V dc, condition A, pulsed (see 4.5.1), $I_D$ = $I_{D2}$ | $r_{DS(ON)1}$ | | | |
| 2N7422, 2N7422U | | | | | 0.080 | Ω |
| 2N7423, 2N7423U | | | | | 0.315 | Ω |
| Static drain to source on-state resistance | 3421 | $V_{GS}$ = -12 V dc, condition A, pulsed (see 4.5.1), $I_D$ = $I_{D1}$ | $r_{DS(ON)2}$ | | | |
| 2N7422, 2N7422U | | | | | 0.085 | Ω |
| 2N7423, 2N7423U | | | | | 0.330 | Ω |
| Forward voltage | 4011 | $V_{GS}$ = 0 V dc, condition A, pulsed (see 4.5.1), $I_D$ = $I_{D1}$ | $V_{SD}$ | | | |
| 2N7422, 2N7422U | | | | | -3.0 | V dc |
| 2N7423, 2N7423U | | | | | -3.6 | V dc |

See footnotes at end of table.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection - Continued.

| Inspection 1/ | MIL-STD-750 | | Symbol | Limits | | Unit |
|---|---|---|---|---|---|---|
| | Method | Condition | | Min | Max | |
| Subgroup 3 | | | | | | |
| High temperature operation: | | $T_C = T_J = +125°C$ | | | | |
| Gate current | 3411 | Bias condition C, $V_{GS}$ = -20 V dc, $V_{DS}$ = 0 V | $I_{GSSF2}$ | | -200 | nA dc |
| Gate current | 3411 | Bias condition C, $V_{GS}$ = 20 V dc, $V_{DS}$ = 0 V | $I_{GSSR2}$ | | 200 | nA dc |
| Drain current | 3413 | Bias condition C, $V_{GS}$ = 0 V dc, $V_{DS}$ = 80 percent of rated $V_{DS}$ | $I_{DSS2}$ | | -0.25 | mA dc |
| Static drain to source on-state resistance | 3421 | $V_{GS}$ = -12 V dc, condition A, pulsed (see 4.5.1), $I_D = I_{D2}$ | $r_{DS(ON)3}$ | | | |
| 2N7422, 2N7422U | | | | | 0.170 | Ω |
| 2N7423, 2N7423U | | | | | 0.669 | Ω |
| Gate to source voltage (threshold) | 3403 | $V_{DS} \geq V_{GS}$, $I_D$ = -1 mA dc | $V_{GS(TH)2}$ | -1.0 | | V dc |
| Low temperature operation: | | $T_C = T_J = -55°C$ | | | | |
| Gate to source voltage (threshold) | 3403 | $V_{DS} \geq V_{GS}$, $I_D$ = -1 mA dc | $V_{GS(TH)3}$ | | -5.0 | V dc |
| Subgroup 4 | | | | | | |
| Forward transconductance | 3475 | $I_D = I_{D2}$, $V_{DD}$ > -15 V dc, see 4.5.1 | $g_{fs}$ | | | |
| 2N7422, 2N7422U | | | | 11.0 | | S |
| 2N7423, 2N7423U | | | | 4.0 | | S |
| Switching time tests | 3472 | $I_D = I_{D1}$, $V_{GS}$ = -12 V dc, $R_G$ = 2.35 Ω, $V_{DD}$ = 50 percent of rated $V_{DS}$ | | | | |
| Turn-on delay time | | | $t_{D(on)}$ | | | |
| 2N7422, 2N7422U | | | | | 40 | ns |
| 2N7423, 2N7423U | | | | | 60 | ns |
| Rise time | | | $t_r$ | | | |
| 2N7422, 2N7422U | | | | | 170 | ns |
| 2N7423, 2N7423U | | | | | 240 | ns |

See footnotes at end of table.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection - Continued.

| Inspection 1/ | MIL-STD-750 | | Symbol | Limits | | Unit |
|---|---|---|---|---|---|---|
| | Method | Condition | | Min | Max | |
| Subgroup 4- Continued | | | | | | |
| Turn-off delay time | | | $t_{D(off)}$ | | | |
| 2N7422, 2N7422U | | | | | 190 | ns |
| 2N7423, 2N7423U | | | | | 225 | ns |
| Fall time | | | $t_f$ | | | |
| 2N7422, 2N7422U | | | | | 190 | ns |
| 2N7423, 2N7423U | | | | | 220 | ns |
| Subgroup 5 | | | | | | |
| Safe operating area test (high voltage) | 3474 | See figures 5 and 6<br>$t_p$ = 10 ms min. $V_{DS}$ = 80 percent of max. rated $V_{DS}$ | | | | |
| Electrical measurements | | See table I, subgroup 2 | | | | |
| Subgroup 6 | | | | | | |
| Not applicable | | | | | | |
| Subgroup 7 | | | | | | |
| Gate charge | 3471 | Condition B | | | | |
| On-state gate charge | | | $Q_{G(ON)}$ | | | |
| 2N7422, 2N7422U | | | | | 200 | nC |
| 2N7423, 2N7423U | | | | | 200 | nC |
| Gate to source charge | | | $Q_{GS}$ | | | |
| 2N7422, 2N7422U | | | | | 35 | nC |
| 2N7423, 2N7423U | | | | | 45 | nC |
| Gate to drain charge | | | $Q_{GD}$ | | | |
| 2N7422, 2N7422U | | | | | 48 | nC |
| 2N7423, 2N7423U | | | | | 85 | nC |
| Reverse recovery time | 3473 | di/dt = -100 A/µs, $V_{DD} \leq$ -50 V<br>$I_D = I_{D1}$ | $t_{rr}$ | | | |
| 2N7422, 2N7422U | | | | | 300 | ns |
| 2N7423, 2N7423U | | | | | 775 | ns |

1/ For sampling plan, see MIL-PRF-19500.
2/ This test required for the following end-point measurements only:
Group B, subgroups 2 and 3 (JANTXV).
Group B, subgroups 3 and 4 (JANS).
Group C, subgroup 2 and 6.
Group E, subgroup 1.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection.

| Inspection 1/ 2/ 3/ 4/ | MIL-STD-750 | | Symbol | Pre-irradiation limits | | Post-irradiation limits | | | | Unit |
|---|---|---|---|---|---|---|---|---|---|---|
| | | | | R and F | | R | | F 5/ | | |
| | Method | Conditions | | Min | Max | Min | Max | Min | Max | |
| Subgroup 1 | | | | | | | | | | |
| Not applicable | | | | | | | | | | |
| Subgroup 2 | | $T_C$ = + 25°C | | | | | | | | |
| Steady-state total dose irradiation ($V_{GS}$ bias) 6/ | 1019 | $V_{GS}$ = -12 V; $V_{DS}$ = 0 V | | | | | | | | |
| Steady-state total dose irradiation ($V_{DS}$ bias) 6/ | 1019 | $V_{GS}$ = 0 V; $V_{DS}$ = 80 percent of rated $V_{DS}$ (pre-irradiation) | | | | | | | | |
| End-point electricals: | | | | | | | | | | |
| Breakdown voltage, drain to source | 3407 | $V_{GS}$ = 0 V; $I_D$ = -1 mA; bias condition C | $V_{(BR)DSS}$ | | | | | | | |
| 2N7422 | | | | -100 | | -100 | | -100 | | V dc |
| 2N7423 | | | | -200 | | -200 | | -200 | | V dc |
| Gate to source voltage (threshold) | 3403 | $V_{DS} \geq V_{GS}$; $I_D$ = -1 mA | $V_{GS(th)1}$ | | | | | | | |
| 2N7422 | | | | -2.0 | -4.0 | -2.0 | -4.0 | -2.0 | -5.0 | V dc |
| 2N7423 | | | | -2.0 | -4.0 | -2.0 | -4.0 | -2.0 | -5.0 | V dc |
| Gate current | 3411 | Bias condition C; $V_{GS}$ = -20 V; $V_{DS}$ = 0 V | $I_{GSSF1}$ | | -100 | | -100 | | -100 | nA dc |
| Gate current | 3411 | Bias condition C; $V_{GS}$ = +20 V; $V_{DS}$ = 0 V | $I_{GSSR1}$ | | 100 | | 100 | | 100 | nA dc |
| Drain current | 3413 | Bias condition C; $V_{GS}$ = 0 V; $V_{DS}$ = 80 percent of rated $V_{DS}$ (pre-irradiation) | $I_{DSS}$ | | -25 | | -25 | | -25 | µA dc |

See footnotes at end of table.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection - Continued.

| Inspection 1/ 2/ 3/ 4/ | MIL-STD-750 | | Symbol | Pre-irradiation limits | | Post-irradiation limits | | | | Unit |
|---|---|---|---|---|---|---|---|---|---|---|
| | | | | R and F | | R | | F 5/ | | |
| | Method | Conditions | | Min | Max | Min | Max | Min | Max | |
| Subgroup 2 - Continued | | $T_C$ = + 25°C | | | | | | | | |
| Static drain to source on-state voltage | 3405 | Condition A; $V_{GS}$ = -12 V; $I_D = I_{D2}$; pulsed (see 4.5.1) | $V_{DS(on)}$ | | | | | | | |
| 2N7422 | | | | | -1.12 | | -1.12 | | -1.12 | V dc |
| 2N7423 | | | | | -2.835 | | -2.835 | | -2.835 | V dc |
| Forward voltage source drain diode | 4011 | Bias condition C; $V_{GS}$ = 0 V; $I_D = I_{D1}$ | $V_{SD}$ | | | | | | | |
| 2N7422 | | | | | -3.0 | | -3.0 | | -3.0 | V dc |
| 2N7423 | | | | | -3.6 | | -3.6 | | -3.6 | V dc |

1/ For sampling plan see MIL-PRF-19500.
2/ Group D qualification may be performed prior to lot formation. Wafers qualified to these group D QCI requirements may be used for any other specification utilizing the same die design.
3/ At the manufacturer's option, group D samples need not be subjected to the screening tests, and may be assembled in its qualified package or in any qualified package that the manufacturer has data to correlate the performance to the designated package.
4/ Unless otherwise noted, electrical characteristics, ratings, and conditions for "U" suffix devices (surface mount) are identical to the corresponding non-"U" suffix devices.
5/ The "F" designation represents devices which pass end-points at both R and F designated Total-Ionizing-Dose (TID).
6/ Separate samples shall be pulled for each bias.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

TABLE III. Group E inspection (all quality levels) for qualification or re-qualification only.

| Inspection | MIL-STD-750 | | Sample plan |
|---|---|---|---|
| | Method | Conditions | |
| Subgroup 1 | | | 45 devices c = 0 |
| Temperature cycle | 1051 | Condition G, 500 cycles | |
| Hermetic seal | 1071 | | |
| Fine leak<br>Gross leak | | | |
| Electrical measurements | | See table I, subgroup 2 | |
| Subgroup 2 1/ | | | 45 devices c = 0 |
| Steady-state gate bias | 1042 | Condition B, 1,000 hours | |
| Electrical measurements | | See table I, subgroup 2 | |
| Steady-state reverse bias | 1042 | Condition A, 1,000 hours | |
| Electrical measurements | | See table I, subgroup 2 | |
| Subgroup 4 | | | Sample size N/A |
| Thermal impedance curves | | See MIL-PRF-19500. | |
| Subgroup 10 | | | 22 devices c = 0 |
| Commutating diode for safe operating area test procedure for measuring dv/dt during reverse recovery of power MOSFET transistors or insulated gate bipolar transistors | 3476 | Test conditions shall be derived by the manufacturer | |

1/ A separate sample for each test may be pulled.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.







FIGURE 3. Thermal impedance curve.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.




2N7422, 2N7422U




2N7423, 2N7423U

FIGURE 4. Maximum drain current versus case temperature graphs.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.





FIGURE 5. Safe operating area graph (2N7422, 2N7422U).



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.





FIGURE 6. Safe operating area graph (2N7423, 2N7423U).



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.1).

d. Product assurance level and type designator.

* 6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land and Maritime, ATTN: VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.daps.dla.mil .

6.4 Cross-reference list. The following table shows the generic P/N and its associated military P/N (without JAN and RHA prefix).

| Commercial types (1) | | |
|---|---|---|
| Preferred types | TO-254AA | "U" |
| 2N7422 | IRHM9_150 | IRHN9_150 |
| 2N7423 | IRHM9_250 | IRHN9_250 |

(1) IRH9_: 100 K Rad (Si)
IRH93: 300 K Rad (Si)

6.5 JANC die versions. The JANHC and JANKC die versions of these devices are covered under specification sheet MIL-PRF-19500/657.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.

6.6 Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
Navy - EC
Air Force - 85
NASA - NA
DLA - CC

Preparing activity:
DLA - CC

(Project 5961-2009-051)

* NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.daps.dla.mil/.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:36Z
Check the source to verify that this is the current version before use.