L-F-001641
AMENDMENT-2
September 24, 1982
Superseding
Amendment-1
September 8, 1971

AMENDMENT

TO

INTERIM FEDERAL SPECIFICATION

FLOOR COVERING TRANSLUCENT OR TRANSPARENT
VINYL SURFACE WITH BACKING

This amendment was developed by the Furniture Commodity Center, Office of Personal Property, General Services Administration, Washington, D.C., 20406, based upon currently available technical information. The General Services Administration has authorized this amendment as a part of Interim Federal Specification L-C-001641 (GSA-FSS), dated January 28, 1971.

Page 1

The approved item name for this document is FLOOR COVERING, VINYL RESIN.

Paragraph 1.1, following the word "inorganic" insert "or filled fibrous composition (non-abestos formulated)".

Paragraph 1.2, delete in its entirety and substitute:

1.2 Classification. Floor covering shall be of the following types and classes as specified (see 6.2).

Type I -Organic fiber backing treated with asphalt or other moisture-resistant materials.
Type II -Filled vinyl backing.
Type III -Inorganic fiber backing saturated with alkali and moisture-resistant materials or filled fibrous composition (non-abestos formulated) backing saturated with alkali and moisture-resistant materials.

Class - Average Wear Layer Thickness, inch.
1. 0.020
2. 0.014
3. 0.010

Page 2

Paragraph 3.1.1, line 4, delete the third sentince in its entirety and substitute: "Each resin shall be poly (vinyl cloride) or a copolymer of vinyl chloride."

FSC 7220

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

L-F-001641

Paragraph 3.1.3, Type III, delete in its entirety and substitute:

Type III Inorganic or filled fibrous composition (non-abestos formulated). Backing shall consist of inorganic fibers treated with an alkali resistant and moisture-resistant materials or filled fibrous composition (non-abestos formulated) treated with an alkali and moisture-resistant materials.

Page 3

Paragraph 3.2.3, following the word "wear" insert the word "layer".
Paragraph 3.3, delete the first sentence and substitute: "Unless otherwise specified, the floor covering shall be furnished in 6, 9, or 12 foot width (plus 1 inch, minus 0 inch) and in the following thicknesses."

Change the title of the two columns to read: "Average Total Thickness, inch" and "Average Wear Layer Thickness, inch". Delete the sentence describing the thickness of the backing and substitute: "The average thickness of the backing shall be 0.020 inch, for all classes."

Delete Table I and footnotes in their entirety and substitute:

TABLE I. Characteristics of floor covering

Characteristic	Requirement	Test Method Fed. Test Method Standard No. 501	Other
Average total thickness, inch	see 3.3	2121 1/	---
Average wear layer thickness, inch	see 3.3	2151	---
Average residual indentation, inch	0.012	3231 2/	4.4.2 3/
Flexibility, 1/4-inch diameter mandrel	No crack or break	3111 4/	---
Dimensional stability, average change in either direction, percent maximum	0.3	----	4.4.3
Resistance to oils and chemicals	No more than slight discoloration, softening or other degradation of surace.	-----	4.4.1

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

TABLE I. Characteristics of floor covering (continued)

Characteristic	Requirement	Test Method Fed. Test Method Standard No. 501	Other
Abrasion resistance			
Class 1 - 1.5 gm. zinc loss Class 2 - 1.0 gm. zinc loss Class 3 - 0.6 gm. zinc loss	No break through of vinyl surface 5/	---	ASTM 6/ D-1242 Method B

1/ Dial micrometer shall have a 6-inch square anvil, flat presser foot 0.250 inch in diameter and a one ounce weight on plunger.
2/ This method with a 75 pound load shall be used when floor covering does not contain a foam layer.
3/ This method shall be used when floor covering contains a foam layer.
4/ The wear layer should be against the mandrel. After the specimen is bent over the mandrel, it shall be straightened and the wear layer examined for cracks or breaks.
5/ There shall be no point at which vinyl surface is abraded through.
6/ Add to test method requirements.
   a. Specimens shall be cut in factory machine direction.
   b. Specific gravity need not be determined.
   c. Coarse grit procedure of Note 5 using OE Flint Abrasive Paper shall be applicable.
   d. Zinc standard shall be weighed prior to start of test.
   e. Sufficient cycles shall be completed to obtain the required zinc weight loss for the applicable class.
   f. Specimens shall be observed at the conclusion of the test using a low power magnifying glass.

Page 7

Paragraph 6.1, delete in its entirety and substitute:

6.1 Intended use. The vinyl floor covering described herein is intended for use as follows:

Class	Traffic Application
1	A, B, C
2	B
3	B

A - For public spaces in multi-family housing.
B - Within living units, residential.
C - Commercial Buildings

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.