L-S-001787(GSA-FSS)
March 9, 1973

INTERIM FEDERAL SPECIFICATION

SHADE, WINDOW, (VINYL), WITH ROLLER, SLAT, RING PULL

AND ACCESSORIES AND VINYL FILM (IN PIECE GOODS)

This Interim Federal Specification was developed by the Federal Supply Service, General Services Administration, Washington, D. C. 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers requirements for vinyl film window shades and vinyl film in piece goods form.

1.2 Classification. The vinyl film window shades and vinyl film shall be of the following types and classes as specified (6.2).

Type I - Shade, window (vinyl).
Type II - Vinyl film (piece goods).

Class 1 - Single ply.
Class 2 - Multiple ply.

Subclass A - Translucent.
Subclass B - Room Darkening.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issues in effect on the date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

PPP-B-636 - Box, Fiberboard.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment.
Fed. Test Method Std. No. 191 - Textile Test Methods.
Fed. Test Method Std. No. 406 - Plastics: Methods of Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-1363 - Measurement of Wood Moisture Content.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Fire Protection Association Standard:

NFPA No. 701 - Standard Methods of Fire Tests for Flame Resistant Textiles and Films - Small Scale Test (701-7), Section 22.

(Application for copies should be addressed to the National Fire Protection Association, 60 Batterymarch Street, Boston, MA 02110.)

National Motor Freight Traffic Association, Incorporated, Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, D. C. 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Preproduction sample. When specified (6.2), a preproduction sample of the vinyl film window shade, including all components and accessories, or vinyl film material, a minimum of 12 inches square, as applicable, shall be submitted to the contracting officer for approval.

3.2 Material. All materials shall be as hereinafter specified. All materials shall be unused and free from defects which affect serviceability or appearance of the finished product.

3.2.1 Vinyl material. The vinyl material for types I and II, classes 1 and 2, shall be as specified in 3.2.1.1 and 3.2.1.2. When subclass A is specified, the material shall be translucent and when subclass B is specified, the material shall be room-darkening (opaque).

3.2.1.1 Type I, class 1, and type II, class 1. The vinyl material for type I, class 1, and type II, class 1, shall be nominal 0.006 inch gage, semi-rigid calendered vinyl film with matte or embossed surfaces. Other physical requirements shall be as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

Characteristic	Requirement	
	Subclass A	Subclass B
Tensile strength, lbs./sq. inch, minimum:		
Machine (lengthwise) direction	2800	2300
Cross (widthwise) direction	2000	1800
Elongation, percent, minimum:		
Machine direction	100	90
Cross direction	100	90
Tear strength, grams, minimum:		
Machine direction	180 1/	250 1/
Cross direction	180 1/	250 1/
Weight, lbs. sq. yd.:		
Minimum	0.360	0.470
Maximum	0.425	0.530
Volatility, percent loss, maximum	2.0	2.0
Specific gravity (25°C.)	1.35 to 1.43	1.75 to 1.83
Color Fastness to:		
Light	Good 2/	Good 2/
Soap and water scrubbing	3/	3/
Sealability (heat sealing)	No peeling	No peeling
Flame resistance	See paragraph 3.2.1.3	See paragraph 3.2.1.3
Resistance to cracking	4/	4/

1/ No single determination shall be less than 125.
2/ Time of exposure shall be 100 hours.
3/ There shall be no exudation, spewing, color streaks, bleeding or other evidence of poor color fastness.
4/ There shall be no cracking or breaking or other evidence of damage.

3.2.1.2 Type I, class 2, type II, class 2. The vinyl material for type I, class 2, and type II, class 2, shall be calendered vinyl film, fabricated into a 3 ply laminate unless otherwise specified (6.2), nominal 0.006 inch gage, semi-rigid, with matte or embossed surfaces. Other physical requirements shall be as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

Characteristic	Requirement
Tensile strength, lbs./sq. inch, minimum:	
Machine (lengthwise) direction	2800
Cross (widthwise) direction	2000
Elongation, percent, minimum:	
Machine direction	100
Cross direction	100
Tear strength, grams, minimum:	
Machine direction	400 1/
Cross direction	400 1/
Weight, lbs. sq. yd:	
Minimum	0.370
Maximum	0.450
Volatility, percent loss, maximum	2.0
Specific gravity (25°C.)	1.35 to 1.43
Color fastness to:	
Light	Good 2/
Soap and water scrubbing	3/
Sealability	No peeling
Flame resistance	See paragraph 3.2.1.3
Resistance to cracking	4/

1/ No single determination shall be less than 300 in the machine or cross direction.

2/ Time of exposure shall be 100 hours.
3/ There shall be no exudation, spewing, color streaks, bleeding or other evidence of poor color fastness.
4/ There shall be no cracking or breaking or other evidence of damage.

3.2.1.3 Flame resistance. The vinyl material specified in paragraph 3.2.1.1 and 3.2.1.2 shall meet the performance described for the small scale test in National Fire Protection Association Standard No. 701.

3.2.1.4 Roll contour and lay-flat. The vinyl material shall not vary by more than 1/8 inch when tested for roll contour and lay-flat.

3.2.2 Shade pull. Unless otherwise specified (6.2), the shade pull shall be a crocheted ring or plastic pull. The ring pull shall be made of a rayon or cotton twisted cord crocheted around a solid metal ring and finished off with an integral cord loop and shall finish approximately 1-1/2 inches in outside diameter with an approximately overall length of 12 inches. The plastic pull shall be of high strength, constructed for firm and easy pulling and secure attachment to the shade, and shall be free of any sharp or rough areas which may cause injury. The color of the pull shall be compatible with that of the shade.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

3.2.3 Rollers. Unless otherwise specified (6.2), rollers shall be made of either wood, metal, a combination of wood and metal, or a comparable quality of roller made of layers of cellulose fiber laminated with adhesive. Metal or a combination wood and metal roller shall be used on shades over 72 inches wide. Metal used shall be as specified in 3.2.6. Wood used shall be of any of the following species: Basswood; hemlock, eastern and western; Idaho white, ponderosa and sugar pine, western red and white fir; redwood; spruce. Moisture content of wood shall not exceed 12 percent. Slope of wood grain shall not exceed 1 inch in 10 inches. Wood shall be free of defects that mineral streaks and sound tight knots of not over 1/4 inch in diameter will be permitted provided the knots are not in clusters.

3.2.3.1 Roller diameter. Unless otherwise specified (6.2), the diameters of the rollers for the width and length of the shade specified shall be as shown in table I and the necessary brackets and screws shall be included with the rollers. Shade widths referenced in table I are nominal widths of vinyl shade material.

TABLE I. Roller diameter (minimum) 1/

Length of shade (feet)	Width of shade (inches)		
	18 to 54 (inch)	Over 54 to 72 (inch)	Over 72 to 120 (inch)
3 to 6, inclusive	15/16 or 1	1 or 1-1/4	1-1/4 or 1-1/2
Over 6 to 8, inclusive	15/16 or 1	1 or 1-1/4	1-1/4 or 1-1/2
Over 8 to 12, inclusive	1-1/4	1-1/4	1-1/4 or 1-1/2

1/ Roller diameters are minimum. Where two minimums under one shade width and one length of shade range (e.g. 15/16 or 1) is shown, it is intended to show popular diameter rolls used and the contractor shall select that minimum compatible with the shade being manufactured to ensure no flimsiness.

3.2.4 Slats. Slats shall be of wood specified in 3.2.3, except that slope of grain shall not exceed 1 inch in 15 inches and knots shall not exceed 1/8 inch in diameter. Unless otherwise specified (6.2), the width of the slat shall be 11/16 (± 1/16) inch wide for shade material up to 54 inches wide, 15/16 (± 1/16) inch wide for shade material over 54 to 72 inches wide and 1-1/4 (± 1/16) inches wide for shade material over 72 inches wide. The shade widths refer to the nominal widths of vinyl shade material. The length of the slat shall not exceed nor be more than 1/4 inch less than the width of the shade material. The cross section of the slats shall be that of commercial practice and when ordered separately the length shall be within a tolerance of plus or minus 1/8 inch.

3.2.5 Springs. The springs of the roller shall be adjustable for the tension required and shall catch readily at each turn of the roller. Spring shall release readily when properly handled. Unless otherwise specified (6.2), the minimum length of the spring for the diameter of the roller shall be as given in table II. This spring length shall be determined by its length when mounted on the dowel.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

TABLE II. Length of spring (minimum) for diameter of rollers

Diameter of rollers (Inches)	Shade length (maximum) (Feet)	Length of spring (minimum) (Inches)	Cross-sectional area of wire (minimum) (Square inch)	Weight of wire per gross of springs (minimum) (Pounds)
15/16	6	7-5/8	0.00104 or 0.00120 1/	7.21 or 10.00 1/
15/16	8	9-3/8	0.00135	12.90
1	6	8-9/16	0.00130	11.03
1	8	13-1/16	0.00185	16.50
1-1/4	12	14 or 14-9/16	0.00195 or 0.00241	28.00 or 33.00
1-1/2	12	18-1/2	0.00300	63.00

1/ Spring lengths are minimum. Where two minimums are shown under a category, it is intended to show popular springs used and the contractor shall select that minimum to ensure sufficient strength to operate the shade properly.

3.2.6 Brackets, metal rollers, ferrules, and ends. The brackets, metal rollers, ferrules and other metal components shall be corrosion resistant steel or malleable iron, nickel or cadmium coated or bright zinc plated. High strength plastic ends are acceptable. Parts shall be free of burrs and rough edges.

3.3 Construction and assembly. The type I window shade shall be fabricated from the material specified in 3.2.1.1 or 3.2.1.2, as applicable, and shall be furnished with roller, slat, brackets, screws and shade pulls. The vinyl material shall be cut square and true. A corrosion resistant eyelet shall be inserted and centered in slat when a crocheted ring pull is used. The finished shade shall be mounted evenly on rollers using suitable substantial fasteners and shall be complete with bottom hem, slat inserted, and pull. The hem shall be heat sealed or securely sewn, unless otherwise specified (6.2), and shall be of sufficient width to include free enclosure of the slat.

3.3.1 Special assembly. When specified in the contract or order (6.2), the type I window shade may be ordered cut to size, with bottom hem and slat, without rollers, springs, brackets and screws. Under this option, an eyelet shall be inserted in slat in accordance with 3.3, when specified (6.2). See 3.4.1 concerning dimensions applicable to the special assembly when ordered.

3.4 Dimensions and tolerances.

3.4.1 Type I, class 1, and type I, class 2. Type I, class 1, and type I, class 2, window shades shall be furnished in finished lengths, after hemming. The dimensions shall include length and width, as specified (6.2, 6.3 and 6.4). The shade width specified shall be tip to tip (see Figure 1). The dimensions shall also be specified in this manner when the special assembly specified in 3.3.1 is required.

3.4.2 Type II, class 1, and type II, class 2. The type II, class 1, and type II, class 2, vinyl material shall be furnished in roll form. Unless otherwise specified (6.2), the dimensions shall include length and tip to tip width (see Figure 1), to allow conformance with 3.4.3.

3.4.3 Roller coverage. The roller shall extend not more than 1/2 inch beyond each end of the shade cloth when shades are intended to be hung between the jambs with inside fixtures. When shades are intended to be hung on the face of window casing, the roller shall extend not more than 3/4 inch beyond each end of the shade cloth (6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

3.5 Color. The color shall be as specified (6.2). The color shall match the Government color sample or the color shall be those colors offered and approved by the contracting officer or purchaser.

3.6 Workmanship. The finished shade and material shall be clean and of high quality construction. Any evidence of defects which detract from the appearance or may impair serviceability shall be cause for rejection of the end item furnished by the supplier.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Preproduction sample inspection. When a preproduction sample is required, inspection shall be made of the completed end item for conformance with all provisions of this specification.

4.3 Inspection for acceptance. Inspection shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated.

4.3.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents.

4.3.1.1 Certificate of compliance.

4.3.1.1.1 Components listed below may be accepted on the basis of suppliers' certificate of compliance with requirements specified for the characteristics as listed below. Test methods shall be as specified in 4.5.5 and 4.5.6.

Component	Characteristic	Requirement
Rollers	Moisture content	3.2.3
Slats	Moisture content	3.2.4
Springs	Cross-sectional area	Table II
	Weight per gross	Table II

4.3.1.1.2 Certificate of compliance may be accepted for roll contour and lay-flat requirement specified in 3.2.1.4. The applicable test method is specified in 4.5.7.

4.3.2 Intermediate inspection.

4.3.2.1 Visual examination. Examination of the slats shall be in accordance with the list of defects set forth in table III. The lot sizes shall be expressed in units of slats for the purposes of determining the sample size in accordance with MIL-STD-105. The sample unit for this examination shall be one complete slat prior to insertion in the shade. The inspection level and AQL shall be as specified in 4.3.3.5.

TABLE III. List of defects

Examine	Defect
Slats for material and workmanship	Not species of wood required. Slope of grain exceeds 1 inch in 15 inches. Any knot exceeding 1/8 inch in diameter. Clustered knots. Not smooth or splinter free.

4.3.3 Examination of the end item. The end item shall be examined for the defects listed in 4.3.3.1, 4.3.3.2, and 4.3.3.3. The inspection levels and AQLs shall be as specified in 4.3.3.5. The lot size for purposes of determining the sample size in accordance with MIL-STD-105 shall be expressed in units of shades.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

4.3.3.1 Visual examination. Examination of the window shades shall be in accordance with the list of defects listed in table IV. The sample unit for this examination shall be one complete window shade (with brackets and screws, when specified).

TABLE IV. List of defects

Examine	Defect
Shade cloth	Pinhole - any. Cut, hole, or tear. Crease or wrinkle (when resulting in doubling or adhesion of surfaces). Wavy, rolled, or folded edges. Spot, stain, or streak. Objectionable odor. Color not as specified. Color nonuniform, shaded, spotted or mottled. Any tacky areas.
Other material construction and workmanship	Pull with attached eyelet missing (when applicable). Pull not a matching color. Wood of roller not species required. Knot in roller over 1/4 inch in diameter, or clustered knots. Hem not as specified. Plastic pull (when applicable) poorly constructed and not free of sharp or rough areas. Slope of grain in wood or roller exceeds 1 inch in 10 inches. Roller not smooth and splinter free. Brackets and screws missing (when specified). Metal or combination wood and metal rollers not used on shades over 72 inches wide. Other type rollers used on shades over 72 inches wide. Material and coating of brackets, metal rollers, ferrules and ends not as required. Metal components not free from burrs or rough edges. Any evidence of flimsiness (not firm) due to improper roller diameter used. Roller barrel extends more than 1/2 inch beyond end of shade cloth when shades are for use between jambs (i.e. inside mounting). Roller barrel extends more than 3/4 inch beyond end of shade cloth when shades are for use on face of window casing. Vinyl material not securely fastened to rollers.

4.3.3.2 Dimensional examination. Examination shall be made of the shades for compliance with dimensions specified. Any deviation from specified dimensions shall constitute a defect. The sample unit for this examination shall be one complete window shade.

4.3.3.3 Examination for spring action and roller performance. Examination shall be made on shades for adjustability and proper catching and releasing. The shade shall be mounted on the brackets, pulled down a minimum of 75 percent of its length and checked for releasing and catching a minimum of three times during rewind. This procedure shall be repeated for a total of 100 cycles. Any failure to readily catch and release or evidence that the spring does not have sufficient strength to operate the shade properly shall be considered a defect. Observation shall also be made to determine if roller is flimsy (not firm) which shall also be classified as a defect. The sample unit for this examination shall be one complete shade.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

4.3.3.4 Examination of preparation for delivery. An examination shall be made to determine that the packaging, packing, and markings comply with the requirements of section 5. Defects will be scored in accordance with table V. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. The lot size shall be the number of containers in the inspection lot. The inspection level shall be S-2 with an AQL of 2.5 defects per 100 units.

TABLE V. List of defects

Examine	Defect
Markings (exterior and interior)	Incorrect; illegible; of improper size, location, sequence or method of application.
Materials	Any nonconforming component; component missing, damaged or otherwise defective affecting serviceability.
Workmanship	Inadequate application of components such as: incomplete closure of container flaps, loose strapping, inadequate stapling, improper wrapping or taping. Bulged or distorted containers.
Weight	Weight of contents exceeds requirements of the box specification.
Count	Less than indicated number of shades per container.

4.3.3.5 Inspection levels and AQLs for examination. The inspection levels for the purposes of determining the sample size and the AQLs expressed in defects per hundred units, shall be as follows:

Examination paragraph	Inspection level	AQL
4.3.2.1	I	4.0
4.3.3.1	II	4.0
4.3.3.2	S-2	2.5
4.3.3.3	S-2	2.5

4.4 Testing of the end item. Tests shall be performed for the characteristics specified below. Unless otherwise specified, the physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes in the applicable test method. The sample unit shall be 1 complete window shade (with brackets and screws, when specified) for type I and 2 yards of full width vinyl material for type II. The sample size shall be as specified in level S-2 of MIL-STD-105 for type I and 2 for a lot size (yards) of 800 or less, 3 for a lot size of 801 up to and including 22,000, and 5 for a lot size of 22,001 and over for type II. For type II, only 1 sample unit shall be selected from any one piece or roll to obtain the sample size. The lot size shall be expressed in units of 1 complete shade for type I and 1 yard full width for type II. The lot shall be unacceptable if one or more units fail to meet any requirement specified. Requirements are specified in paragraphs 3.2.1.1 and 3.2.1.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

Testing of the end item

Characteristic	Test Method
Tensile strength	Method B of 1013 1/
Elongation	Method B of 1013 1/
Tear strength	5132 2/
Volatility	6081 1/
Color fastness to:	
Light	5660 2/ 3/
Soap and water scrubbing	Para. 4.5.1
Sealability (heat sealing)	Para. 4.5.2
Flame resistance	Para. 4.5.3
Resistance to cracking	Para. 4.5.4

1/ Fed. Test Method Std. No. 406.
2/ Fed. Test Method Std. No. 191.
3/ Time of exposure shall be 100 hours.

4.5 Test methods.

4.5.1 Colorfastness to soap and water scrubbing. A piece of shade cloth approximately 12 inches by 24 inches shall be laid on a flat horizontal surface and approximately one half gently scrubbed with a clean white cotton cloth pad that has been wet out with a lukewarm (approximately 100°F.) water solution containing 0.5 percent neutral soap. The specimen shall be scrubbed by using a unidirectional motion accomplished by allowing the pad to make contact with the surface of the cloth just after the beginning of the stroke and lifting the pad from the surface just before the end of the stroke. Each unit area of the specimen shall be scrubbed with 10 to 15 strokes at such a rate that 1 square foot shall be fully treated within 3 minutes when a 3 by 3 inch pad is used. After completion of the scrubbing with soap solution, the washed area shall be rinsed by repeating the washing operation except that lukewarm (approximately 100°F.) water shall be used in place of the soap solution. The washed portion of the cloth shall be examined for streaking. Bleeding is indicated by any discoloration of the cloth during the washing or rinsing of the specimen or discoloration of the water. To determine discoloration, a sample of the water after test shall be compared against the original sample of water by viewing through test tubes.

4.5.2 Sealability (heat sealing). The material shall be heat sealed full width, simulating hem formation, with conventional heat sealing equipment. The seal shall be strong and shall not peel. Tension applied shall be by hand and reasonably stronger than would occur in normal handling.

4.5.3 Flame resistance. The vinyl material shall meet the performance described for the small scale test in National Fire Protection Association Standard No. 701. Small scale test (701-7) is covered by Section 22 of NFPA No. 701 standard.

4.5.4 Resistance to cracking. Cut a 2 by 2 inch specimen of the vinyl material. Crease the specimen to form a crease parallel to the direction of the filling. A five pound weight not greater than 2-1/2 inches in diameter shall be placed on the fold for a minute while the specimen rests on a hard surface. Remove the weight, then fold the specimen in the same position as the first crease but in the opposite direction and the weight again applied for a minute. Repeat the procedure until 5 double folds have been made. Examine the specimen for cracking, breaking or other evidence of damage along the crease line.

4.5.5 Moisture content. Moisture content of wood shall be determined in accordance with MIL-STD-1363.

4.5.6 Cross-sectional area and weight per gross of springs. The cross-sectional area and weight per gross of springs shall be determined in accordance with standard commercial practice.

4.5.7 Roll contour and lay-flat. The rolls to be tested shall be conditioned by storage for at least 24 hours in a room held at a temperature from 20°C to 30°C. Each roll tested shall be placed horizontally on a flat surface. The roll diameter shall be determined at each end with a caliper. The measurement taken shall be the end diameter and not include any of the surface or body of the roll. The difference between the diameters at each end shall be the variance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, or C, as specified (6.2).

5.1.1 Level A.

5.1.1.1 Shades. The hardware, ring pull and accessories (when required), shall be packaged in a kraft paper, plastic envelope or bag and the opening sealed. Each shade, rolled, together with hardware (when required), shall be wrapped with kraft paper or plastic material. The wrap shall be secured with gummed paper or pressure sensitive adhesive tape.

5.1.1.2 Vinyl film. The vinyl film shall be rolled and wrapped with kraft paper or plastic material. The wrap shall be secured with gummed paper or pressure sensitive adhesive tape.

5.1.2 Level C.

5.1.2.1 Shades. The shades and accessories when required shall be packaged to insure protection during shipment and safe delivery to destination.

5.1.2.2 Vinyl film. The film shall be packaged to insure protection during shipment and safe delivery to destination.

5.2 Packing. Packing shall be level A, B, or C, as specified (6.2).

5.2.1 Level A.

5.2.1.1 Shades. The shades of one dimension only, shall be packed in a close-fitting box conforming to PPP-B-636, class weather resistant. The box shall be closed, waterproof sealed and strapped in accordance with the appendix to the box specification.

5.2.1.2 Vinyl film. The film of one dimension only, shall be packed in a close-fitting box conforming to PPP-B-636, class weather resistant. The box shall be closed, waterproof sealed and strapped in accordance with the appendix to the box specification.

5.2.2 Level B.

5.2.2.1 Shades. The shades shall be packed as specified in 5.2.1.1, except that the box shall be class somestic and waterproofing will not be required.

5.2.2.2 Vinyl film. The film shall be packed as specified in 5.2.1.2, except that the box shall be class domestic and waterproofing will not be required.

5.2.3 Level C.

5.2.3.1 Shades. The shades of one dimension only, shall be packed to insure carrier acceptance and safe delivery at destination at lowest rates, in containers complying with the Uniform Freight Classification or National Motor Freight Classification, as applicable.

5.2.3.2 Vinyl film. The film of one dimension only, shall be packed to insure carrier acceptance and safe delivery at destination at lowest rates, in containers complying with the Uniform Freight Classification or National Motor Freight Classification, as applicable.

5.3 Marking. In addition to any special marking required by the contract or order, all marking shall be in accordance with 5.3.1 or 5.3.2, as specified (6.2).

5.3.1 Civil agencies. All marking shall be in accordance with Federal Standard No. 123.

5.3.2 Military agencies. All marking shall be in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The items described in this specification are intended for both household and public buildings use. For most general use situations in these types of installations, class 1 and class 2 shades and vinyl film material are satisfactory. Particular and special engineering situations may prevail at the on-site installation to dictate use of either class 1 or class 2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

For example, for translucency the class 1 item may be selected and where handling conditions are such as to require a special high tearing strength the class 2 item may be selected. Both the class 1 and class 2 items can be furnished as opaque shades and material. Each installation must be judged carefully as to the peculiar conditions expected.

6.2 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(a) Type, class and subclass required (1.2).
(b) When preproduction sample is required (3.1).
(c) Ply of class 2 shade and material, if other than as specified (3.2.1.2).
(d) Type of shade pull, if other than as specified (3.2.2).
(e) Type of roller, if other than as specified (3.2.3).
(f) Diameter of roller, if other than as specified (3.2.3.1).
(g) Width of slat, if other than as specified (3.2.4).
(h) Spring length, if other than as specified (3.2.5).
(i) Type of hem, if other than as specified (3.3).
(j) Special assembly when required, and whether eyelet required (3.3.1).
(k) Dimensions required (3.4.1 and 3.4.2).
(l) Whether inside or outside mounting is required (3.4.3).
(m) Color required (3.5).
(n) Selection of applicable levels of packaging and packing (5.1 and 5.2).
(o) Selection of civil or military marking (5.3).

6.3 The length of window shades shall normally be specified in one foot intervals (e.g. 4 ft., 5 ft., etc.) and should be 12 inches longer than the window opening in order to minimize the chance of pulling the shade from the roller.

6.4 Some popular widths of shades (tip to tip measurement) are: average sizes of 37-1/4, 46-1/4, 55-1/4, 73-1/4 and larger sizes of 97-1/4 and 121-1/4 inches.




FIGURE 1.

Preparing activity:

GSA-FSS

Civil Agency Coordinating Activity:

GSA-FSS

GSA DC 73-11724

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.