MILITARY SPECIFICATION
MICROCIRCUIT, DIGITAL, CMOS (INITIAL LOGIC)

This amendment forms a part of Military Specification MIL-M-63320A(AR) dated 8 April 1981, and is approved for use by the US Army Armament Research and Development Command and is available for use by all the Departments and Agencies of the Department of Defense.

PAGE 3

3.4, line 1: Delete "Environmental tests" and substitute "Mechanical tests".

Mechanical shock, Conditions: Delete "D" and substitute "C".

Resistance to solvents: Delete "2015" and substitute "2015.1".

PAGE 5

3.5.4., (a) and (b): Delete (-45° C to +85°C) and substitute (-40° C to +70° C).

PAGE 7

4.3.1 Submission: Delete last sentence and substitute "The first article sample, after screening, shall consist of the quantities needed for double samplings stipulated in Table III."

PAGE 8

4.3.4: Add "e. A lapse in production for a period exceeding 90 days or as stipulated in the contract".

PAGE 9

TABLE III, Subgroups a, b, c, d: Delete "25" and substitute "8/";

Subgroup b, Mechanical shock: Delete condition "D" and substitute condition "C";

Subgroup c, Resistance to solvent: Delete "Method 2015" and substitute "Method 2015.1".

PAGE 10

TABLE III, Subgroup g: Delete "25" and substitute "9/";

NOTES: Delete present content of note 1 and substitute "Devices which fail any test criteria in the screening sequence shall be

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:38Z
Check the source to verify that this is the current version before use.

removed from the first article sample. The contractor should choose a first article sample that will provide, after screening, the quantities stipulated in notes 8 and 9.

PAGE 11

TABLE III: Add the following notes:

8/ A double sampling plan shall be used as follows: 25-0-2, 38-1-2. For group b replace fallouts from subgroup a.

9/ A double sampling plan shall be used as follows: 45-0-2, 77-1-2.

PAGE 15

4.4.2.3, Subgroup 2, Resistance to solvents: Delete "Method 2015" and substitute "Method 2015.1".

PAGE 16

4.4.2.4, Subgroup 2, Mechanical shock: change Condition "D" to Condition "C".

PAGE 20

4.5.18, Steady state life, line 3: Change

"Test duration shall be 100 hours minimum at 125° C ± 5° C." to "Test duration shall be 1000 hours minimum at 125° C ± 5° C or equivalent per Method 1005 of MIL-STD-883B. Temperature in excess of 135° C shall not be allowed".

PAGE 21

6.3 and 6.5: Delete "QAA" amd substitute "QAT".

PAGE 23

FIGURE 1: Delete present and substitute revised FIGURE 1 attached to this amendment.

PAGE 38


FIGURE 15: Delete present and substitute revised FIGURE 15 attached to this amendment.

Custodian:
Army-AR

Preparing Activity:
Army-AR

(Project 1345-A212)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:38Z
Check the source to verify that this is the current version before use.



	NOMINAL	TOLERANCE	STYLE	TYPE	TCC
C1	0.01 uf	± 1.0%	Ceramic	NPO	± 25 ppm
R1	2.0 M ohms	± 5.0%	Composition		
R2	470 K ohms	± 1.0%	Metal Film		± 50 ppm

FIGURE 1. Test Circuit for Leakage Current (Oscillator) and Oscillator Function tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:38Z
Check the source to verify that this is the current version before use.




FIGURE 15. Burn-in and Steady State Life-Test Circuit.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:38Z
Check the source to verify that this is the current version before use.