MIL-C-0016809C(DM)
7 August 1969
USED IN LIEU OF
MIL-C-0016809B(DM)
1 June 1964
and
MIL-C-16809A
16 June 1958

MILITARY SPECIFICATION

* CASE, MEDICAL INSTRUMENT AND SUPPLY SET, NONRIGID, NO. 4

This limited coordination Military Specification has been prepared by the Defense Personnel Support Center based upon currently available technical information, but it has not been approved for promulgation as a coordinated revision of Military Specification MIL-C-16809A. It is subject to modification. However, pending its promulgation as a coordinated Military Specification, it may be used in procurement

1. SCOPE

1.1 This specification covers an empty case made of vinyl-coated fabric, comprising three compartments with zipper closure, for holding first aid medications to be used for battle dressings in jungle and arctic climates Each case is fitted with a carrying handle and two flaps fitted with curtain fastener sockets and plates.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein·

SPECIFICATIONS

Federal

V-F-106	Fasteners, Slide, Interlocking.
V-T-285	Thread, Polyester
TT-S-735	Standard Test Fluids, Hydrocarbon.
CCC-C-419	Cloth, Cotton, Duck, Unbleached, Plied-Yarns, (Army and Numbered).

FSC 6545

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

PPP-B-585	Boxes, Wood, Wireboard.
PPP-B-601	Boxes, Wood, Cleated-Plywood
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-T-76	Tape, Pressure-Sensitive Adhesive Paper, (for Carton Sealing).

Military

MIL-F-495	Finish, Chemical, Black, for Copper Alloys.
MIL-F-10884	Fasteners, Snap.
MIL-L-10547	Liners, Case, and Sheet, Overwrap, Water-Vaporproof or Waterproof, Flexible
MIL-T-43566	Tape, Textile, Cotton, General Purpose, Natural or in Colors.

STANDARDS

Federal

Fed Test Method Std No. 151	Metals, Test Methods.
Fed. Test Method Std No. 191	Textile Test Methods.
Fed Std. No. 595	Colors.
Fed. Std No. 751	Stitches, Seams, and Stitchings.

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	Marking for Shipment and Storage
MS16686	Medical Services Symbol.
MS27977	Fastener, Snap, Style 1
MS27980	Fastener, Snap, Style 2

DRAWING

Defense Personnel Support Center

20729	Case, Medical Instrument and Supply Set, Nonrigid, No. 4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards, and drawing required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer)

2.2 Other publications The following documents form a part of this specification to the extent specified herein Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply

THE COLOR ASSOCIATION OF THE UNITED STATES, INC.

Department of Defense Standard Shades for Sewing Threads 1968.

United States Army Color Card of Standard Shades for Slide Fastener Tapes.

(Application for copies should be addressed to The Color Association of the United States, Inc , 200 Madison Avenue, New York, N Y. 10016).

3 REQUIREMENTS

* 3.1 Component parts. The case shall consist of three compartments, one large compartment to which a carrying handle is sewn and two small compartments Each compartment shall be equipped with a slide fastener closure The back of the large compartment shall be fitted with top and bottom flap, each containing four female curtain-type lift fasteners for securing the case in aircraft

* 3.2 Materials. Except as herein specified, materials shall conform to the applicable portions of the specifications, standards, and drawing listed in section 2, and shall be capable of meeting the requirements shown therein In addition, the metal shall conform to the chemical requirements of their applicable specifications when tested as specified in 4 2 2. When materials to be used are not specifically designated, those used shall be of the highest commercial quality, and entirely suitable for the purpose intended

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

3.2.1 Body fabric The body fabric shall be ply yarn cotton duck conforming to Specification CCC-C-419 for type III, 9.85 ounces per square yard, minimum, as shown in table II of the same specification, coated with a suitably compounded polymer or copolymer vinyl resin, with the color incorporated therein, so that the finished fabric shall be olive drab No. 7 The coating shall be applied by a solution or dispersion method to thoroughly and evenly impregnate both sides of the base cloth. Calendar coating is not permissible. No more coating than is necessary to meet the water and abrasion resistance requirements, and to obtain a uniform shade shall be applied to one side of the cloth; the balance shall be applied to the other side The coated fabric shall be made mildew-resistant by the use of the copper-8-quinolinolate as the mildew inhibitor The coating compound shall contain 1.25 to 1 50 percent by weight of copper-8-quinolinolate evenly dispersed in the coating

3 2.1 1 Crocking The finished coated fabric shall be tested as specified in 4 4 1.2. The resistance to dry crocking and to wet crocking shall be good.

3.2 1 2 Fabric weight The finished fabric weight shall be tested as specified in 4 4 1.3, and shall be not less than 16 nor more than 20 ounces per square yard

3 2 1.3 Breaking strength The finished coated fabric shall be tested as specified in 4 4.1 4 The minimum breaking strength shall be 160 pounds in the warp direction and 110 pounds in the filling direction.

3.2.1 4 Tearing strength The finished coated fabric shall be tested as specified in 4 4 1 5 The standard temperature tear strength shall be not less than corresponds to a scale reading of 50 for the warp direction, and 40 for the filling direction

3 2 1 5 Water-resistance The finished coated fabric shall be tested as specified in 4 4 1.6 The maximum leakage in a period of 10 minutes shall be 5 milliliters No water shall penetrate the unabraded portion

3.2 1.6 Weathering-resistance The finished coated fabric shall be tested as specified in 4 4 1 7 The loss in breaking strength shall not exceed 15 percent The finished fabric shall not crack when folded sharply on itself, nor shall it show signs of blooming or material color change

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

* 3.2.1.7 Adhesion. The finished coated fabric shall be tested as specified in 4 4 1.8 The adhesion shall be not less than 8 0 pounds per 2-inch width

* 3 2.1.8 Low-temperature-resistance The finished coated fabric shall be tested as specified in 4 4 1 9 The coating shall neither crack nor break

* 3.2.1 9 Heat-resistance The finished coated fabric shall be tested as specified in 4 4 1.10. The coating shall show no evidence of adhesion or exudation. The blocking shall have a maximum scale ratting of No. 3.

* 3.2.1 10 Abrasion-resistance The finished coated fabric shall be tested as specified in 4 4.1.11. The loss in breaking strength shall not exceed 25 percent, and the color of the abraded portion shall be olive drab No. 7

* 3.2.1.11 Gasoline-resistance The finished coated fabric shall show no evidence of cracking, flaking, or separation of the coating from the base fabric, and only a slight stiffening of the coated fabric, when tested as specified in 4 4 1 12.

* 3.2.2 Thread The thread shall be polyester conforming to type I or II, class I or 2, letter size FF of Specification V-T-285 The shade of the thread shall be vat dyed olive drab shade S-1, conforming to the Department of Defense Standard Shades for Sewing Threads, 1968.

* 3.2.3 Thongs Tape for slide fastener thongs shall conform to the requirements of MIL-T-43566, type I, class 4, 3/8 inch width. Color shall be olive drab No. 7

3.2 4 Fasteners, Slide Except as specified herein, the slide fasteners shall conform to Specification V-F-106, and shall be as follows·

a. Fasteners, slide, nonseparating. Nonseparating slide fasteners shall be type I, style 19, size M, two slider with short tab pulls fitted with thongs Metal parts shall be brass with a black chemical finish conforming to Specification MIL-F-495.

b. Fasteners, slide, separating. Separating slide fasteners shall be type IV, style 8, left hand separating unit, size M, single slider with short tab pulls fitted with thongs. Metal parts shall be brass with a black chemical finish conforming to Specification MIL-F-495.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

* 3.2.4.1 Tape. The slide fastener tapes shall be vat dyed olive drab, shade S, conforming to the U. S. Army Color Card of Standard Shade for Slide Fastener Tapes, and shall be water-repellent and mildew-resistant in accordance with V-F-106 Mildew resistance shall be obtained by using copper-8-quinolinolate only

* 3.2.5 Fasteners, curtain Curtain fasteners affixed to the case are for the purpose of mounting the case on a panel in an aircraft. Curtain fasteners shall consist of the female half of style 1, regular prong, of MIL-F-10884, (MS27977, Part Nos. MS27977-1B and MS27977-3B). Finish shall be black in accordance with MIL-F-10884

3 2 6 Fasteners, snap. Snap fasteners shall conform to the requirements of MIL-F-10884, Style 2, (MS27980, Part Nos. MS27980-1B, MS27980-6B, MS27980-7B, MS27980-8B). Finish shall be black in accordance with MIL-F-10884

3.2.7 Ink Ink shall be of a good commercial vinyl grade Colors shall completely fuse with the vinyl surface to which applied, and remain completely flexible without cracking and crazing in service

3 3 Construction. Construction shall meet the requirements specified herein, and those shown in the drawing

3.3.1 Stitches, seams, and stitchings All seams and stitchings shall conform to Federal Standard No. 751, shall be straight, and shall consist of stitch type 301 stitch, with not less than seven nor more than nine evenly spaced stitches per inch. Thread tension shall be properly maintained so that lock will be imbedded in the center of the material sewed

3 3.1.1 Anchorage The ends of each continuous row of stitches (including ends due to thread breaks) shall be anchored by backstitches for a length of not less than 1 inch, except where anchorage is provided by another seam or stitching Thread tension shall be properly maintained so that the lock will be embedded in the center of the stitch

* 3.3.2 Placement of fasteners. The eight female halves of the curtain fasteners and the three snap fasteners shall be positioned as shown on the drawing The pocket shall not be distorted when the snap fasteners are closed The finished cases shall be tested as specified in 4 4 2 and shall fit on the test panel without distortion

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

* 3.3.3 Attachment of fastener elements. Holes shall be punched in the fabric before insertion of tube of male element and prongs of female element Holes shall be small enough to require tubes and prongs to be forced through. Fastener elements shall be tightly clinched so as not to become detached from the fabric in normal use Holes in cloth at center of lift fastener shall be large enough so as not to impede insertion of studs in sockets

* 3.4 Marking for identification. Each case shall be permanently and legibly marked as shown on the drawing The marking inks shall conform to the requirements of 3.2.7. Colors shall be Color 31136 (lusterless red) and 37038 (lusterless black) as shown in FED-STD-595.

3 5 Workmanship. Workmanship shall be first class throughout Completed cases shall be well made and free from defects which detract from their appearance or may impair their serviceability.

4 QUALITY ASSURANCE PROVISIONS

* 4 1 Responsibility for inspection Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties).

4 1.2 Certificates of quality Certificates of Quality, supplied by the manufacturer of the cotton duck, curtain fasteners, slide fasteners, snap fasteners, thongs and thread, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government The Certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the FSN, the Item Identification, the name of the component/material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, the specification requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

4.2 Quality conformance inspection. The examinations and tests required to assure conformance of those items or lots of items to be offered for acceptance are classified as specified in tables I and II (see 4.2.1 and 4.2.2) and table III (see 4.3).

4.2.1 Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105. The inspection levels and acceptable quality levels (AQL) expressed in defects per 100 units shall be as indicated in table I. Unit of product for examination purposes shall be one case.

Table I. Sampling for Examination

Examination	Inspection level	AQL	
		Major	Total
For visual defects	II	2.5	10 Major and Minor A. 25 Major and Minor A and B
For dimensional defects	S-3		4.0 One Class.

4.2.2 Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and table II. Sufficient samples of the component materials shall be selected from each lot of material used in the manufacture of the case to perform tests as required by the applicable referenced specifications, or by tests specified herein. When sample size is not specified, it shall be as indicated for inspection level S-1 of MIL-STD-105, except that the acceptance number shall be zero for all sample sizes, and a minimum of three samples shall be taken regardless of lot size. The unit of product for testing shall be the quantity of material necessary to perform all required tests one time each. The same material may be used to perform two or more tests. Lot sizes are expressed in multiples of the following:

Cloth	Yard or fraction of a yard
Tape	Yard or fraction of a yard
Thread, polyester	Cone or spool
Hardware items	Each

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

Table II. Sampling for Tests

Component	Reqmt.	Test Procedure	Inspection level
Cloth	3.2.1.1-3.2.1.11	4.4.1.1 - 4.4.1.12	S-1
Thread	3 2.2	V-T-285	S-1
Thongs	3 2.3	MIL-T-43566	S-1
Slide Fasteners	3.2.4	V-F-106	S-1
Curtain Fasteners	3.2.5	MIL-F-10884	S-1
Snap Fasteners	3.2.6	MIL-F-10884	S-1
Placement of Fasteners	3.3.2	4 4 2	S-1

* 4.3 Examination The cases shall be examined for defects including, but not limited to those listed in table III.

Table III. Classification of defects

Visual

Examine	Defect	Classification Major	Minor A	Minor B
Cloth	Any hole, cut, or tear	X		
	Fabric defects:			
	seriously affecting serviceability.	X		
	affecting serviceability, but not seriously.		X	
Tape	Frayed or scalloped edges, not tightly and firmly woven	X		
Hardware	Broken or malformed, failing to serve intended purpose, finish omitted, corroded areas, burrs or sharp edges.	X		

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification		
		Major	Minor A	Minor B
Seams and stitching:				
Open seams	Up to and including 1/2 inch			X
	More than 1/2 inch, but not more than 1 inch		X	
	More than 1 inch. A seam shall be classified as open when one or more stitches joining a seam are broken or when two or more continuous skipped stitches or run-offs occur. On double stitched seams, a seam shall be considered open when either one or both sides of seam are open	X		
Raw edges (on outside of case)	Any raw edge when securely caught in stitching			X
	Raw edges not securely caught in stitching shall be classified as open seams.			
Run-offs (see open seams).				
Seam and stitch types	Wrong seam or stitch type.	X		
Stitch tension	Loose, resulting in loose top or bobbin thread		X	
	Tight, resulting in excessive tightness of fabric on seams		X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification		
		Major	Minor A	Minor B
Stitches per inch	One stitch less than minimum specified			X
	Two or more stitches less than minimum specified.		X	
	One or more stitches in excess of maximum specified			X
	Variation in the number of stitches per inch caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy seams, heavy places or in turning corners shall be classified as follows: A. Within the minor B defect classification-no defect. B Within the minor A defect classification-minor B defect.			
Stitching margin· stitching gage	Not as specified, affecting serviceability.			X
Stitching ends	Backstitched less than 1 inch (except where ends are held down by other stitching).	X		
Thread breaks	Backstitches less than 1 inch as specified (stitch type 301).			X
	Overstitched less than 3/4 inch (overedged stitching)			X

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification		
		Major	Minor A	Minor B
	Thread breaks not back-stitched shall be classified as open seams.			
Stitching rows.	One or more required rows of stitching omitted	X		
Strap stitching	Incomplete:			
	one row of stitching omitted		X	
	two or more rows of stitching omitted	X		
Components and assembly	Any component or required operation omitted (unless otherwise classified herein).	X		
	Mends, darns, or patches	X		
	Needle chews.	X		
Markings	Omitted, incorrect, illegible, misplaced, or size of characteristics not as specified	X		
Cleanness	Grease, oil, dirt, or other foreign matter clearly noticeable. Thread ends not trimmed throughout.		X	
	Dimensional			
Finished case	Overall dimensions not within specified tolerances			

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

* 4.4 Tests Tests of the materials used in fabrication of the cases shall be made as specified herein. Other tests may be made, to determine that the finished cases comply with this specification, and that the materials comply with the applicable portions of the specifications and drawings listed in section 2.

4.4.1 Body fabric.

* 4.4.1.1 Mildew-inhibitor-content. The finished coated fabric shall be tested for compliance with the chemical requirements of this specification, by either method 2050 or method 2051 of Specification CCC-T-191

* 4.4.1.2 Crocking. The crocking of the finished coated fabric shall be determined in accordance with method 5651, using method B and white crock cloth as specified in Specification CCC-T-191.

* 4.4.1.3 Fabric weight. The weight of the finished coated fabric in ounces per square yard shall be determined by method 5041 of Specification CCC-T-191

* 4 4 1.4 Breaking strength. The breaking strength of the finished coated fabric shall be determined by method 5100 of Specification CCC-T-191.

* 4.4.1.5 Tearing strength The finished coated fabric shall be tested by method
• 5132 of CCC-T-191. The standard instrument shall be used with the augmenting weight One series of tests shall be made with specimens in standard condition. The result of this series shall be the standard temperature tear strength.

* 4 4.1.6 Water-resistance. Specimens of the finished coated fabric shall be tested by method 5516 of Specification CCC-T-191, except as follows: Before each specimen is placed in the apparatus, it shall be abraded by means of a 2 inch square piece of grade 1/0 Garnet paper. The Garnet paper shall be uniformly loaded within an 8 0 ounce weight. The specimen shall be abraded over an area 6 inches long by 2 inches wide on heavily coated side by moving the loaded Garnet paper five times in each direction parallel to the filling so that the center of the abraded area is the center of the specimen. The specimen shall be placed in the apparatus so that its center coincides with the center of the ring clamp and with the abraded area exposed to the water. The hydrostatic head shall be 20 inches of water and the time of exposure 10 minutes

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

4.4.1.7 Weathering-resistance. The finished coated fabric shall be tested by method 5804 of Specification CCC-T-191. The number of hours of exposure shall be 150. Filters shall not be used.

4.4.1.8 Adhesion The finished coated fabric shall be tested by method 5970 of Specification CCC-T-191, using a suitable solvent or cement as specified by the fabric coater

4.4.1.9 Low-temperature-resistance. The finished coated fabric shall be tested as follows: Specimens shall be cut 4 inches long by 1 inch wide There shall be six specimens from each Unit-of-Product as defined in 2.1.4 of Specification CCC-T-191, of which three shall have the long dimension parallel to the warp, and three parallel to the filling. Each specimen shall be placed in an enclosure in which the temperature is maintained at minus 40degrees ± 2 degrees Fahrenheit and kept there for a period of 4 hours Immediately after removal from the enclosure, the specimen shall be bent over a glass rod 1/8 inch in diameter so that the backs of the specimen touch each other within a distance of 1/8 inch from the rod The specimen shall be touched only by material having low thermal conductivity so as to minimize change of temperature during the manipulation The specimen shall be kept for 10 minutes in the bent condition, then straightened and allowed to warm in still air to normal room temperature after which it shall be examined

4.4.1.10. Heat-resistance (blocking). The finished coated cloth shall be tested for blocking by method 5872 of CCC-T-191.

4.4.1.11 Abrasion-resistance The finished coated fabric shall be tested by method 5304 of Specification CCC-T-191, except as follows: The abradant shall be silicon carbide cloth (see 6.2). The tension shall be 6 pounds. The specimen shall be subjected to 750 continuous cycles on each side, and the abraded portion on one side shall be opposite the abraded portion on the other side.

4 4 1.12 Gasoline-resistance A sample, 1 by 6 inches, with the long dimension parallel to the warp, shall be immersed for 5 minutes in 40 percent aromatic fuel. The composition of the fuel shall conform to type II of Specification TT-S-735 The sample shall be allowed to dry at room temperature for 2 hours ± 5 minutes, and then, shall be creased at room temperature as specified in method 5874 of Specification CCC-T-191. A similar sample, cut with the long dimension parallel to the filling, shall be tested in the same manner.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

* 4.4.2 Test for placement of curtain fastener sockets and plates. A metal panel shall be made as shown in the drawing The studs on the panel shall be selected from those shown in MS 27977, and shall fit the specified curtain fastener sockets and plates as specified in 3.2.5 The finished cases shall be tested for placement of curtain fastener sockets and plates by attaching them to the studs on the panel. The cases shall then be inspected for distortion

5. PREPARATION FOR DELIVERY

5.1 Packaging

5 1.1 Unit of issue One (1) case, as specified, constitutes one unit of issue.

* 5 1.2 Packaging quantities. The number of units of issue indicated in Table IV shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document

Table IV. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	Not required	24 units

* 5 1 2.1 Packing variation permitted If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units may be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5 1 3 Level A

* 5 1 3 1 Unit package. Unit package shall be a box of appropriate size and design constructed in accordance with PPP-B-636, type CF, class weather-resistant Boxes shall be closed by taping the top and bottom flaps with 2 inch wide tape conforming to PPP-T-76 Closing of bottom flap with adhesive conforming to MMM-A-250 or metal stitches is permitted

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

5 1 4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5 2 Packing

5 2 1 Level A

5 2.1.1 Exterior container Exterior container shall be designed for type 2 load, and constructed in accordance with PPP-B-585, style 3, for class 3 use, PPP-B-601, table III, using type I, class plywood; PPP-B-621, table III; or PPP-B-636, type CF, class weather-resistant. Closure and strapping shall be in accordance with appendix of applicable box specification.

5 2.2 Level B

5 2 2 1 Exterior container. Exterior container shall conform to PPP-B-601, table II, using type III, class 1 plywood, or shall be designed for type 2 load and constructed in accordance with PPP-B-585, style 3, for class 2 use, PPP-B-621, table I; or PPP-B-636, type CF, class domestic Closure shall be in accordance with appendix of applicable box specification.

5 2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order

5 3 Marking

5.3.1 Interior packages. Each unit package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5 3 2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6 NOTES

6 1 Intended use Case, Medical Instrument and Supply Set, Nonrigid, No. 4, is intended to be used as the container for FSN 6545-919-6900, First Aid Kit, Air Force, General, Battle Dressing, and FSN 6545-935-7093 Medical Instrument

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

and Supply Set, Field Casualty Treatment. The kit may be secured during flight in aircraft suitably equipped with studs which fit the lift fasteners of the case, and may be readily carried when removed from the aircraft

* 6 2 The abradant silicon carbide cloth referenced in 4 3.1.11 shall be 3 M Company's No. 240J, or equal.

* 6.3 Ordering data Procurement documents should specify the following:

a. Number and date of this specification.

b. Selection of applicable levels of packaging and packing (see 5 1 and 5 2)

6 4 Availability of color chips. The individual 3- by 5-inch chips of the colors referenced in 3.4 are available from the General Services Administration, Busines Service Center, Region 3, Seventh and D Streets, S.W., Washinton, D.C. 14025

6 5 This specification does not include all types, classes, grades, sizes, etc , of the commodity indicated by the title of this specification, or which are commercially available, but is intended to cover the types, etc , which are normally procured to meet Military requirements.

6 6 The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document (s) or serve to amend contractual requirements.

SPECIFICATION
MIL-C-0016809C(DM) FSN

ORGANIZATION

CITY AND STATE | CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1 HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2 COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3 IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4 REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.)*

SUBMITTED BY *(Printed or typed name and activity - Optional)* | DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64, WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

Fold

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

DEFENSE SUPPLY AGENCY
OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

Fold

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:23Z
Check the source to verify that this is the current version before use.