|INCH/POUND|

MIL-C-16775D
12 June 1989
SUPERSEDING
MIL-C-0016775C(DM)
8 March 1965

MILITARY SPECIFICATION

CHESTS, FIELD, ALUMINUM, EMPTY

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the standard series of deep drawn, empty, lightweight, aluminum field chests, composed of standardized elements as hereinafter specified. Chests shall be suitable for the safe transportation of medical material under field conditions in any global environmental conditions without additional outer packaging or crating.

1.2 Classification. Chests shall be furnished as specified for the appropriate stock number and item identification as specified in the contract. Table I identifies the size and nominal inner dimensions.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-RST, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

\MSC/NA FSC 6545

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

TABLE I. Size and dimensions.

Size	Dimensions (inches)		
	Length	Width	Depth
1	24-1/4	12-1/4	6-1/4
2	30-1/4	18-1/4	6-1/4
3	30-1/4	18-1/4	10-1/4
4	30-1/4	18-1/4	12-1/4
5	30-1/4	18-1/4	16-1/4
6	30-1/4	18-1/4	20-1/4

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

QQ-A-200/3	Aluminum Alloy Bar, Rod, Shapes, and Tube, Extruded, 2024.
QQ-A-225/6	Aluminum Alloy Bar, Rod, and Wire, Rolled, Drawn, or Cold Finished, 2024.
QQ-A-250/8	Aluminum Alloy, 5052, Plate and Sheet.
QQ-S-766	Steel Plates, Sheets, and Strip Corrosion Resisting.
TT-E-527	Enamel, Alkyd, Lustreless.
QQ-W-470	Wire, Steel, High Carbon, Spring, Bright, Music.
TT-P-1757	Primer Coating, Zinc Chromate, Low Moisture Sensitivity.

MILITARY

MIL-C-5541	Chemical Films and Chemical Film Materials for Aluminum and Aluminum Alloys.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED-STD-151	Metals; Test Methods.
FED-STD-595	Colors.

MILITARY

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

DRAWING

Defense Medical Supply Center

20577	Chests, Medical Instrument and Supply Set, Field, Empty (5 sheets).

(Copies of specifications, standards and drawing required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM Standards and Tentative Standards

Designation D 395	Standard Methods of Test for Compression Set of Vulcanized Rubber.
Designation D 412	Tentative Method of Tension Testing of Vulcanized Rubber.
Designation D 1054	Standard Method of Test for Impact Resilience and Penetration of Rubber by the Rebound Pendulum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia 3, Pa.)

3. REQUIREMENTS

3.1 Material. Except as specified herein, materials shall conform to the applicable portions of the specifications, standards, and drawing specified herein, and shall be capable of meeting the requirements specified therein. In addition, the metals shall conform to the chemical requirements of their applicable specifications when tested as specified in 4.4.4. When materials to be used are not specifically designated, those used shall be of the highest commercial quality, and entirely suitable for the purpose intended.

3.1.1 Aluminum.

3.1.1.1 The chest body, cover, separator pan, gasket retaining channel, drawbolt hanger plate, drawbolt lock, handle-plate, packboard hook plate, and corner reinforcement shall be constructed of 5052-T0 aluminum alloy sheet conforming to QQ-A-250/8.

3.1.1.2 The handle shall be constructed of aluminum alloy conforming to grade AA-6063 of SAE AA-2024. The handle sleeve shall be constructed of 2024-T3 aluminum alloy conforming to QQ-A-200/3. The strap and shouldered screw shall be constructed of 2024-T4 aluminum alloy conforming to QQ-A-225/6.

3.1.2 Corrosion-resisting steel.

3.1.2.1 The drawbolt top hinge pin, separator pan washer, hexagon nuts and rivets shall be fabricated of corrosion-resisting steel conforming to class 302 or 304 of QQ-S-766.

3.1.2.2 The slot clip, and packboard hook shall be fabricated of corrosion-resisting steel conforming to class 430 of QQ-S-766.

3.1.3 Spring handle. Handle springs shall be constructed of steel wire conforming to QQ-W-470, except that the wire shall be uniformly coated with commercially pure zinc. The minimum weight of zinc coating shall be 0.30 ounces per square foot of surface.

3.1.4 Rubber. Rubber for the gasket shall be a natural rubber, pure gum compound. The rubber shall be tested as specified in 4.4.2.2; the physical properties shall conform to the following requirements:

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

Minimum tensile strength	1,000 pounds per square inch (p.s.i).
Minimum ultimate elongation	500 percent.
Maximum compression set	50 percent.
Maximum durometer reading	40 plus 5, minus 2.
Maximum loss in tensile strength on accelerated aging	20 percent.
Maximum loss in ultimate elongation on accelerated aging	30 percent.
Maximum increase in durometer reading on accelerated aging	10.

3.1.5 Primer. The primer shall be zinc chromate conforming to color Y of TT-P-1757.

3.1.6 Enamel. The enamel shall be synthetic lustreless olive drab, conforming to TT-E-527. The color shall be 34087 of FED-STD-595 (see 6.2). The enamel for identification marking (3.7) shall be black, color 37038 of FED-STD-595 (see 6.3), and shall also conform to TT-E-527.

3.1.7 Sealer. Sealer shall be 3M No. EC-800 or No. 2216, or Product Research & Chemical Corporation sealant, Part No. RR-1422-B1/2 or a commercial sealer with the same specifications and tolerances.

3.1.8 Drawbolt fastener. Material for the drawbolt fastener shall be as specified on the drawing.

3.2 Construction. The chest shall conform in all details to the requirements specified herein and as shown on the drawing, except that the embossed surfaces on the top of chests, elements 6 and 7, shall have a tolerance of 3/16 inch in concavity and convexity. The construction shall be sound, durable, and capable of meeting all tests hereinafter specified. All hardware shall be flush-mounted. However, handles and draw-bolt fasteners shall project no further than 1/8 inch beyond the plane of the chest outer surface.

3.2.1 Detail. Each chest shall consist of an aluminum body with cover and separator pan where indicated, symmetrically made, smoothly and properly finished. The chest body, cover, separator and channel retaining member for the rubber gasket shall be seamlessly die-drawn and trimmed as shown on the drawing. Slight flex warp to the cover element is acceptable. All other component shall have no flex, dimensional warp or structural deficiency.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

3.2.2 Component parts. Each chest shall be composed of the respective chest elements as indicated in Table II, and constructed in accordance with the applicable portions of the drawing.

TABLE II. Component parts listing.

Size	Element No.		Pan required
	Cover	Body	
1	2	1	No
2	4	3	No
3	4	5	No
4	6	3	Yes
5	6	5	Yes
6	7	5	Yes

3.2.3 Catch-draw. All parts shall be die-stamped and formed for uniform and interchangeable assembly. The slots in chest elements Nos. 2, 4, 6, and 7, respectively, wherein the drawbolt strike engages, shall be reinforced by a corrosion-resisting steel clip as shown on the drawing.

3.2.4 Gasket. The gasket shall be molded of the material specified in 3.1.4 and shall conform to the applicable portions of the drawing. The molded gasket shall be placed into the chest (see 5.2). The gasket shall be suitably treated to prevent adhesive at the sealing edge. The finished gasket shall be capable of sealing and resealing the chest during functional testing of the completed chest, rendering it watertight in repeated use. When chests are tested to determine compliance with specification requirements, the gasket shall be fitted into its retaining member (see 4.4).

3.2.5 Drawbolt fasteners. The drawbolt fastener shall be fabricated in accordance with the drawing.

3.3 Welding. All welding shall be done with appropriate equipment properly regulated and operated by thoroughly trained and experienced welders skilled in the operations of aluminum welding. Seam and fillet welds shall be continuous, even, and

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

smooth. Spot welds shall be on not more than 2-inch centers, and shall be accomplished so as to insure sound welds of sufficient strength and completeness to tear the spot out of the parent metal when pulled apart. All exposed spot welds, seam and fillet weld shall be smooth and finished in accordance with best commercial practice.

3.4 Tolerances. Standard commercial tolerances shall be permissible on material gage sizes. Dimensional tolerances shall be as specified on the drawing. Tolerances shall be held to a minimum for hinges, hinge-pins, bearings, channels, and all other fittings where accuracy is of paramount importance for proper operation and interchangeability of component parts. Sub and general assemblies shall be precision-fitted for durable, smooth, and consistent functioning. End item interchangeability is most important due to varying end item uses.

3.4.1 Application of tolerances. The tolerances shown on the drawing shall be taken in such a manner that the following requirements through V, inclusive, are conformed to:

I. Chest elements shall be of such size that the appropriate "GO" gage can be freely inserted (see 4.4.3).

II. Rim of body shall be of sufficient height to prevent cover from contacting shoulder when properly secured to body.

III. Chest cover shall be of such size as to freely overlay chest body and shall assemble thereto by the use of the drawbolt fastener attached to the chest body. The container as totally assembled, with gasket in place, shall be leakproof.

IV. Drawbolts and other hardware shall operate smoothly, shall not bind, and shall be capable of being easily operated by hand without the use of tools.

V. Chest bodies and chest covers shall be completely interchangeable and, when so interchanged, shall meet the requirements specified in subparagraph IV, above.

3.5 Finish. The entire unit, including outside and all accessible inside surfaces, shall be finished with acid, alkali, and solvent-resisting enamel, as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

3.5.1 Degreasing. All surfaces to be enameled shall be thoroughly cleaned and chemically degreased.

3.5.2 Primer. After degreasing, a primer coat shall be applied. The primer shall be zinc-chromate conforming to TL-P-1757. The primer coat shall form a grounding bond and base for the finishing enamel. All surfaces, after degreasing, may be given a chemical treatment conforming to MIL-C-5541 in lieu of the zinc-chromate primer specified herein.

3.5.3 Enamel. The primer coat shall be followed by one coat of lustreless olive drab enamel conforming to TT-E-527. Each coat shall be sprayed on and baked in high-temperature oven in accordance with the paint manufacturer's recommendations. The resultant finish shall be hard, smooth, and highly resistant to abrasion, chipping, and cracking.

3.5.3.1 Color. The color of the final finish shall be lustreless olive drab conforming to color 34087 of FED-STD-595 (see 6.2).

3.5.4 Touchup coat. If assembly of body, cover, and component parts, after painting, as specified in 3.5.3, results in scratching and chipping of paint, the entire exterior of the body and cover shall receive a mist of lustreless olive drab enamel conforming to TT-E-527. After application of mist coat, chest shall be allowed to air-dry in accordance with paint manufacturer's recommendations.

3.6 Sealing. After finishing, a continuous fillet of sealer (see 3.1.7) shall be applied at the junction of the gasket retainer and the inner walls of chest element Nos. 6 and 7 as shown on the drawing. The sealer shall prevent water leaking out of the chest element through the openings in slots for the drawbolts when tested as specified in 4.4.2.

3.7 Identification marking. All components shall be permanently and legibly marked with black, lustreless enamel (see 3.1.6), in letters one-half inch high, with the name of the manufacturer or registered trademark. Refer to Table III for marking instructions.

3.8 Preproduction samples of chests. Before production is begun, the contractor shall submit to the procuring activity, for approval two (2) preproduction samples. The chests shall be in strict accordance with applicable specification requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

They shall be produced from the specified material and under the same conditions of production as the contractor proposes to use in the manufacture of the specified chests. Approval by the Government of the samples shall not relieve the contractor of his obligation to conform to the specifications set forth herein. If the preproduction samples submitted by the contractor do not conform to the specifications, they will be rejected without cost to the Government and new preproduction samples shall be submitted by the contractor for approval in the same manner as before.

3.9 Workmanship. Workmanship shall be first class throughout. The unit shall be free from any defects that may affect its appearance or impair its serviceability. Pan nuts shall be permanently fastened by peening or other suitable means.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

4.1.3 Certificates of quality. When available, certificates of quality, supplied by the manufacturer of the component or material, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

4.2 Sampling. Sampling for examination shall be conducted in accordance with MIL-STD-105.

4.2.1 Examination. The chests shall be examined to determine compliance with specification requirements.

4.2.2 Tests. Tests shall be conducted to determine compliance with specification requirements.

	Inspection level	AQL (percent defective)	Minimum sample size
Component material testing	S-1	*	3
End item testing	S-1	*	3

* Acceptance number shall be zero (0) for all sample sizes.

4.2.3 For chemical analysis of metals. Four ounces of each lot of each metal used in the construction of the chests shall be selected for chemical analysis as specified in 4.4.4.

4.2.4 Component materials. Sufficient samples of the component materials shall be selected from each lot of material used in the manufacturer of the chests to perform tests as required by the applicable subsidiary specifications or by tests specified herein. When sample size for component materials covered by the subsidiary specifications is not specified, the sample size for each test shall be as indicated in 4.2.2. The unit of product for testing shall be the quantity necessary to perform all required tests, one time each, taking into consideration the fact that, where possible, the same material may be used to perform two or more tests.

4.3 Examination. The chests shall be examined to determine compliance with all requirements contained in this specification.

4.4 Tests. Tests shall be conducted in accordance with the applicable specifications to determine compliance with this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

4.4.1 Drawbolts. As warranted by inspection conditions, chest drawbolts shall be tested after each test is completely assembled to determine that each drawbolt latches properly.

4.4.2 Watertightness. Chests chosen at random shall be inspected for watertightness in the following manner: The chest and cover at equilibrium with room temperature shall be half-filled with water at the same temperature, and the cover latched into position. The chest shall then be placed in an upright position on each of its four sides for a period of not less than 5 minutes on each side. At the end of this time, the outside surfaces shall be inspected for water leakage. Any indication of leakage shall be cause for rejection of the lot.

4.4.2.1 Gaskets. Tests of the completed gaskets and of materials used in their fabrication shall be made as specified herein. The contractor shall submit, as directed by the procuring activity, two copies of reports from a commercial laboratory showing the results of all the tests required herein. The commercial laboratory shall be the laboratory of the contractor, the laboratory of the subcontractor who supplied the relevant material, or an approved independent testing laboratory. When the materials used in fabrication are from more than one lot, the laboratory reports shall show the various lot numbers tested. The contractor shall submit data necessary to show that all materials used in fabrication are from lots covered by laboratory reports demonstrating compliance with the requirements. Other tests may be made, if necessary, to determine compliance with this specification.

4.4.2.2 Rubber. The rubber for the gaskets shall be tested for tensile strength and ultimate elongation in accordance with Tentative Standard D 412-62 T; for impact resilence in accordance with Standard D 1054-55; for compression set in accordance with Standard D 395-61; and for durometer reading in accordance with Tentative Standard D 676-59 T. There shall be two series of tests, one series being made on specimens representative of the rubber in the gasket as it is to be delivered, and the other series being representative of the rubber in the gasket after the gasket has been subjected to accelerated aging by being maintained for 70 hours at a temperature in the range of 69° centigrade (C) to 71° C. The compression set shall be determined by method B, using a heat-treatment of 22 hours in the range 69° C to 71° C. The specimens for the second series of tests shall be prepared after the samples shall have cooled to room temperature.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

4.4.3 Measurements. Chest elements shall be tested with the proper size "GO" gage as specified hereinafter. The "GO" gage shall be freely inserted into the chest element.

Chest element No.	Size of gage, inches
1	24-3/16 by 12-3/16
3 and 5	30-3/16 by 18-3/16
6 and 7	29-1/16 by 17-1/16

4.4.4 Chemical analysis of the metals. The samples selected in accordance with 4.2.3 shall be analyzed in conformance with methods 111 or 112 of FED-STD-151. In case of dispute, method 111 shall be used for reference analysis.

5. PREPARATION FOR DELIVERY.

5.1 Packaging.

5.1.1 Unit of issue. One chest as specified, constitutes one unit of issue.

5.1.2 Level A. The rubber gasket shall be removed from its retaining channel and placed within the chest. Attached to the gasket shall be a tag bearing the following legend: "REPLACE RUBBER GASKET IN RETAINING CHANNEL OF CHEST COVER BEFORE USING CHEST. GROOVED SIDE OF RUBBER GASKET MUST BE PLACED TO CONTACT BOTTOM SURFACE OF RETAINING CHANNEL". The Chest shall be closed and the closure secured.

5.2 Marking. The chest shall be marked in accordance with MIL-STD-129. The required information shall be printed or stenciled on water-resistant shipping tags which shall be securely affixed to the container by means of metal ties.

5.3 Unitized loads. Unitized loads, commensurate with the level of packing specified in the contract or order, shall be used whenever total quantities for shipment to one destination exceeds 250 pounds or 20 cubic feet. Loads shall be unitized on pallets conforming to MIL-STD-147. Quantities less than 20 cubic feet need not be unitized. Pallet loads including the pallet shall not exceed 43 inches in length, 52 inches in width, and 54 inches in height. Pallet shall conform to Type IV or Type V.

6. NOTES

6.1 Intended use. The chest covered by this specification are intended for use as a shipping and storage container of medical equipment and supplies.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Size required (see 1.2).

6.3 Subject items (Key Word Listing).

Construction
Field
Finish
Gages
Tolerances
Watertightness

6.4 Availability of color chips. Individual chips of the colors specified herein are available from:

Commanding Officer
U. S. Naval Publications and Forms Center
5801 Tabor Ave.
Philadelphia, PA 19120

6.5 Cross reference data. Table III designates the end item and item identification.

TABLE III. Cross reference data.

End Item Stock No.	Size	Item Identification
6545-00-914-3460	1	CHEST, MEDICAL INSTRUMENT AND SUPPLY SET, Field, No. 1
6545-00-914-3470	2	CHEST, MEDICAL INSTRUMENT AND SUPPLY SET, Field, No. 2
6545-00-914-3480	3	CHEST, MEDICAL INSTRUMENT AND SUPPLY SET, Field, No. 3
6545-00-914-3490	4	CHEST, MEDICAL INSTRUMENT AND SUPPLY SET, Field, No. 4
6545-00-914-3500	5	CHEST, MEDICAL INSTRUMENT AND SUPPLY SET, Field, No. 5

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

TABLE III. Cross reference data continued.

End Item Stock No.	Size	Item Identification
6545-00-914-3510	6	CHEST, MEDICAL INSTRUMENT AND SUPPLY SET, FIELD, No. 6

6.6 This specification does not include all types, classes, grades, sizes, etc., of the commodity indicated by the title of this specification, or which are commercially available, but is intended to cover the types, etc., which are normally procured to meet military requirements.

Custodians:

Army - MD
Navy - MS
Air Force - 03

Review activities:

Army - MD
Navy - MS
Air Force - 03

Preparing activity:

Defense Supply Agency - DM

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Project No. 6545-0091

Location: Disk No. 14
MIL/SPEC/CHESTS/ALUMINUM/S3B

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 4968 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
ATTN: DPSC- RSTE
2800 South 20th Street
Philadelphia, Pennsylvania 19101-8419

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:21Z
Check the source to verify that this is the current version before use.