MIL-C-16809A
16 JUNE 1958
SUPERSEDING
MIL-C-16809(BuMed)
15 NOVEMBER 1951

MILITARY SPECIFICATION

# CASE, MEDICAL INSTRUMENT AND SUPPLY SET, NONRIGID, NO. 4, EMPTY

*This specification has been approved by the Department of Defense and is mandatory for use by the Departments of the Army, the Navy, and the Air Force.*

## 1. SCOPE

1.1 This specification covers an empty case made of vinyl-coated fabric, comprising three compartments with zipper closure, for holding first aid medications to be used for battle dressings in jungle and arctic climates. Each case is fitted with a carrying handle and two flaps fitted with curtain fastener sockets and plates.

## 2. APPLICABLE DOCUMENTS

2.1 The following specifications, standards, and drawings, of the issue in effect on date of invitation for bids, form a part of this specification:

### SPECIFICATIONS

FEDERAL

V-F-106 — Fasteners, Slide Interlocking.

CCC-C-419 — Cloth, Cotton, Duck, Unbleached, Plied-Yarns (Army and Numbered).

CCC-T-191 — Textile Test Methods.

DDD-S-751 — Stitches; Seams; and Stitching.

PPP-B-585 — Boxes; Wood, Wirebound.

PPP-B-601 — Boxes, Wood, Cleated-Plywood.

PPP-B-621 — Boxes, Wood, Nailed and Lock-Corner.

PPP-B-636 — Boxes, Fiber.

MILITARY

MIL-F-495 — Finish, Chemical, Black, for Copper Alloys.

MIL-W-530 — Webbing, Textile, Cotton, General Purpose, Natural or in Colors.

MIL-S-3136 — Standard Test Fluids Hydrocarbon and Iso-Octane.

MIL-T-3530 — Treatment, Mildew-Resistant, for Thread and Twine.

FSC 6545

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:22Z
Check the source to verify that this is the current version before use.

MIL-T-5660 — Thread, Cotton, High-Tenacity.

MIL-L-7178 — Lacquer, Cellulose Nitrate, Gloss, for Aircraft Use.

MIL-B-10377 — Box, Wood, Cleated, Veneer, Paper Overlaid.

MIL-L-10547 — Liners, Case, Waterproof.

STANDARDS

MILITARY

MIL-STD-105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129 — Marking for Shipment and Storage.

MS16686 — Medical Services Symbol.

DRAWINGS

AIR FORCE-NAVY AERONAUTICAL STANDARD

AN227 — Fasteners-Snap and Curtain.

MILITARY MEDICAL SUPPLY AGENCY

1265 — Case, Medical Instrument and Supply Set, Nonrigid, No. 4, Empty.

(Copies of specifications, standards, and drawings required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

**2.2 Other publications.** The following documents form a part of this specification. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

COLOR ASSOCIATION OF THE UNITED STATES, INC.

United States Army Standard Color Card for the Official Standardized Shades of Sewing Threads.

United States Army Color Card of Standard Shades for Slide Fastener Tapes.

(Application for copies should be addressed to the Color Association of the United States, Inc., 200 Madison Ave., New York 16, N. Y.)

## 3. REQUIREMENTS

**3.1 Component parts.** The case comprises a large compartment and two small compartments, each with a slide fastener closure and a carrying handle. Two flaps carrying eight curtain type fastener sockets and plates are attached to the outside of the large compartment.

**3.2 Materials.** Except as hereinafter specified, materials shall conform to the applicable portions of the specifications and drawings listed in section 2, and be subjected to the tests and the requirements specified therein. When materials are used which are not specifically designated, they shall be suitable for the purpose intended.

3.2.1 *Body fabric.* The body fabric shall be ply yarn cotton duck conforming to Specification CCC-C-419 for type III, 9.85 ounces per square yard, minimum, as shown in table II of the same specification, coated with a suitably compounded polymer or copolymer vinyl resin, with the color incorporated therein, so that the finished fabric shall be olive drab No. 7. The coating shall be applied by a solution or dispersion method to thoroughly and evenly impregnate both sides of the base cloth. Calendar coating is not permissible. No more coating than is necessary to meet the water and abrasion resistance requirements, and to obtain a uniform shade shall be applied to one side of the cloth; the balance shall be applied to the other side. The coated fabric shall be made mildew-resistant by the use of copper-8-quinolinolate as the mildew inhibitor. The coating compound shall contain 1.25 to 1.50 percent by weight of copper-8-quinolinolate evenly dispersed in the coating. The loss in breaking strength shall not exceed 10 per-



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:22Z
Check the source to verify that this is the current version before use.

cent of the initial tensile strength when the fabric is subjected to the 14-day soil burial test, unleached (see 4.3.1.1).

3.2.1.1 *Crocking.* The finished coated fabric shall be tested as specified in 4.3.1.2. The resistance to dry crocking and to wet crocking shall be not less than corresponds to a Munsell value of 9.0.

3.2.1.2 *Fabric weight.* The finished fabric weight shall be tested as specified in 4.3.1.3, and shall be not less than 16 nor more than 20 ounces per square yard.

3.2.1.3 *Breaking strength.* The finished coated fabric shall be tested as specified in 4.3.1.4. The minimum breaking strength shall be 160 pounds in the warp direction and 110 pounds in the filling direction.

3.2.1.4 *Tearing strength.* The finished coated fabric shall be tested as specified in 4.3.1.5. The standard temperature tear strength shall be not less than corresponds to a scale reading of 75 for the warp direction and 60 for the filling direction; the low-temperature tear strength shall be not less than corresponds to a scale reading of 50 for the warp direction, and 40 for the filling direction.

3.2.1.5 *Water-resistance.* The finished coated fabric shall be tested as specified in 4.3.1.6. The maximum leakage in a period of 1 hour shall be 5 milliliters. No water shall penetrate the unabraded portion during the final 40 minutes of the hour.

3.2.1.6 *Weathering-resistance.* The finished coated fabric shall be tested as specified in 4.3.1.7. The loss in breaking strength shall not exceed 15 percent. The finished fabric shall not crack when folded sharply on itself, nor shall it show signs of blooming or material color change.

3.2.1.7 *Adhesion.* The finished coated fabric shall be tested as specified in 4.3.1.8. The adhesion shall be not less than 8.0 pounds per 2-inch width.

3.2.1.8 *Low-temperature-resistance.* The finished coated fabric shall be tested as specified in 4.3.1.9. The coating shall neither crack nor break.

3.2.1.9 *Heat-resistance.* The finished coated fabric shall be tested as specified in 4.3.1.10. The coating shall show no evidence of adhesion or exudation.

3.2.1.10 *Abrasion-resistance.* The finished coated fabric shall be tested as specified in 4.3.1.11. The loss in breaking strength shall not exceed 25 percent, and the color of the abraded portion shall be olive drab No. 7.

3.2.1.11 *Gasoline-resistance.* The finished coated fabric shall show no evidence of cracking, stiffening, flaking, or separation of the coating from the base fabric when tested as specifed in 4.3.1.12.

3.2.2 *Thread.* Thread shall conform to Specification MIL–T–5660 and shall be style A, type II, size thread No. 3, and shall be vat dyed olive drab shade S–1, conforming to U. S. Army Standard Color Card for the Official Standardized Shades of Sewing Threads. The thread shall be treated for mildew-resistance in accordance with Specification MIL–T–3530, using class I mildew inhibiting agent (see 4.3.2).

3.2.3 *Fasteners, slide.* Except as specified herein, the slide fasteners shall conform to Specification V–F–106, and shall be as follows:

(a) *Fasteners, slide, nonseparating.* Nonseparating slide fasteners shall be type I, style 19, class B, size M, two slider with short tab pulls fitted with webbing thongs. Metal parts shall be brass with a black chemical finish conforming to Specification MIL–F–495.

(b) *Fasteners, slide, separating.* Sepa-



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:22Z
Check the source to verify that this is the current version before use.

rating slide fasteners shall be type IV, style 8, class B, size M, single slider with short tab pulls fitted with webbing thongs. Metal parts shall be brass with a black chemical finish conforming to Specification MIL-F-495.

3.2.3.1 *Tape.* The slide fastener tapes shall be vat dyed olive drab, shade S, conforming to the U. S. Army Color Card of Standard Shade for Slide Fastener Tapes, and shall be water-repellent and mildew-resistant. Mildew-resistance shall be obtained by evenly depositing within the tape 0.18 ± 0.05 percent copper from copper-8-quinolinolate using one of the methods specified in Specification MIL-W-530 (see 4.3.3.2).

3.2.3.1.1 *Water-repellence.* When tested as specified in 4.3.3.1, the finished tape shall comply with the water-repellence requirements of Specification V-F-106.

3.2.3.2 *Salt spray resistance.* The slide fasteners shall meet the salt spray resistance requirements specified in Specification V-F-106 for class A fasteners. Fasteners shall be tested as specified in 4.3.3.4.

3.2.4 *Fasteners, lift.* Lift fasteners shall be large curtain type fasteners. Sockets and plates shall conform to Drawing AN227 and shall be 15BS sockets and 16B plates. The material shall be brass with a black chemical finish conforming to Specification MIL-F-495.

3.2.5 *Fasteners, snap.* Snap fasteners shall consist of 6B button, 7B socket, 8B stud, and 9B eyelet, as shown on Drawing AN227. Material shall be brass with a black chemical finish conforming to Specification MIL-F-495.

3.2.6 *Webbing for thongs.* Webbing for slide fastener pull thongs shall be ⅜ inch wide, have a breaking strength of not less than 40 pounds, be vat dyed olive drab to match the fastener tape, and shall be class 4 of Specification MIL-W-530. Webbing, when tested as specified in 4.3.4, shall comply with the chemical and mildew-resistance requirements of Specification MIL-W-530.

3.2.7 *Lacquer.* Lacquer shall conform to Specification MIL-L-7178.

3.3 **Construction.** Construction shall meet the requirements specified herein, and those shown on Drawing 1265.

3.3.1 *Stitches, seams, and stitchings.* All seams and stitchings shall conform to Specification DDD-S-751, shall be straight, and shall consist of type 301 stitches, with not less than seven nor more than nine evenly spaced stitches per inch. Thread tension shall be properly maintained so that lock will be imbedded in the center of the material sewed.

3.3.1.1 *Anchorage.* The ends of each continous row of stitches (including ends due to thread breaks) shall be anchored by backstitches for a length of not less than 1 inch, except where anchorage is provided by another seam or stitching.

3.3.2 *Attachment of fastener elements.* Holes shall be punched in the fabric before insertion of tube of male element and prongs of female element. Holes shall be small enough to require tubes and prongs to be forced through. Fastener elements shall be tightly clinched so as not to become detached from the fabric in normal use. Holes in cloth at center of lift fastener shall be large enough so as not to impede insertion of studs in sockets.

3.3.3 *Placement of curtain fastener sockets and plates.* The curtain fastener sockets and plates as specified in 3.2.4, shall be located as shown on Drawing 1265. When the finished cases are tested as specified in 4.3.5, they shall fit on the panel without distortion.

3.4 **Marking for identification.** Each case



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:22Z
Check the source to verify that this is the current version before use.

shall be marked in accordance with Drawing 1265, using lacquer as specified in 3.2.7, of color No. 505 where drawing calls for yellow, color No. 509 where drawing calls for red, and color No. 511 where drawing calls for white; all color numbers shall be as defined in Specification MIL–L–7178. The white square shall be applied first, and then the red cross.

3.5 **Workmanship.** Workmanship shall be first class throughout. Completed cases shall be well-made and free from defects which detract from their appearance or may impair their serviceability.

## 4. QUALITY ASSURANCE PROVISIONS

**4.1 Sampling.**

4.1.1 *For visual examination.* Sampling procedures for visual examination shall be conducted in accordance with the procedures set forth in Standard MIL–STD–105.

4.1.2 *For tests.* Sufficient samples of the components shall be selected to perform tests as required by the applicable subsidiary specifications or by tests specified herein. When sample size for components covered by subsidiary specifications is not specified, the sample size for each test shall be as indicated for inspection level L2, table VII in appendix to Standard MIL–STD–105, for the finished coated fabric, thread, slide fasteners, and webbing. No test result shall fall below the minimum or exceed the maximum values specified. Not less than three (3) samples shall be taken regardless of lot size. Lot sizes are expressed as follows:

| | |
|---|---|
| Coated fabric | Yards. |
| Thread | Cone or spool. |
| Slide fasteners | Each. |
| Webbing | Yards. |

In lieu of testing as specified above, certificates of quality, showing specific test results to indicate that the material meets the specification requirements, may be furnished.

Government furnished material shall not be sampled or tested unless specifically requested by the Government (see 6.3).

4.1.3 *Placement of curtain fastener sockets and plates.* Sampling for test of the placement of curtain fastener sockets and plates shall be conducted in accordance with Standard MIL–STD–105. The acceptance quality level shall be 1 percent.

**4.2 Inspection.**

4.2.1 *Components.* The inspector shall ascertain that prior to assembly, all components of the case have been examined and tested in accordance with specification requirements.

4.2.2 *End item.* Each sample selected in accordance with 4.1.1 shall be subjected by the inspector to visual examination for style, design, dimensions, construction details, etc.

**4.3 Tests.** Tests of the materials used in fabrication of the cases shall be made as specified herein. Other tests may be made, if necessary, to determine that the finished cases comply with this specification, and that the materials comply with the applicable portions of the specifications and drawings shown in section 2.

4.3.1 *Body fabric.*

4.3.1.1 *Mildew inhibitor content.* The finished coated fabric shall be tested for compliance with the chemical requirements of this specification by either method 2050 or method 2051 of Specification CCC–T–191. If the material conforms to the requirements for mildew inhibitor content, the test specified in 4.3.1.1.1 shall not be required and material shall be considered as complying with mildew-resistance requirements. The material shall be rejected if the mildew inhibitor content is found to exceed the maxi-



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:22Z
Check the source to verify that this is the current version before use.

mum requirements. If the mildew inhibitor content is found to be below the minimum requirements, the material may be accepted with respect to mildew-resistance provided it passes the test specified in 4.3.1.1.1.

4.3.1.1.1 *Mildew-resistance.* The finished coated fabric shall be tested by method 5762 of Specification CCC-T-191, except that the leaching process shall be omitted, and the breaking strength determined by method 5100 of the same specification

4.3.1.2 *Crocking.* The crocking of the finished coated fabric shall be determined in accordance with method 5650 of Specification CCC-T-191.

4.3.1.3 *Fabric weight.* The weight of the finished coated fabric in ounces per square yard shall be determined by method 5041 of Specification CCC-T-191.

4.3.1.4 *Breaking strength.* The breaking strength of the finished coated fabric shall be determined by method 5100 of Specification CCC-T-191.

4.3.1.5 *Tearing strength.* The finished coated fabric shall be tested by method 5132 of Specification CCC-T-191. The standard instrument shall be used with the augmenting weight. There shall be two series of tests. One series of tests shall be made with specimens in standard condition; the result of this series shall be the standard temperature tear strength. Each test of the other series shall be made immediately after the specimen shall have been removed from an enclosure wherein the temperature is maintained between minus 65 degrees and minus 70 degrees Fahrenheit; the specimen shall have been in said enclosure for a period of 60 minutes. The results of this series shall be the low-temperature tear strength.

4.3.1.6 *Water-resistance.* Specimens of the finished coated fabric shall be tested by method 5516 of Specification CCC-T-191, except as follows: Before each specimen is placed in the apparatus, it shall be abraded by means of a 2 inch square piece of grade ½ Garnet paper. The Garnet paper shall be uniformly loaded with an 8.0 ounce weight. The specimen shall be abraded over an area 6 inches long by 2 inches wide on one side only by moving the loaded Garnet paper five times in each direction parallel to the filling so that the center of the abraded area is the center of the specimen. The specimen shall be placed in the apparatus so that its center coincides with the center of the ring clamp, and with the abraded area exposed to the water. The hydrostatic head shall be 20 inches of water and the time of exposure 60 minutes. At the end of 20 minutes, any drops of water which may be on the underside of the fabric shall be removed by wiping with a dry cloth.

4.3.1.7 *Weathering-resistance.* The finished coated fabric shall be tested by method 5804 of Specification CCC-T-191. The number of hours of exposure shall be 150. Filters shall not be used.

4.3.1.8 *Adhesion.* The finished coated fabric shall be tested by method 5970 of Specification CCC-T-191, using a suitable solvent or cement as specified by the fabric coater.

4.3.1.9 *Low-temperature-resistance.* The finished coated fabric shall be tested as follows: Specimens shall be cut 4 inches long by 1 inch wide. There shall be six specimens from each Unit-of-Product as defined in 2.1.4 of Specification CCC-T-191, of which three shall have the long dimension parallel to the warp, and three parallel to the filling. Each specimen shall be placed in an enclosure in which the temperature is maintained between 65 degrees and minus 70 degrees



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:22Z
Check the source to verify that this is the current version before use.

Fahrenheit and kept there for a period of 4 hours. Immediately after removal from the enclosure, the specimen shall be bent over a glass rod 1/8 inch in diameter so that the backs of the specimen touch each other within a distance of 1/8 inch from the rod. The specimen shall be touched only by material having low thermal conductivity so as to minimize change of temperature during the manipulation. The specimen shall be kept for 10 minutes in the bent condition, then straightened and allowed to warm in still air to normal room temperature after which it shall be examined.

4.3.1.10 *Heat-resistance.* Two samples, 2 by 2 inches, shall be heated for 2 hours at 170 degrees Fahrenheit in a thermostatically controlled oven, while being held face to face between glass plates and subjected to a uniform pressure of 0.25 plus or minus 0.01 pound per square inch. After 2 hours, the samples and weight shall be removed from the oven. The weight shall be removed from the samples and the samples shall be allowed to cool in a conditioned atmosphere. Five minutes after removal from the oven, the two surfaces shall show no evidence of adhesion or exudation when separated.

4.3.1.11 *Abrasion-resistance.* The finished coated fabric shall be tested by method 5304 of Specification CCC–T–191, except as follows: The abradant shall be silicon carbide cloth (see 6.2). The tension shall be 6 pounds. The specimen shall be subjected to 750 continuous cycles on each side, and the abraded portion on one side shall be opposite the abraded portion on the other side.

4.3.1.12 *Gasoline-resistance.* A sample, 1 by 6 inches, with the long dimension parallel to the warp, shall be immersed for 5 minutes in 40 percent aromatic fuel. The composition of the fuel shall conform to type II of Specification MIL–S–3136. The sample shall be allowed to dry at room temperature for 2 hours ± 5 minutes, and then, shall be creased at room temperature as specified in method 5874 of Specification CCC–T–191. A similar sample, cut with the long dimension parallel to the filling, shall be tested in the same manner.

4.3.2 *Thread.*

4.3.2.1 *Midew inhibitor content.* The treated thread shall be tested as specified in the test section of Specification MIL–T–3530. If the thread conforms to the requirements for mildew inhibitor content, the tests specified in 4.3.2.2 shall not be required and material shall be considered as complying with mildew-resistance requirements. The material shall be rejected if the mildew inhibitor content is found to exceed the maximum requirements. If the mildew inhibitor content is found to be below the minimum requirements, the material may be accepted with respect to mildew-resistance provided it passes the tests as specified in 4.3.2.2.

4.3.2.2 *Mildew-resistance.* The finished thread shall be tested by either the 14-day soil burial method or the direct inoculation method as specified in Specification MIL–T–3530. The leaching process shall be omitted.

4.3.3 *Fasteners, slide.* The slide fasteners shall be tested as specified in Specification V–F–106, except as modified herein.

4.3.3.1 *Water-repellence.* The finished tape shall be tested for water-repellence by method 5500 of Specification CCC–T–191. The specimens shall conform to 2.3 and the blotting paper to 3.1.1 of method 5502 of the same specification.

4.3.3.2 *Mildew inhibitor content.* The copper content of the finished slide fastener tape shall be determined by either the electrolytic method or the polarographic method specified in the test section of Specification MIL–W–530. If the material conforms to the requirements for mildew inhibitor content, the test specified in 4.3.3.3 shall not be required, and material shall be considered as complying with mildew-resistance requirements. The material shall be rejected if the mildew



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:22Z
Check the source to verify that this is the current version before use.

inhibitor content is found to exceed the maximum requirements. If the mildew inhibitor content is found to be below the minimum requirements, the material may be accepted with respect to mildew-resistance provided it passes the test requirements in 4.3.3.3.

4.3.3.3 *Mildew-resistance.* The finished slide fastener tape shall be subjected to the 14-day soil burial test by method 4762 of Specification CCC–T–191, except that the leaching process shall be omitted. The test specimens shall include the chain. At the end of the test, the slide fastener crosswise shall meet the requirements of Specification V–F–106 for the minimum breaking strength of the fastener specified.

4.3.3.4 *Salt spray resistance.* The slide fasteners shall be tested in conformance with the salt spray test specified in the section in Specification V–F–106 which includes test procedures.

4.3.4 *Tests on webbing.* Tests on finished webbing for thongs, for compliance with the requirements of this specification, shall be conducted as specified in the test section of Specification MIL–W–530, except as modified below.

4.3.4.1 *Mildew inhibitor content.* The copper content of the finished webbing shall be determined by either the electrolytic or the polarographic method specified in the test section of Specification MIL–W–530. If the material conforms to the requirements for mildew inhibitor content, the test specified in 4.3.4.2 shall not be required, and material shall be considered as complying with mildew-resistance requirements. The material shall be rejected if the mildew inhibitor content is found to exceed the maximum requirements. If the mildew inhibitor content is found to be below the minimum requirements, the material may be accepted with respect to mildew-resistance provided it passes the test specified in 4.3.4.2.

4.3.4.2 *Mildew-resistance.* The finished webbing shall be tested by method 4762 of Specification CCC–T–191, except that the leaching process shall be omitted.

4.3.4.3 *Water-resistance.* The finished webbing shall be tested by method 5500 of Specification CCC–T–191, as specified in the test section of Specification MIL–W–530. The specimens shall conform to 2.3 and the blotting paper to 3.1.1 of method 5502 of Specification CCC–T–191.

4.3.5 *Test for placement of curtain fastener sockets and plates.* A metal panel shall be made as shown on Drawing 1265. The studs on the panel shall be selected from those shown on Drawing AN227, and shall fit the specified curtain fastener sockets and plates as specified in 3.2.4. The finished cases shall be tested for placement of curtain fastener sockets and plates by attaching them to the studs on the panel. The cases shall then be inspected for distortion.

**4.4 Supplier responsibilities for inspection.** The supplier shall perform examinations and tests set forth in this specification to substantiate conformance of supplies to specification requirements. The examinations and tests shall be at the expense of the supplier. Suppliers shall have adequate test facilities or shall arrange for test facilities acceptable to the Government to be used for executing specific prescribed tests. Records of examinations and tests performed by the supplier shall be maintained by the supplier and made available to the Government upon the Government's request, at any time, or from time to time, for a period of 2 years after the delivery of the supplies to which these records relate. The supplier shall be responsible for compliance with all requirements of this specification, and all other technical requirements of the contract.

## 5. PREPARATION FOR DELIVERY

**5.1 Packaging.**



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:22Z
Check the source to verify that this is the current version before use.

5.1.1 *Unit of issue.* One (1) case, as specified, constitutes one unit.

5.1.2 *Packaging quantities.* The number of units of issue indicated in table I shall be packaged in each unit and exterior container, as applicable, for the required level of protection specified in procurement document.

TABLE I. *Packaging quantities*

| Federal stock number | Unit package | Intermediate package | Shipping container |
|---|---|---|---|
| 6545–912–9880 | 1 unit | Not required | 24 units |

5.1.2.1 *Packing variation permitted.* If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.1.3 *Level A.*

5.1.3.1 *Unit package.* Each unit shall be packaged in a carton of appropriate size constructed in accordance with Specification PPP–B–636, type I, class 1. Closure shall be adequate to prevent spillage of contents under normal handling.

5.1.4 *Level C.* Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose within the continental limits of the United States of America.

5.2 Packing.

5.2.1 *Level A.*

5.2.1.1 *Exterior container.* Exterior container shall be designed for type 2 load and constructed in accordance with Specification PPP–B–585, style 3, for class 3 use; PPP–B–601, table II, using type III, class 1 plywood; PPP–B–621, table III; or MIL–B–10377, table II.

5.2.1.2 *Case liner.* Each level A box shall be lined with a waterproof case liner conforming to Specification MIL–L–10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto.

5.2.1.3 *Strapping.* Strapping, when required, shall be in accordance with applicable box specifications.

*Note.* Strapping will not be required for shipment forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

5.2.2 *Level B.*

5.2.2.1 *Exterior container.* Exterior container shall conform to Specification PPP–B–601, table I, using type III, class 1 plywood, or shall be designed for type 2 load and constructed in accordance with Specification PPP–B–585, style 3, for class 2 use; PPP–B–621, table I; or MIL–B–10377, table I.

5.2.3 *Level C.* The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 *Unit package.* Each unit package shall be marked in accordance with section 5 of Standard MIL–STD–129.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:22Z
Check the source to verify that this is the current version before use.

5.3.2 *Shipping container.* Shipping container shall be marked in accordance with Standard MIL–STD–129. Service color and service symbol markings are required only on direct shipments from the contractor's plant to overseas activities.

## 6. NOTES

**6.1 Intended use.** Case, Medical Instrument and Supply Set, Nonrigid, No. 4, Empty, is intended to be used as the container for FSN 6545–919–6900, Frst Aid Kit, Air Force, General, Battle Dressing. The kit may be secured during flight in aircraft suitably equipped with studs which fit the lift fasteners of the case, and may be readily carried when removed from the aircraft.

6.2 The abradant silicon carbide cloth referenced in 4.3.1.11 shall be Minnesota Mining Co.'s No. 240J, or equal.

**6.3 Ordering data.** Procurement documents should specify the following:

(a) Number and date of this specification.

(b) When sampling or testing of Government supplied material is required (see 4.1.2).

(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.4 This specification covers the following item appearing in the Armed Services Medical Stock List:

6545–912–9880 CASE, MEDICAL INSTRUMENT AND SUPPLY SET, Nonrigid, No. 4, Empty.

6.5 This specification does not include all types, classes, grades, size, etc., of the commodity indicated by the title of this specification, or which are commercially available, but is intended to cover the types, etc., which are normally procured to meet Military requirements.

**Notice.** When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto

Custodians.
Army—Army Medical Service
Navy—Bureau of Medicine and Surgery
Air Force

Preparing activity:
Navy—Bureau of Medicine and Surgery
(MMSA)



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:22Z
Check the source to verify that this is the current version before use.