QQ-A-250/25A
June 25, 1974
SUPERSEDING
Int. Fed. Spec.
QQ-A-00250/25(ASG)
14 October 1969

FEDERAL SPECIFICATION

ALUMINUM ALLOY ALCLAD 7075, PLATE AND SHEET (IMPROVED EXFOLIATION RESISTANT)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for use of all Federal agencies.

(This specifications forms a part of the latest issue of Specification QQ-A-250).

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the specific requirement for improved exfoliation resistant aluminum alloy alclad 7075, plate and sheet. The general requirements are covered in QQ-A-250. The plate and sheet covered by this specification shall be an integral composite product consisting of a heat-treated aluminum alloy (7075) core with thin layers of an aluminum alloy (7072) anodic to the core and of approximately equal thickness, bonded to both surfaces.

1.2 Classification. Sheet shall be furnished in the T76 temper only and plate shall be in the T7651 temper only, as specified (see 6.2). The definitions of these tempers, in accordance with ANSI H35.1, are as follows:

T76 - Solution heat-treated and artificially aged sufficient to produce improved resistance to exfoliation and stress corrosion cracking.

T7651 - Solution heat-treated, stress relieved by stretching to produce a permanent set of 2 percent nominal but not less than 1-1/2 percent nor more than 3 percent, and artificially aged sufficient to produce improved resistance to exfoliation and stress-corrosion cracking. Plate shall receive no further straightening after stretching.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.

Federal Specification:

QQ-A-250	Aluminum and Aluminum Alloy Plate and Sheet; General Specification for

Federal Standards:

Fed. Test Method Std. No. 151	Metals; Test Methods
Fed. Std. No. 184	Identification Markings of Aluminum, Magnesium and Titanium

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-I-8950	Inspection, Ultrasonic, Wrought Metals, Process for

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials

ASTM D 1193	Standard Specification for Reagent Water
ASTM G 34	Standard Method of Test for Exfoliation Corrosion Susceptibility in 7XXX Series Copper Containing Aluminum Alloys (EXCO Test)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.

ASTM G 38 Recommended Practices for Making and Using the C-Ring Stress-Corrosion Cracking Test Specimen

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

American National Standards Institute Publication

ANSI H35.1 Alloy and Temper Designation Systems for Aluminum

(Application for copies should be addressed to the American National Standards Institute, 1430 Broadway, New York, N.Y. 10018.)

3. REQUIREMENTS

3.1 Chemical composition. The chemical composition of the core ingots or slabs and of the cladding plates used for the manufacture of the clad plates and sheets shall conform to the requirements shown in Table I for core and cladding, respectively.

Table I. Chemical composition 1/

Element	Composition			
	Core alloy (7075) Percent		Cladding alloy (7072) Percent	
	Minimum	Maximum	Minimum	Maximum
Zinc	5.1	6.1	0.8	1.3
Magnesium	2.1	2.9	--	0.10
Copper	1.2	2.0	--	0.10
Chromium	0.18	0.35	--	--
Manganese	--	0.30	--	0.10
Iron	--	0.50	--	2/
Silicon	--	0.40	--	2/
Titanium	--	3/	--	--
Zirconium	--	3/	--	--
Others, each	--	0.05	--	0.05
Others, total	--	0.15	--	0.15
Aluminum	Remainder		Remainder	

1/ Analysis shall regularly be made only for the elements specifically mentioned in the table. If, however, the presence of other elements is indicated in the course of routine analysis, further analysis shall be made to determine conformance to the limits specified for other elements.

2/ Iron plus silicon, 0.7 percent maximum.

3/ Titanium plus zirconium, 0.25 percent maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.

3.2 Mechanical properties. The mechanical properties perpendicular to the direction of final rolling, except for material less than 9 inches in width, shall conform to the requirements of Table II for the temper specified. For material less than 9 inches in width, the mechanical properties parallel to the direction of final rolling shall conform to the requirements of Table II for the temper specified.

Table II. Mechanical properties

Temper	Thickness in inches	Tensile strength (psi) minimum	Yield strength at 0.2 percent offset (psi)	Elongation in 2 in. or 4 times D 1/ 2/
T76	0.040 thru 0.062	67,000	56,000	8
	0.063 thru 0.187	68,000	57,000	8
	0.188 thru 0.249	70,000	59,000	8
T7651	0.250 thru 0.499	69,000	58,000	8
	0.500 thru 1.000	71,000 3/	60,000 3/	6

1/ Not required for material 1/2 inch or less in width.
2/ D represents specimen diameter.
3/ The properties for these thicknesses are those of the core alloy since the test is made on a round specimen machined from the plate.

3.3 Cladding thickness.

3.3.1 Thickness of cladding plates. The aluminum alloy (7072) plates that are bonded to the two sides of the aluminum alloy (7075) ingot or slab to form a composite that is to be rolled to the finished thickness shall each have a thickness as specified in Table III.

3.3.2 Average thickness of cladding. When specified (see 6.2), the average cladding thickness of the finished sheet or plate shall be determined. Samples, examined in accordance with QQ-A-250, shall show an average of cladding on each side as specified in Table III.

Table III. Cladding thickness

Thickness of finished sheet or plate in inches	Nominal cladding thickness per side; percent of composite thickness	Average minimum cladding thickness per side on finished sheet or plate; percent of sheet or plate thickness
Up thru 0.062	4	3.2
0.063 thru 0.187	2.5	2
0.188 and over	1.5	1.2 1/

1/ For plate 0.500 inch and over, the average cladding thickness per side shall have a maximum value of 3 percent of the plate thickness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.

3.4 Internal defects. When specified (see 6.2), plate shall be ultrasonically inspected (see QQ-A-250). Acceptance limits shall be as specified in Table IV.

Table IV. Ultrasonic discontinuity acceptance limits 1/

Size		Discontinuity class 2/
Thickness in inches	Maximum weight per piece in pounds	
0.500 thru 1.000	2,000	B

1/ Discontinuities in excess of those listed in Table IV may be allowed subject to the approval of the procuring activity, if it is established that they will be removed by machining or that they are in noncritical areas.
2/ The discontinuity class limits are defined in MIL-I-8950.

3.5 Exfoliation and stress-corrosion cracking. Material in the T76 and T7651 tempers, when tested in accordance with 4.2.1 and 4.2.2, shall show neither exfoliation corrosion equivalent to or in excess of that depicted in Figure 2 of ASTM G 34 for category B nor stress corrosion cracking susceptibility beyond the acceptance criteria as detailed in 4.2.2.5.

3.5.1 Lot acceptance control criteria for T76 and T7651 tempers. Resistance to exfoliation and stress-corrosion cracking for each lot of T76 and T7651 temper material shall be determined by the following control criteria (see 4.1.2 and 4.2.2).

a. Determine mechanical properties and electrical conductivity.
b. If the conductivity is 38 percent IACS or higher, and the tensile properties meet the minimum limits specified herein, the material is acceptable.
c. If the conductivity is at least 36 percent IACS but less than 38 percent IACS, the material shall be tested as specified in 4.2.1 or reprocessed.
d. If the conductivity is below 36 percent IACS, the material is not acceptable and must be reprocessed.

3.6 Marking. In addition to the marking required in Fed. Std. No. 184, plate and sheet shall be identified by a lot number marked in at least one location on each piece.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

(See QQ-A-250.)

4.1 Sampling.

4.1.1 For exfoliation and stress-corrosion cracking tests. Two samples shall be taken for each 4,000 pounds or less of the first three production lots for each size range of sheet and plate listed in Table II. Thereafter, surveillance testing shall be performed on at least one sample per month for each size range of sheet and plate produced during that month which had previously been produced with acceptable exfoliation resistance. The surveillance test samples shall be taken from a lot which has met the requirements of 3.5.1(b). Samples as above shall be taken for stress-corrosion cracking test when thickness permits (see 4.2.2).

4.1.2 For mechanical property and conductivity tests. Sampling shall be in accordance with QQ-A-250 for mechanical property tests. Mechanical properties and conductivities shall be determined on the same samples except cladding must be removed before testing for conductivity (see 4.2.3). Conductivity shall be determined prior to testing for mechanical properties.

4.2 Tests.

4.2.1 Exfoliation corrosion test. Test shall be performed in accordance with ASTM G 34. Full thickness specimens of sheet and plate large enough to provide visual assessment of attack may be used, however, for all materials, 0.100 inch or more in thickness, 10 percent of the thickness shall be removed by machining one surface. The machined surface shall be evaluated.

4.2.2 Stress-corrosion cracking test. Stress-corrosion cracking tests shall be performed on plate 0.750 inch and over in thickness as follows.

4.2.2.1 Specimens. Specimens shall be selected in a manner such as to permit application of the specific tension stress in the short transverse direction. Specimens shall be C-rings as detailed in Fed. Test Method Std. No. 151, Method 823 or in ASTM G 38.

4.2.2.2 Exposure period. Exposure shall be for 30 days.

4.2.2.3 Tension stress. The tensile stress applied in the short transverse direction (perpendicular to grain flow) shall be 25,000 psi, and the specimen shall be held at constant strain.

4.2.2.4 Exposure procedure. The stressed specimen shall be exposed to a 3.5 percent salt solution prepared by dissolving reagent grade sodium chloride (NaCl) in distilled or deionized water, conforming to ASTM D 1193, Type II. The pH of the solution shall be 6.4 to 7.2. The solution temperature shall be 75 $\pm$2°F, air temperature shall be 80 $\pm$2°F, and with a relative humidity of 45 $\pm$6 percent. The alternate immersion cycle shall consist of 10

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.

minutes immersion in solution and 50 minutes in air, with sufficient circulation to dry the specimens slowly before the next immersion.

4.2.2.5 Stress-corrosion test results. After a 30-day exposure, the specimen shall exhibit no visual evidence of stress-corrosion cracking. Any highly directional attack which is suspected of concealing a stress-corrosion crack shall be cross sectioned and examined metallographically. An example of stress corrosion cracking is shown on Figure 1. Figure 2 illustrates pitting type attack which does not constitute failure.

4.2.3 Electrical conductivity tests. The conductivity shall be determined by taking three electrical conductivity readings at random on each sample. For thicknesses less than 0.100 inch, the conductivity shall be determined on the surface after removal of the cladding. For thicknesses of 0.100 inch and over, the conductivity shall be determined on the machined surface after machining one surface of the sample to a depth of approximately 10 percent of the product thickness. The surface machining may be accomplished by chemical milling. The average of the three reading shall be used as the conductivity acceptance criteria of 3.5.1.

4.3 Records. The producer shall maintain records of the performance of all lots sampled and tested. Upon request of the procuring activity, such records shall be made available. These records shall be maintained for not less than one year after completion of the contract or purchase order.

5. PREPARATION FOR DELIVERY

(See QQ-A-250.)

6. NOTES

6.1 Intended use. This alloy is intended for use where high strength is required, and where exfoliation and corrosion resistance superior to 7075-T6 is required. 7011 Alclad 7075 plates and sheets should be used where fatigue strength and mechanical properties higher than those provided by 7072 Alclad 7075 are required and where good resistance to corrosion is needed.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

a. Title, number, and date of this specification.
b. Form and temper required (see 1.2.1).
c. Dimensions required.
d. Requirements for sizes not specifically covered (see QQ-A-250).
e. Whether cladding thickness determination is required (see 3.3.2).
f. Whether ultrasonic inspection of material is required (see 3.4).
g. Selection of applicable levels of preservation, packaging, and packing required, if other than level C (see QQ-A-250).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.




FIGURE 1

75X - UNETCHED, STRESS CORROSION CRACKS IN
7075-T7651 SPECIMEN, NOT ACCEPTABLE




FIGURE 2

75X - UNETCHED, PITTING TYPE ATTACK, IN
7075-T7651, ACCEPTABLE

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.

MILITARY CUSTODIANS:

Army - MR
Navy - AS
Air Force - 11

Review activities:

Army - AV, ME, WC, EL
Navy - None
Air Force - None
DSA - IS

User activities:

Army - MU
Navy - EC, SH, OS
Air Force - None

Preparing Activity:

Navy - AS
(Project No. 9535-0219)

CIVIL AGENCY COORDINATING ACTIVITIES:

GSA - FSS
NASA - JFK, MSF

Orders for this publication are to be placed with the General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 30 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE: QQ-A-250/25A ALUMINUM ALLOY ALCLAD 7075, PLATE AND SHEET (IMPROVED EXFOLIATION RESISTANT)

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?
   ☐ YES ☐ NO (If "Yes", in what way?)

4. REMARKS

SUBMITTED BY (Printed or typed name and address - Optional)

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-26112:042
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY
Naval Air Engineering Center
Philadelphia, PA 19112

OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEPARTMENT OF THE NAVY
DOD 316



Engineering Specifications and Standards Department (Code ES)
Naval Air Engineering Center
Philadelphia, PA 19112

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.