INCH-POUND

A-A-55280

26 April 1993

COMMERCIAL ITEM DESCRIPTION

CLOTH, COATED: GLASS SILICONE RUBBER

The General Services Administration has authorized the use of this Commercial Item Description in preference to MIL-C-10797.

Abstract. This Commercial Item Description covers silicone rubber-coated, glass cloth to be used in the fabrication of stovepipe shields for tentage.

Salient Characteristics. The base cloth shall be glass cloth in either a plain or 4 harness (crowfoot) satin weave. The coating compound shall be a composition of a silicone rubber suitably compounded and pigmented to match the standard shade. The color shall match the standard sample under artificial daylight having a color temperature of 7000 ±500 Kelvin and shall be a good approximation of the standard sample under incandescent lamplight at 2850 ±100 Kelvin. The base cloth shall be coated on both sides with approximately equal amounts of the coating compound and shall be vulcanized. The minimum width of the coated cloth shall be 36 inches (914 mm).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Clothing and Textiles Directorate, Attn: DPSC-FSSD, 2800 South 20th Street, Philadelphia, PA 19101-8419, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A

FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Table I Physical requirements of coated cloth

Characteristic	Requirement Minimum	Maximum
Weight, ounces/square yard (grams per square meter)	18.0 (610)	21.0 (712)
Breaking strength, pounds (newton):		
Warp	140 (623)	
Filling	120 (534)	
Tearing strength, grams (millinewton):		
Warp	6000 (58842)	
Filling	6000 (58842)	
Hydrostatic resistance, p.s.i (kPa):		
Initial	180 (1241)	
After accelerated weathering	170 (1172)	
Stiffness, warp direction, centimeters:		
At 75°F (24°C)		21.0
At minus 60°F (16°C)		22.0
After heat stability 1/		23.0
Flame resistance, after flame, seconds-		
Initial:		
Warp		13
Filling		13
After accelerated weathering:		
Warp		13
Filling		13
Abrasion resistance	Pass 2/	
Blocking, scale rating		3

1/ There shall be no appreciable change in color in any of the specimens when tested as specified in Table II. Appreciable change in color means a change which is immediately noticeable in comparing the test specimen with the original comparison specimen. If closer inspection or a change of angle of light is required to make a slight change in color, the change is not considered appreciable.

2/ The coating shall not be worn through to the base cloth on any of the specimens when tested as specified in Table II.

Source: https://assist.dla.mil -- Downloaded: 202640-26T09:45Z
Check the source to verify that this is the current version before use.

Table II. Instructions for testing

Characteristic	Test method		Number of determinations per sample unit	Results reported to the nearest
Weight ounces	ASTM D3776-Opt C		5	0.1
Breaking strength pounds	ASTM D5035		5 (each direction)	1.0
Tearing strength grams	ASTM D1424		5 (each direction)	100
Hydrostatic resistance:				
Initial	FED STD 191-5512		5	2 p.s.i.
After accelerated weathering	AATCC 111A	1/		
	FED STD 191-5512		5	2 p.s.i.
Stiffness: (warp direction only)				
At 75°F.	FED STD 191-5204		5	0.1 centimeter
At minus 60°F	FED STD 191-5204	2/	5	0.1 centimeter
After heat stability	FED STD 191-5204	3/	5	0.1 centimeter
Flame resistance:		4/		
Initial	FED STD 191-5903		5 (each direction)	0.2 seconds
After accelerated weathering	AATCC 111A	1/	5 (each direction)	0.2 seconds
	FED STD 191-5903	4/	5 (each direction)	0.2 seconds
Abrasion resistance	ASTM D3886	5/	3	Pass or fail
Blocking	FED STD 191-5872		1	Scale rating

1/ The exposure period shall be 100 hours.

2/ The specimens and the instrument shall be conditioned for 4 hours at minus 60° ±2°F before testing at that temperature.

3/ Heat stability. Five specimens 1-1/4 by 8 to 12 inches with the long dimensions parallel to the warp shall be placed flat on a clean, asbestos board in a muffle furnace or in a suitably controlled high temperature oven for a period of 4 hours at a temperature of between 575°F and 600°F. After exposure, the specimens shall be removed and brought to standard conditions before testing. The stiffness shall be determined according to FED STD 191-5204. The exposed specimens shall be visually compared with an equivalent area of unexposed material for colorfastness. Color change shall be reported as pass ("Good") or fail.

4/ Except that the glow time and char length need not be reported.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

5/ Abrasion resistance. The abrasion resistance shall be determined according to ASTM method D3886 except that 3 specimens shall be tested. The three specimens shall be selected across the width of the sample unit so that two of these specimens are obtained from opposite sides and one from the middle. The diaphragm shall be solid rubber (no contact pin) 0.050 to 0.058 inches thick. The abradent shall be "fine" emery cloth and the abradent arm shall be weighted with a 1/2-pound weight. The air pressure shall be 1.2 p.s.i. and the abrasion shall be multidirectional. The specimen shall be abraded on either side for 20 cycles and then visually examined for exposure of the base cloth.

Workmanship. The finished coated cloth shall conform to the quality of product established by this Commercial Item Description. The occurrence of defects shall not exceed the specified quality levels

Product Demonstration Model. When required, offerers shall submit samples of their intended production. The Product Demonstration Model will consist of units independently developed. Product Demonstration Models will be analyzed and evaluated by the government. Evaluation criteria and basis for award are contained in the solicitation. Product Demonstration Models will be retained by the government. One (1) Product Demonstration Model approved by DPSC under the resultant contract will serve as a manufacturing standard for the corresponding production items delivered under this contract. Offerers are advised that the Product Demonstration Model does not relieve the successful offerer of his responsibility to perform in accordance with the Commercial Item Description specified above.

Regulatory Requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

Quality Assurance

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description and that the product conforms to the producer's own specifications, standards and quality assurance practices. The government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for, under the provisions of the contract. Reliance on contractor QA systems shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the government for acceptance comply with all requirements of the contract.

Examination. Rolls of fabric shall be inspected in accordance with "Sampling Procedures and Tables for Inspection by Attributes", ANSI/ASQC Z1.4, published by the American Society for Quality Control.

Yard by yard visual examination. The end item shall be examined in accordance with the classification of defects at the inspection levels and acceptable quality levels (AQL's) as specified. The lot size for purposes of determining the sample size for the examinations shall be expressed in units of yards. The required yardage of each roll shall be examined on one side only (however, the sample shall be alternated on every other roll examined) and visual defects classified as listed below. The same yardage shall be given a through-light inspection for pinholes,

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

and lightly coated areas. The through-light shall be performed in accordance with MIL STD 1487 (Glossary of Cloth Coating Imperfections). The defects listed below shall be counted, regardless of their proximity to each other, except that two or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warp-wise yard or fraction thereof in which it occurs. The sample unit for this examination shall be one linear yard. The acceptable quality level for this examination, including the pinholes and lightly coated areas found in the through-light examination, shall be 1.5 defects per 100 yards. The inspection level shall be level II and the number of rolls from which the sample is to be selected shall be in accordance with Table III. An approximately equal number of yards shall be examined in each roll sampled.

Table III

Lot size (yards)	Sample size (rolls)	Acceptance Number
Up to 1,200 inclusive 1/	3	0
1201 up to and including 3,200	5	0
3,201 up to and including 10,000	8	0
10,001 up to and including 35,000	13	0
35,001 up to and including 150,000	20	1
150,001 and over	32	2

1/ If lot contains fewer than 3 rolls, each roll in the lot shall be examined.

Defects. The cloth shall be examined for the following defects:

Examine	Defect
Coating	Any uncoated area. Any thinly coated area evidenced by light area or windows. Any lump or heavily coated area. Any blister, tunnel or delamination of coating. Any pinhole. Crease or wrinkle resulting in doubling or adhesion of surfaces that cannot be corrected by manual pressure.
Color	Color not as specified, off shade, uneven or mottled.
Width	Width less than minimum specified
Workmanship	Any cut, hole or tear. Any stains or streaks other than coating or pigment clearly visible and exceeding one half inch in combined length and width. 1/ Curled, folded, scalloped or rolled edge. Not clean. Objectionable odor. 2/ Any abrasion exposing base cloth.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

1/ At normal inspection distance (approximately 3 feet)

2/ Aromatic odors usually associated with specific types of coating compounds or solvents shall not be regarded as objectionable.

Dimensional examination for length. Each individual roll in the sample shall be examined for the defects listed below. The sample unit for this examination shall be one roll. The sample size and acceptance number shall be as shown in Table IV.

Any roll containing more than 3 pieces.
Any piece in roll less than 15 yards.
Any roll with a gross length of less than 75 yards or more than 100 yards.
Any roll with a gross length more than 2 yards below that marked on the ticket.

Examination for total yardage in sample. The rolls examined shall be those selected for examination in individual rolls as specified above. The lot shall be unacceptable if the total of the gross lengths of the rolls in the sample is less than the total of the gross lengths marked on the tickets.

Packaging Examination. Examination shall be made in accordance with the provisions of PPP-P-1136 (Packaging and Packing of Coated (Plastic, Rubber) and Laminated Fabrics) to determine that the packing and marking comply with the section 5 requirements.

End Item Performance Testing. The methods of testing as specified in Table II whenever applicable shall be followed. The requirements for all tests are referenced in Table I. The physical values specified apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods, except for abrasion, blocking and flame resistance, for which these values apply to each single determination. The sample unit shall be 3 continuous yards, full width, of the coated cloth. The lot size shall be expressed in units of one linear yard and the sample size (number of sample units) shall be as specified in Table IV. The lot shall be unacceptable if one or more units fail to meet any requirement specified. The number of determinations per sample unit, as well as the reporting of test results, shall be as required by the referenced test method except as otherwise indicated in Table II.

Table IV

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 or more	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Packaging, Packing, Palletization, and Marking. The cloth shall be put-up, preserved, packed, and marked in accordance with the requirements cited in PPP-P-1136.

Source of Government Documents. Copies of Military and Federal documents are available from:

Standardization Documents Order Desk
Bldg. 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Sources of Nongovernment Documents.

ANSI/ASQC Z1.4 - Sampling Procedures and Tables For Inspection By Attributes

(Applications for copies should be addressed to American National Standards Institute, 11 West 42nd Street, New York, NY 10036-8002.)

ASTM-D 3951 - Standard Practice for Commercial Packaging
Other ASTM tests

(Applications for copies should be addressed to American Society For Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

AATCC tests

(Applications for copies should be addressed to American Association of Textile Chemists and Colorists (AATCC), P.O.Box 12215, Triangle Park, NC 27709-2215

Custodian:

Army - GL

Review Activities:

Army - MD
DLA - CT

Civil Agency Coordinating Activity:
GSA - FSS

Preparing Activity:

DLA - CT

Project No. 8305-0482

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	A-A-55280	93/4/26

3. DOCUMENT TITLE

CLOTH, COATED: GLASS SILICONE RUBBER

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON - DSN
Defense Personnel Support Center ATTN: DPSC-FSSD (12-3-D) - DLA-CT	215-737-8105	444-8105
c. ADDRESS (Include Zip Code) 2800 South 20th Street P. O. Box 8419 Philadelphia, Pennsylvania 19101-8419	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

Source: https://assist.dla.mil - Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.