INCH-POUND
A-A-55296A
December 13, 2021
SUPERSEDING
A-A-55296
April 1, 1996

COMMERCIAL ITEM DESCRIPTION

CLOTH, TWILL, COTTON, 10.0 OUNCES

The General Services Administration has authorized the use of this Commercial Item Description (CID) for all Federal Agencies.

1. SCOPE. This document covers the requirements for a 10.0 ounces, cotton twill cloth.

2. CLASSIFICATION. The cloth shall be available in the following classes:

2.1 Classes.

Class 1 - Natural or bleached
Class 2 - Natural or bleached, mildew-resistant treated

3. SALIENT CHARACTERISTICS

3.1 Material. The cloth shall be made of 100 percent cotton, which has been carded, drawn and spun into single yarns. The weave shall a three (3) up and one (1) down (3/1) right hand twill.

3.2 Color.

3.2.1 Class 1. The color of Class 1 cloth shall be natural or bleached white.

3.2.2 Class 2. The color of the Class 2 cloth shall be the shade imparted as a result of the mildew resistant treatment.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Attn: DLA Troop Support, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Since contact information can change, verify the currency of the address information using Acquisition Streamlining and Standardization Information System (ASSIST) online database https://assist.dla.mil.

FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

3.3 Mildew resistant treatment (Class 2 only). The Class 2 cloth shall be given a durable organic mildew resistant treatment that is EPA registered under the FIFRA (see 7.1.4) and the observable fungi shall be no greater than "Microscopic Growth" (visible only under the microscope) after leaching when tested in accordance with AATCC TM30 Test III. Leaching shall be conducted in accordance with procedure in Appendix A1 of AATCC TM30 prior to testing.

3.4 Physical requirements. The finished cloth shall conform to the physical requirements specified in Table I when tested in accordance with the test methods specified in Table I.

TABLE I. Physical requirements.

Characteristic	Requirements	Test Method
Fiber identification	100% cotton	AATCC TM20 (see 7.4)
Weave	3/1 twill	Visual (see 7.4)
Weight, oz./yd^2, (max.)	10.0	ASTM D3776/D3776M, Option C
Yarns per inch, (min.) Warp Filling	 85 38	ASTM D3775
Breaking strength, pounds, (min.) Warp Filling	 130 125	ASTM D5034

3.5 Length and put-up. For Government procurements only, unless otherwise specified (see 6.2). The cloth shall be furnished in continuous lengths, each length not less than 40 yards. Each length shall be put-up full width on a roll as specified in 5.1.

3.6 Fiber identification. Each roll of finished cloth shall be labeled or ticked for fiber content in accordance with the 16 CFC Part 303 Rules and Regulations under the Textile Fiber Products Identification Act (see 7.1.2).

3.7 Workmanship. The finished cloth shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the contractor's own quality assurance standards and the quality assurance standards defined by the technical data in the bid package.

4. REGULATORY REQUIREMENTS. Unless otherwise specified, the offeror/contractor is encouraged to use recovered, recycled, bio based, and environmentally preferable materials to the maximum extent practicable, in accordance with paragraph 23.403, 23.404(b) of the Federal Acquisition Regulation FAR, or the sustainable acquisition of EO 13693; as applicable. (See 7.1.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product conformance. The cloth shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product that is offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance.

5.2 Market acceptability. The finished cloth must have been sold to the government or commercial market.

5.3 Inspection procedures. Sampling for inspection shall be conducted in accordance with ASQ/ANSI Z1.4 - Sampling Procedures and Tables for Inspection of Attributes (see 7.2.2).

5.4 Visual examination. The finished cloth shall be examined for the defects listed below as defined in ASTM D3990.

Material	Any hole, cut, or tear. Puckered, wrinkled or creased/pleated material. Finish not as specified (Class 2).
Label	Label missing, incorrect, or illegible. Required information missing from the label.
Packaging	Not packaged in accordance with the contract or purchase order.

5.5 Acceptance criteria. Acceptance criteria shall be as specified in the contract or purchase order (see 7.5).

6. PACKAGING. Preservation, packing and marking shall be as specified in the contract or purchase order (see 7.5).

7. NOTES.

7.1 Source of Government documents.

7.1.1 Copies of Government documents are available online at https://quicksearch.dla.mil.

7.1.2 16 CFC Part 303 Rules and Regulations under the Textile Fiber Products Identification Act and the Wool Products Labeling Act are available online at https://www.ftc.gov.

7.1.3 EPA and EO 13693 information is available online at https://www.epa.gov.

7.1.4 Federal Insecticide, Fungicide and Rodenticide Act (FIFRA), (40 CFR Part 162) State Registration of Pesticide Products is available online at https://www.epa.gov/pesticides.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

7.2 Source of non-Government documents.

7.2.1 AATCC test methods are available online at https://aatcc.org.

7.2.2 ASQ/ANSI Z1.4 - Sampling Procedures and Tables for Inspection of Attributes are available online at https://asq.org.

7.2.3 ASTM Standards are available online at https://www.astm.org.

7.3 Intended use. The cloth shall be used in the lining of boots and shoes.

7.4 Certificate of compliance. The contracting activity may select to accept a certificate of compliance for stated requirement.

7.5 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this commercial item description
b. Class of cloth required (see 2.1)
c. When natural or bleached is required (2.1)
d. Length put-up other than specified (see 3.5)
e. Product conformance (see 5.1)
f. Acceptance criteria (see 5.5)
g. Packaging requirements (see 6.)

7.6 Key words.

Boot lining
Mildew resistant
Shoe lining
Twill weave

MILITARY INTERESTS:

Custodian:

Army - GL
Navy - NU
Air Force - 11

CIVIL AGENCY COORDINATING ACTIVITY:
GSA-FAS

Preparing Activity:
DLA - CT

(Project 8305-2022-005)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIST Online database at https://assist.dla.mil/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.