A-A-53272A
20 February 1989
SUPERSEDING
A-A-0053272 (DM)
14 December 1987

COMMERCIAL ITEM DESCRIPTION

MIXING PAD, PAPER, DENTAL

The General Services Administration has authorized the use of this Commercial Item Description.

This commercial item description covers a polyethylene-coated pad suitable for use in mixing dental pulp protectors, zinc oxide-eugenol cements, pastes, and all types of impression materials.

Salient characteristics:

The mixing pad shall be a white, bleached polyethylene-coated kraft paper pad of at least 100 cleanly trimmed sheets. The pad shall be 6 ± 1/8 inches in length and 6 ± 1/8 inches in width.

Two opposing sides of the pad shall be glued and the remaining sides free, so as to permit vigorous mixing of materials without wrinkling or tearing, yet facilitate easy removal of the top sheet.

Each pad shall be mounted on cardboard with a minimum thickness of 0.060 inch to serve as a base. Each base shall feature a non-skid surface of a minimum of 1/8 inch of foam rubber to prevent the pad from slipping when mixing is being done on the pad.

The basis weight of the uncoated paper for the pad shall be 47.0 pounds ± 5%, when tested as specified below (24 by 36 inches-500 sheets). The total basis weight of the coated paper shall be 57.8 pounds ± 5%.

The polymer coating shall be impervious to all materials mixed upon its surface, so that there shall be no evidence of staining or contamination of the next underlying sheet.

The tensile strength of the polyethylene-coated paper shall be 27.5 pounds per inch, minimum, in the machine direction and 16.0 pounds per inch, minimum, in the cross direction, when tested as specified below.

AMSC N/A FSC 6520

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:17Z
Check the source to verify that this is the current version before use.

The tearing resistance of the polyethylene-coated paper shall be a minimum of 104 grams in both machine and cross directions, when tested as specified below.

The mixing pad shall contain no toxic or harmful ingredients, and shall be furnished clean and ready for use.

Workmanship. The mixing pad shall be free from defects which detract from its appearance or impair its serviceability.

Unit. Each (EA). One pad of 100 sheets, as specified, constitutes one unit.

QUALITY ASSURANCE PROVISIONS.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Certificates of quality. Certificates of quality, supplied by the manufacturer of the raw materials, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:17Z
Check the source to verify that this is the current version before use.

Quality conformance inspection.

Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, with an AQL of 2.5 (percent defective) and an inspection level of S-2. The unit of product for examination shall be the individual pad.

Sampling for raw material testing. A sufficient quantity from each lot of polyethylene-coated paper shall be selected for testing basis weight, tensile strength, and tearing resistance as specified below. Where feasible, the same sample unit shall be used for the determination of two or more test characteristics.

Examination. The mixing pads shall be examined to determine compliance with requirements contained in this specification. Any mixing pad in the sampling which contains one or more defects shall be rejected, and if the number of defective pads in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected. The mixing pads shall be examined for defects including, but not limited to, those listed below:

Defects

Sheets of paper not cleanly trimmed.
Dimensions of sheets not as specified.
Sheets not clean and free of foreign material.
Sheets wrinkled, torn, or folded.
Sheets have holes or cuts.
Polyethylene coating not as specified.
Pads have crushed edges.
Pads insufficiently glued or not glued as specified.
Sheets not easily and cleanly removed from pad.
Number of sheets in pad not as specified.
Thickness of cardboard base or foam rubber not as specified.

Tests. Tests for physical characteristics of the polyethylene-coated paper shall be conducted in accordance with the standards of the Technical Association of the Pulp and Paper Industry (TAPPI). The tests for basis weight, tensile strength and tearing resistance shall be performed in accordance with TAPPI standards 410, 404, and 414, respectively.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:17Z
Check the source to verify that this is the current version before use.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended, and as implemented by Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Number is covered by this document.

National Stock Number	Item Identification
6520-01-257-1908	MIXING PAD, PAPER, DENTAL, Polymer coated, 6 by 6 inch (15.2 by 15.2 cm), 100 sheets

Ordering data. Intermediate/exterior package quantities, labeling, and marking must be as specified in the contract and/or order.

MILITARY INTERESTS:

Custodians:
Army - MD
Navy - MS
Air Force - 03

PREPARING ACTIVITY:

DoD-MB

Agent:

DLA-DM

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:17Z
Check the source to verify that this is the current version before use.

CIVIL AGENCY COORDINATING ACTIVITIES:
VA-OSS
PHS
FDA-MPQAS

PROJECT NO. 6520-2209

LOCATION: NCR DISK # 5

61163

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:17Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1 DOCUMENT NUMBER	2 DOCUMENT TITLE
A-A-53272A	MIXING PAD, PAPER , DENTAL

3a. NAME OF SUBMITTING ORGANIZATION	4 TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)* _____

5 PROBLEM AREAS

a. Paragraph Number and Wording

b Recommended Wording

c Reason/Rationale for Recommendation

6 REMARKS

7a NAME OF SUBMITTER *(Last, First, MI)* – Optional	b WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8 DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:17Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE. This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 4966 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
Attn: DPSC-RSTE
2800 South 20th Street
Philadelphia, PA 19101

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:17Z
Check the source to verify that this is the current version before use.