MIL-F-50809 (MU)
AMENDMENT 2
14 February 1973
SUPERSEDING
AMENDMENT 1
22 July 1971

MILITARY SPECIFICATION

FIBER, ACRYLIC, FIBRILLATABLE

This amendment forms a part of Military Specification MIL-F-50809 (MU), dated 22 July 1970.

Paragraph 4.3.1, delete last sentence in its entirety and substitute the following:

"Each lot shall consist of drums of fibrillatable acrylic fiber from the same continuous extrusion that has been subjected to the same processing operations and conditions, and in accordance with the same specification and specification revision."

Add new paragraph:

"4.4.4.1 Fibrillation, Alternate Method.-Gradually charge 22 liters of distilled water to 1.5 pound Niagara type beater and start circulation with no load on the bed plate. Then slowly add 250 grams ± 5 grams, oven dry basis, of the fiber to the beater. The time of addition of fiber to the beater shall be 3 to 5 minutes. The fiber water slurry shall be circulated for 1 hour at maximum clearance. After 1 hour, change the beater bed plate by 0.070 inch clearance. Then continue circulation for 2 hours and then reduce beater roll bed plate by 0.010 inch to 0.060 inch. Again circulate for 2 hours and reduce the beater roll bed plate by 0.010 inch to 0.050 inch clearance. Continue beating until the drainage rate specified is attained as determined in accordance with TAPPI Method T1002. Record total beating time. Photomicrographs of the fiber before and after fibrillation shall appear as shown in Figure 1A and 1B, respectively."

CUSTODIAN:
ARMY-MU

PREPARING ACTIVITY:
ARMY-MU

Project No. 1320-A178

FSC: 1320

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:39Z
Check the source to verify that this is the current version before use.