INCH-POUND

A-A-55071
07 August 1992

COMMERCIAL ITEM DESCRIPTION

TAPE, TEXTILE, 1-INCH

The General Services Administration has authorized the use of this Commercial Item Description in preference to Military Specification MIL-T-10372.

Abstract. The tape shall be one type of cotton tape for use in the manufacturing of dust respirators.

SALIENT CHARACTERISTCS

General Description. The cotton used in the manufacture of the yarn, used to produce this tape, shall be thoroughly cleaned and carded or combed, and evenly drawn, spun, and twisted into 2-ply yarn. The warp yarn shall be 26/2 count and the filling yarn shall be 30/2 count.

Material. The fabric shall have a minimum total warp of 114 and 46 picks per inch in the filling. And the weave shall be a four-harness herringbone twill, 2/2, with five divisions alternating to the right and to the left.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Clothing and Textiles Directorate, Attn: DPSC-FSSD, 2800 South 20th Street, Philadelphia, PA 19101-8419, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A

FSC 8315

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:42Z
Check the source to verify that this is the current version before use.

Physical Requirements. The finished cloth shall conform to the following requirements:

Characteristics	Requirement	Test Method 1/
	TEST METHODS	
Weight, oz./linear yard (minimum)	0.20	5040
Yarn Count (per inch/minimum)		
Total Warp	114	5050
Picks (Filling)	46	5050
Width (per inch)	± 1/32	5020
Length (yards per roll)	36	5010
Warp Breaking Strength (minimum) (lbs)	140	5102
Colorfastness to Water	Good	5630 2/
Sulfur Dye Content	No Presence	3

1/ The test methods indicated, from FED-STD-191 Textile Test Methods, have been found acceptable to determine if the cloth meets the stated requirements. If the Government requires proof that the cloth meets the stated requirements, the test methods indicated shall be used.

2/ Colorfastness. The dyed and finished yarn, used in this tape, shall show "good" colorfastness to laundering equal to or better than the standard sample when tested as specified. When no standard sample is established, or when the standard sample is not referenced for colorfastness, the dyed and finished tape shall show "fair" colorfastness to laundering when tested as specified under end item performance testing.

3/ Detection of sulfur dyes. Analytical reagent grade chemicals and distilled water shall be used throughout the test. Place a 1-inch square piece of cloth, taken from the unit of product, place it in a test tube and cover it with a solution containing 1 gram of stannous chloride for every 2 milliliters of 6N hydrochloric acid. Cover the mouth of the test tube with a piece of filter paper which has been moistened with a few drops of 0.5N solution of lead acetate. Boil the solution in the test tube. The appearance of a black stain on the filter paper indicates the presence of a sulfur dye.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

Standard Sample. When a standard sample is available, the tape shall match the standard sample for shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced.

Color. The color shall be olive drab. The color is to be designated by the procuring Activity. The use of sulfur dye and dyes containing elementary sulfur or compounds capable of oxidation to sulfuric acid is prohibited. The dyestuff shall be chosen and applied so that the dye and finished tape shall contain no more labile sulfur than that shown by the standard sample when tested as specified under end item performance testing.

Label/Marking. Each roll shall be labeled, ticketed, or invoiced for fiber content in accordance with The Textile Fiber Products Identification Act.

Workmanship. After completion, the finished tape shall be thoroughly cleaned, and all loose thread, lint, and foreign matter removed.

QUALITY ASSURANCE

Certification. The contractor shall certify, and maintain substantiating evidence, that the product offered meets the salient characteristics and requirements of this Commercial Item Description that the product conforms to the producer's own drawings, specifications, standards and quality assurance practices. The Government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for, under the provisions of the contract.

Visual Examination. Lots of tape shall be inspected in accordance with "Sampling Procedures and Tables for Inspection by Attributes", ANSI/ASQC Z1.4, published by the American Society for Quality Control.

The inspection level for visual examination shall be in accordance with ANSI/ASQC Z1.4. The inspection level shall be I and the Acceptable Quality Level (AQL), expressed in terms of defects per hundred units, shall be 4.0. The tape shall be examined for the following defects: any spot or stain, clearly visible at normal inspection distance (approximately 3 feet); any jerked-in filling, slough-off, or foreign matter sewn into the tape; wrong color, any part shaded or off-shade; any hole, needle chew, cut, or tear; weakening defect (i.e., abrasion marked area, slub, smash, float); any mend or burn; not material specified; thread ends not trimmed; edges of tape cut frayed or torn (i.e., loopy or slack), any tape that is rolled or wavy which will not flatten under normal pressure; and any fine or light or heavy filling or picks, knots or slubs; label missing, incorrect or illegible; and measurement of item not as specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

Regulatory Requirements. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practicable.

PACKAGING

Packaging, Packing, Marking, and Palletization.

Packaging, packing, marking and palletization shall be in accordance with ASTM-D 3951, Standard Practice for Commercial Packaging, as specified for shipments to the Department of Defense, including Section 7.

Packaging. The cotton tape shall be packaged to afford adequate protection from the supply source to the first receiving activity for immediate use.

Packing. The cotton tape shall be packed to insure carrier acceptance and safe delivery to the first domestic destination. Containers shall comply with The Uniform Freight Classification Rules and Regulatio of other carriers applicable to the mode of transportation.

Marking. In addition to any special marking required by the contract or purchase order, unit packages and shipping shall be marked in accordance with MIL-STD-129.

Palletization. When specified, shipping containers shall be palletized in accordance with load Type Ia of MIL-STD-147. Pallet pattern shall be in accordance with the appendix of MIL-STD-147. The containers shall be bonded onto wing type commercial 4-way entry pallets.

Unitized loads, placing boxes on pallets, shall be used whenever total quantity for shipment to one destination exceeds 250 pounds (excluding the pallet) or 20 cubic feet. Pallets shall have a length of 40 inches and a width of 48 inches. Pallet loads, including the pallet, shall not exceed 54 inches in height, 43 inches in length and 52 inches in width.

Prohibited Packing Materials. The use of asbestos, excelsior, newspaper or shredded paper (all types including waxed paper, computer paper and similar hygroscopic or non-neutral material) are prohibited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

Source of Government Documents. Copies of Military and Federal documents are available from:

Standardization Documents Order Desk
Bldg. 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Sources of Non-government Documents.

ANSI/ASQC Z1.4 - Sampling Procedures and Tables For Inspection By Attributes

(Applications for copies should be addressed to American National Standards Institute, 1430 Broadway, New York, NY 10018-3308.)

ASTM-D 3951 - Standard Practice for Commercial Packaging

(Applications for copies should be addressed to American Society For Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Custodian:
Army - EA

Review Activity:
Army - EA
Army - GL

Civil Agency Coordinating Activity:
GSA - FSS

Preparing Activity:
DLA - CT

Project No.
8315-0360

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8 In block 1, both the document number and revisior letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification o requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER A-A-55071	2. DOCUMENT DATE (YYMMDD) 07 August 1992

3. DOCUMENT TITLE
TAPE, TEXTILE (1-INCH)

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME *(Last, First, Middle Initial)*	b. ORGANIZATION	
c. ADDRESS *(Include Zip Code)*	d. TELEPHONE *(Include Area Code)* (1) Commercial (2) AUTOVON *(If applicable)*	7. DATE SUBMITTED *(YYMMDD)*

8. PREPARING ACTIVITY

a. NAME DLA - CT	b. TELEPHONE *(Include Area Code)* (1) Commercial (215) 737-8105	(2) AUTOVON 444-8105
c. ADDRESS *(Include Zip Code)* DEFENSE PERSONNEL SUPPORT CENTER DPSC-FSS (Bldg. 12-3-D) 2800 S. 20th St., Phila., PA 19101	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.